INCH-POUND

A-A-55100
10 NOVEMBER 1992

COMMERCIAL ITEM DESCRIPTION

YARN: COTTON

The General Services Administration has authorized the use of this Commercial Item Description in preference to Military Specification MIL-Y-16698(GL).

ABSTRACT

Abstract. The yarn shall be one type of cotton, suitable for carpet warps in hand weaving occupational therapy.

SALIENT CHARACTERISTICS

General description. The yarn shall be made of clean cotton which has been carded, spun, and twisted into yarn. The yarn shall be 8/4 ply ± 3 percent, 6 to 7 1/2 turns per inch of "S" twist in the ply. The plied yarn shall have a breaking strength of 7 pounds minimum when tested as specified under end item performance testing.

Color. The color of the yarn shall be natural, bleached white, or color, as specified, and shall conform to an approved shade standard. When white is specified, the yarn shall be bleached using a peroxide type bleach. No tinting is permissible and the use of optical bleaches is not permitted. When natural is specified, the yarn shall be the natural shade.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Clothing and Textiles Directorate, Attn: DPSC-FSSD, 2800 South 20th Street, Philadelphia, PA 19101-8419, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A

FSC 8310

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

Labile Sulfur. The use of dyes and compounds containing elementary sulfur or compounds capable of oxidation to sulfuric acid is prohibited when tested as specified under end item performance testing.

Shade Matching. The color shall match the standard sample under natural (north sky) daylight or artificial daylight having a color temperature of 7500° Kelvin and shall be a good approximation to the standard sample under incandescent lamplight at 2800° Kelvin.

Colorfastness. The dyed and finished yarn shall show a minimum of Class 3 fastness to laundering when tested as specified under end item performance testing.

Put-up. The yarn shall be put up on spools containing 840 yards ± 10 percent.

Label/marking. Each spool shall be labeled or ticketed for fiber content in accordance with the Textile Fiber Products Identification Act.

Workmanship. After completion, the finished yarn shall be thoroughly cleaned, and all loose thread, lint, and foreign matter removed.

QUALITY ASSURANCE

Certification. The contractor shall certify, and maintain substantiating evidence, that the product offered meets the salient characteristics and requirements of this Commercial Item Description, and that the product conforms to the producer's own specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Visual examination. Yarn lots shall be inspected in accordance with ANSI/ASQC Z1.4. The inspection level shall be I and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5. The lot size shall be expressed in units of one spool. The sample unit shall be one spool.

Defects. The yarn shall be examined for the following defects: any spot or stain, clearly visible at normal inspection distance (approximately 3 feet), any burr, shive or foreign matter; wrong color, off shade, i.e. not within established tolerances; package which is cut, torn, chafed, or otherwise damaged, affecting the free unhampered unwinding of yarn or affecting strength of yarn, or affecting the secure holding of yarn winds on the package, type of package other than specified; thread ends not removed; label missing, incorrect or illegible; measurement of item not as specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

Regulatory requirements. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practicable.

End Item Performance Testing.

The yarn shall be tested as specified in the table below. The sample unit shall be one spool. The lot shall be unacceptable if one or more sample units fail to meet any test requirements specified. The lot size shall be expressed in units of one spool. The sample size (number of sample units) shall be in accordance with the following:

Lot Size (Spools)	Sample Size
800 or less	2
800 thru 22,000	3
22,001 and over	5

TEST METHODS

Characteristic	Test Method
Material	1/
Yarn size	ASTM-D 1907
Twist direction	ASTM-D 1423
Twist turns per inch	ASTM-D 1423 2/
Yarn ply	Visual 3/
Breaking strength	ASTM-D 2256
Labile sulfur	1/
Colorfastness to laundering	AATCC 61, Test 3A

1/ A certificate of compliance shall be acceptable for this requirement.

2/ Twist contraction is not required.

3/ One determination per sample unit and results reported as "pass or fail".

PACKAGING

Packaging. Twelve spools of yarn of one color only, put up as specified herein, shall be packaged in a snug-fitting partial telescope or shallow lid folding paperboard box. The lid for the boxes shall be not less than 1-inch in depth. Box closure shall be secured with a commercially acceptable 2-inch minimum width gummed paper tape.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

Packing. Ninety-six spools of yarn of one color only, packaged as specified in packaging paragraph, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF (variety SW) or SF, class domestic, grade 275. Each shipping container shall be closed either with glue, hot melt adhesive or tape in accordance with good commercial practice.

Marking. In addition to any special markings required by the contract or purchase order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

NOTES

Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this commercial item description.
b. Color required.
c. Selection of applicable levels of packaging and packing.

Source for Government documents. Copies of Military and Federal documents are available from:

Standardization Documents Order Desk
Building 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

Rules and Regulations Under the Textile Fiber Products Identification Act is available from:

Federal Trade Commission
Washington, DC 20580

Source for Non-Government documents.

ASTM Test Methods are available from:

American Society for Testing and Materials
1916 Race Street
Philadelphia, PA 19111-5094

AATCC Test Methods are available from:

American Association of Textile Chemists and Colorists (AATCC)
P.O. Box 12215
Triangle Park, NC 27709-2215

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

ANSI/ASQC Z1.4 - Sampling Procedures and Tables for Inspection By Attributes is available from:

American National Standards Institute
1430 Broadway
New York, NY 10018-3308

Standard sample. For access to standard sample, address the procuring office issuing the invitation for bids.

The standard shade samples have been dyed by the use of the following dyes:

Black 281	Direct Black 38, C.I. 30235
Blue 282	Direct Blue 106, C.I. 51300
Brown 283	Direct Brown 95, C.I. 30145
Gray 284	Direct Black 3, C.I. 27710
Green 285	Direct Green 26, C.I. 34045
Orange 286	Direct Orange 34, C.I. 40215/20
Red 287	Direct Red 80, C.I. 35780
Yellow 288	Direct Yellow 28, C.I. 19555

Civil Agency Coordinating Activity:
GSA-FSS

Preparing Activity:
DLA-CT

Project No.
8310-0190

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	A-A-55100	92/11/10

3. DOCUMENT TITLE
YARN: COTTON

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code)	
Defense Personnel Support Center ATTN: DPSC-FSSD (12-3-D) - DLA-CT	(1) Commercial 215-737-8105	(2) AUTOVON DSN 444-8105
c. ADDRESS (Include Zip Code) 2800 South 20th Street P.O. Box 8419 Philadelphia, PA 19101-8419	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

DD Form 1426, OCT 89 Previous editions are obsolete 198-290

Source: https://assist.dla.mil - Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.