INCH-POUND

A-A-55107
17 DECEMBER 1992

COMMERCIAL ITEM DESCRIPTION

SOCKS: MEN'S, NYLON, CUSHION SOLE, STRETCH TYPE

The General Services Administration has authorized the use of this Commercial Item Description in preference to Military Specification MIL-S-43823.

ABSTRACT

Abstract. The socks shall be a seamless, stretch type, with a true 1X1 rib-knit or mock-rib knit elastic top, and a plain knit leg and foot with a terry stitch on the inside of the high heel, heel, sole, toe and ring toe, the color shall be Olive Green, intended for use by personnel of the Department of Defense.

Sizes. The socks shall be provided in the following sizes:

SMALL	(Sizes 7, 7-1/2, 8, 8-1/2)
MEDIUM	(Sizes 9, 9-1/2, 10, 10-1/2)
LARGE	(Sizes 11, 11-1/2, 12, 13)

Note: The sizes (SMALL, MEDIUM, LARGE) may be abbreviated as SM, MED, LG.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Clothing and Textiles Directorate, Attn: DPSC-FSSD, 2800 South 20th Street, Philadelphia, PA 19101-8419, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A

FSC 8440

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

SALIENT CHARACTERISTICS

General Description. The yarn for knitting the elastic cuff, the leg portion of the sock down to the heel, the leg portion adjacent to the high heel, the top of the foot, and for plating the high heel, heel, sole, toe, and ring toe shall consist of a single end of a 70 denier, 3 ply stretch nylon yarn. The yarn for the terry stitch on the inside of the high heel, heel, sole, toe and ring toe shall consist of a single end of a 70 denier, 3 ply stretch nylon yarn. The seaming thread shall be nylon, natural white, commercial size 4, 1 or 2 ply. The elastic yarn for the cuff shall be a nominal 420 or 466 denier Spandex core having a 30 denier stretch type nylon inner and outer cover. The toes shall be closed by seaming using nylon, natural white, commercial size 4, 1 or 2 ply thread. The seam shall be as elastic as the knit fabric and shall be pulled flat to lie smooth and shall be free from lumps, laps, cuts, and bruises. A thread chain of 1/4 to 1 inch shall be left at the ends of the stitching to prevent raveling.

A double thickness of the terry portion (terry to terry) of the finished socks shall have a minimum thickness of 0.070 inches when tested according to Test Method ASTM-D 1777. The presser foot shall be a circular with a diameter of 0.375 ± 0.001 inches and with the moving parts connected therewith weighted so as to apply a total load of nine pounds per square inch. Two readings shall be taken on each of the five specimens. The thickness of the sample unit shall be the average of ten results obtained from the specimens tested and shall be reported to the nearest 0.001 inch.

The dyed socks shall show fastness to laundering, perspiration and crocking. The socks shall show a minimum of Class 4 for laundering and perspiration, and a minimum of Grade 4 for crocking when tested according to AATCC Test Method 61 (Test No. 1A) for Laundering; AATCC 15 for Perspiration; and AATCC 8 for Crocking.

Measurements and Weight. The measurements and weight of the finished socks shall conform to the table below . All measurements shall be made with the sock laid out flat, under no tension:

	See Fig. 1	Small	Medium	Large	Tolerance
Leg: Length (inches)	A	14	15	16	Minimum
Foot: Length (inches)	B	6 1/2	8 1/2	10 1/2	± 1/2

Source: https://assist.dla.mil - Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

	See Fig. 1	Small	Medium	Large	Tolerance
Top: Length (inches)	C	3	3	3	± 1/4
Top: Width (inches)	D	3	3	3	± 1/2
High Heel: (inches)	E	1 1/4	1 1/4	1 1/4	Minimum
Ring Toe: (inches)	F	1/2	1/2	1/2	Minimum
Conditioned Weight per dozen pairs: (ounces)		15	17	19	Minimum
Crosswise Stretch: 4/					
Leg 1/		8.5	9.0	9.0	Minimum
Foot 2/		8.5	9.0	9.0	Minimum
Elastic Top 3/		8.5	9.0	9.0	Minimum
Lengthwise Stretch: 5/: Foot		10.0	11.5	13.0	Minimum

1/ Measure across a point midway between the bottom heel and bottom of rib top.

2/ Measure across a point midway between heel and toe.

3/ Measure across a point midway between top and bottom of elastic top.

4/ The crosswise stretch measurement shall be evaluated on a Houchin modification of a Schieffer machine described in Method 7560 of FED-STD-191. The sock shall be pulled over the form so that the 2 inch edges shall be parallel to the foot of the sock. The indicator pin shall be inserted in the upper 2 inch edge of the separating form and a 10 pound weight slowly applied so as to cause separation of the upper and lower slotted form with resultant stretch of the sock under a uniform load over the 2 inch edges. The socks shall be evaluated after the weight has hung freely for 30 seconds and shall be expressed in inches as the distance between the upper and lower edges of the separated form.

Source: https://assist.dla.mil Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

5/ The lengthwise stretch of the socks shall be measured using the sock measuring machine apparatus and measurement of specimen procedure specified in Method 7560 of FED-STD-191. The measurement shall be taken to the nearest 0.1 of an inch and the measured stretch "foot length" obtained in accordance with this procedure shall be considered as the lengthwise foot stretch.

Label/marking. Each sock shall have a size marking and fiber content applied to it just below the instep and centered between the ankle and toe. The color of the marking shall be white. The size label shall be printed with characters a minimum of 5/16 inch in height and shall contain the sock size and the legend.

Workmanship. The socks shall be scoured and boarded on drying forms to their proper shape and size. After completion, the finished socks shall be thoroughly cleaned, and all loose thread, lint, and foreign matter removed.

Product Demonstration Model. Offerors are required to submit two (2) pairs of socks of their intended production. The Product Demonstration Model will consist of units independently developed. Product Demonstration Models will be analyzed and evaluated by the government. Evaluation criteria and basis for award are contained in the solicitation. Product Demonstration Models will be retained by the government. One (1) Product Demonstration Model approved by DPSC under the resultant contract will serve as a manufacturing standard for the corresponding production items delivered under this contract. Offerers are advised that the Product Demonstration Model does not relieve the successful offeror of his responsibility to perform in accordance with the Commercial Item Description specified above.

QUALITY ASSURANCE

Certification. The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Examination. Sock lots shall be inspected in accordance with ANSI/ASQC Z1.4, published by the American Society for Quality Control.

Visual Examination. The inspection level shall be II and the AQL, expressed in terms of defects per hundred units, shall be 2.5. The lot size shall be expressed in units of one sock. The sample unit shall be one sock.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

Defects. The sock shall be examined for the following defects: Any hole, run or dropped stitch including hole in looping or seaming; thin area or mends, welt omitted, cut, frayed or ravelled; noticeable variation in shade between two socks of a pair; variation in size in pair; ring toe omitted, terry stitch omitted; non-uniform in overall appearance, not well shaped, slubby yarn, streak, stain, shade bar or spot, rancid or bad odor, any burn or scorch in fabric; skipped stitches, run-offs, or broken thread, resulting in any open seam; any dimension or weight not as required; any spot or stain (outside); thread ends not removed; label missing, incorrect, misplaced, or illegible; measurement of item not as specified.

Dimensional Examination. The finished sock shall conform to the dimensions specified. Any dimension that is not within the established tolerance shall be classified as a defect. The sample unit shall be one individual sock and the selection shall be by pairs. The inspection shall be S-3 and the AQL shall be 2.5.

Packaging Examination. The fully packaged shipping containers shall be examined in accordance with defects listed below. The lot size shall be the number of shipping containers in the inspection lot. The inspection level shall be S-2 and AQL shall be 1.5.

Examination	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, or method of application.
Material	Any component missing, damaged, or not as specified.
Workmanship	Inadequate application of components, such as: incomplete closure of container flaps, loose strapping, improper taping, or inadequate stapling.
Content	Number of items per container is more or less than required.
	NSN shown on one or more items not as specified on shipping container.
Palletization	Length, width, or height exceeds specified maximum requirements.
	Pallet type not as specified.
	Load not bonded as specified.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

Regulatory Requirements. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practicable.

PACKAGING

Preservation, Packing, and Marking. The preservation, packing, and marking shall be as specified in the contract or order.

NOTES

Source for Government documents. Copies of Federal documents such as FED-STD-191 are available from:

Standardization Documents Order Desk
Building 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

Source for Non-Government documents.

Copies of AATCC Test Methods are available from:

American Association of Textile Chemists and Colorists
P. O. Box 12215
Research Triangle Park, NC 27709-2215

ANSI/ASQC Z1.4 - Sampling Procedures and Tables for Inspection By Attributes is available from:

American National Standards Institute
1430 Broadway
New York, NY 10018-3308

Custodian:
Army - GL
Navy - SA

Review Activity:
Army - GL

User Activity:
Navy - YD

Civil Agency Coordination Activity:
GSA - FSS

Preparing Activity:
DLA - CT

Project No.
8440-0205

Source: https://assist.dla.mil -- Downloaded: 2026-04-26T09:42Z
Check the source to verify that this is the current version before use.




FIGURE 1 SOCKS, MEN'S, NYLON, CUSHION SOLE, STRETCH TYPE

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	A-A-55107	92/12/17

3. DOCUMENT TITLE

SOCKS: MEN'S, NYLON, CUSHION SOLE, STRETCH TYPE

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code)	
Defense Personnel Support Center ATTN: DPSC-FSSD (12-3-D) - DLA-CT	(1) Commercial 215-737-8105	(2) AUTOVON – DSN 444-8105
c. ADDRESS (Include Zip Code) 2800 South 20th Street P. O. Box 8419 Philadelphia, Pennsylvania 19101-8419	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:42Z
Check the source to verify that this is the current version before use.