MILITARY SPECIFICATION

CLAMPS, LOOP, TUBE SUPPORT

This amendment forms a part of military Specification MIL-C-8956, dated 2 December 1970, and is approved for use by all Departments and Agencies of the Department of Defense.

Page 2

2.1 Delete MIL-G-23652 and add the following item in sequence:

"MIL-R-25988 Rubber, Fluorosilicone Elastomer, Oil and Fuel Resistant, Sheets, Strips, Molded Parts, and Extruded Shapes."

Page 3

Add the following new paragraph:

"2.2 Other publications - The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply:

American Society for Testing and Materials Publication

D 1149-64 Accelerated Ozone Cracking of Vulcanized Rubber

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103)"

Page 4

3.2.2.2 Type III - Delete reference to MIL-G-23652 and substitute MIL-R-25988.

FSC 5340

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T11:46Z
Check the source to verify that this is the current version before use.

4.6.2.2.1 Original properties - Delete reference to MIL-G-23652 and substitute MIL-R-25988.

Page 10

4.6.2.2.4 Delete this paragraph in its entirety and substitute the following new paragraphs:

"4.6.2.2.4 Weathering or ozone resistance - Three samples of the elastomeric cushion material, 0.030 inch thick in the shape of the tensile specimens shall be tested in accordance with either 4.6.2.2.4.1 or 4.6.2.2.4.2.

4.6.2.2.4.1 Weathering - Specimens shall be tested in accordance with Federal Test Method Standard No. 601, Method No. 7311. Specimens shall be stretched to 10 percent elongation. The stretched samples shall be exposed for 100 hours in the weathering unit and then subjected to the tensile test specified in MIL-S-6855.

4.6.2.2.4.2 Ozone resistance - Specimens shall be tested in accordance with ASTM Method D1149-64T under the following conditions:

Specimen elongation	10%
Ozone concentration	100 ±5pphm (volume)
Exposure period	60 ±1 minute at 50 ±1°C (120° - 123°F)

Following the test there shall be no evidence of cracking when specimens are inspected with 7 X magnification."

Custodians:
Navy - AS
Army - AV
Air Force - 82

Review activity:
Navy - AS
Army - AV
Air Force - 82

Preparing activity:
Navy - AS
Project No. 5340-0966

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T11:46Z
Check the source to verify that this is the current version before use.