[INCH-POUND]
A-A-59168
17 June 1998
SUPERSEDING
MIL-L-83795B
3 October 1994

COMMERCIAL ITEM DESCRIPTION

LAYOUT FLUID (DYE), BLUE

The General Services Administration has authorized the use of this commercial item description as a replacement for MIL-L-83795B for all federal agencies.

1. SCOPE. This commercial item description (CID) establishes the government acquisition requirements for a blue layout fluid (dye) used to coat metal and glass surfaces for scribing or marking purposes.

2. CLASSIFICATION. The blue layout fluid shall be classified into three products container Types.

Type 1	Aerosol container
Type 2	Applicator-in-cap container
Type 3	Screw-top container

3. SALIENT CHARACTERISTICS

3.1.1 Materials

3.1.2 Composition. The blue layout fluid shall be a uniform mixture of suitable organic solvents, film former, and blue dye with a sweet solvent odor. The mixture shall be free of sediments and suspended particles that can be detected by visual examination.

3.1.3 Propellant. The propellant for Type 1 products shall consist of a mixture of propane and isobutane.

3.1.4 Physical properties

3.1.5 Color. The layout fluid shall be blue such that it will match or be darker than Color Chip No. 25102 (Table VI) of FED-STD-595 by visual comparison.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any other data which may improve this document should be sent to: Defense Supply Center Richmond (DSCR), ATTN: DSCR-VBD, 8000 Jefferson Davis Highway, Richmond, VA 23297-5678.

AMSC N/A FSC 6850

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:05Z
Check the source to verify that this is the current version before use.

3.1.6 Flash point. The layout fluid shall have a minimum flash point of 53 °F (11.7 °C) when tested in accordance with ASTM D 56. For Type 1 products, this requirement shall be verified on the bulk layout fluid prior to aerosol packaging.

3.1.7 Viscosity. The layout fluid shall have a maximum efflux time of 32 seconds when tested using Gardco Zahn Signature Series viscosity cup No.1. The manufacturer's instructions for the use and care of the Zahn cup shall be followed.

3.1.8 Dry film. A layer of layout fluid applied onto a dry, smooth, and flat ferrous metal surface in accordance with ASTM D 823 (Practice E) shall have the following properties:

3.1.8.1 Drying time. The film shall air-dry within no more than five minutes such that the coating will not visibly rub off on finger by light rubbing.

3.1.8.2 Appearance. The dry film shall be visually non-glaring with a uniform finish and color.

3.1.8.3 Thickness. The dry film shall have a maximum thickness of 0.3 mils (0.0003 inches) when measured in accordance with ASTM D 1186.

3.1.8.4 Adhesion. The dry film shall not flake or peel such that when tested in accordance with ASTM D 3359 (Test Method B) shall have a classification rating of 5.

3.1.9 Chemical resistance. The layout fluid dried on a metal or glass surface shall not wash away with synthetic coolants, chlorinated solvents, oils, cutting oils, or water. The manufacturer shall provide safe removal instructions.

3.1.10 Containment

3.1.11 Pressurized container. Pressurized container of Type 1 products shall not leak, and shall contain 25 to 30 percent by weight of the required propellant to completely empty the fluid contents over a normal period of use.

3.1.12 Non-pressurized container. Type 3 products container shall have screw-top closures and Type 2 products container shall incorporate an applicator such as a brush or a dauber, as an integral part of the closure.

4. REGULATORY REQUIREMENTS

4.1 Material safety data sheet. Manufacturers shall prepare and submit material safety data sheet (MSDS) in accordance with FED-STD-313 and the Code of Federal Regulations (29 CFR 1910.1200).

5. QUALITY ASSURANCE PROVISIONS

5.1 Product conformance. The blue layout fluid products provided shall meet the salient characteristics requirements of this commercial item description; shall conform to the producer's own drawings, specifications, standards, and quality assurance practices; and shall be the same product offered for sale in the commercial market. The government reserves the right to require proof of such conformance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:05Z
Check the source to verify that this is the current version before use.

5.2 Market acceptability criteria. The blue layout fluid products procured under this commercial item description shall have been previously sold to the government or commercial customers.

6. PACKAGING

6.1 Preservation, packing, and marking. The blue layout fluid products shall be preserved, packed, and marked as specified in the acquisition contract or order.

7. NOTES

7.1 Source of documents

7.1.1 Copies of ASTM Standards may be obtained from the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

7.1.2 For bidding purposes, copies of Federal Standards 313 and 595 may be obtained from the General Services Administration, Federal Supply Service Bureau, Specification Section, Suite 8100, 479 L'Enfant Plaza SW, Washington, DC 20407.

7.2 National stock number (NSN). This commercial item description is associated with NSNs 6850-00-015-0834 (Type 1, 12 ounces net weight), 6850-00-584-2879 (Type 2, 4 ounces), 6850-00-985-6227 (Type 2, 8 ounces), 6850-00-664-9067 (Type 3, 1 pint), and 6850-01-276-5396 (Type 3, 1 gallon). Other NSNs may also correspond to the blue layout fluid specified in this commercial item description.

7.3 Part numbers. For cataloging purposes, part numbers associated with this commercial item description may be CID-A-A-59168-* with the final character (*) being 1, 2, or 3 to designate the Type of container (see 2.1).

MILITARY INTERESTS:

Custodians:
Air Force - 68
Navy - AS

Preparing activity:
DLA - GS

(Project 6850-1196)

Reviewer:
Navy - SH

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:05Z
Check the source to verify that this is the current version before use.