INCH-POUND

MIL-W-14742A (AR)
AMENDMENT 5
10 August 1998
SUPERSEDING
AMENDMENT 4
25 March 1994

MILITARY SPECIFICATION

WARHEAD SECTION, GUIDED MISSILE, PRACTICE, M220, ASSEMBLING AND PACKING

This Amendment forms a part of Military Specification MIL-W-14742A (AR), dated 17 January 1972, and is approved for use by the U.S. Army Armament, Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

2.1: Delete “UU-T-106-Tape, Pressure Sensitive Adhesive Masking, Paper” and substitute “PPP-T-42-Tape, Packaging/Masking Paper.”

2.1: Delete, Specifications, as follows:

“FEDERAL
PPP-T-42 - Tape, Packaging/Marking Paper
UU-T-450 - Tissue, Facial.”
PPP-T-42 - Tape, Packaging/Marking Paper
UU-T-450 - Tissue, Facial.”

PAGE 2

2.1: Delete:

“PICATINNY ARSENAL” and substitute “U.S. ARMY ARMAMENT RESEARCH AND DEVELOPMENT COMMAND (ARRADCOM).”

“Command (ARRADCOM)” and substitute “Center (ARDEC).”

* 2.1: Add A NEW STANDARD as follows:

“AMERICAN SOCIETY OF TESTING AND MATERIALS (ASTM)
ASTM D3359 – Standard Test Method for Measuring Adhesion by Tap test”

AMSMC N/A FSC 1336
DISTRIBTIQN STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T04:39Z
Check the source to verify that this is the current version before use.

3.4: Delete in its entirety.

PAGE 3

* 3.7: Add new paragraph as follows:

" 3.7 Adhesion of paint. - Removal of three (3) or more complete squares of paint constitutes test failure when tested as specified in 4.4.4."

* 3.8: Add new paragraph as follows:

" 3.8 Salt Spray Test.- the paint coating of the warhead assembly shall not exhibit sign of corrosion except adhesion tested area when tested as specified in 4.3.3.1.8 and 4.3.3.2.5."

* 3.9: Add as follows:

"3.9 Protective Coating. - The paint coating shall be a smooth, continuous, adherent film which is free of such surface imperfections as runs, sags, blisters, orange peel, eyes, seediness or pinholes."

PAGE 6

4.3.2.1: Add Major 103 as follows:

"Major 103	AQL 1.0 Percent Improper chamfer	Gage	01006"

4.3.2.1: Delete Minor 202 in its entirety.

4.3.2.1: Add Major 104 as follows:

*

"Major 104	protective coating AQL 0.40 Percent as specified	Visual	01007"

PAGE 7

4.3.2.3: Add Major 307 as follows:

"Major 107	AQL 1.0 Percent True position of holes (4 places)	Gage	- "

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T04:39Z
Check the source to verify that this is the current version before use.

4.3.3.1.6: Delete in its entirety.

4.3.3.2.4: Delete in its entirety.

4.3.3.1.4: change “4.3.3.2.4” to “4.3.3.2.2.”

4.3.3.1.5: change “4.3.3.2.5” to “4.3.3.2.3.”

* 4.3.3.1.7: Add new paragraph as follows:

“ 4.3.3.1.7 Adhesion of paint (see 3.7). Warhead assemblies shall be tested for Adhesion of paint in accordance with 4.4.4 upon the completion of the adhesion test, the same warhead assemblies shall be tested for salt spray in accordance with 4.3.3.1.8.”

* 4.3.3.1.8: Add new paragraph as follows:

“ 4.3.3.1.8, Salt Spray (see Dwg. 9260040 and 3.8). - The same war head assemblies from the adhesion Test, shall be tested for Salt Spray exposure in accordance with drawing 9260040.”

* 4.3.3.2.4: Add new paragraph as follows:

“ 4.3.3.2.4 Adhesion (see 3.7). – Major Defect-Code No. 01008. The warhead assembly shall be tested for adhesion in accordance with 4.4.4 Testing shall be performed on one warhead assembly for each weekly continuous production quantity of no more than one thousand warhead assemblies. Failure to comply will be cause for rejection of the production since the previous test.”

* 4.3.3.2.5: Add new paragraph as follows:

“4.3.3.2.5: Salt Spray Test (see Dwg. 9260040 and 3.8). – Major Defect-Code No. 01009. - The same warhead assembly from the adhesion test, shall be tested for salt spray exposure in accordance with drawing 9260040. Failure to comply will be cause for rejection of the production since the previous test.”

4.4.1, Line 5: Delete “location of countersink (one hole only).”

4.4.3.1, Line 2- Delete “UU-T-106” and substitute “PPP-T-42.11

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T04:39Z
Check the source to verify that this is the current version before use.

PAGES 9 & 10

4.4.3: Delete in its entirety.

4.4.3.1: Delete in its entirety.

4.4.3.2: Delete in its entirety.

4.4.4: Add new paragraph as follows:

" 4.4.4 Adhesion of paint. - Perform adhesion test on each ogive and body of the warhead assembly, in accordance with ASTM D 3359, method B, cross cut tape adhesion, using the 6-line pattern and 2 mm spacing."

PAGE 11

6.3.6, Line 8: Delete "Picatinny Arsenal" and substitute "ARRADCOM."

6.4, Line 4: Delete "Picatinny Arsenal" and substitute "ARRADCOM."

6.4, Line 6: Delete "Picatinny Arsenal, ATTN: SMUPA-N1, ..." and substitute "U.S. Army Research and Development Command, ATTN: DRDAR-QAM-Q."

6.4, Line 6: Delete "(MU)" wherever it appears in the specification and substitute " AR)."

6.3.6, Line 8: Delete "ARRADC6M" and substitute "ARDEC."

6.4, Line 4: Delete "ARRADCOM" and substitute "ARDEC."

Line 6; Delete "U.S. Army Research and Development Command, ATTN: AMSMC-QAM-Q" and substitute "U-S. Army Research and Development Center, ATTN: AMSMC-QAQ-V."

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T04:39Z
Check the source to verify that this is the current version before use.

NOTE: The margins of this amendment are marked with an asterisk or vertical line to indicate where changes (additions, modifications, deletions) from previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document in relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1336-0031)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T04:39Z
Check the source to verify that this is the current version before use.