MIL-W-14743C (PA)
AMENDMENT 7
17 March 1977
SUPERSEDING
AMENDMENT 6
15 October 1976

MILITARY SPECIFICATION

WARHEAD SECTION, GUIDED MISSILE
HE, M207 LESS S&A DEVICE PARTS FOR

This amendment forms a part of MIL-W-14743C (PA) dated 25 October 1974, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 1

*Under para. 2.1 Specification, Military

Add: "MIL-E-45782 - Electrical Wiring, Procedure for".

PAGE 2

Under para. 2.1 Standards Military
add: "MIL-STD-1460 Soldering of Electrical Connections and Printed Wiring Assemblies, Procedure for"

Under Drawings
delete: "Inspection Equipment Drawings
9246410-Fixture, Test to Failure of Ring Retaining"

PAGE 3

Para. 3.8 - delete: paragraph in its entirety.

PAGE 4

add: new para.

"3.11 Dimensional Stability of Ring, Retaining.-The ring, retaining shall not exhibit any deformation when subjected to a temperature conditioning of 200°F plus or minus 50°F for 4 hours, min."

Under para 3.11 - delete: paragraph in its entirety.

*Add: New para. 3.12:

"3.12 Tensile strength of terminal assembly.-The terminal assembly (see Dwg. 9225128) shall meet the requirements of MIL-E-45782 para. 3.4.2.1, when subjected to a tensile strength test as specified in 4.4.7 herein".

FSC:1336

Source: https://assist.dla.mil -- Downloaded: 202610-18T04:40Z
Check the source to verify that this is the current version before use.

PAGE 10

Under para. 4.3.2.7 - Minor
delete: "AQL 0.65 percent" and substitute: "AQL 1.5 percent"

add: "202. Length of black wire, Min Gage
203. Length of brown wire, min Gage"

Para. 4.3.2.9 - delete: paragraph in its entirety.

PAGE 11

Under para. 4.3.2.9 - Majors 101, 102 and 103
add: "(see 3.11)"

add new para. 4.3.3.1.7:
"4.3.3.1.7 Visual Examination of Stripped Wires
(See dwg. 9225128 and 4.3.3.2.7)"

Under para. 4.3.2.9 - Majors 101, 102, and 103 delete: (see 3.11)

Para. 4.3.3.1.6 - delete: paragraph in its entirety.

*Add: New para. 4.3.3.1.8

"4.3.3.1.8 Tensile strength of terminal assembly (See 3.12)-Major Defect.-This test shall be performed on each terminal assembly in accordance with procedure in 4.4.7 using equipment as specified in 4.3.4".

PAGE 12

Para. 4.3.3.2.6 - delete: paragraph in its entirety.

add new para. 4.3.3.2.7:
"4.3.3.2.7 Visual Examination of Stripped Wires (See dwg. 9225128)-Major defect.-This examination shall be performed as specified in MIL-STD-1460."

*Add: New para. 4.3.3.2.8:

"4.3.3.2.8 Tensile strength of terminal assembly (see 3.12)-Major Defect.-The sampling plan for this test shall be in accordance with MIL-STD-105, using inspection Level I with an AQL of 4.0 percent. This test shall be performed in accordance with procedure in 4.4.7 using equipment as specified in 4.3.4".

Source: https://assist.dla.mil -- Downloaded: 202610-18T04:40Z
Check the source to verify that this is the current version before use.

Under para. 4.4.3
delete: "500 volts plus or minus (±) 50 volts" and substitute:
"500 volts plus or minus (±) 50 volts d.c. for two (2) seconds, Min."

Para. 4.4.6 - delete: paragraph in its entirety.

*Add: New para. 4.4.7:

"4.4.7 Tensile strength of terminal assembly.-The terminal assembly shall be subjected to a tensile strength test in accordance with MIL-E-45782, para. 3.4.2.1 and 4.6.2.12, except the speed of the holding head shall not exceed 10 inches per minute. (Destructive test)."

*NOTE: The margins of this amendment are marked with an asterisk to indicate where changes from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army - PA

Preparing Activity:
Army - PA

Project No. 1336-A 278

Source: https://assist.dla.mil -- Downloaded: 202610-18T04:40Z
Check the source to verify that this is the current version before use.