INCH-POUND

A-A-58207
05 July 1994

COMMERCIAL ITEM DESCRIPTION

CROSSARMS, WOOD

The General Services Administration has authorized the use of this commercial item description as a replacement for Military Specification MIL-C-12436, which has been canceled.

1. SCOPE. This commercial item description covers treated and untreated crossarms. The crossarms shall be used for support and to space the wires on wooden telephone and electric poles.

2. SALIENT CHARACTERISTICS:

2.1 Type. The crossarm type/use and the width X depth shall be as specified in the contract or order.

2.2 Classification. Crossarms must be specified as treated or untreated. If treated, the crossarms preservative treatment of either creosote or pentachlorophenol shall be as specified in the contract or order. The retention of the preservative treatment must be specified in pounds per cubic foot in accordance with AWPA Standards C1, C25, or C26.

2.3 Species. The species of wood, Douglas Fir or Dense Southern Pine, for the crossarms must be as specified in the contract or order. Douglas Fir may be furnished in either dense or close grain grade or a mixture of both grades.

2.4 Seasoning. Wood used in the manufacture of the crossarms shall be kiln dried or air dried to a moisture content of 22 percent or less. Moisture content shall be determined prior to treatment.

2.5 Dimensions. The length, boring details, pin hole arrangement, brace bolt hole spacing, and incising shall be as specified in contract or order. Tolerances for these dimensions shall conform to the requirement of ANSI 05.3.

2.6 Edges. The edges shall be rounded or chamfered as specified in ANSI 05.3.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to: WR-ALC/TILCC 255 Second St., Robins AFB, GA 31098-1637

AMSC N/A FSC 5510

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:00Z
Check the source to verify that this is the current version before use.

2.7 Identification marking. Each crossarm shall be marked with typical brand and key information contained in AWPA M6. The information shall be permanently and legibly burn-branded on the crossarm or shall include the information of a recessed noncorrosive metal tag attached thereto. The code letters shall not be less the 1/2 inch high if burn-branded, and not less the 1/8 inch high if on a metal tag; the metal tags shall be attached after treatment, if treated.

ABCO = Supplier's brand
91 = Year of treatment, if applicable
SPC = Species of wood and preservative treatment
8 = Retention pounds per cubic foot

The issues of the ANSI and AWPA standards in effect on the date of the solicitation shall be used to determine compliance with the stated requirement.

3. REGULATORY REQUIREMENTS.

3.1 Recovered materials. The offeror/contractor is encouraged to use recovered materials to the maximum extent possible in accordance with paragraph 23.403 of the Federal Acquisition Regulations (FAR).

4. QUALITY ASSURANCE PROVISIONS.

4.1 Contractor Certification. The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards and quality assurance practices. That the product offered is the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance prior to the first delivery and thereafter as may be otherwise provided for under the provisions of the contract or order.

5. PACKAGING REQUIREMENTS.

5.1 Packaging, packing, and marking. The packaging and packing shall be in accordance with normal commercial practice and assure acceptance by common carrier and provide product protection against loss and damage during multiple shipments, handing, and storage. The shipping container shall be in compliance with National Motor Freight Classification and Uniform Freight Classification. Shipping containers shall be marked as specified in the contract or order.

6. NOTES.

6.1 Part Identification Number (PIN). The following part numbering procedure is for Government and does not constitute a requirement for the contractor.

Source: https://assist.dla.mil -- Downloaded: 202610-26T10:00Z
Check the source to verify that this is the currentversion before use.

Example of PIN number: AA58027-1A10-0806

Type:	1	- Type I
	2	- Type II
	3	- Type III
	4	- Type IV
	5	- Type V
	6	- Type VI
	7	- Type VII
Class:	A	- No class identified
	B	- Class 1
	C	- Class 2
Pins:	Number of pins is expressed in numerically (XX)	
Length:	Length is expressed in feet (XX) and inches (XX)	

6.2 Source of documents.

6.2.1 The Federal Acquisition Regulations (FAR) may be obtained from the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

6.2.2 ANSI standards are available from the American National Standards Institute, 1430 Broadway, New York, NY 10018.

6.2.3 AWPA standards are available from the American Wood-Preservers' Association, 1012 14th Street NW, Washington, DC 20005.

MILITARY INTEREST:

Preparing Activity:
Air Force - 84

Custodians:
Air Force - 99
Army - ME
Navy - YD

Project 5510-0320

Review Activity:
Army - CE

CIVIL AGENCY COORDINATING ACTIVITY:
GSA - FSS (7FXE)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:00Z
Check the source to verify that this is the current version before use.