MMM-A-00150B (GSA-FSS)
April 29, 1976
SUPERSEDING
Int. Fed. Spec. MMM-A-00105A(GSA-FSS)
October 5, 1962

INTERIM FEDERAL SPECIFICATION

ADHESIVE FOR ACOUSTICAL MATERIALS

This Interim Federal Specification was developed by the General Services Administration, Federal Supply Service, Washington, DC 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

1. SCOPE

1.1 Scope. This specification covers one type of adhesive for bonding prefabricated acoustical materials to the inside walls and ceilings of rooms in buildings.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

TT-E-485 - Enamel, Semigloss, Rust-inhibiting.
PPP-C-96 - Cans, Metal, 28 Gage and Lighter.
PPP-D-729 - Drums, Shipping and Storage, Steel, 55-Gallon.
PPP-P-704 - Pails, Metal. (Shipping, Steel, 1 through 12-Gallon).

Federal Standards:

Fed. Std. No. 123 - Marking for Shipment (Civil Agencies).

Fed. Test Method Std. No. 141/GEN - Paint, Varnish, Lacquer, and Related Materials, Methods of Inspection, Sampling and Testing.

Fed. Test Method 141/5132 - Chlorinated Compounds (Presence of).

Fed. Test Method 141/7356 - Solvent Content of Enamels and Enamel Thinners (Gas Liquid Chromatography).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

FSC 8040

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM) Standards

C 37 - Gypsum Lath.
D 86 - Distillation of Petroleum Products.
D 897 - Tensile Properties of Adhesive Bonds.
E 104 - Maintaining Constant Relative Humidity by Means of Aqueous Solutions.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Uniform Classification Committee, Agent.

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

National Motor Freight Traffic Association, Inc., Agent.

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

3. REQUIREMENTS

3.1 Material. The adhesive shall consist of a rosin in a volatile solvent, modified to the extent that the requirements of this specification are met.

3.1.1 The manufacturer is given latitude in the selection of solvents or blend of solvents, provided the material meets the requirements specified in 3.1.1.1 and 3.1.1.2.

3.1.1.1 The volatile solvent when tested as specified in 4.4.2 shall contain no benzene or halogenated compounds.

3.1.1.2 The volatile solvent when tested as specified in 4.4.2 shall conform by volume to the requirements controlling the emission of solvents into the atmosphere as called out in (a), (b), (c), (d), and (e).

(a) Total of aldehydes and branched chain ketones: 20 percent maximum.
(b) Total of aromatic compounds with eight or more carbon atoms to the molecule except ethylbenzene. 8 percent maximum.
(c) Total of ethylbenzene and toluene: 20 percent maximum.
(d) Total of solvents with olefinic or cyclo-olefinic unsaturation 5 percent maximum.
(e Total of (a) + (b) + (c) + (d) = 20 percent maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

3.2 Shelf storage life. When the adhesive is stored as specified in 4.4.3, the consistency shall not have changed appreciably from the originally specified consistency (see 3.3), and the adhesive shall meet the requirements of 3.4 and 3.5.

3.3 Consistency. When tested as specified in 4.4.4, the consistency of the adhesive shall be such that it will adhere to the surfaces being bonded, shall spread or be capable of being applied readily, and shall not sag from walls or drop from ceilings.

3.4 Tensile strength.

3.4.1 Before aging. When tested as specified in 4.4.5.1, the tensile strength of the adhesive film before aging shall be not less than 210 grams per square centimeter (3.0 pounds per square inch).

3.4.2 After aging. When tested as specified in 4.4.5.2, the tensile strength of the adhesive film after aging shall be not less than 1054 grams per square centimeter (15.0 pounds per square inch).

3.5 Adhesion. When tested as specified in 4.4.6, none of the adhesion specimens prepared with the adhesive shall fail under the stress conditions specified therein.

3.6 Wetting. The adhesive shall completely wet the surfaces when tested as specified in 4.4.7.

3.7 Shrinkage. The shrinkage in volume shall not exceed 10 percent when tested as specified in 4.4.8.

3.8 Cracking. There shall be no evidence of cracking at the exposed surface or at the interface of the glass plate and the adhesive when tested as specified in 4.4.9. The adhesive shall retain sufficient plasticity to permit indentation by a fingernail.

3.9 Migration or bleeding. The vehicle shall not pass through a medium-texture filter paper when tested as specified in 4.4.10.

3.10 Accelerated aging. When tested as specified in 4.4.11, the adhesive shall not change appreciably in volume and consistency. The adhesive shall not separate in such a manner that it cannot be readily restored by hand mixing.

3.11 Workmanship. The adhesive shall be uniform, even-spreading, and free of dirt, lumps, foreign matter, coarse particles, and all other defects which would adversely affect its usability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 The supplier shall submit in writing to the contracting officer assurance that the adhesive complies with the shelf storage life requirement as specified in 3.2, in lieu of actual testing. The Government reserves the right to test such items to determine the validity of the certificate.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

4.2 Sampling.

4.2.1 Lot. For the purposes of sampling, a lot of the adhesive shall consist of a manufacturer's batch. A batch is defined as the end product of all raw materials mixed, blended, or processed in a single operation.

4.2.2 Sampling for inspection of filled containers. A random sample of filled containers shall be selected in accordance with MIL-STD-105 at inspection level I and acceptable quality level (AQL) = 2.5 percent defective to verify compliance with this specification regarding fill, closure, and marking and other requirements not involving tests.

4.3 Inspection.

4.3.1 Inspection of containers. Each sample filled container shall be examined for defects of construction of the container and the closure, for evidence of leakage, and for unsatisfactory markings, each filled container shall also be gauged to determine the amount of contents. Any container in the sample having one or more defects or under required fill shall be rejected, and if the number of defective containers in any sample exceeds the acceptance number for the appropriate sampling plan of MIL-STD-105, the lot represented by the sample shall be rejected.

4.3.2 Inspection of preparation for delivery requirements. An inspection shall be made to determine that the packaging, packing, and marking comply with the requirements of section 5. Defects shall be scored in accordance with Table I. For examination of interior packaging, the sample unit shall be one shipping container fully prepared for delivery selected at random just prior to the closing operations. Sampling shall be in accordance with MIL-STD-105. Defects of closure listed shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 4.0 defects per hundred units.

TABLE I. Classification of preparation for delivery defects

Examine	Defects
Markings (exterior and interior)	Omitted; improper size, location, sequence, or method of application.
Materials	Any component missing or damaged.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, loose strapping, inadequate stapling. Bulging or distortion of container.

4.3.3 Testing of the end item. The methods of testing specified in 4.4 shall be followed. For purposes of sampling, the lot shall be expressed in units of gallons of adhesive. The sample unit for testing shall be one quart of adhesive, randomly selected from containers in the lot. The adhesive shall be placed in separate clean, dry metal or glass containers, sealed, marked and forwarded to the testing laboratories. The sample size shall be as follows:

Lot size (gallons)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and more	5

Tests shall be performed on a sample unit basis. All test reports shall contain the individual values utilized in expressing the final result. The lot shall be unacceptable if one or more sample unit fails to meet any test requirement specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

4.4 Test procedures.

4.4.1 Standard test conditions. Unless otherwise specified, all test specimens shall be prepared and tested in a room having a temperature of 23 ± 1°C (74 ± 2°F) and a relative humidity of 50 ± 5 percent.

4.4.2 Solvent analysis.

4.4.2.1 Solvent extraction. The solvent from 100 milliliters of the adhesive shall be extracted in accordance with ASTM D 86.

4.4.2.2 Solvent composition. The solvent composition shall be determined in accordance with 4.4.2.2.1, method 7356 of Fed. Test Method Std. No. 141, 4.4.2.2.2, and 4.4.2.2.3 to determine compliance with the requirement of 3.1.1.

4.4.2.2.1 Aromatic and oxygenated solvents. The 1.83m (6 ft.) column shall be installed and the operating conditions described in method 7356 shall be followed. About 3 microliters of the isolated distillate shall be injected and the chromatogram scanned. The aliphatic solvents will emerge within 1 minute and the complete chromatogram should develop in about 5 minutes. From the position of the peaks observed on the chromatogram, an internal standard that will be free of interference shall be selected, such as cyclopentanol or cyclohexanol. Six-tenths of a milliliter of internal standard shall be added to 3 milliliters of the distillate. The sample shall be analyzed according to the above procedure. Peaks emerging after 1 minute are aromatic solvents along with any oxygenated solvents that may be present. The percent of aromatic and oxygenated solvents shall be calculated as follows:

$$\text{percent aromatic and oxygenated solvents, v/v} = \frac{A \times B}{C \times D}$$

Where, A = percent of internal standard added (in this case, 20).
B = area of aromatic and oxygenated solvents.
C = Calibration factor for the internal standard. This factor is dependent on the internal standard used and on the performance of the chromatograph, and should be determined daily.
D = Area of the internal standard (in this case cyclopentanol or cyclohexanol).

4.4.2.2.2 Halogenated compounds. The presence of halogenated compounds shall be determined in accordance with method 5132 of Fed. Test Method Std. No. 141.

4.4.2.2.3 Benzene. When the solvent is tested in accordance with 4.4.2.2.1, a trace benzene peak of not more than 2 percent of the toluene peak will be allowed.

4.4.3 Shelf storage life. A one gallon quantity of adhesive shall be stored in the original unopened container or containers for 18 months from the date of manufacture at standard conditions (see 4.4.1) and then shall be tested to determine compliance with the requirements of 3.2.

4.4.4 Consistency. The consistency of the adhesive shall be determined by applying the adhesive in a film thickness of approximately 9.6 mm (3/8 in) to 30.5 cm (12 in) square plywood and gypsum board surfaces, two each, with hand tools and then applying one each of the coated surfaces to a wall and the remaining surfaces to a ceiling to determine compliance with the requirements of 3.3.

4.4.5 Tensile strength.

4.4.5.1 Before aging. The tensile strength of the adhesive film before aging shall be determined in accordance with ASTM D 897 to determine compliance with the requirement of 3.4.1. Only the metal test specimens shall be used. The testing machine shall be set at a full scale of 9.07 kg (20 lb) and a crosshead speed of 1.3 mm (0.05 in) per minute. The adhesive shall be applied to the metal specimen at a film thickness of 1.6 mm (1/16 in) and the bond shall be tested within five minutes of assembly. Ten metal-to-metal specimens shall be tested for each sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

4.4.5.2 After aging. The tensile strength of the adhesive film after aging, shall be determined in accordance with 4.4.5.1, except that the specimens shall be aged at standard conditions (see 4.4.1) for 168 hours after assembly and before testing.

4.4.6 Adhesion. The adhesion of the adhesive shall be determined by means of subjecting bonded specimens to dead-weight loads under specified temperatures and relative humidities. The adherends shall be 6.98 ± 0.08 cm (2-3/4 ± 1/32 in) disks of gypsum lath 9 6 mm (3/8 in) thick, conforming to ASTM C 37. The specimen shall be prepared at standard conditions (see 4.4.1) by applying the adhesive to one gypsum lath disk and pressing it against the other disk until the adhesive thickness specified in Table II is obtained. A hook, cup, or similar device shall be attached to each face of the bonded specimen, the top device to suspend the specimen and the lower one from which to hang the weight. Specimens shall be subjected within 5 minutes after preparation to the tests listed in Table II Each of the tests shall be run in triplicate to determine compliance with the requirement of 3.5.

TABLE II - Adhesion Test Requirements

Test	Adhesive Thickness, mm	(in)	Temperature, degrees Centigrade	Relative Humidity, percent a/	Load, kg	(lb)	Duration, hours
1	4.8	(3/16)	21 to 27	50 ± 5	1.02	(2-1/4)	72
2	4.8	(3/16)	21 to 27	80 to 85	1.02	(2-1/4)	72
3	4.8	(3/16)	21 to 27	50 ± 5	0		24
4	4.8	(3/16)	49	10	0.79	(1-3/4)	72
5	9.6	(3/8)	21 to 27	50 ± 5	0.79	(1-1/4)	72
6	9.6	(3/8)	21 to 27	80 to 85	0.79	(1-1/4)	72
7	9.6	(3/8)	21 to 27	50 ± 5	0		24
8	9.6	(3/8)	49	10	0.34	(3/4)	72

a/ Saturated salt solutions for maintaining constant relative humidity are given in ASTM E 104.

4.4.7 Wetting. A fresh portion of the adhesive approximately one inch thick at a temperature of 20 to 30°C (68 to 86°F) shall be placed on clean surfaces of plywood and of gypsum board. The adhesive shall be immediately pressed with a flat hand tool such as a trowel or putty knife to a thickness of about 6.4 mm (1/4 in). Immediately thereafter, the hand tool shall be withdrawn without sliding. On withdrawal, the area that was covered by the adhesive shall be completely coated with the adhesive to be in compliance with the requirement of 3.6.

4.4.8 Shrinkage.

4.4.8.1 Equipment.

a. A piece of thin nylon string approximately 15 cm (6 in) long.
b. A brass ring 7.0 cm (2-3/4 in) inside diameter and 4.8 mm (3/16 in) thickness.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

c. Two sheets of thin polytetrafluoroethylene (Teflon or equal) at least 10.2 cm (4 in) square.
d. A block of solid carbon dioxide or a cold box set to maintain a temperature of between -90 and -80°C (-130 and -112°F).
e. A spatula.
f. A glass plate at least four inches square.
g. An arm balance.
h. 500 ml of 1% by weight aqueous alkyl aryl sulfonate wetting agent[1/] in a tightly closed bottle.
i. A liter beaker.
j. An oven set to maintain a temperature of 49 ± 2°C (120 ± 4°F).

4.4.8.2 Procedure. One end of the string shall be tied around the ring through the hole. The ring shall be placed horizontally on one of the sheets of Teflon which in turn shall be placed on the block of solid carbon dioxide or in the cold box. A sufficient amount of the adhesive to fill the hole shall be placed in the ring with the spatula. The other Teflon sheet shall be placed over the adhesive and ring. The glass plate shall be placed on the Teflon sheet and pressed downward until the top Teflon sheet is flat against the ring, in order for the adhesive to completely fill the hole. The glass plate shall be removed. When the adhesive has sufficiently solidified, the Teflon sheets shall be removed. The ring shall be placed in a vertical position by means of the string for 24 hours at standard conditions (see 4.4.1). The pan shall be removed from the balance, and the string shall be attached to the balance arm so that the ring hangs freely. The weight of the ring in air (W1) shall be determined. All weights shall be accurate to the nearest hundredth of a gram. The wetting agent solution shall be equilibrated at standard conditions (see 4.4.1) and poured into the beaker. The ring, still attached to the balance arm shall be placed into the solution so that the ring is completely submerged and is not touching the bottom or sides of the beaker. The weight of the ring in solution (W2) shall be determined. The ring shall be removed from the balance and beaker. The solution shall be returned to its bottle, and the bottle shall be tightly closed. The ring shall be placed vertically in the oven and conditioned for 30 days. During the first 14 days, the ring shall be rotated daily 90° about its axis. After 30 days, the ring shall be removed from the oven and equilibrated vertically at standard conditions (see 4.4.1). The weight of the conditioned ring in air (W3) and in solution (W4) shall be determined as described above for W1 and W2, respectively. The ring shall be thoroughly cleaned and dried, and the weight of the empty ring in air (W5) and in solution (W6) shall be determined as described above for W1 and W2, respectively. The percent shrinkage shall be calculated as follows:

$$S = \frac{W1 - W2 - W3 + W4}{W1 - W2 - W5 + W6} \times 100$$

Where: S = percent shrinkage.
W1 = weight of ring and adhesive suspended in air after 24 hours at standard conditions.
W2 = weight of ring and adhesive suspended in solution after 24 hours at standard conditions.
W3 = weight of ring and adhesive suspended in air after 30 days at 49 ± 2°C (120 ± 4°F).
W4 = weight of ring and adhesive suspended in solution after 30 days at 49 ± 2°C (120 ± 4°F).
W5 = weight of ring only suspended in air.
W6 = weight of ring only suspended in solution.

4.4.9 Cracking. A 3.2 mm (1/8 in) thick layer of adhesive shall be spread over one entire surface of a glass plate, 10.2 cm (4 in) square. The plate with the adhesive shall be immediately placed in an oven at 49 ± 2°C (120 ± 4°F) for a period of 7 days. After having been equilibrated at standard conditions (see 4.4.1), the specimen shall be examined to determine compliance with the requirement of 3.8.

1/ Santomerse S made by Monsanto Chemical Company is an example.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

4.4.10 Migration or bleeding. Ten plus or minus 0.1 g of the adhesive shall be placed between two pieces of medium texture filter paper. The specimen shall be pressed between flat plates to a thickness of 4.8 cm (3/16 in), removed from between the plates, and placed on a flat glass plate. The glass plate with the specimen shall be placed in an oven at 49 ± 2°C (120 ± 4°F) for 28 days. At the end of the 28-day period, the glass surface and the outer surfaces of the filter paper shall be examined for indication of passage of the adhesive through the filter paper to determine compliance with the requirement of 3.9.

4.4.11 Accelerated aging. A wide-mouth, 1-pint container of aluminum or steel shall be filled with adhesive. The container shall be closed securely and stored for 15 days at 60 ± 1°C (140 ± 2°F). The container of adhesive shall then be stored at standard conditions (see 4.4.1) for 24 hours. The consistency of the adhesive shall be determined in accordance with 4.4.4 to determine compliance with the requirement of 3.10. The test specimen shall be examined for separation and ability to be reconstituted by hand mixing.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Adhesive shall be packaged level A, B, or C, as specified in the contract or order (see 6.2).

5.1.1 Level A.

5.1.1.1 Cans. Quantities of one gallon or less shall be packaged in round cans conforming to type V, class 2 of PPP-C-96. Exterior plan B coating and side seam stripping shall be required. Containers of one half gallon capacity and above shall be provided with wire handles which shall be galvanized or otherwise protectively coated to resist corrosion.

5.1.1.2 Pails. Quantities of five gallons shall be packaged in pails conforming to type II, class 3, or type III, class 3 of PPP-P-704. Exterior coating of pails shall be required and conform to TT-E-485. Wire handles or bails shall be required. Wire handles or bails shall be galvanized or otherwise protectively coated to resist corrosion.

5.1.1.3 Drums. Quantities of fifty-five gallons shall be packaged in drums conforming to type III of PPP-D-729. Exterior coating of drums shall be required and shall conform to TT-E-485.

5.1.2 Level B.

5.1.2.1 Cans. Quantities of one gallon or less shall be packaged in round cans conforming to type V, class 2 of PPP-C-96. The cans shall have exterior coating plan A. Containers of one half gallon capacity and above shall be provided with wire handles as specified in 5.1.1.1.

5.1.2.2 Pails and drums. Quantities of five gallons in pails and 55 gallons in drums shall be furnished as specified in 5.1.1.2 and 5.1.1.3, respectively.

5.1.3 Level C. Adhesive in the quantities as specified (see 6.2) shall be packaged in accordance with the manufacturer's commercial practice, providing that this insures protection for the adhesive during shipment and provide for safe delivery to its destination.

5.2 Packing.

5.2.1 Levels A and B.

5.2.1.1 Cans. Adhesive furnished in quantities of one gallon or less, packaged as specified (see 6.2), shall be packed as specified (see 6.2) in accordance with the appendix of PPP-C-96.

5.2.1.2 Pails and drums. Adhesive furnished in 5-gallon pails and 55-gallon drums shall require no additional packing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

5.2.2 Level C. Adhesive, packaged as specified (see 6.2), shall be packed in containers that will assure carrier acceptance and safe delivery at destination in compliance with the Uniform Freight Classification or National Motor Freight Classification, as applicable.

5.3 Marking.

5.3.1 Civil agencies. In addition to any special marking required by the contract or order, marking of shipping containers shall be in accordance with Fed. Std. No. 123.

5.3.2 Military agencies. In addition to any special marking required by the contract or order, marking of shipping containers shall be in accordance with MIL-STD-129.

5.3.3 Special marking. In addition to markings specified in 5.3.1 or 5.3.2 as applicable, information shall appear on each unit container and shipping container as follows:

(a) Manufacturers instructions for use (to include thinning directions if applicable).
(b) Date of manufacture (by month and year, not by code).
(c) Date of first reinspection (18 months from date of manufacture).
(d) Flash point in degrees Centigrade and degrees Fahrenheit.
(e) Any special directions for storage or use of the adhesive.

6. NOTES

6.1 Intended use. The adhesive covered by this specification is intended for bonding prefabricated acoustical materials to inside wall and ceilings. This adhesive is not recommended as the sole means for holding acoustical materials weighing more than 2-1/2 pounds per square foot to ceiling surfaces.

6.2 Ordering data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Size and type of container required (see 5.1).
(c) Quantity required.
(d) Level of packaging and packing required (see 5.1 and 5.2).
(e) Special marking required (see 5.3).

Preparing activity:

GSA - FSS

GSA DF 76 9362

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.