MMM-A-185B
November 4, 1974
SUPERSEDING
Int Fed Spec MMM-A-00185A
November 10, 1964 and
Fed Spec ZZ-C-191A(In Part)
August 22, 1938

FEDERAL SPECIFICATION

ADHESIVE, RUBBER (FOR PAPER BONDING)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1 SCOPE

1 1 This specification covers one type of rubber adhesive, commonly known as rubber cement, suitable for mounting photographic prints, maps, drawings and charts and for general paper-to-paper bonding

2 APPLICABLE DOCUMENTS

2 1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein

Federal Specifications:

UU-P-465 - Paper, Book
PPP-B-566 - Boxes, Folding, Paperboard
PPP-B-585 - Boxes, Wood, Wirebound
PPP-B-591 - Boxes, Shipping, Fiberboard, Wood-Cleated
PPP-B-601 - Boxes, Wood, Cleated-Plywood
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner
PPP-B-636 - Box, Shipping, Fiberboard
PPP-B-640 - Boxes, Fiberboard, Corrugated, Triple-Wall
PPP-B-665 - Boxes, Paperboard, Metal Edged and Components
PPP-B-676 - Boxes, Setup
PPP-C-96 - Cans, Metal, 28 Gage and Lighter
PPP-D-729 - Drums, Shipping and Storage, Steel, 55-Gallon
PPP-D-732 - Drums, Metal, 55-Gallon Reconditioned (For Shipment of Non-corrosive Material)
PPP-F-320 - Fiberboard, Corrugated and Solid, Sheet Stock (Container Grade), and Cut Shapes
PPP-P-704 - Pails, Metal (Shipping, Steel, 1 through 12 Gallon)

Federal Standards

Fed Std No 123 - Marking for Domestic Shipment (Civil Agencies)
Fed Test Method Std No 141/GEN - Paint, Varnish, Lacquer, and Related Materials, Methods of Inspection, Sampling, and Testing
Fed Test Method Std No 141/5132 - Chlorinated Compounds (Presence of)
Fed Test Method Std No 141/7356 - Solvent Content of Enamels and Enamel Thinners (Gas Liquid Chromatography)

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index The Index, which includes cumulative monthly supplements as issued is for sale on a subscription basis by the Superintendent of Documents, U S Government Printing Office, Washington, DC 20402

(Single copies of this specification and other Federal specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies)

FSC 8040

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

Military Standards

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM) Standards

D 56 - Flash Point by Tag Closed Tester
D 86 - Distillation of Petroleum Products
D 297 - Chemical Analysis of Rubber Products
D 1084 - Viscosity of Adhesives

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Uniform Classification Committee, Agent

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

National Motor Freight Traffic Association, Incorporated, Agent

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Materials. The adhesive shall be a crepe natural rubber or synthetic rubber base material, modified to the extent that the requirements of this specification are met (see 4.1.1).

3.1.1 The manufacturer is given latitude in the selection of solvents or blend of solvents provided the material meets the requirements specified in 3.1.1.1 and 3.1.1.2.

3.1.1.1 The solvent system when tested as specified in 4.4.2 shall contain no benzene (benzol) or halogenated compounds (see 4.3.3).

3.1.1.2 The solvent system when tested as specified in 4.4.2 shall conform by volume to the requirements controlling the emission of solvents into the atmosphere as called out in (a), (b), (c), (d), and (e) (see 4.3.3).

(a) A combination of hydrocarbons having branched chain structures, alcohols, aldehydes, esters, or ethers. 5 percent maximum.
(b) A combination of aromatic compounds with eight or more carbon atoms to the molecule except ethylbenzene. 8 percent maximum.
(c) A combination of ethylbenzene or toluene. 20 percent maximum.
(d) Total of (a) + (b) + (c) = 20 percent maximum.
(e) A combination of ketones and solvents with an olefinic or cyclo-olefinic type of unsaturation. trace.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

3.2 Nonvolatile content. When tested as specified in 4.4.3, the total nonvolatile content of the adhesive shall be not less than 12 percent (see 4.3.3).

3.3 Acetone extract of nonvolatile components. When tested as specified in 4.4.4, the acetone extract of the nonvolatile components shall be not more than 1.4 percent by weight of the adhesive (see 4.3.3).

3.4 Ash content. When tested as specified in 4.4.5, the ash content shall be not more than 0.5 percent by weight of the total adhesive (see 4.3.3).

3.5 Viscosity. The viscosity of the adhesive shall be not less than 2800 nor more than 400 cps when tested as specified in 4.4.6 (see 4.3.3).

3.6 Color. The adhesive, in bulk, shall be a colorless, transparent or translucent liquid, and the dried film of adhesive shall be colorless when tested as specified in 4.4.8 (see 4.3.3).

3.7 Discoloration of paper. When tested as specified in 4.4.9, the adhesive shall not discolor or stain the paper (see 4.4.7 and 4.3.3).

3.8 Adhesion strength. When tested as specified in 4.4.10, the adhesion strength of the adhesive shall be not less than 165 grams (see 4.3.3).

3.9 Wrinkle, curl, and shrink properties. No wrinkle, curl, or shrink shall occur when the adhesive, tested as specified in 4.4.11, is applied to paper. The paper shall remain flat and smooth during and after the drying period (see 4.3.3).

3.10 Shelf storage life. When stored as specified in 4.4.12, the adhesive shall meet the requirements of 3.5, 3.6, 3.7, 3.8, and 3.9 except that the viscosity shall not have changed more than 10 percent plus or minus from the originally specified viscosity (see 3.5 and 4.3.3).

3.11 Flash point. The flash point of the adhesive shall be not less than 22°C (71.6°F) when tested as specified in 4.4.13 (see 4.3.3).

3.12 Workmanship. The adhesive shall be uniform, even-spreading, and free of dirt, lumps, foreign matter, coarse particles, and all other defects which would adversely affect its usability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 The supplier shall submit to the contracting officer a certificate of compliance indicating that the adhesive is composed of crepe natural or synthetic rubber as specified in 3.1 and that the adhesive complies with the shelf storage life requirement as specified in 3.10. When certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certificate.

4.2 Sampling.

4.2.1 Lot. For the purposes of sampling, a lot of the adhesive shall consist of a manufacturer's batch. A batch is defined as the end product of all raw materials mixed, blended, or processed in a single operation.

4.2.2 Sampling for inspection of filled containers. A random sample of filled containers shall be selected in accordance with MIL-STD-105 at inspection level I and acceptable quality level (AQL) = 2.5 percent defective to verify compliance with this specification regarding fill, closure, and marking and other requirements not involving tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

4 3 Inspection

4 3.1 Inspection of containers Each sample filled container shall be examined for defects of construction of the container and the closure, for evidence of leakage, and for unsatisfactory markings, each filled container shall also be gaged to determine the amount to contents Any container in the sample having one or more defects or under required fill shall be rejected, and if the number of defective containers in any sample exceeds the acceptance number for the appropriate sampling plan of MIL-STD-105, the lot represented by the sample shall be rejected

4 3.2 Inspection of preparation for delivery requirements An inspection shall be made to determine that the packaging, packing, and marking comply with the requirements of section 5 Defects shall be scored in accordance with table I For examination of interior packaging the sample unit shall be one shipping container fully prepared for delivery selected at random just prior to the closing operations Sampling shall be in accordance with MIL-STD-105 Defects of closure listed shall be examined for on shipping containers fully prepared for delivery The lot size shall be the number of shipping containers in the end item inspection lot The inspection level shall be S-2 and the AQL shall be 4 0 defects per hundred units

TABLE I Classification of preparation for delivery defects

Examine	Defects
Markings (exterior and interior)	Omitted, improper size, location, sequence or method of application
Materials	Any component missing or damaged
Workmanship	Inadequate application of components such as incomplete closure of container flaps, loose strapping, inadequate stapling. Bulging or distortion of container

4 3 3 Testing of the end item The methods of testing specified in 4 4 shall be followed For purposes of sampling, the lot shall be expressed in units of gallons of adhesive The sample unit for testing shall be one quart of adhesive, randomly selected from containers in the lot The adhesive shall be placed in separate clean, dry metal or glass containers, sealed, marked and forwarded to the testing laboratories The sample size shall be as follows

Lot size (gallons)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and more	5

Tests shall be performed on a sample unit basis All test reports shall contain the individual values utilized in expressing the final result The lot shall be unacceptable if one or more sample unit fails to meet any test requirement specified

4 4 Test procedures.

4 4 1 Standard test conditions Unless otherwise specified, all test specimens shall be prepared and tested in a room having a temperature of 77 5° ± 2°F (23 1° ± 1 1°C) and a relative humidity of 50 ± 5 percent

4 4 2 Solvent analysis

4 4 2 1 Solvent extraction The solvent shall be distilled from 100 milliliters of the adhesive according to ASTM D 86

4 4 2 2 Solvent composition The solvent composition shall be determined in accordance with 4 4 2.2 1, method 7356 of Fed Test Method Std No 141, 4 4 2 2 2, 4 4 2 2 3, and 4 4.2 2 3 to determine compliance with the requirement of 3 : 1

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:47Z
Check the source to verify that this is the current version before use.

4 4.2 2 1 Aromatic and oxygenated solvents The 6-ft column shall be installed and the operating conditions shall be followed as described in method 7356 About 3 microliters of the isolated distillate shall be injected and the chromatogram scanned The aliphatic solvents will emerge within 1 minute and the complete chromatogram should develop in about 5 minutes From the position of the peaks observed on the chromatogram, an internal standard that will be free of interference shall be selected, such as cyclopentanol or cyclohexanol Six-tenths of a milliliter of internal standard shall be added to 3 milliliters of the distillate The sample shall be analyzed according to the above procedure Peaks emerging after 1 minute are aromatic solvents along with any oxygenated solvents that may be present The percent of aromatic and oxygenated solvents shall be calculated as follows

$$\% \text{ aromatic and oxygenated solvents, v/v} = \frac{20^{*} \times A}{1\ 02^{**} \times B}$$

Where A = area of aromatic and oxygenated solvents
B = area of internal standard
* = is percent of internal standard added
** = is correction factor if cyclopentanol is used If another internal standard is used, calibrate to determine the correction factor

NOTE If the above determination exceeds 8 percent, proceed with method 7356

4 4.2 2.2 Ketones.

4 4 2 2 2 1 Reagent Two grams of 2,4-dinitrophenylhydrazine+ 4 milliliters of concentrated sulfuric acid + 30 milliliters of methanol (slowly added) + 10 milliliters of water

4 4 2 2.2 2 Procedure One milliliter of reagent shall be pipetted into a 20 x 170 mm test tube Ten drops of distillate shall be added and the test tube shaken for 30 seconds A yellow precipitate or cloud in the reagent layer indicates the presence of ketones A blank shall be run using one milliliter of reagent and 10 drops of mineral spirits

4 4 2 2 3 Halogenated compounds The presence of halogenated compounds shall be determined in accordance with method 5132 of Fed Test Method Std No 141

4 4 2 2 4 Benzene When the solvent is tested in accordance with 4 4 2 2 1, a trace benzene peak of not more than 2 percent of the toluene peak will be allowed

4 4 3 Nonvolatile content A 150-ml capacity, high-form porcelain crucible 1 25 inches deep shall be heated for 1 hour at 100° ± 5°C (212° ± 9°F) then cooled in a desiccator, and weighed All weighings shall be to the nearest hundredth of a gram Approximately 10 g of the sample shall be placed in the prepared crucible, the crucible immediately covered and weighed The cover shall be removed, and the crucible placed on a steam bath until most of the solvent has evaporated (Caution Care should be taken to remove as much of the solvent as is practicable by this method in order to eliminate any fire hazard which might otherwise exist when the material is subjected to the subsequent drying operation) The crucible and contents shall then be placed in an oven at 100° ± 5°C (212° ± 9°F) heated for 5 hours, and the original cover replaced The crucible contents and cover shall then be cooled in a desiccator and weighed The heating and weighing procedure shall be continued by heating periods of 1/2 hour at 100° ± 5° (212° ± 9°F) until the loss in weight is less than 0 05 g The percentage of nonvolatile matter shall be calculated by the following equation to determine compliance with the requirements in 3 2

$$\text{Percent of nonvolatile matter} = \frac{a \times 100}{b}$$

Where a = weight of sample after heating
b = weight of sample for determination

4 4 4 Acetone extract of nonvolatile components The solvent shall be evaporated from approximately 50 grams of adhesive, weighed to the nearest hundredth of a gram The residue shall be used to determine the amount of acetone extract in accordance with ASTM D 297 The percent of acetone extract shall be calculated on the basis of the total adhesive by weight to determine compliance with the requirement of 3 3

4 4 5 Ash content The test specimen shall be that which was prepared in 4 4 3 The crucible and contents shall be ignited to constant weight in a muffle furnace at 1500° ± 45°F (816° ± 25°C) The ash content shall be calculated by means of the following equation to determine compliance with the requirement of 3 4

$$\text{Percent ash} = \frac{a \times 100}{b}$$

Where a = weight of ash
b = weight of sample adhesive from 4 4 3

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:47Z
Check the source to verify that this is the current version before use.

4 4 6 Viscosity The viscosity shall be determined in accordance with method B of ASTM D 1084 to determine compliance with the requirement of 3 5 A Brookfield Syncro-Lectric viscosimeter, or equal, equipped with a No 2 spindle and operated at 4 r p m shall be used

4 4 7 Paper used in test procedures When paper is to be used in test procedures of this specification, that paper shall be in accordance with UU-P-465, type I - litho, coated

4 4 8 Color A thin film of the adhesive shall be brushed onto the paper (see 4 4 7) and allowed to dry The wet film, immediately upon application to the paper, and the dry film shall be examined for the presence or absence of color to determine compliance with the requirement of 3 6

4 4 9 Discoloration of paper The adhesive shall be applied in approximately a one inch circle in the center of the sheet of paper (see 4 4 7) When the wet film has dried, the residual adhesive shall be rubbed off with the finger tips or a clean cloth The paper beneath the applied area shall be examined for any discoloration or stains to determine compliance with the requirement of 3 7

4 4 10 Adhesion strength A 5 cm by 28 cm wet film of the adhesive shall be cast evenly onto one-half of each of 2 sheets of paper (see 4 4 7) using a doctor blade having a gap of 0 002 inch The wet film shall be allowed to dry for 20 minutes, and then the two adhesive-coated surfaces shall be pressed together so as to prevent the formation of air pockets The bonds shall be allowed to stand for 2 hours The cemented sheets of paper shall be cut into strips of 15 mm wide and 28 cm. long The free ends of the strip shall be fastened in the jaws of a testing machine equipped with an automatic recording device The jaw through which the load is applied shall be moved at a uniform rate of 12 inches per minute The tension required to separate the cemented portion shall be recorded automatically and compared to a 165 gram base line All curves with large sudden variations shall be discarded On a normal curve, both ends shall be neglected and only the central portion used in the calculations An adhesive shall be considered to have met the requirement of 3 8 if 50 percent by separation distance of each curve is above the 165 gram base line

4 4 11 Wrinkle, curl, and shrink properties An even film of the adhesive shall be applied by brush to an area approximately 2-1/2 by 3-1/2 inches in the center of a 3- by 4-inch sheet of paper (see 4 4 7) The cemented area shall not include the edge of the paper During the application and during and after the drying process, the paper shall be examined for wrinkle, curl, and shrink to determine compliance with the requirement of 3 9

4 4 12 Shelf storage life A one pint container, or an equivalent amount of smaller size containers of the adhesive shall be stored in the original unopened containers or containers for 18 months from the date of manufacture at standard conditions (see 4 4 1) and then shall be tested to determine compliance with the requirement of 3 10

4 4 13 Flash point The flash point shall be determined in accordance with ASTM D 56 to determine compliance with the requirement of 3 11

5 PREPARATION FOR DELIVERY

5 1 Packaging Packaging shall be level A, B, or C as specified (see 6 2)

5 1 1 Level A The adhesive furnished in quantities as specified (see 6 2) shall be packaged in containers in accordance with table II and as specified herein

TABLE II

Packaging				Packing
Unit Container		Intermediate Container		
Quantity	Container	Quantity	Container	Quantity
1 Oz	Tube (see 5 1 1 1 1)	48	(see 5 1.1 2)	144
2 oz	Tube (see 5 1 1.1 1)	48	(see 5 1.1 2)	144
4 oz	Jar (see 5 1 1 1 2)	12	(see 5 1 1 2)	72
1/2 pt	Can (see 5 1 1 1 3)			72
1 pt	Can (see 5 1 1 1 3)			24
	Jar (see 5 1 1 1 2)			24
1 qt	Can (see 5.1 1.1 3)			24
1 gal	Can (see 5 1 1 1 3)			6
5 gal	Pail (see 5 1 1 1 4)			None
55 gal	Drum (see 5 1 1 1 5)			None

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:47Z
Check the source to verify that this is the currentversion before use.

5 1 1 Unit containers

5 1 1 1 Collapsible tubes The collapsible metal tubes shall consist of a seamless, cylindrical body (wall) with integral shoulder and threaded neck Tubes shall be fabricated of tin, tin-copper alloy, tin-lead alloy, or aluminum and shall have suitable flexible characteristics and an opening which shall permit ready dispensing of the material Tube wall shall be of uniform thickness and may be treated with an interior protective coating An inner seal in the form of a disk shall be adhered completely to the mouth of the tube The tubes shall be provided with a screw cap to protect the contents once the seal is punctured

5.1 1 1.2 Glass jar The jar shall consist of an amber color glass body, provided with a metal screw cap closure and brush applicator The brush shall consist of sterilized bristles or horsehair mounted with a metal or plastic handle The brush shall be an integral part of the screw cap with not more than 1/8 inch clearance from the bottom of the jar when the cap is tightly in place

5 1 1 1 3 Metal cans Metal cans shall conform to PPP-C-96, type V, class 4, oblong

5 1 1 1 4 Pails Pails shall conform to PPP-P-704, type I, class 3, 4, or 5 with pouring device

5 1 1 1 5 Drums Drums shall conform to PPP-D-729, type I, or PPP-D-732, type I

5 1 1 2 Intermediate containers Filled metal cans shall be intermediate packaged in accordance with the appendix to PPP-C-96 Other unit containers shall be intermediate packaged in paperboard boxes conforming to PPP-B-566, PPP-B-665 or PPP-B-676 which shall be provided with paperboard partitions to individually contain the unit packages

5 1 2 Level B The adhesive shall be packaged as specified in table II and 5 1 1 except that commercial type exterior coating shall be utilized for drums

5 1 3 Level C The adhesive shall be packaged in accordance with the manufacturer's standard practice, providing that this insures protection for the adhesive during shipment and provides for safe delivery to its destination

5 2 Packing Packing shall be level A, B, or C as specified (see 6 2)

5 2 1 Level A The adhesive, furnished in quantities as specified in table II, shall be packed in a close-fitting fiberboard box conforming to PPP-B-636, class weather-resistant The box shall be closed and reinforced in accordance with the appendix to the box specification

5.2 1 1 Overpacking When specified (see 6 2), the fiberboard boxes shall be overpacked in close-fitting boxes conforming to PPP-B-585, class 3, PPP-B-591, class 1, PPP-B-601, overseas type, PPP-B-621, class 2, or PPP-B-640, class weather-resistant The boxes shall be closed and reinforced in accordance with the applicable specification or appendix thereto The gross weight shall not exceed 200 pounds

5 2 2 Level B The adhesive, furnished in quantities as specified in table II, shall be packed in a close-fitting fiberboard box conforming to PPP-B-636, class domestic The box shall be closed in accordance with the appendix to the box specification

5 2 3 Level C The adhesive, packaged as specified in 5 1 3, shall be packed in containers that will assure carrier acceptance and safe arrival at destination in compliance with the Uniform Freight Classification rules and the National Motor Freight Classification rules When fiberboard boxes are used, the fiberboard from which they are fabricated shall conform to PPP-F-320

5 3 Marking Marking shall be in accordance with 5 3 1 or 5 3 2, and 5 3 3 as specified (see 6 2)

5 3 1 Civil agencies In addition to any markings required by the contract or order, all interior packages and shipping containers shall be marked in accordance with Fed Std No 123

5 3 2 Military agencies In addition to any markings required by the contract or order, all interior packages and shipping containers shall be marked in accordance with MIL-STD-129

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

5 3 2 Special marking In addition to markings specified in 5 3 1 or 5 3 2 as applicable, information shall appear on each unit container and shipping container as follows

(a) Manufacturers instructions for use (to include thinning directions if applicable)
(b) Date of manufacture (by month and year, not by code)
(c) Date of first reinspection (date 18 months from date of manufacture)
(d) Flash point in degrees centigrade and degrees Fahrenheit

6 NOTES

6 1 Intended use The adhesive covered by this specification is intended for mounting photographic prints, maps, drawings and charts Application to one surface will provide only temporary joining If more permanent joining is desired, both surfaces should be coated liberally with the adhesive, allowed to dry, and then brought together under firm pressure

6 2 Ordering data Purchasers should select the preferred options permitted herein and include the following information in procurement documents

(a) Title, number, and date of this specification
(b) Size and type of container required (see 5 1)
(c) Quantity required
(d) Level of packaging and packing required (see 5 1 and 5 2).
(e) Special marking required (see 5 3)
(f) Whether overpacking is required (see 5 2 1 1)

MILITARY INTERESTS

Custodians

Army-MR
Air Force - 84

Coordinating Activity

Navy-AS

User Activity

Navy-MC

Preparing activity

GSA-FSS

CIVIL AGENCY COORDINATING ACTIVITIES

NASA-JFK
COM-NBS

Orders for this publications are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents See section 2 of this specification to obtain extra copies and other documents referenced herein Price 30 cents each

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.