NNN-J-35B
August 6, 1975
SUPERSEDING
Int. Fed. Spec.
NNN-J-0035a (DSA-DM)
May 31, 1972 and
NNN-J-35 (DSA-DM)
March 12, 1965

FEDERAL SPECIFICATION

JARS, CYLINDRICAL

This specification was approved by the Commissioner, Federal Supply Services, General Services Administration, for use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers two types of cylindrical glass jars used for containing cleaning solutions and for keeping small animals during laboratory procedures.

1.2 Classification.

1.2.1 Types and sizes. Cylindrical glass jars shall be of the following types and sizes as specified (see 6.1):

Type I - Cleaning solution

Size 1 - 3-1/2 gallons (gal.)
Size 2 - 4-1/2 gal.

Type II - Animal

Size 1 - 3/4 gal.
Size 2 - 1-1/4 gal.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

FSC 6640

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

Federal Specification:

PPP-B-585 - Boxes, Wood, Wirebound.
PPP-B-601 - Boxes, Wood, Cleated-Plywood.
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-C-843 - Cushioning, Material, Cellulosic.
PPP-C-850 - Cushioning Material, Polystyrene Expanded, Resilient (for Packaging Uses).

Federal Standard:

Fed. Std. No. 123 - Marking for Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal specification and standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-L-10547 - Liners, Case, and Sheet, Overwrap; Water-Vaporproof or Waterproof, Flexible.

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply.

American Society for Testing and Materials (ASTM) Standards:

C 148 - Polariscopic Examination of Glass Containers.
C 162 - Definition of Terms Relating to Glass and Glass Products.
E 438 - Glass in Laboratory Apparatus.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

3. REQUIREMENTS

3.1 Material. The glass shall conform to Type I, Class A or B of ASTM E 438.

3.2 Construction. The jars shall be cylindrical in shape, and the junction of the sides with the bottom shall be well-rounded. The bottom of the jar shall be flat or slightly concave with the plane of the resting surface perpendicular to the vertical axis of the jar. The jar shall rest evenly on a smooth flat surface. The open end shall be fire-polished or ground and slightly bevelled to prevent chipping.

3.2.1 Capacity and dimensions. The jars shall conform to the requirements of the Table I for the type and size specified.

TABLE I Capacities and dimensions

Type	Size	Capacity (gallons) ± 1/8	Outside diameter (inches)	Overall height (inches)	Sides and base thickness (inches) minimum
I	1	3-1/2	8-3/4 ± 3/16	18 ± 1/8	0.109
I	2	4-1/2	12 ± 3/16	12 ± 1/8	0.187
II	1	3/4	6 ± 1/8	8 ± 1/8	0.109
II	2	1-1/4	8-1/4 ± 1/8	8 ± 1/8	0.109

3.3 Annealing. Ring strain shall be not greater than Temper No. 1 when tested as specified in 4.4.1. Any longitudinal strain, if present, shall be faint and highly diffused.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

3.4 Identification marking. Each jar shall be permanently and legibly marked with the name or registered trademark of the manufacturer.

3.5 Workmanship. Workmanship shall be first class throughout. Jars shall be free from defects which detract from their appearance or may impair their serviceability. Thickness of walls shall be uniform, particularly where base joins sidewalls.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificate of quality. Certificate of quality, supplied by the manufacturer of the glass, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The Certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the NSN, the Item Identification, the name of the material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and Table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

Table II. For examination

	Inspection level	AQL (Percent defective)
For visual examination		
Major defects	II	1.0
Minor defects	II	4.0
For dimensional examination	S-3	2.5

4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and Table III.

Table III. For sampling

Component (unit of product)	Characteristic	Requirement	Test procedure	Inspection level	AQL
Jar	Strain	3.3	4.4.1	S-3	*

* Acceptance number shall be zero.

4.3 Examination. The jars shall be examined to determine compliance with all requirements contained in this specification.

4.3.1 Classification of defects. Examination shall be conducted in accordance with the following classification of defects:

Table IV. Classification of defects

Categories	Defects*
Major	
101	Jar not free of chips, cracks and breaks.
102	Jar not free of checks and open blisters.
103	Jar not firmly stable on smooth flat surface.
104	Junction of sides and bottom not well rounded.
105	Jar not free of sharp edges.
106	Jar not free of deformation.
107	Glass not clear.
108	Thickness not uniform where base joins sidewalls.
Minor	
201	Marking not present, correct, legible or permanent.
202	Jar not free of scratches, bubbles and seeds.
203	Jar not free of stones and striae.
204	Jar not free of grease, oil and foreign matter.

* Examination shall not be restricted to the classified possible defects listed above. Definitions of glass defects shall be in accordance with ASTM C 162.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

4.3.2 Examination for preparation for delivery. An examination shall be made to determine whether the packaging, packing and marking comply with the requirements of Section 5. Defects shall be scored as specified in Table V. Sampling shall be in accordance with MIL-STD-105. The sample unit shall be one container fully prepared for delivery. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 and the acceptable quality level shall be 4.0 percent defective.

Table V. Examination for preparation for delivery

Examination	Defect
Containers	Not as specified.
Quantity	Quantity in interior packages and shipping containers not as specified.
Packaging and packing materials	Any component missing or damaged.
Workmanship	Inadequate application of components, such as incomplete closure of container flaps, tape improperly applied, or containers distorted.
Markings	Omitted, incorrect, illegible, improper size, location, sequence, or method of application.

4.3.3 Examination of closure, waterproofing and banding of containers shall be in accordance with the appendix of the applicable box specification.

4.3.4 Dimensional examination. The jars shall be examined for defects in dimensions. Any dimensions not within the tolerance specified in Table I shall be classified as a defect.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Strain. Jar shall be tested for strain in accordance with method A or B of ASTM C 148.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.1).

5.1.1 Unit of issue. One jar, of the type and size specified, constitutes one unit of issue.

5.1.2 Level A.

5.1.2.1 Unit package. Each jar shall be packaged in a box of appropriate size constructed in accordance with PPP-B-636, type CF, class domestic. Bursting strength of the box shall conform to the special requirements specified in applicable table of PPP-B-636. The box shall contain a minimum of 2 inches of cushioning material on the top, bottom and sides of the jar and form a snug-fitting cell. Cushioning material shall conform to PPP-C-843, type 2; or polystyrene conforming to PPP-C-850. Closure of the box shall be adequate to prevent spilling of contents under normal handling.

5.1.3 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.1).

5.2.1 Level A.

5.2.1.1 Exterior container. One (1) unit (type I) of six (6) units (type II), packaged as specified in 5.1.2.1, shall be packed in an exterior container constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, class weather-resistant, grade V3c. Closure and strapping shall be as specified in the appendix of the applicable box specification. Special requirements of applicable table of PPP-B-636 shall apply for PPP-B-636 box.

5.2.1.2 Case liner. Each Level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes. Fiberboard box shall be waterproof in accordance with 30.4 of PPP-B-636.

5.2.2 Level B.

5.2.2.1 Exterior container. One (1) unit (type I) or six (6) units (type II), packaged as specified in 5.1.2.1, shall be packed in an exterior container constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, class domestic. Closure shall be as specified in the appendix of the applicable box specification. Fiberboard box shall be closed by method II of PPP-B-636. Special requirements of applicable table of PPP-B-636 shall apply for PPP-B-636 box.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

5.2.3 Packing variation permitted. If the required number of units in the entire shipment is less than the number of units specified to be over-packed in an exterior container, such units may be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5.2.4 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Civil agencies. Marking for shipment shall be in accordance with FED-STD-123. The unit container shall be the container specified in 5.1.2.1 or 5.1.3, and the shipping container shall be the box specified in 5.2.1.1, 5.2.2.1, 5.2.3 and 5.2.4.

5.3.2 Military activities.

5.3.2.1 Unit package. Each unit package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown.

5.3.2.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents.

a. Title, number and date of this specification.
b. Type and size required (see 1.2.1).
c. National Stock Number (NSN).
d. Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

6.2 This specification covers the following items as listed in the Federal Supply Catalog:

National Stock No.	Item Identification
6640-00-430-1210	JAR, CYLINDRICAL, LABORATORY, Glass, 1-1/4 gallon
6640-00-430-1230	JAR, CYLINDRICAL, LABORATORY, Glass, 3-1/2 gallons

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
DSA-DM

Project No. 6640-0915

Civil Agency Coordinating Activities:
GSA-FSS
HEW-NIH, HSM
VA-DMS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 35 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:48Z
Check the source to verify that this is the current version before use.