MIL-S-2063H
24 February 1984
SUPERSEDING
MIL-S-2063G
24 March 1977

MILITARY SPECIFICATION

SCARF, NECKWEAR, WOOL

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers the requirements for a knitted wool scarf.

1.2 Classification. The scarfs shall be of one type in the following classes as specified (see 6.2):

Class 1 - Olive Green 208
Class 2 - Gray 1155
Class 4 - Blue 3346

2. APPLICABLE DOCUMENTS

* 2.1 Government documents. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein.

SPECIFICATION

FEDERAL

V-T-276 - Thread, Cotton
UU-P-268 - Paper, Kraft, Wrapping

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research and Development Center, Natick, MA 01760 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8440

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

DDD-L-20 - Label: For Clothing, Equipage and Tentage (General Use)
DDD-T-86 - Tape, Textile; Cotton, General Purpose (Unbleached, Bleached, or Dyed)
PPP-B-636 - Boxes, Shipping, Fiberboard

MILITARY

MIL-C-43665 - Cloth Wool: Mothproofing Treatment of

FEDERAL

FED-STD-191 - Textile Test Methods
FED-STD-751 - Stitches, Seams, and Stitchings

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads

(Copies of documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

OTHER GOVERNMENT DOCUMENTS

Laws and Regulations

U.S. DEPARTMENT OF AGRICULTURE (USDA)

Methods of Test for Grades of Wool Top

(Application for copies should be addressed to the U.S. Department of Agriculture, Agricultural Marketing Service, Washington, DC 20402.)

* 2.2 Other publications. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein.

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

Chromatic Transference Scale

(Application for copies should be addressed to the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

* 2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence.

3. REQUIREMENTS

3.1 Sample.

3.1.1 Guide sample. Samples when furnished, are solely for guidance and information to the contractor (see 6.3). Variation from this document may appear in the sample, in which case this document shall govern.

* 3.1.2 Standard sample. The finished scarf shall match the standard sample for shade and finish appearance and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

3.2 Material.

3.2.1 Wool yarn. The yarn for knitting and for overedging the end of the scarfs shall be a 2-ply, worsted yarn made of fleece or pulled sheep's wool, or a combination of both, not lower in grade than 56's U.S. Standard.

3.2.1.1 Mothproofing. The wool shall be mothproofed in accordance with MIL-C-43665.

3.2.2 Knitted fabric. The fabric for the scarf shall be a flat-jersey knit tube made on a circular machine using two ends of 2-ply worsted yarn (see 3.2.1) in each feed.

3.2.2.1 Finishing. The face (wale side) of the fabric shall have a lightly brushed finish on both sides of scarf.

* 3.2.3 Thread. The cotton thread for seaming and stitching shall conform to type IA3, ticket No. 50, 3 ply of V-T-276. The color of the thread for class 1 scarfs shall be Olive Drab, S-1, C.A. 66022; for class 2 scarfs, the thread shall match shade Gray 1155; for class 4 scarfs, the thread shall match shade Blue 3346. The dyed thread shall show fastness to laundering and light equal to or better than the standard sample when tested as specified in V-T-276. When no standard sample is available, the dyed thread shall show good fastness to laundering and light.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

3.2.4 Tape. The cotton tape for reinforcing the scarf ends shall conform to type I, class 3, 1/4 inch width of DDD-T-86. The color of the tape for class 1 scarfs shall be Olive Drab 7; for class 2 scarfs the tape shall match shade Gray 1155; for class 4 scarfs, the tape shall match shade Blue 3346. The dyed tape shall show fastness to laudering equal to or better than the standard sample when tested as specified in DDD-T-86. When no standard sample is available, the dyed tape shall show good fastness to laundering.

3.3 Color. The color of the scarf shall be as specified (see 1.2).

* 3.3.1 Matching. The color shall match the standard sample under artificial daylight having a color temperature of 7000 ± 500 K and shall be a good approximation to the standard sample under incandescent lamplight at 2850 ± 100 K.

3.3.2 Colorfastness. The dyed scarf shall show fastness to laundering, perspiration, light and crocking equal to or better than the standard sample. When no standard sample is available, the dyed scarf shall show good fastness to laundering, perspiration and light, and shall show an AATCC Chromatic Transference Scale rating for crocking not lower than 3.5. Testing shall be as specified in 4.2.6.

3.4 Shrink resistant treatment. The wool shall be treated for resistance to felting shrinkage in stock, top, yarn or fabric by a controlled oxidation process approved by the contracting activity. The shrink resistant process used shall not be identified by name or trademark, either on the scarf or on the package.

3.4.1 Alkali solubility. The alkali solubility of the shrink resistant treated wool for the finished scarf, in the form in which it has been treated (stock, top, yarn or fabric) shall not be increased by more than 6.0 percent absolute) over the untreated material when tested as specified in 4.2.6.

* 3.5 Label. Each scarf shall have a combination size, identification and instruction label conforming to type VI, class 14 of DDD-L-20. Instructions shall be as follows:

DRY CLEAN
OR
HANDWASH GENTLY
IN LUKEWARM SUDS.
DO NOT TWIST OR
WRING. DRY ON
FLAT SURFACE
AWAY FROM HEAT.
DO NOT TUMBLE DRY.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

3.6 Design. The scarf shall be tubular seamless type with reinforced ends.

3.7 Construction.

3.7.1 Manufacturing operations requirements. The scarfs shall be manufactured in accordance with the operation requirements specified in table I. The contractor is not required to follow the exact sequence of operations.

3.7.2 Stitches, seams and stitchings. Stitches, seams and stitching types specified in table I shall conform to FED-STD-751. Thread breaks shall be backstitched not less than 1/2 inch.

3.7.3 Stitches per inch. The minimum and maximum number of stitches per inch shall be as specified in table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

TABLE I. MANUFACTURING OPERATIONS REQUIREMENTS

NO.		STITCH TYPE	SEAM AND STITCHING TYPE	STITCHES PER INCH	THREAD		
					NEEDLE	BOBBIN/ LOOPER	COVER
1.	Cutting. Cut tubing to the specified scarf length (see table II).						
2.	Reinforce scarf ends. Place single layer of tape around inside of both ends of the scarf with ends of tape overlapped not less than 1/2 inch.						
3.	Overstitching. Overstitch ends of scarf.	504 or 505	SSa-1 SSa-1	12-16 12-16	50-3 Knit-ing yarns	Knit-ting yarns Knit-ting yarns	Knit-ting yarns Knit-ting yarns
4.	Bartacking. Bartack the overlapping ends of tape to the scarf with a 1/2 inch bartack.	Bartack		28 per bartack			
5.	Attach label. Position and sew label on inside of scarf with the top of the label (1/2 ± 1/8) inch below and parallel to the edge. The stitching shall extend not less than 1/2 inch beyond each end of label. Stitching shall not be through the printing.	301		10-14	50-3	50-3	
6.	Press scarf. Press scarf flat with the label centered (off-center tolerance) 1 inch.						

NATICK Form 903
1 Dec 76 EDITION OF 1 OCT 76 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

3.8 Physical requirements.

3.8.1 Measurements and weights. The measurements and weights of the finished scarfs shall conform to table II. All measurements in table II shall be made with the scarf laid out flat under no tension.

TABLE II. Measurements and weights

		Tolerance
Courses per inch	10	Minimum
Wales per inch	8	Minimum
Width, inches	9	± 1/2
Length, inches	54	± 1-1/2
Weight, ounces per scarf	6.0	Minimum

3.8.2 Bursting strength. The knitted fabric of the finished scarf shall have a bursting strength of not less than 60 pounds when tested as specified in 4.2.6.

3.8.3 Wool content. The knitted fabric of the finished scarf shall contain not less than 95 percent wool based on the dry weight of the specimen when tested as specified in 4.2.6.

3.8.4 Shrinkage requirements. The finished scarf shall not shrink or elongate more than 13.0 percent in either direction after one laundering cycle when tested as specified in 4.2.6.

3.9 Workmanship. The finished scarf shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the applicable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.2.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified or qualified in this document or applicable purchase document. In addition, the contractor shall submit certificates of compliance for the ply of yarn (2-ply) used, that worsted yarn made of fleece or pulled sheep's wool, or a combination of both has been used, that an approved shrink resistant treatment has been used, and that the yarn has been mothproofed in accordance with MIL-C-43665.

4.2.1.1 Wool grade. The wool shall be tested for grade in top form by comparison with the applicable U.S. Standard. In the event of a dispute, the wool grade shall be determined by the width (wedge) method. The sample unit shall be one yard of undyed (or untreated) top. The lot size shall be expressed in units of one pound. The sample size shall be in accordance with table II and the lot shall be unacceptable if one or more units fail to meet any requirements specified.

TABLE III. Sample size

Lot size	Sample size
800 or less	3
801 up to and including 22,000	5
22,001 and over	

4.2.2 End item visual examination. The end item shall be examined for the defects listed in table IV. The lot size shall be expressed in units of one scarf. The sample unit shall be one scarf. The inspection level shall be II and the acceptable quality level (AOL), expressed in terms of defects per hundred units, shall be 4.0.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

TABLE IV. End item defects

Defect
Any hole, cut, tear, or dropped stitches.
Any mend.
Reinforcing tape omitted at either end or not applied to inside end of scarf.
Ends of tape not securely bartacked.
Broken or missing yarn over 1 inch in length.
Rolled, puckered or ragged scarf ends.
Overedge stitching omitted, broken, skipped, incorrect seam type or number of stitches less or more than specified.
Non-uniform in overall appearance, slubby yarn or tiger stripes, clearly visible.*
Burr, shive, or sisal clearly visible.*
Knot not pulled through from face of fabric.
Face of fabric not lightly brushed.
Wrong color.
Shade bar, off shade, or stains clearly visible.*
Label missing, incorrect, or illegible, or improperly attached.
Scarf not tubular seamless type with reinforced open ends.

*At normal inspection distance (approximately 3 feet).

4.2.3 End item dimensional examination. The end item shall be examined for the defects listed below. The lot size shall be expressed in units of one scarf. The sample unit shall be one scarf. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 4.0.

TABLE V. Dimensional defects

Examine	Defect
Overall length	Less than 52-1/2 inches or more than 55-1/2 inches
Overall width	Less than 8-1/2 inches or more than 9-1/2 inches

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

4.2.4 Packaging inspection. An examination shall be made to determine that preservation, packing and marking comply with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully packaged with the exception that it need not be closed. Examination for closure defects listed below shall be made on shipping containers fully packaged. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Material	Any component missing, damaged, or not as specified.
Workmanship	Inadequate application of components, such as incomplete closure of container flap, loose strapping, improper taping, or inadequate stapling. Bulged or distorted container.
Content	Number of bundles per container is more or less than required. Number per bundle is more or less than required. 1/
Preservation	Omitted or improperly applied.

1/ For this defect, 2 bundles shall be examined from each shipping container in the sample.

4.2.5 Palletization examination. An examination shall be made to determine that the palletization complies with section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one palletized unit load fully packaged. The lot size shall be the number of palletized unit loads in the end item inspection lot. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width or height exceeds specified maximum requirement.
Palletization	Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded with required straps as specified.
Weight	Exceeds maximum load limits.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

4.2.6 Testing of the end item. The test methods listed in table VI shall be in accordance with FED-STD-191 except as otherwise noted, and as described herein. The physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test methods. The sample unit shall be four scarfs. The lot size shall be expressed in units of one scarf each. The sample size shall be in accordance with table III and the lot shall be unacceptable if one or more units fail to meet any requirement specified.

*TABLE VI. End item tests

Characteristic	Requirement reference	Test methods
Type of knit	3.2.2	Visual 1/
Colorfastness to:		
Crocking	3.3.2	5651
Laundering	3.3.2	5614
Light	3.3.2	5660
Perspiration	3.3.2	5680
Alkali solubility (stock, top, yarn fabric)	3.4.1	2800 2/
Texture:		
Courses per inch	3.8.1	5070
Wales per inch	3.8.1	5070
Weight of scarf	3.8.1	3/
Bursting strength	3.8.2	5120
Wool content	3.8.3	2101
Shrinkage (after 1 laundering cycle)	3.8.4	5556 4/

1/ One determination per sample unit and the results reported as "pass" or "fail".

2/ Sample unit for test shall consist of treated and untreated material as follows:
Stock - 1/4 pound, top - 1 yard, yarn - 1 cone, fabric - 1/4 yard.

3/ Prior to determination of any other test characteristic, the four scarfs encompassing the sample unit for testing shall be allowed to reach equilibrium under standard conditions as defined in FED-STD-191. After reaching

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

equilibrium, the four scarfs shall be individually weighed to the nearest ounce and the average of the four determinations shall be reported to the nearest 0.1 ounce.

4/ The wool laundering procedure shall be used except the specimens shall be air dried (not tumble dried) and shall not be pressed prior to measuring.

5. PACKAGING

* 5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A. Each scarf shall be laid out flat. The width shall be folded in half and the length lap folded. The folded scarf shall measure approximately 14-1/2 in length by 4-1/2 inches in width. Five folded scarfs of one class only shall be stacked and tied with cotton tape or twine, 2 inches in from each end to form a bundle.

* 5.1.2 Commercial. Each scarf shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Level A packing. Seventy-five scarfs of one class only, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container, conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Level A unit packs shall be packed flat, five in length, one in width and three in depth, within a shipping container. Inside dimensions of each container shall approximate 23-1/2 inches in length, 15 inches in width, and 15 inches in depth. Approximate dimensions are furnished as a guide only. Each container shall have the contents completely covered on the top and bottom with a sheet of 30-pound minimum basis weight kraft paper conforming to type I, grade B of UU-P-268. Each fiberboard container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced in accordance with the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.2.4.

* 5.2.2 Level B packing. Seventy-five scarfs of one class only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container, conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Level B units packs shall be packed flat, five in length, one in width, and three in depth within a shipping container. Inside dimensions of each container shall approximate 23-1/2 inches in length, 15 inches in width, and 15 inches in depth. Approximate dimensions are furnished as a guide only. Each container shall have its contents completely covered on the top and bottom with a sheet of 30-pound minimum basis weight kraft paper conforming to type I, grade B of UU-P-268. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.2.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

* 5.2.2.1 Weather-resistant fiberboard containers. When specified (see 6.2), the shipping container shall be grade V3c, V3s or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.2.4.

* 5.2.3 Commercial packing. Scarfs preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

5.3 Palletization. When specified (see 6.2), scarfs, packed as specified in 5.2, shall be palletized in accordance with load type I of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L. Pallet patterns shall be in accordance with the appaendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course. If the container is of a size which does not conform to any of the patterns specified in MIL-STD-147, the pallet pattern used shall first be approved by the contracting officer.

5.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

6.1 Intended use. The scarfs are intended for use by personnel of the Department of Defense.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number and date of this document.
b. Class required (see 1.2).
c. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
d. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
e. When palletization is required (see 5.3).

6.3 Samples. For access to samples, address the contracting activity issuing the invitation for bids.

6.4 Changes from previous issue. The margins of this document are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activities:

Army - MD
Air Force - 82
DLA - CT

User activity:

Navy - MC
Air Force - 45

Preparing activity:

Army - GL

Project No. 8440-0146

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use i submitting comments and suggestions for improvements. All users of military standardization documents are invited to provid suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, an mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, w too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced *document(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY
US Army Natick Research and Development Center
Natick, Massachusetts 01760

NO POSTAG
NECESSAR
IF MAILED
IN THE
UNITED STAT

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development Center
ATTN: STRNC-ES
Natick, MA 01760

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-S-2063H	Scarf, Neckwear, Wool

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK OP, 1 APR 83

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T14:17Z
Check the source to verify that this is the current version before use.