INCH-POUND
A-A-59505
29 June 2000
SUPERSEDING
MIL-T-46114B
13 July 1978

COMMERCIAL ITEM DESCRIPTION

# TAPE, GLASS-SETTING: RUBBER, UNCURED (FOR SEALING GLASS WINDOWS)

The General Services Administration has authorized the use of this commercial item description by all federal agencies.

1. SCOPE. This commercial item description (CID) covers one type of glass-setting tape, composed of one of three compounds identified herein, used for sealing glass in metal channels.

2. SALIENT CHARACTERISTICS

2.1 Material Requirements:

2.1.1 The material shall be a compound of one of the following, as specified in the acquisition order (see 6.2(b)):

a. Uncured natural rubber and cotton fiber
b. Synthetic rubber and cotton fiber
c. Uncured natural and synthetic rubbers and cotton fiber

2.1.2 The glass-setting tape shall consist of 70 ± 3 percent uncured rubber and 30 ± 3 percent finely dispersed cotton fiber evenly distributed throughout.

2.1.3 Physical property characteristics. The physical property characteristics shall comply with room temperature requirements as well as those for after heat aging.

2.1.3.1 Room temperature requirements. The room temperature requirements are:

a. Durometer hardness (Shore A) shall be 65 with a tolerance of five.
b. The minimum tensile strength is 250 PSI.
c. Elongation percentage is 15 percent minimum.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: Defense Supply Center Richmond (DSCR), ATTN: DSCR-VBD, 8000 Jefferson Davis Highway, Richmond, VA 23297-5610.

AMSC N/A FSC 9320

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:16Z
Check the source to verify that this is the current version before use.

d. The swell or dimensional change from original shall be 5 percent maximum. This may be determined by immersing a sample in distilled water at 23° ± 1.1 °C (73.4° ± 2 °F) for 48 hours ± 1 hour.

2.1.3.2 Requirements for after heat aging. After heat aging requirements are: (The aging period shall be 48 ± 1 hour at an oven temperature of 70° ± 1 °C (158° ± 2 °F).

a. The durometer hardness (Shore A) shall be 65 with a tolerance of five.
b. The maximum tensile strength shall be 400 PSI.
c. The minimum elongation shall be 24 percent.

2.2 Dimensions. The length of roll, and width and thickness of tape shall be as specified in the acquisition order (see 6.2(c)). The length shall be within one percent, the width within 1/16 of an inch, and the thickness shall be within 0.004 inches of the specified dimensions.

2.3 Glass-Setting Tape. The glass-setting tape shall be furnished in rolls. Each roll shall be evenly and neatly wound around its own center without telescoping and shall be suitably restrained from unwinding. The tape shall unroll evenly and uniformly and shall not stick together so as to cause injury to the surface. Each roll shall be one continuous strip.

2.3.1 Color. The color of the glass-setting tape shall be black.

2.3.2 Texture. The texture of the glass-setting tape shall be uniform.

2.3.3 Shelf life. The glass-setting tape shall meet the requirements of this specification when stored in original containers at moderate temperature (not to exceed 37.8 °C (100 °F)) for six months.

## 3. REGULATORY REQUIREMENTS

3.1 Recovered materials. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

## 4. PRODUCT CONFORMANCE PROVISIONS

4.1 Product conformance. The products provided shall meet the salient characteristics of this commercial item description, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The government reserves the right to require proof of such conformance.

## 5. PACKAGING

5.1 Preservation, packing, and marking. For acquisition purposes, the glass-setting tape shall be preserved, packed, and marked as specified in the acquisition order (see 6.2(d)).



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:16Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The glass setting tape furnished under this specification is for use as a sealer for glass (windows) prior to insertion in metal channels (window lifts, vent windows, windshields).

6.2 Ordering data. Procurement documents shall specify the following:

a. CID document number, revision, and CID PIN
c. Material compound (see 2.1.1)
b. Length, width and thickness of tape (see 2.2)
d. Packaging requirements (see 5.1)

6.3 Part or identification number (PIN). The part or identification numbering procedure is AA59505-1. It is for government purposes and does not constitute a requirement for the contractor.

6.4 Sources of documents.

6.4.1 FAR. The FAR may be obtained from the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402-0001.

MILITARY INTERESTS:

Custodians:
Army - MR
Navy - YD
Air Force - 99

Reviewers:
Army - AT, MD

CIVIL AGENCY COORDINATING ACTIVITY:

GSA - 7FXE

Preparing activity:
DLA - GS

(Project 9320-0127)



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:16Z
Check the source to verify that this is the current version before use.