INCH - POUND

MIL-T-60916C(MI)
29 March 1991
SUPERSEDING
MIL-T-60916B(MI)
31 July 1979

MILITARY SPECIFICATION

TUBE, MOTOR, INTEGRAL BULKHEAD, FOR ROCKET MOTOR 2.75 INCH, MARK 4 and MARK 40

This specification is approved for use by the U.S. Army Missile Command, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the quality assurance provisions and special requirements not covered by the drawings for one type of tube designated as Tube, Motor, Integral Bulkhead for Rocket Motor Mark 4 and Mark 40.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, U.S. Army Missile Command, ATTN: AMSMI-RD-SE-TD-ST, Redstone Arsenal, AL 35898-5270 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 1340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

MILITARY

MIL-A-2550	Ammunition, General Specification for
MIL-C-5541	Chemical Conversion Coatings on Aluminum and Aluminum Alloys

STANDARDS

MILITARY

MIL-STD-1167	-	Ammunition Data Card
MIL-STD-1168	-	Ammunition Lot Numbering
MIL-STD-1169	-	Packaging, Packing and Marking for Shipment of Inert Ammunition Components
MIL-STD-1190	-	Minimum Guidelines for Level C Preservation, Packing and Marking

(Unless otherwise indicated, copies of the federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Bldg. 4D, 700 Robbins Ave., Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DRAWINGS

NAVY

1569403	-	Integral Bulkhead Motor Tube, 2.75-Inch FFAR.

(Copies of the drawings and publications required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM B 117 - Salt Spray (Fog) Testing, Standard Method of

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.4.

3.2 Material. Material utilized in the fabrication of the tube shall be in accordance with drawings and specifications specified herein.

3.3 Motor tubes. The motor tubes shall comply with all requirements specified on drawing 1569403, and with all requirements specified in applicable specifications.

3.4 Air test requirements. Each motor tube shall withstand not less than 15 pounds per square inch (psi) air pressure for 10 seconds with no evidence of bubbles if the part is submerged in water as the leak detection method or with a leak rate to be not greater than 10^{-4} cubic centimeters/see. (c.c./sec.) leak rate if a dry method is used (see 4.8.3).

3.5 Surface and internal defects. All motor tubes prior to painting shall be free of surface imperfections on the interior and exterior surfaces of the part which are indications of discontinuities internal to the metal: cracks, lube bursts, pipes, laminations, segregations, porosity, flakes, inclusions and other internal defects. Surface imperfections including pits, seams, scale, blisters, shallow *lube* bursts, and other discontinuities which do not intrude into the metal shall not be considered defects of this type.

3.6 Salt spray test. The finished assemblies, after painting, shall comply with an accelerated corrosion teat as specified in 4.8.5.

3.6.1 Salt spray panel test. The test panel, after receiving a chemical film treatment, in accordance with MIL-C-5541, shall conform to an accelerated corrosion test as specified in 4.8.6.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

3.7 Workmanship. All parts shall be fabricated and finished in a thorough workmanlike manner. They shall be free of burrs, chips, sharp edges, unblended radii metal shavings, dirt, grease, rust corrosion products and other foreign matter. The cleaning method used shall not be injurious to any part nor shall the parts be contaminated by the cleaning agent. Exterior surface coatings shall be continuous except for light scratches not exposing bare material. All required markings shall be neat and sharply defined. Known item defects shall not be submitted with the lot.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.4)

b. Quality conformance inspection (see 4.5)

4.3 Inspection conditions. Unless otherwise specified, all inspections shall be performed in accordance with the test conditions specified in 4.4, 4.5 and 4.6.

4.4 First article inspection. When specified in the contract or order (see 6.2), a first article sample shall be subjected to first article inspection. Subsequent units shall not be considered for acceptance until Government approval of the first article sample has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

4 .4.1 First article sample.

4.4.1.1 Submission. The contractor shall submit a first article sample to a Government approved facility as specified in the contract for evaluation in accordance with the provisions of 4.6.1. The first article sample shall consist of 30 tubes after painting, 30 tubes before painting and one chemical film treated test panel which have been produced by the contractor or furnished by a supplier and which have been produced by the contractor production processes, procedures and equipment which will be used in fulfilling the contract. All parts and materials including packaging and packing, shall be obtained from the same source of supply as will be used in regular production. Prior to submission, the contractor shall inspect the sample to the degree necessary to assure that it conforms to the requirements of the contract and submit as specified in the contract or order (see 6.2), a record of this inspection with the sample, including statements of findings, certificates of conformance for materials. A first article sample, or portion thereof, as directed by the contracting officer, shall also be submitted whenever there is a lapse in production for a period no greater than 90 days or whenever a change occurs in manufacturing, material used, drawing or specification such as to significantly affect product uniformity as determined by the Government.

4.5 Quality conformance inspection. Quality conformance inspections shall be as specified in the applicable drawings, as specified herein, and as specified by the contracting officer (see 6.2) .

TABLE I. Quality conformance inspect ion

Inspection	Requirement paragraph	Test paragraph
First Article	3.1	4.4
Material	3.2	4.4.1.1
Air test	3.4	4.8.3
Salt spray	3.6	4.8.5
Salt spray panel	3.6.1	4.8.6
Workmanship	3.7	4.11

4.6 Inspection provisions for production.

4.6.1 Submission of product. At the time each completed lot of items deliverable under the contract is submitted to the Government for acceptance, the contractor shall supply as specified in the contract or order (see 6.2), the following information accompanied by a certificate which attests that the information provided is correct and applicable to the product being submitted:

a. A statement that the lot complies with all of the quality assurance provisions specified in this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

b. Drawing and specification number and date, together with identification and date of changes thereto.

c. A statement that all material purchased by the contractor meets requirements, when such material is controlled by Government or commercial specifications referenced in any of the contractual documents, and that certificates of conformance are on file and available for review.

d. Number of items in the lot.

e. Date submitted.

The certificates shall be signed by a responsible agent of the certifying organization. The initial certificate submitted shall be substantiated by evidence of the agent's authority to bind his principal. Substantiation of the agents authority will not be required with subsequent certificates unless, during the course of the contract, this authority is vested in another agent of the certifying organization.

4.6.2 Lot formation. In this specification the term inspection lot is an essentially homogeneous collection of units of products from which a representative sample is drawn and inspected to determine conformance with applicable requirements. The sample selected shall represent only that quantity of units from which the sample was drawn and shall not be construed to represent any prior or subsequent quantities presented for inspection. Homogeneity shall be considered to exist provided the inspection lot has been produced by one manufacturer, in one unchanged process, in accordance with the same drawing, same drawing revision, same specification and same specification revision. Changes to the process, specification or drawing not affecting safety, performance, interchangeability, or storage as determined by the Government, shall not be deemed to alter the homogeneity of the inspection lot . All material submitted for inspection in accordance with this specification shall comply with the homogeneity criteria specified herein regardless of the type of sampling procedure which is being applied to determine conformance with requirements. Lot numbering as required, shall be in accordance with MIL-STD-1168. Each inspection lot shall bear a unique lot number. Unless otherwise approved by the contracting officer, the inspection lot size of end items deliverable under the contract shall be not less than 10,000 nor greater than 50,000 units.

4.6.3 Examination. The examinations specified herein shall be performed on inspection lots (see 4.6.2) of the components or assemblies in the applicable paragraph headings. Sampling plans shall be in accordance with Tables II, III and IV of this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

TABLE II. Sampling plan I.

Lot size	Sample size
2 to 50	All
51 to 500	50
501 to 1200	75
1201 to 10,000	116
10,001 to 35,000	135
35,001 to 150,000	170
150,001 to 500,000	200
500,001 and over	244
In all cases: Acceptance number is ZERO Rejection number is ONE	

TABLE III. Sampling Plan II.

Lot size	Sample size
2 to 32	All
33 to 280	32
281 to 500	48
501 to 3200	73
3201 to 10,000	86
10,001 to 35,000	108
35,001 to 150,000	123
150,001 to 500,000	156
500,001 and over	189
In all cases: Acceptance number is ZERO Rejection number is ONE	

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

TABLE IV. Sampling plan III.

Lot size	Sample size
2 to 3	All
4 to 25	3
26 to 50	5
51 to 90	6
91 to 150	7
151 to 280	10
281 to 500	11
501 to 1200	15
1201 to 3200	18
3201 to 10,000	22
10,001 and over	29
In all cases: Acceptance number is ZERO Rejection number is ONE	

4.7 Classification of defects. Each sample shall be tested for defects as specified in 4.7.1 and 4.7.2.

4.7.1 Integral bulkhead motor tube, 2.75 inch FFAR prior to painting (see drawing 1569403 and table V).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of defects, integral bulkhead motor tube.

Categories	Defects	Method of Inspection	Sampling Plan (Tables)
Critical:			
1.	Evidence of surface and internal defects (see 3.5)	Visual	100%
2.	Hydrostatic test stamp missing	Visual	100%
Major:			
101.	Depth of lockwire groove	Gage	II
102.	Inside diameter of motor tube aft of the lockwire groove	Gage	II
103.	Inside diameter for length of of motor tube in the aft chamber	Gage	IV
104.	Motor tube not straight	Gage	IV
105.	Motor tube wall thickness in the aft chamber, minimum	Gage	IV
106.	Depth of thread, minimum (based on configuration)	Gage	IV
107.	Stub Acme thread pitch diameter	Gage	IV
108.	Concentricity of threads with the aft outside diameter of tube	Gage	IV
109.	Length of motor tube, minimum	Gage	IV
110.	Concentricity of forward outside diameter of motor tube with aft outside diameter	Gage	IV
111.	Inside diameter forward of bulkhead section	Gage	IV
112.	Concentricity of inside diameter forward of bulkhead section with threads	Gage	IV
113.	Distance from aft end to lockwire groove	Gage	IV
114.	Inside diameter of tube adjacent to thread	Gage	IV
115.	Distance from forward edge of lockwire slot to forward edge of lockwire groove, minimum	Gage	IV
116.	Distance from aft edge of lockwire slot to aft edge of lockwire groove, minimum	Gage	IV
117.	Length of lockwire slot, minimum	Gage	IV
118.	Runout of surfaces X and Y excessive	Gage	IV

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of defects, integral bulkhead motor tube (continued).

Categories	Defects	Method of Inspection	Sampling Plan (Tables)
119.	Width of lockwire groove	Gage	IV
120.	Surface finish improper or not free of imperfections from aft end to 1" from aft end	Visual	IV
121.	Burrs present on corners of groove	Visual	IV
122.	Inside diameter of the lockwire groove	Visual	IV
123.	Wall thickness in lockwire groove	Gage	IV
124.	Depth of thread relief, minimum if thread relieved	Gage	IV
125.	Depth from forward end to bulkhead	Gage	IV

4.7.2 Integral bulkhead motor tube, 2.75 inch FFAR (see drawing 1569403 and table VI) .

TABLE VI. Classification of defects, integral bulkhead motor tube.

Categories	Defects	Method of Inspection	Sampling Plan (Table)
Critical:	None defined.		
Major:			
101.	Marking missing, incorrect or inadequate	Visual	III

4.8 Testing.

4.8.1 Bearing surface evaluation test (see drawing 1569403, note 6B). A sample consisting of one motor tube shall be taken from a period not greater than four hours of production. The sample shall be tested as specified in 4.9.1. Any bearing surface reduced greater than that allowed in note 6B of drawing 1569403 shall be considered defective. Each defective tube shall cause rejection of the units produced since the last acceptable tube was inspected.

4.8.2 Hydrostatic test (see drawing 1569403, note 2). This test shall be performed before the inspection in paragraph 4.7.1, 100 percent as specified in 4.9.2. Any tube that does not conform to the requirements shall

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

be considered defective, and the lot shall be defective. Acceptable motor tubes shall be marked with the letter H indent stamped with 0.09375 character and shall not be deformed by marking. Marking shall be located outside of the pressure area.

4.8.3 Air test (see paragraph 3.4). This test shall be performed after hydrostatic testing. The sampling plan for this test shall be in accordance with table II. This test shall be performed as specified in 4.9.3. my tube that emits bubbles during test, if the water submergence test is used, or is greater than the leak rate of 10^{-4} cc/see if the dry test is used shall be considered defective.

4.8.4 Section test (see drawing 1569403). Five motor tubes shall be randomly selected from each inspection lot and tested as specified in 4.9.4. Any tube that has a portion of the transition area which is less than the thickness required on the drawing or on which the angle of the bulkhead is incorrect shall cause rejection of the lot.

4.8.5 Salt spray test (see 3.6). The sample size for this test shall be as follows: During production, one motor tube from every tenth lot shall be subjected to the salt spray test as specified in 4.9.5. If a failure occurs, the lot shall be rejected. No lots shall be accepted until three consecutive lots conform to the salt spray requirements. Upon conformance, the sample shall revert to *every* tenth lot again. Any motor tube which does not comply with all of the following test criteria shall be considered a failure. The tube when subjected to the salt spray test as specified in 4.9.5 shall show no greater than five spots or pits, none greater than 0.03125 inch in diameter on the exterior surfaces except in areas within 0.0625 inch of sharp edges and in the lockwire groove. There shall be no greater than three spots or pits, none greater than 0.03125 inch in diameter, in the lockwire groove. The total of powdery areas or loose films covering greater than 10 percent of the total surface shall also be cause for rejection.

4.8.6 Salt spray panel test (see 3.6.1). The sample size for this test shall be as follows: During production, for every tenth motor tube lot, one panel shall be prepared *in* accordance with MIL-C-5541 while the tube lot is being treated. The panel shall be subjected to the salt spray test as specified in 4.9.6 and shall show no greater than five spots or pits, none greater than 0.03125 inch in diameter on the bottom side panel as exposed to salt spray except in areas within 0.0625 inch of sharp edges. The total or powdery areas or loose films covering greater than 10 percent of the total surface shall also be cause for rejection. If a failure occurs, the lot shall be rejected. No tube lots shall be accepted until it has been demonstrated that the test panel conforms to the accelerated salt spray requirements. Upon conformance of three motor tube lots and representative panels, the panel sample shall revert to every tenth lot, submission criteria above.

4.8.7 Permanent deformation test (see drawing 1569403 Note 2). This test will be performed on a minimum of one motor tube per hour of production.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

In the event of a rejection, all motor tubes processed since the last successful test will be rejected and held for engineering evaluation and disposition. The test will be performed as specified in 4.9.7.

4.9 Test methods and procedures.

4.9.1 Bearing surface evaluation test (see 4.8.1). An impression of the bearing surace shall be made by pouring four plaster casts about the 360 degree periphery. The cast shall be measured to determine reduction in the bearing surface.

4.9.2 Hydrostatic test (see 4.8.2). The hydrostatic test shall be run on the integral bulkhead motor tube after machining, prior to painting and prior to dimensional checkout. Each motor tube shall be subjected to an internal hydrostatic pressure of 2,000 + 50, - 0 psi for not less than 15 seconds, applied to the 2.606 diameter. Observation shall be made for pressure drop. Pressure drop shall be noted after pressurization (pumping action or supply of fluid) is terminated. The tube aft of the bulkhead shall be tested as a true pressure vessel and shall be free to expand in all directions during the pressure test. Hydrotesting of that portion of the motor tube which is forward of the bulkhead is not required.

4.9.3 Air test (see 4.8.3). The air test shall be run on the integral bulkhead motor tube, nondestructively. An air pressure of not less than 15 psi shall be applied to the 2.606 diameter for 10 seconds. Observation shall be made for bubbles if the tube is submerged in water or observation shall be made for leak rate not greater than the requirement if the dry method is utilized. Air testing of that portion of the motor tube which is forward of the bulkhead is not required.

4.9.4 Section test (see 4.8.4). Each motor tube in the sample shall be sectioned through the centerline of the longitudinal axis of the aft chamber. The longitudinal section shall be deburred to facilitate accurate measurement. The thinnest portion of the transition area shall be measured. The angle of deviation of the aft face of the bulkhead from perpendicularity with the centerline of the aft chamber shall also be measured.

4.9.5 Salt spray test (see 4.8.5). An accelerated corrosion test shall be performed using the equipment and procedures specified in ASTM B 117. The tube shall be placed in a vertical position in the test chamber with the interior surfaces down to preclude accumulation of solution. A 20 percent concentration of sodium chloride solution shall be used and the duration of test shall be 144 hours. The tube shall be air dried for not less than 96 hours before testing. The tube shall then be exposed to the 20 percent salt spray as specified in ASTM B 117.

4.9.6 Salt spray panel test (see 4.8.6). An accelerated corrosion test, using a 20 percent concentration of sodium chloride solution shall be performed on the test panel using the equipment specified in MIL-C-5541. The

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

duration of the test shall be 144 hours. The panel shall be air dried for not less than 96 hours before testing.

4.9.7 Permanent deformation test (see 4.8.7). The selected motor tube shall be tested for integral bulkhead position before and after the hydrostatic test. Deformation in excess of the drawing requirement shall be basis for rejection.

4.10 Inspection of packaging. The sampling and inspection of the preservation, packing and container marking shall be in accordance with the requirements of MIL-STD-1169.

4.11 Workmanship. The materials used in the manufacture of the tube motor shall be of the highest quality to assure a well formulated product (see 3.7).

5. PACKAGING

5.1 Preservation, packing, unitization and marking Level A, B or C (see 6.2).

5.1.1 Level A or B. Preservation, packing, unitization, and marking shall be in accordance with MIL-STD-1169.

5.1.2 Level C. Unless otherwise specified in the contract or order, preservation, packing, and marking shall be in accordance with MIL-STD-1190.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The tube, motor, designated Mark 4 and Mark 40 is intended to be used as the integral bulkhead in the 2.75 inch rocket motor.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of the specification

b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1)

c. Drawings when required, providing dimensions, tolerances, hardness, and other design details (see 3.2).

d. When first article is required (see 3.1 and 4.4)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

e. First article sample size (see 4.4.1.1)

f. Conditions for quality conformance inspection (see 4.5)

g. Requirements for preservation, packing and marking (see 4.8 and section 5)

h. Data cards - Data cards shall be prepared for each lot in accordance with MIL-STD-1167.

6.3 First article. When first article inspection is required, the contracting officer should provide specific guidance to offerers whether the item(s) should be a first article sample, a first production item, or a number of items to be tested as specified in 4.4. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examinations, approval of first article test results and disposition of first articles. Invitations for bids should provide that the Government reserves the right to waive the requirement for samples for first article inspection to those bidders offering a product which has been previously acquired or tested by the Government, and that bidders offering such products, who wish to rely on such production or test, must furnish evidence with the bid that prior Government approval is presently appropriate for the pending contract.

6.4 Metrication. Metric equivalents in accordance with FED-STD-376 are acceptable for use in this specification.

6.5 Subject term (keyword) listing.

Container
Cylinder
Sleeve

6.6 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodian:
Army - MI

Preparing Activity:
Army - MI

Project No. 1340-A835

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:05Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	MIL-T-60916C(MI)	29 March 1991

3. DOCUMENT TITLE

TUBE, MOTOR, INTEGRAL, BULKHEAD, FOR ROCKET MOTOR 2.75 INCH, MARK 4 AND MARK 40

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code)	
COMMANDER U.S. ARMY MISSILE COMMAND	(1) Commercial (205) 876-6980	(2) AUTOVON 746-6980
c. ADDRESS (Include Zip Code) ATTN: AMSMI-RD-SE-TD-ST REDSTONE ARSENAL, ALL 35898-5270	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

DD FORM 1426 89 OCT

Source: https://assist.dla.mil -- Downloaded: 202640-23T01:05Z
Check the source to verify that this is the current version before use.