C-F-158a
SEPTEMBER 22, 1959
SUPERSEDING
Int. Fed. Spec. C–F–00158(GSA–FSS)
July 29, 1959 and
Fed. Spec. C–F–151a (In Part)
July 24, 1940

FEDERAL SPECIFICATION

FEATHERS, LAND FOWL, (CRUSHED)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—This specification governs the requirements for crushed chicken feathers intended for use as a filling material.

1.2 Classification.

1.2.1 *Type.*—The crushed land-fowl feathers covered by this specification shall be of one type.

2. APPLICABLE SPECIFICATIONS AND STANDARDS

2.1 The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification:

Federal Specifications:

V–T–276—Thread, Cotton.
QQ–S–781—Strapping, Flat, Steel.
RR–S–366—Sieves, Standard for Testing Purposes.
CCC–C–429—Cloth, Cotton, Osnaburg.
CCC–T–191—Textile Test Methods.
PPP–B–636—Boxes, Fiber.

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging and Packing Levels.
Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).
Fed. Std. No. 751—Stitches; Seams; and Stitching.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

Military Specifications:

JAN–C–485—Cloth, Cotton, Sheeting.

Military Standards:

MIL–STD–105 — Sampling Procedures and Tables for Inspection by Attributes.
MIL–STD–129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:04Z
Check the source to verify that this is the current version before use.

procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Laboratory report approval. — Unless otherwise specified (see 6.1), prior to or upon submission of bids to the contracting officer, the prospective contractor shall furnish the contracting officer a certified copy of a recent laboratory report from any of the following:

(*a*) An independent or commercial laboratory report.
(*b*) The prospective contractor's own laboratory report.
(*c*) A Government laboratory report from a recent contract.

The laboratory report shall contain test data which demonstrates that the crushed feathers which the contractor proposes to deliver have been previously tested and found to comply with all the requirements of this specification.

3.2 Preproduction sample approval.—Unless otherwise specified (see 6.1), before production is commenced, the contractor shall submit for approval to the contracting officer a one-pound sample of crushed feathers.

3.3 Materials.—All feathers shall be new, not previously used or reclaimed (see 6.1), and sterilized.

3.4 Definitions.—The materials covered by this specification are defined as follows:

3.4.1 *Feathers (or natural feathers).* — Bird or fowl plumage having quill shafts and barbs and which have not been processed in any manner other than by washing, dusting, and sterilizing.

3.4.2 *Land-fowl feathers.* — The feathers from any breed of domesticated chicken.

3.4.2.1 *Land-fowl quill feathers (or quills).* —Wing and tail feathers commonly known and referred to as quills.

3.4.2.2 *Crushed land-fowl feathers.*—Land-fowl feathers which have been processed by a crushing, chopping or curling machine which has changed the original form of the feathers without removing the quill.

3.4.3 *Residual matter.*—Residual matter is defined as quill pith, trash, and foreign matter.

3.4.4 *Percentage composition.*—The percent composition as stated in 3.8 is based on the total weight of the sample tested when tested as specified in table II.

3.5 Processing. — The feathers shall be thoroughly washed, including the use of suitable blood solubilizing agents to remove all traces of blood, dried (see 6.2), and sterilized.

3.5.1 *Sour.*—A commercial laundry sour of the fluoride type, namely sodium acid or silico fluoride or combinations thereof shall be utilized in the final rinse of the washing procedure to bring the pH of the finished dry product within the limits of 3.5 to 6.0 when tested as specified in table II.

3.5.2 *Wet feathers.*—Wet feathers which cannot be processed within 12 hours after plucking (see 6.2) shall be preserved by steeping in an acid bath prepared by mixing 10 ounces of the fluoride sour specified in 3.5.1 with every 100 gallons of water used. Not more than 24 hours shall be permitted to elapse before processing as specified in 3.5. Feathers which have been steeped in the acid-medium shall be rinsed in clean water before proceeding with the scouring process.

3.5.3 *Certification.*—The contractor shall certify in writing that he has complied with all of the processing requirements specified in 3.5, 3.5.1 and 3.5.2.

3.6 Cleanliness.

3.6.1 *Oxygen number.*—The oxygen number shall not exceed 24 when tested as specified in table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:04Z
Check the source to verify that this is the current version before use.

3.6.2 *Solvent soluble matter.*—The solvent soluble matter of the feathers shall not exceed 2.5 percent by weight when tested as specified in table II.

3.7 **Acidity.**—The acidity (pH) of the finished dry product shall be within the limits of 3.5 to 6.0 when tested as specified in table II.

3.8 **Composition.**—The percentage composition of the crushed feathers shall be as follows when tested as specified in table II:

Crushed feather	Minimum 90 percent
Whole feathers	Maximum 5 percent
Quill feathers (in excess of 4 inches)	Maximum 3 percent
Residual matter	Maximum 2 percent

3.9 **Packaging and packing.**

3.9.1 *Materials purchased by a contractor.*—When the crushed feathers are purchased as a component of an end item they shall be packaged and packed in clean condition in accordance with the feather supplier's commercial practice.

3.9.2 *Materials purchased directly by the Government.* — When the crushed feathers are purchased directly by the Government, they shall be packaged and packed in the levels specified in accordance with the requirements of section 5 and inspected in accordance with 4.5 through 4.6.1.5.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 **Contractor's inspection responsibility.**—Unless otherwise specified herein, the supplier is responsible for the performance of all inspection requirements prior to submission for Government inspection and acceptance. Except as otherwise specified, the supplier may utilize his own facilities or any other commercial laboratory, acceptable to the Government. Inspection records of the examination and tests shall be kept complete and made available to the Government as specified in the contract or order.

4.2 **Pre-acceptance inspection.**

4.2.1 *Laboratory report.*—The pre-award laboratory report (see 3.1) shall contain actual test results showing that the crushed feathers have been tested and comply with all physical and chemical requirements of section 3.

4.2.2 *Preproduction sample inspection.*—The preproduction sample submitted in accordance with 3.2 shall be examined and tested to determine compliance with the requirements of section 3.

4.3 **Inspection for acceptance.** — Unless otherwise indicated, inspection shall be in accordance with the provisions of Military Standard MIL–STD–105 except as specified hereinafter.

4.4 **Testing.**—Testing of the end item shall be performed in accordance with methods specified in table II. The test methods indicated by number apply to Federal Specification CCC–T–191. The sample unit (unit of product) for testing shall be a 12-ounce composite of crushed feathers. The sample shall be obtained by drawing approximately 4 ounces each of the material from top, center, and bottom on two opposite sides of each bag selected for sampling, so that approximately 24 ounces of material will be drawn from each sample bag. Bags shall be cut in the specified locations for drawing the sample. The sample size (number of bags to be selected) shall be in accordance with level L–7 of table IIIB of Military Standard MIL–STD–105, and the lot size shall be expressed in terms of bags. For Civil agencies the sample size and the number of defects acceptable shall be as specified in table I of this specification.

4.4.1 *Cleanliness test.*

4.4.1.1 *Oxygen number.*—Ten grams ± 1 gram of crushed feathers shall be placed in a

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:04Z
Check the source to verify that this is the current version before use.

TABLE I.—*Sampling for test—civil agencies*

Number of bags in lot	Number of bags in test sample	Acceptance number (defects)	Rejection number (defects)
25 and under	2	0	1
26 to 65	3	0	1
66 to 110	5	0	1
111 to 300	7	0	1
301 to 500	10	1	2
501 to 800	15	1	2
801 to 1,300	25	2	3
1,301 to 3,200	35	3	4
3,201 to 8,000	50	4	5
8,001 to 22,000	75	6	7
22,001 and over	110	8	9

The material obtained from the sample bags shall be thoroughly mixed in a container and a 12-ounce sample shall be drawn from the container. Care shall be taken in mixing to prevent damaging or compresing of the materials. The requirements indicated in table II are applicable to lot average.

TABLE II.—*Test methods*

Characteristics	Requirement reference	Test method	Determinations per sample unit
Cleanliness	3.6	--	--
Oxygen number	3.6.1	(see 4.4.1)	2
Solvent soluble matter	3.6.2	(see 4.4.2)	2
Acidity (pH)	3.7	2811	2
Composition	3.8	(see 4.4.3)	1

tumbler jar of the type specified in method 5500 of Federal Specification CCC–T–191, or in an equivalent agitating device, with one liter of distilled water and tumbled at room temperature for one hour. The resulting suspension shall be filtered through a 74-micron (standard No. 200) sieve conforming to Federal Specification RR–S–366 and evaluated as specified in 4.4.1.1.1.

4.4.1.1.1 A 100-milliliter aliquot of the above filtrate shall be transferred to a porcelain casserole, neutralized and made acid with 1 to 2 milliliters excess of 6*N* sulfuric acid. The solution shall be titrated with 0.1*N* potassium permanganate, adding approximately 0.05 milliliters at a time, until a pink color persists for 60 seconds. Calculate oxygen number to number of grams of oxygen per 100,000 grams of sample as follows:

$$\text{Oxygen number} = \text{milliliters of } 0.1N\ KMnO_4 \times 80$$

4.4.2 *Solvent soluble matter.*—Three grams ± 0.5 gram of crushed feathers shall be placed in a fat-free extraction thimble (Whatman single thickness) to prevent escape of sample. Thimble with product shall be extracted in a Soxhlet extractor, using carbon tetrachloride or chloroform, for a minimum of 20 cycles. The extract shall then be evaporated on a water bath, dried to constant weight in an oven at 105° ± 2°C, cooled and weighed. Report residue as the solvent soluble matter. All weighings shall be determined to the nearest 0.001 gram.

4.4.3 Composition analysis by weight of the crushed feathers.

4.4.3.1 *Atmospheric conditions.* — Except in settlement of disputes the test for composition analysis may be made under prevailing atmospheric conditions. In the case of dispute the test shall be performed under standard conditions as specified in Federal Specification CCC–T–191.

4.4.3.2 *Preparation of specimen.*—Specimens of the end product shall be prepared as specified in 4.4. Approximately one ounce of the material shall be exposed in the relaxed state (without packing) in a screen container for a period of not less than one day. The material shall be mixed with a rod over the exposure period to insure complete conditioning.

4.4.3.3 *Apparatus.*

4.4.3.3.1 A wooden box of the following approximate dimensions:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:04Z
Check the source to verify that this is the current version before use.

Base—18 inches long by 12 inches wide
Front—6 inches high
Back—12 inches high

The box shall have a glass lid hinged to the top edge of the back panel to provide a clear view of its interior and a free and secure closure during examinations of the sample. It shall also have two openings, one at each end of the front panel, sufficiently large to permit the examiner's hand to enter the box to separate and examine the particles in the sample, and shall be equipped with a light to provide sufficient illumination of its interior.

4.4.3.3.2 Tared weighing bottles or beakers with covers to be used as containers in the separating process.

4.4.3.3.3 A pair of tweezers suitable for extracting and separating the components.

4.4.3.3.4 *Balance.*—An analytical balance capable of accurately weighing to the nearest 0.001 gram shall be utilized in the weighings.

4.4.3.4 *Procedure.*

4.4.3.4.1 The sample consisting of approximately four grams of specimen prepared as in 4.4 and 4.4.3.2 shall be transferred into a weighing container of known weight and shall then be weighed to determine its exact weight.

4.4.3.4.1.1 *Weighing.*—All weights shall be determined to the nearest 0.001 gram.

4.4.3.4.2 The weighing bottle or beaker containing the sample shall be placed on the floor of the separating box along with as many empty containers of known weight as necessary for the separation of the sample. In the event of dispute, prior to their use, all weighing bottles or beakers shall be kept in a conditioned atmosphere as defined in Federal Specification CCC–T–191. The lid of the separating box shall be kept closed.

4.4.3.4.3 Each component of the crushed feathers in the sample to be analyzed shall be extracted individually and shall be closely examined to determine its nature. Each particle shall be classified in accordance with definitions in 3.4 and shall be placed into the appropriate weighed container. The weighing bottles or beakers shall be identified as follows:

Crushed feathers
Whole feathers
Quill feathers (in excess of 4 inches)
Residual matter

4.4.3.5 *Evaluation.*

4.4.3.5.1 Upon completion of the separating process, the weight of the contents of each weighing bottle or beaker shall be determined by subtracting the tare weight of the containers from the gross weight.

4.4.3.5.2 The percentage of each component shall be determined in accordance with the following formula:

$$\text{Percent of component in sample} = \frac{\text{Total weight of material in component}}{\text{Weight of sample}} \times 100$$

4.4.3.6 *Report.*

4.4.3.6.1 The percent of each component of the mixture shall be reported to the nearest 0.1 percent based on the weight of the sample prior to separation.

4.4.3.6.2 In the event that the sum of the weights of all components varies more than one percent from the original sample weight, the test shall be repeated and the original results discarded.

4.4.3.7 *Preservation of specimens.*

4.4.3.7.1 When test reports indicate failure, each separate portion of the sample shall be kept in a properly identified envelope for ready reference in the event of dispute. If test results are not questioned within three months from date of the report, these sam-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:04Z
Check the source to verify that this is the current version before use.

ples may be discarded. If results indicate failure, a recheck shall be performed on another specimen obtained in a similar manner from the original sample.

4.5 Inspection of components.

4.5.1 *Inspection of cloth and fiberboard.*— Cloth and fiberboard used in the fabrication of fabricated bags and bale boards shall be inspected to determine conformance with the requirements of referenced specifications and applicable supplemental provisions specified in 5.1 and 5.2.

4.5.2 *Inspection of fabricated bags and bale boards.* — Fabricated bags and bale boards shall be inspected to determine conformance with the applicable requirements of 5.1 and 5.2. The acceptable quality level shall be 4.0 defects per hundred units, and the inspection level shall be L–3 of table IIIB of Military Standard MIL–STD–105. For civil agencies the sample size and the number of defects acceptable shall be as specified in table III of this specification.

TABLE III.—*Sampling for inspection of fabricated bags and bale boards—civil agencies*

Number of bags or bale boards in lot	Number of bags or bale boards in sample	Acceptance number (defects)	Rejection number (defects)
300 and under	1	0	1
301 to 500	2	0	1
501 to 800	3	0	1
801 to 1,300	5	0	1
1,301 to 3,200	7	0	1
3,201 to 8,000	10	1	2
8,001 to 22,000	15	1	2
22,001 and over	25	2	3

4.6 Inspection of the end product.

4.6.1 *Examination of the end item.*—The end item (completely packaged and packed product) shall be inspected in accordance with the examinations and tests specified in 4.6.1.1, 4.6.1.2, 4.6.1.3 and 4.6.1.4.

4.6.1.1 *Weight.*—The lot shall be unacceptable if the total net weight of the bags in the sample is less than the total net weight indicated on the bags.

4.6.1.2 The sample size (number of bags to be selected) for the weight examination shall be in accordance with level L–8, table IIIB of Military Standard MIL–STD–105. For civil agencies, the sample size shall be as specified in table IV of this specification. The net weight of the material contained in the sample bags shall be obtained by deducting the tare weights from the gross weights of the sample bags.

TABLE IV.—*Sampling for weight examination—civil agencies*

Number of bags in lot	Number of bags in sample
25 and under	2
26 to 40	3
41 to 65	5
66 to 110	7
111 to 300	10
301 to 500	15
501 to 800	25
801 to 1,300	35
1,301 to 3,200	50
3,201 to 8,000	75
8,001 to 22,000	110
22,001 and over	150

4.6.1.3 *Packaging examination.*—The unit of product shall be one bag of crushed feathers.

Defects

Not packaged in accordance with specified packaging level.
Bag not new, or any patch.
Not closed in the specified manner.
Wire tie broken or not tightly turned to accomplish a secure closure.
Any hole, rip, tear or open seam; any weak places in bag which may develop into a hole.
Bag wet.
Marking missing, incomplete, illegible, incorrect, not accomplished in the specified manner, or not in proper location.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:04Z
Check the source to verify that this is the current version before use.

4.6.1.4 *Packing examinaton.*—The sample unit shall be one bale or shipping container.

Defects

Not packed in accordance with the specified packing level.

Bags not compressed to specified size.

Does not contain the specified number of bags.

Kraft facing of baling board not on outside.

Any board or strap missing.

Baling board or strap too loose or not placed in proper location to a degree where safe delivery of contents may be impaired.

Marking — missing, incomplete, illegible, incorrect, not accomplished in the specified manner or not in proper location.

4.6.1.5 *Acceptable quality levels.*—Acceptable quality levels (AQL's) and inspection levels shall be as follows: AQL's are expressed in defects per 100 units.

Examination	*Inspection level*	*AQL*
4.6.1.3 (packaging)	I	6.5
4.6.1.4 (packing)	I	6.5

For civil agencies the sample size and the number of defects acceptable shall be as specified in table V.

TABLE V.—*Sampling for packaging and packing examination—civil agencies*

Number of bags or bales in lot	Number of bags or bales in sample	Acceptance number (defects)	Rejection number (defects)
110 and under	5	0	1
111 to 300	7	1	2
301 to 500	10	1	2
501 to 800	15	2	3
801 to 1,300	25	3	4
1,301 to 3,200	35	5	6
3,201 to 8,000	50	6	7
8,001 to 22,000	75	9	10
22,001 and over	110	12	13

5. PREPARATION FOR DELIVERY

Federal Standard No. 102 should be referred to for definitions and applications of the various levels of packaging protection for supplies and equipment (for civil agencies only).

5.1 Packaging.—Packaging shall be level A or C as specified (see 6.1).

5.1.1 *Level A.* — Fifty ± 5 pounds of crushed feathers shall be packaged in a new (not used or laundered) plain textile bag fabricated from cotton sheeting conforming to type I of class D, Military Specification JAN–C–485 or type I, class 2, finish A of Federal Specification CCC–C–429. Fabrics in other widths of equivalent weight and construction will be acceptable.

5.1.1.1 *Bag, construction.*—The bags shall have a finished length and width measured flat of approximately 72 by 36 inches and shall be constructed in accordance with the following requirements. The side and bottom shall be seamed with 5 to 6 stitches per inch with either seam and stitching type 401, SSa–2 or 301, SSa–2, conforming to Federal Standard No. 751. The stitching shall be at least ⅝ inch from the cut edge of the fabric or ¼ inch from a selvage edge and shall be at least ⅛ inch apart. The ends of all seams shall be backstitched at least 1 inch. The thread used for seaming shall be cotton, machine, soft finish, type IIIA, unbleached, ticket no 10/3, 3 ply conforming to Federal Specification V–T–276, (table V).

5.1.1.1.1 *Type 301 stitching.* — Thread breaks in stitching shall be back-stitched not less than 1 inch at each break. Thread tension shall be maintained so that there will be no loose stitching and that the lock will be embedded in the center of the materials sewed. Thread ends shall be trimmed.

5.1.1.1.2 *Type 401 stitching.* — Thread breaks in stitching shall be overstitched not less than 1½ inches at each break. Thread

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:04Z
Check the source to verify that this is the current version before use.

tension shall be maintained so that there will be no loose stitching. The chain portion of the stitching shall not appear on the outside of the bag. Thread ends shall be trimmed.

5.1.1.2 *Closure.*—The closure of the top of the bag after filling shall be effected by means of two 6-inch, 15-gage soft-iron or steel wire ties having a ½-inch-diameter eye formed at each end. One tie shall be applied at the base of an ear formed by gathering the cloth evenly and the second tie applied at a distance approximately 1 inch from the first tie with the twisted ends of two ties alternated and facing in opposite directions.

5.1.2 *Level C.*—Feathers shall be packaged in accordance with good commercial practice.

5.2 **Packing.**—Packing shall be levels A, B, or C as specified (see 6.1).

5.2.1 *Levels A and B.*—Three bags (150 pounds of feathers with permissible tolerances, as specified in 5.1.1) shall be placed between two baling boards and compressed by machine so as to form a bale approximately one fifth of the original volume. Bales thus formed shall measure approximately 60 by 24 by 20 inches.

5.2.1.1 *Baling boards.*—Baling boards shall be not less than 0.075-inch-thick solid fiberboard conforming to type II, class 1 of Federal Specification PPP–B–636, except that at least one face of the board shall be not less than 0.010-inch kraft paperboard, and the bursting strength of the combined board shall be not less than 200 p.s.i. Two such baling boards, size 58 by 36 inches, each with a score line placed 6 inches from each 58-inch edge in such a manner that the kraft facing is on the outside when in a folded position, shall be used in each bale; one board on top of bags being baled and one on the bottom. The boards shall be bent at the score lines thereby forming a fiberboard cap 58 inches in length, 24 inches in width, with 6-inch flanges extended down over the side of the bale.

5.2.1.2 *Strapping.*—Not less than eight straps shall be used on each bale; straps shall be affixed girthwise around the sides, top, and bottom of the bale over the baling boards. The two outside straps shall be placed 4 inches in from each end and the intermediate straps placed equidistant between the end bands. All strapping shall be flat steel not less than ⅜ inch wide by 0.020 inches thick conforming to type I, class A of Federal Specification QQ–S–781.

5.2.2 *Level C.* — Feathers, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination. Containers shall be in accordance with Uniform Freight Classification Rules or regulations of other carriers applicable to the mode of transportation.

5.3 **Marking.**

5.3.1 *Civil agencies.*—In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the requirements of Federal Standard No. 123.

5.3.2 *Military agencies.* — In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the requirements of Military Standard MIL–STD–129. All shipments for level A or level B shall be designated "A/A".

6. NOTES

6.1 **Ordering data.** — Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

(*a*) Title, number, and date of this specification.
(*b*) When laboratory report is not required (see 3.1).
(*c*) When preproduction sample is not required (see 3.2).
(*d*) When an affidavit is required to show that the material supplied is new and not used (see 3.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-28T11:04Z
Check the source to verify that this is the current version before use.

(*e*) Selection of applicable level of packaging and packing (see 5.1 and 5.2).

6.2 Preparation of feathers.—With reference to 3.5, good results have been obtained with the following procedure:

6.2.1 *Wet plucking.*—Within 30 minutes after wet plucking, the feathers are given a clear-water rinse (at tap temperature of not over 105° F.) to remove excess foreign matter and blood. The feathers are then agitated for 20 minutes in water at 95° ± 5° F. to which has been added a blood solubilizing agent in the proportion of 1 oz. of the agent to 10 gallons of water. Following the blood solubilizing treatment the feathers are washed, using a synthetic non-ionic detergent, and then thoroughly rinsed. The final rinse contains one of the commercial fluoride sours available as laundry sours, namely, sodium silica fluoride or combinations thereof. The feathers are them centrifuged and dried in steam-heated feather-drying equipment.

6.2.2 *Wet feathers.*—Wet feathers which cannot be processed within 12 hours after plucking should be preserved by steeping in an acid bath prepared by mixing 10 ounces of fluoride sour in every 100 gallons of water. Not more than 24 hours should be permitted to elapse before processing as above. Feathers which have been steeped in the acid medium should be rinsed in clean water before proceeding with the scouring process.

6.3 Supersession data.—This specification supersedes those requirements for crushed chicken feathers only of Federal Specification C–F–151a, dated July 24, 1940. Federal Specification C–F–160 for Feathers, Waterfowl, and Down, Waterfowl supersedes those requirements of Federal Specification C–F–151a for duck and goose feathers.

6.4 Transportation description.—The transportation description applicable to this item is:

Feathers, chicken, in machine pressed bales.
Carload minimum weight 28,000 pounds, subject to rule 34, Uniform Freight Classification.

Feathers NOI, in packages having a density of:
Less than 4 lbs. per cubic foot.
Motor volume minimum weight, any quantity.

4 lbs. per cubic foot but less than 7 lbs.
Truckload minimum weight, 5,600 pounds subject to rule 34, National Motor Freight Classification.

7 lbs. per cubic foot but less than 12 lbs.
Truckload minimum weight 10,000 pounds, subject to rule 34, National Motor Freight Classification.

12 lbs. per cubic foot or over.
Truckload minimum weight 12,900 pounds, subject to rule 34, National Motor Freight Classification.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:
Army—M Q
Navy—S Sh
Air Force.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:04Z
Check the source to verify that this is the current version before use.