RR-P-1818
September 11, 1973
SUPERSEDING
MIL-P-40154A
July 31, 1968

FEDERAL SPECIFICATION

PAD, BAKERY (COTTON)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE

1.1 This specification covers one type and size of protective hand pad.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

V-T-276 - Thread, Cotton.
CCC-C-443 - Cloth, Duck, Cotton (Single and Plied Filling Yars, Flat).
PPP-B-566 - Boxes, Folding, Paperboard.
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-B-665 - Boxes, Paperboard, Metal Edged and Components.
PPP-B-676 - Boxes, Setup.
PPP-T-45 - Tape, Gummed, Paper, Reinforced and Plain, for Sealing and Securing.

Federal Standards:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).
Fed. Test Method Std. No. 191/GEN (General Provisions) - Textile Test Methods.
Fed. Test Method 191/4021 - Yarn Number (Linear Density) of Yarn from Package.
Fed. Test Method 191/5030 - Determination of Thickness of Textile Material.
Fed. Test Method 191/5041 - Determination of Weight of Textile Materials: Small Specimen Method.
Fed. Test Method 191/5050 - Yarns Per Inch in Woven Cloth.
Fed. Test Method 191/5070 - Wales and Courses in Knit Cloth.
Fed. Test Method 191/5120 - Strength of Cloth; Bail Bursting Method.
Fed. Std. No. 751 - Stitches, Seams, and Stitchings.

FSC 7330

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-130 - Identification Marking of U.S. Military Property.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply:

National Motor Freight Traffic Association, Inc., Agent

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), the supplier shall furnish a sample for first article inspection and approval (see 4.2 and 6.3).

3.2 Materials.

3.2.1 Cloth, cotton, knitted, terry. The unbleached, undyed cotton knitted terry cloth shall conform to the physical requirements specified in table 1 when tested as specified in 4.3.1.1 (see 3.6).

TABLE I. Physical requirement for terry cloth

Characteristic	Requirement
Cotton content	100 percent
Weight, oz/yd^2 (min)	23.0
Wales and courses (min)	Wales - Courses 8 13
Yarn counts (cotton, nominal)	Face - Back 6/1 8/1
Thickness @ 0.6 psi (inch)	0.130
Weave	Terry knit
Bursting strength (min)	60 pounds

3.2.2 Cloth, cotton, duck. The unbleached, undyed cotton duck shall conform to the physical requirements specified in type I of CCC-C-443, except that the thickness of a single layer shall be a minimum of 0.024 inch at 0.6 psi when tested in accordance with test method (TM) 5030 of Fed. Test Method Std. No. 191 (see 3.6).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

3.2.3 Tape, elastic. An unbleached elastic tape shall be provided to permit the pad to be retained at the wrist of the user. The elastic strands for the tape shall be made of compounded natural rubber, synthetic rubber, or a mixture thereof, and shall be heat resistant. The strands shall be of a nonimal gage of 30, and shall be wrapped with multiple ends of cotton yarns (4 ends for bottom cover and one end for top cover). There shall be a minimum of 10 elastic strands across the full width of the tape. The minimum width of the tape shall be one-inch and shall be woven on a shuttle or a needle type of loom and shall weigh a minimum of 0.55 ounces per linear yard. The warp and filling yarns shall be of cotton. Testing shall be as specified in 4.3.1.1 (see 3.6).

3.2.3.1 Method of securing tape (see 3.3.2). The tape shall be securely attached through minimum 1/2-inch end folds and centered crosswise to the back of the pad. The tape shall be located 1-1/2 inches, plus or minus 1/4-inch, from the top and the two sides of the pad. If metal fasteners are used in securing the tape, they shall be noncorrosive.

3.2.4 Thread, cotton. The cotton threads for the pad shall be unbleached and undyed conforming to type 1A1, or dyed conforming to type IA3, ticket No. 30, 3 ply of V-T-276.

3.2.5 Film, plastic, flexible, vinyl chloride. The flexible plastic film shall be a minimum 0.006-inch thick at 0.6 psi and the weight in oz/sq yd shall be a minimum of 6.3 when tested as specified in 4.3.1.1 (see 3.5 and 3.6). The plastic film shall also be free of holes.

3.3 Construction. The construction shall conform in all respects to the requirements specified herein.

3.3.1 Stitches, seams and stitching. All seams and stitching shall conform to Fed. Std. No. 751 as follows:

For edge stitching	Stitch type 301 or 401, seam type SSa-1, 6 to 8 stitches per inch, 1/8 to 3/16-inch from edge and supplemented with overedge stitching type EFd-1, 504 or 505, 10 to 14 stitches per inch, 3/16 to 1/4-inch gage.
For attaching elastic wrist tape	One bartack 7/8 to 1 inch with 42 stitches per tack or 2 bartacks 7/16 to 1/2-inch with 28 stitches per tack.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

3.3.1.1 Automatic stitching. Any of the stitching operations cited in this specification may be performed with an automatic machine provided the requirements for stitch pattern, stitches per inch, size and types of thread are met; and at least three tying overlapping or backstitches are used to secure the ends of stitching.

3.3.1.2 Thread breaks. Thread breaks in overedge stitching shall be over-stitched not less than 3/4-inch beyond each break. Thread tensions shall be maintained so that there will be no excessively loose or tight stitching resulting in puckering of the materials sewn.

3.3.2 Material cutting. The cotton terry cloth (see 3.2.1), cotton duck (see 3.2.2), and flexible vinyl film shall be cut ~~9-inches by 12-inches ± 1/8-inch.~~ to sizes specified in 3.4. The cotton elastic tape (see 3.2.3), shall be cut 6 ± 1/8-inches long. Sides of cut pieces shall be smooth, free of ragged edges and also the cotton cloths shall be free of loose threads.

3.3.3 Assembly.

3.3.3.1 Attachment of wrist tape. Both 1-inch tape ends shall be folded back smoothly upon itself, 3/8 to 1/2-inch, forming LSb-1 seams and then superimposed upon the cotton duck cloth in a location that will place the lengthwise lay of the tape centrically in the 9-inch width direction, and a distance of 1-1/4 ± 1/4-inches ~~between the 12-inches long~~ edge of the cotton duck cloth and the adjacent edge of the tape. After the wrist tape is placed in the above position, it shall be securely tacked at both ends through all layers of material. Tacking shall be located 3/16 to 1/4-inch from turned edges. Metal fasteners may be used in lieu of thread to secure the tape, provided they are non-corrosive.

3.3.3.2 End item assembly (see 6.4 and 6.5). One cut piece of knitted cotton terry cloth, one cut piece of vinyl chloride plastic film and two cut pieces of cotton duck cloth shall be superimposed on each other with the above material edges being aligned, the assembled materials being flat and smooth without wrinkles. The vinyl film shall be sandwiched between the knitted terry and cotton duck cloths. The elastic tape shall be outside of the assembly (against the last layer of cotton duck). The four edges of the assembled layers of material (excluding elastic tape, see 3.3.3.1) shall be sewed together by a single row of stitch type 301 or 401, seam type SSa-1, which shall be supplemented with overedge stitching with stitch types 504 or 505, stitching type EFd-1. The overedging shall utilize either the unbleached or dyed thread. The completed stitched pad shall be free of wrinkles and puckers.

3.3.3.3 Thread ends. All thread ends shall be trimmed to 1/4-inch maximum length.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

3.4 Size. The finished bakery pad shall be rectangular in shape, with rounded or square corners, and shall measure 8-1/2 by ~~11-3/4~~ 11-1/2 inches wide 8 long plus or minus 1/8-inch.

3.5 Grease penetration. There shall be no evidence of grease penetration when tested as specified in 4.3.3.4.1.

3.6 Launderability. The percentage of shrinkage in the finished pad shall not be more than 9.0 percent in the length, nor more than 9.0 percent in the width when tested as specified in 4.3.3.4.2. The pads shall remain soft and pliable, and the elastic tape shall retain its elasticity after testing as specified in 4.3.3.4.2.

3.7 Marking. The identification marking shall be applied on the outer surface of the cotton duck cloth of the finished fabricated pad in a location which the wrist tape shall not obstruct the marking after attachment. The bakery pads shall be marked with a nontoxic ink in accordance with MIL-STD-130.

3.8 Workmanship. The completed fabricated bakery pad shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 First article inspection. When required (see 6.2), the first article sample submitted in accordance with 3.1 shall be inspected for all the provisions of this specification applicable to end item inspection.

4.3 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

4.3.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase document.

4.3.1.1 Testing of components. Testing of components, unless otherwise specified, shall be in accordance with Fed. Test Method Std. No. 191 and shall be performed on components listed in table III for the characteristics shown. The sample size (number of sample units) shall be as specified in table II, and the lot shall be unacceptable if one or more units fail to meet any one of the specified requirements. The sample unit, except for yarn count, shall be one bakery pad component assembly prior to stitching. The sample unit for determining the yarn count shall be one cone or tube and the basis of lot size shall be cone or tube.

TABLE II. Sample size

Lot size (units)	Sample size
800	2
801 up to and including 22,000	3
22,001 and over	5

TABLE III. Component testing

Component	Characteristic	Requirement reference	Test method
Plastic film	Weight, oz/sq yd	3.2.5	5041
	Thickness @ 0.6 psi	3.2.5	5050
Cloth, cotton, terry	Weight, oz/sq yd	3.2.1	5041
	Fiber content	3.2.1	1/
	Yarn counts (face and back)	3.2.1	4021
	Terry knit	3.2.1	Visual
	Bursting strength	3.2.1	5120
	Wales and courses	3.2.1	5070
	Thickness	3.2.1	5030
Elastic, tape	Color (unbleached)	3.2.3	Visual
	Heat resistant rubber	3.2.3	1/
	Elastic strands	3.2.3	5050 1/

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

TABLE III. Component testing (con.)

Component	Characteristic	Requirement reference	Test method
Elastic, tape (cont'd)	Cotton bottom and cotton top cover yarns	3.2.3	Visual 1/
	Width	3.2.3	Visual
	Weight	3.2.3	5041 1/
	Warp and filling yarns	3.2.3	1/

1/ A supplier's certificate of compliance will be acceptable for this characteristic.

4.3.2 Intermediate examination. Inspection shall be performed prior to fabrication to determine that cut length and width of cut pieces is in accordance with 3.3.2 and that the vinyl film is in accordance with 3.2.5 and free of defects specified in 4.3.3.1. Defects found in this examination shall be classified as specified in 4.3.3. The sample unit shall be one complete unassembled bakery pad. The inspection levels and AQL's shall be in accordance with 4.3.3.3.

4.3.3 Examination of the end item. The classification of defects shall be in accordance with 4.3.3.1 and 4.3.3.2. The inspection levels and AQL's shall be in accordance with 4.3.3.3. The sample unit for these examinations shall be one completed bakery pad.

4.3.3.1 Visual examination.

Examine	Defect	Classification Major	Minor
Fabric	Hole, cut or tear, smash, broken or missing yarn, or open place clearly visible at normal inspection distance (approximately 1 foot)	X	
Tape, elastic	Any cut, hole, tear or smash	X	
	Broken or missing yarn		X
	Multiple floats		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification Major	Classification Minor
Stitching:			
Open stitching	1/2-inch or less		X
	More than 1/2-inch	X	
NOTE:	Stitching shall be classified as open when one or more stitches joining a seam are broken or when two or more skipped stitches or runoffs occur.	X	
Types of stitching	Not as specified	X	
Raw edge (on edge required to be finished)	More than 1/2-inch when securely caught in stitching	X	
NOTE:	Raw edge not securely caught in stitching shall be classified as an open stitching.		
Runoff (see open stitching)			
Stitch tension	Excessive puckering of fabric on stitching		X
Stitches per inch (except on bartack)	Up to two stitches less than minimum specified		X
	Three or more stitches less than minimum specified	X	
	One or more stitches in excess of maximum specified		X
Thread break	Overstitched less than 3/4-inch (overedge stitching)		X
NOTE:	Thread break not overstitched shall be classified as open stitching.		

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification Major	Minor
Components and assembly	Any component part omitted or not as specified or required operation omitted (unless otherwise classified herein)	X	
Metal fastener (when used)	Insecurely or improperly clinched	X	
	Needle chews	X	
	Any mend, darn, patch or burn	X	
	Frayed or ravelled edge		X
Marking	Omitted, illegible, incorrect, or misplaced		X
Cleanness	Any spot or stain		X
Thread ends	Not trimmed to 1/4-inch maximum length		X

4.3.3.2 Dimensional examination.

Examine	Defect
Bakery pad body (completed assembly)	
Height	Less than 11-5/8-inches
Width	Less than 8-3/8-inches
Wrist tape strap (after fabrication)	Less than 5-1/2-inches

4.3.3.3 Inspection levels and AQL's. The inspection levels and AQL's expressed in defects per hundred units shall be as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

Examination	Inspection level	AQL Major	AQL Total
For defects applicable to 4.3.3.1	II	2.5	6.5
For defects applicable to 4.3.3.2	S-2		6.5
For defects applicable to 4.3.2	S-3		2.5

4.3.3.4 Testing of the end item. The method of testing specified in Fed. Test Method Std. No. 191 wherever applicable, shall be followed. The physical and chemical values specified below apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test method. The sample unit for testing shall be three pads. The lot shall be unacceptable if a single sample unit fails to meet any of the specified requirements. All test reports shall contain the individual values utilized in expressing the final results. The sample size shall be as follows:

Lot size (pads)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

4.3.3.4.1 Grease penetration test. Each pad shall be forced, face up, through the ring of a horizontally held ring clamp (approximately 3-1/2-inches in diameter) to form a pocket approximately 3 inches in diameter and 2 inches deep. Rapidly pour 100 milliliters of vegetable cooking oil heated to 400 degrees F. into the pocket. The test period shall be 10 minutes. Failure shall be evidenced by the first sign of staining on the underside or back of the sample before the test period has elapsed.

4.3.3.4.2 Launderability test. Each pad shall be subjected to 5 laundering and drying cycles. Testing shall be in accordance with TM 5550 Fed. Test Method Std. No. 191 except that shrinkage shall be determined by the outside measurements taken at the center of each direction (length and width) of the pad. Drying shall be conducted as specified for knit cloths. The pads shall not be pressed before measuring the shrinkage. The pads shall be examined for any decrease in softness or pliability and for retention of elasticity of the elastic tape. The lot shall be unacceptable if a single sample fails to meet the requirements specified in 3.6.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

4.3.4 Examination of preparation for delivery requirements. An examination shall be made to determine that the packaging, packing, and marking comply with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery, except that it need not be closed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 4.0 defects per hundred units.

Examine	Defect
Markings (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Materials	Any nonconforming component; component missing, damaged, or otherwise defective.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, improper taping, loose strapping, inadequate stapling, bulging or distortion of container.
Contents	Number of items per package or number of packages per container is more or less than required.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C, as specified (see 6.2).

5.1.1 Level A. Twenty-four pads shall be packaged in a snug-fitting folding paperboard box conforming to variety 1, style III or VIII, type G, class i, group I of PPP-B-566; set-up paperboard box conforming to type I, variety 1, class A, style 4 of PPP-B-676; or metal stayed paperboard box conforming to class 1, style A of PPP-B-665. Closure of boxes shall be effected with 2-inch minimum width gummed paper tape conforming to type III, grade B of PPP-T-45.

5.1.2 Level B (civil agencies). Pads shall be packaged in accordance with 5.1.1.

5.1.3 Level C. Pads shall be packaged to afford adequate protection against physical damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets this requirement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A. Two hundred and eighty-eight pads, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636. Each shipping container shall be closed, waterproofed, and reinforced in accordance with the appendix of the container specification.

5.2.2 Level B. Two hundred and eighty-eight pads, packaged as specified in 5.1, shall be packed in a snug-fitting, fiberboard shipping container conforming to style RSC, type CF (variety SW), or SF, class domestic, grade 275 of PPP-B-636. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636.

5.2.2.1 When specified (see 6.2), shipping containers shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of the box specification.

5.2.3 Level C. Pads packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

5.3 Marking.

5.3.1 Civil agencies. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 Military requirements. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The pad covered by this specification is intended to be used for handling hot pots and pans in galleys and kitchens.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) When first article is required (see 3.1, 4.2, and 6.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

(c) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(d) When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of ASPR 7-104.55. The first article should be a preproduction sample. The first article should consist of one completed bakery pad. The contracting officer should include specific instructions in all procurement instruments regarding arrangements for inspection and approval of the first article.

6.4 Face. The terry surface of the pad which comes in contact with hot objects.

6.5 Back. The duck surface of the pad which comes in contact with the hand.

MILITARY INTERESTS:

Custodians:

Army - GL
Navy - SA
Air Force - 84

Review activities:

Army - MD
Navy - MS

User activity:

Navy - MC

Preparing activity:

Army - GL

Project No. 7330-0452

Civil Agency Coordinating Activities:

GSA-FSS
VA-DMS

14

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price [illegible] cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE
RR-P-1818 PAD, BAKERY (COTTON)

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?
   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
US ARMY NATICK LABORATORIES
NATICK, MA 01760

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

STSNLT-EQS

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD – 314



Commander
US Army Natick Laboratories
ATTN: STSNLT-EQS
Natick, Massachusetts 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.