SS-C-450a
April 10, 1967

SUPERSEDING
Int. Fed. Spec. SS-C-00450 (GSA-FSS)
May 28, 1964,
Fed. Spec. HH-C-581a
December 18, 1935, and
Fed. Spec. HH-C-591
July 3, 1935

FEDERAL SPECIFICATION

CLOTH, IMPREGNATED (WOVEN COTTON CLOTH, ASPHALT IMPREGNATED; COAL TAR IMPREGNATED)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers bituminized cotton fabric, composed of woven cotton cloth waterproofed with either asphalt or coal-tar pitch for membrane system of waterproofing and built up roof covering.

1.2 Classification.

1.2.1 *Types.* Cloth shall be of the following types, as specified (see 6.2):

Type I—Asphalt impregnated cloth.
Type II—Coal-tar impregnated cloth.

1.2.2 *Size.* The size of rolls shall be as follows:

Width—36 inches.
Length—150 feet per roll.

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification to the extent specified herein.

Federal Specifications:

UU-P-268—Paper, Kraft, Untreated, Wrapping.
PPP-T-76—Tape, Pressure-Sensitive Adhesive Paper, (For Carton Sealing).

Federal Standard:

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-R-3423—Roofing Felt—In Rolls, Packaging of.

Military Standards:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129—Marking for Shipment and Storage.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.

MIL-STD-147—Palletized Unit Loads (40 Inches X 48 Inches, 4-Way Partial and 4-Way Pallets).

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

American Society for Testing and Materials (ASTM) Publications:

D 146—Sampling and Testing Felted and Woven Fabrics Saturated with Bituminous Substances for Use in Waterproofing and Roofing.

D 173—Specification for Woven Cotton Fabrics Saturated with Bituminous Substances for Use in Waterproofing.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race St., Philadelphia, Pa., 19103.)

Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.

3. REQUIREMENTS

3.1 Material.

3.1.1 *Type I.* Type I cloth shall conform to the requirements for asphalt saturated cotton cloth in ASTM D 173.

3.1.2 *Type II.* Type II cloth shall conform to the requirements for coal-tar pitch saturated cloth in ASTM D 173.

3.2 Workmanship. The finished cloth shall be free of visible external defects such as ragged or untrue edges, breaks, rents, or cracks.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any other commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Sampling.

4.2.1 *Lot.* Unless otherwise specified (see 6.2), a lot shall consist of all impregnated cloth of the same type submitted for inspection at the same time.

4.2.2 *Dimensional and visual examination of end item, and tests.* Sampling for these characteristics and tests shall be in accordance with ASTM D 146.

4.3 Examination.

4.3.1 *End item.* Impregnated cloth shall be examined and measured for defects listed in table I. The acceptable quality levels (AQL's) in accordance with MIL-STD-105 shall be 2.5 percent defective for major defects, and 4.0 percent defective for minor defects. Cloth shall be measured using a rule graduated in 1/32 inch increments.

TABLE I. *Classification of defects, end item*

Defects	Major	Minor
Saturant not as specified	X	
Rolls tear or crack upon unrolling	X	
Holes in fabric	X	
Ragged or untrue edges	X	
Width not within tolerance	X	
Rolls, flattened, unusable	X	
Ends of rolls battered, unusable	X	
Damage or defects affecting function or serviceability	X	
Damage or defects not affecting function or serviceability		X

4.3.2 *Inspection of preparation for delivery.* An inspection shall be made to determine that packaging, packing and marking requirements of section 5 are complied with. Defects shall be scored in accordance with

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.

table II. For examination of contents, the sample unit shall be one shipping container fully prepared for delivery selected just prior to the closing operations. Defects of closure listed shall be examined on shipping containers fully prepared for delivery. Sampling shall be conducted in accordance with MIL-STD-105, inspection level II. AQL shall be 2.5 percent defective.

TABLE II. *Classification of preparation for delivery defects*

Examine	Defects
Markings (exterior and interior)	Omitted; incorrect; illegible; or improper size, location, sequence, or method of application.
Materials	Any component missing or damaged.
Workmanship	Inadequate application of components such as incomplete closure of wrap or loose strapping.

4.4 **Test methods.** Tests shall be conducted in accordance with ASTM D 146 (see 3.1.1 and 3.1.2).

5. PREPARATION FOR DELIVERY

5.1 **Packaging.** Packaging shall be level A, B, or C, as specified (see 6.2).

5.1.1 *Level A.* The cloth shall be packaged in accordance with MIL-R-3423.

5.1.2 *Level B.* The cloth shall be rolled on mandrels or rigid hollow fiber cylinders not less than 2 inches in diameter or 2 inches square, extending not more than 4 inches beyond the ends of the rolls. Each roll shall be wrapped with paper conforming to UU-P-268, grade B, and secured with PPP-T-76 tape.

5.1.3 *Level C.* The cloth shall be packaged in accordance with the supplier's commercial practice.

5.2 **Packing.** Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 *Level A.* The cloth shall be packed in accordance with MIL-R-3423.

5.2.2 *Level B.* The rolls of cloth shall be palletized in accordance with MIL-STD-147.

5.2.3 *Level C.* The cloth shall be packed to insure carrier acceptance and safe delivery at destination in containers complying with the rules and regulations applicable to the mode of transportation.

5.3 **Marking.**

5.3.1 *Civil agencies.* In addition to markings required by the contract or order, the rolls and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 *Military agencies.* In addition to markings required by the contract or order, the rolls and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 **Intended use.** Impregnated cotton cloth covered by this specification is intended for use in the membrane system of waterproofing or for the construction of built-up roof covering.

6.2 **Ordering data.** Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(*a*) Title, number, and date of this specification.
(*b*) Type of cloth required (see 1.2).
(*c*) Size of lot, if different from 4.2.1.
(*d*) Selection of applicable levels of packaging and packing required (see 5.1 and 5.2).

MILITARY CUSTODIANS:

Army—MO
Navy—YD
Air Force—69

Review activities:

Army—MO
Navy—YD
Air Force—69

User activities:

Army—CE
Navy—None
Air Force—None

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.

Review/user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing of DOD Standardization Documents.

Orders for this publication are to be placed with General Services Administration, acting as agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 5 cents each.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:13Z
Check the source to verify that this is the current version before use.