SS-P-00402B(GSA-FSS)
September 22, 1970
SUPERSEDING
Int. Fed. Spec. SS-P-00402A(GSA-FSS)
February 16, 1965, and
INTERIM REVISION OF
Fed. Spec. SS-P-402
May 5, 1945

INTERIM FEDERAL SPECIFICATION

PLASTER, GYPSUM

This Interim Federal Specification was developed by the General Services Administration, Federal Supply Service, Washington, D.C. 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized Federal agencies to use this Interim Federal Specification as a valid exception to Federal Specification SS-P-402, dated May 5, 1945.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers gypsum plaster used as a base coat and finish coat for interior applications.

1.2 Classification.

1.2.1 Types and classes. Gypsum plaster procured under this specification shall be of the following types and classes, as specified (see 6.2):

Type I - Gypsum ready - mixed plaster.
II - Gypsum neat plaster.
Class 1 - Sand aggregate addition.
2 - Variety aggregate addition.
III - Gypsum wood-fibered plaster.
IV - Gypsum bond plaster.
V - Gypsum gauging plaster, finish coat.
VI - Gypsum veneer plaster.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issues in effect on the date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

UU-S-48 - Sacks, Shipping, Paper.
MMM-A-260 - Adhesive, Water-Resistant, (For Sealing Waterproofed Paper).
PPP-B-636 - Box, Fiberboard.
PPP-B-1055 - Barrier Material, Waterproofed, Flexible.
PPP-C-650 - Crates, Wood, Open and Covered.
PPP-D-723 - Drums, Fiber
PPP-S-50 - Sacks, Shipping, Paper, Reinforced.

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D. C. 20402.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver San Francisco, Los Angeles, and Seattle, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procudures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-1186 - Cushioning, Anchoring, Bracing, Blocking, and Waterproofing, with Appropriate Test Methods.

(Copies of Military Specifications and Standards, required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM) Standards:

C28 - Specification for Gypsum Plasters.
C37 - Specification for Gypsum Lath.
C471 - Gypsum and Gypsum Products, Chemical Analysis of.
C472 - Gypsum Plasters and Gypsum Concrete, Physical Testing of.
C587 - Specification for Gypsum Veneer Plaster.
C588 - Specification for Gypsum Base for Veneer Plasters.
E96 - Tests for Water Vapor Transmission of Materials in Sheet Form.

National Classification Board:

National Motor Freight Classification.

(Application for copies shall be addressed to the American Trucking Association, Inc., Attn: Tariff Order Section, 1616 P Street N.W., Washington, D. C. 20036.)

Uniform Classification Committee:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, 202 Union Station, Chicago, Illinois 60606.)

3. REQUIREMENTS

3.1 Types I, II, III, IV, and V. Gypsum plaster, shall be in accordance with ASTM C28, except for packaging and marking, inspection, rejection, and rehearing (see 4.4.2.1 and 4.4.2.2). Gypsum plaster shall be suitable for application on gypsum lath covered by ASTM C37.

3.2 Type VI, gypsum plaster, and base.

3.2.1 Gypsum veneer plaster. Veneer plaster shall be in accordance with ASTM C587, except for packaging and marking, and for rejection and rehearing (see 4.4.3.1).

3.2.2 Gypsum base. Gypsum base for veneer plaster shall be in accordance with ASTM C588 except for packaging and marking, and for rejection and rehearing (see 4.4.2.1 and 4.4.2.2). Thickness of base shall be 3/8, 1/2 or 5/8 inch, as specified (see 6.2). Width shall be 48 inches, and length shall be 6 to 16 feet, as specified (see 6.2).

3.3 Workmanship.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.

3.3.1 Types I, II, III, IV, and V. Gypsum plaster shall be free from lumps, and extraneous particles.

3.3.2 Type VI. Gypsum veneer bonded to gypsum base shall be free from raised areas and curled edges.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Sampling for lot acceptance.

4.2.1 Inspection lot. A lot shall consist of each type of gypsum plaster offered for delivery at the same time.

4.2.2 Sampling for examination and tests. Size of sample for visual examination shall be in accordance with level S-3 in MIL-STD-105. Samples for test shall be in accordance with ASTM C28 for types I to V inclusive, and in accordance with ASTM C588 for type VI.

4.3 Examination and tests.

4.3.1 Examination for visual characteristics. Examine gypsum plaster in accordance with table I. The acceptable quality levels (AQL's) for defects shall be 2.5 percent defective for major defects and 4.0 percent defective for minor defects.

TABLE I. Classification of defects, end item

Defects	Major	Minor
Lumps in plaster.		X
Plaster not dry.	X	
Extraneous particles in plaster.	X	
Veneer gypsum not fully bonded.	X	
Damage or defects not affecting function or serviceability.		X

4.3.2 Inspection preparation for delivery requirements. An inspection shall be made to determine that the packaging, packing and marking requirements comply with section 5 of this specification. Defects shall be scored in accordance with table II. Sampling shall be in accordance with MIL-STD-105. Defects of closure listed shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be II and the AQL shall be 4.0 defects per hundred units.

TABLE II. Classification of preparation for delivery defects

Examine	Defects
Markings (exterior and interior)	Omitted; illegible; improper size, location, sequence, or method of application.
Materials	Any component missing, or damaged.
Workmanship	Inadequate application of components such as incomplete closure of container.

4.4 Test methods.

4.4.1 Tests, AQL. The AQL for all tests, and for all specimens in individual tests shall be 4.0 percent defective.

4.4.2 Types I, II, III, IV, and V.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.

4.4.2.1 Chemical analysis. Analysis gypsum and gypsum products in accordance with ASTM C471 (see 3.1).

4.4.2.2 Physical. Test gypsum plasters in accordance with ASTM C472 (see 3.1).

4.4.3 Type VI.

4.4.3.1 Joint strength, bond, impact, and flexure. Test for these characteristics in accordance with ASTM C587 (see 3.2.1).

4.4.3.2 Water vaper transmission. Test for water vaper transmission in accordance with ASTM E96 (see 3.2.1).

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B or C as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Type II. Type II plaster furnished in 6 pound quantities shall be packaged in a sack conforming to PPP-S-50, grade W.

5.1.1.2 Type VI. Type VI, gypsum veneer plaster of like description shall be carefully and uniformly piled. Finished surfaces shall be facing each other. Each pile shall be wrapped with waterproof paper conforming to PPP-B-1055, class B-1, with all folds, seams, and laps sealed with adhesive conforming to MMM-A-260, type I or II, grade B, class optional. Each package shall contain the number of sheets most convenient for handling.

5.1.2 Level B.

5.1.2.1 Type II. Type II plaster furnished in 6 pound quantities shall be packaged as specified in 5.1.1.1.

5.1.2.2 Type VI. Type VI shall be packaged as specified in 5.1.1.2.

5.1.3 Level C. Type II and Type III shall be packaged in accordance with the supplier's commercial practice.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Level A. The plaster furnished in quantities as specified (see 6.3) shall be packed in sacks or drums (see 6.3) conforming to UU-S-48, X grades and PPP-D-723, type III, grade A, respectively. A plastic liner shall be provided for the drums in accordance with PPP-D-723.

5.2.1.1 Type II. Unless otherwise specified (see 6.3) 10 unit packages of type II plaster shall be packed in a close-fitting box conforming to PPP-B-636, V3c. The box shall be closed, waterproofed sealed and strapped in accordance with the appendix to the box specified.

5.2.1.2 Type VI. Type VI gypsum veneer plaster of like description, packaged as specified in 5.1.1.2, shall be packed in quantities not to exceed the weight limitations of the crate, in an open crate conforming to PPP-C-650, style A, type V, class 1. Sheets longer than twelve feet shall use style B crates. Anchoring, closing, strapping, and marking shall be in accordance with appendix to the crate specification and in accordance with MIL-STD-1186.

5.2.2 Level B. The plaster furnished in quantities as specified (see 6.3) shall be packed in sacks or drums (see 6.3) conforming to UU-S-48, L/W grades and PPP-D-723, type I, grade A. A plastic liner shall be provided for the durms in accordance with PPP-D-723.

5.2.2.1 Type II. Ten unit packages of type II plaster shall be packed in a close-fitting box conforming to PPP-B-636, class-domestic. The box shall be closed in accordance with the appendix to the box specification.

5.2.3 Level C. The plaster and gypsum veneer plaster packaged as specified in 5.1 shall be packed in containers to assure carrier acceptance and safe arrival at destination in compliance with Uniform Freight Classification or National Motor Freight Classification.

5.3 Marking.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.

5.3.1 Civil agencies. In addition to markings required by the contract or order, the packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.2.2 Military activities. In addition to markings required by the contract or order, the packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use.

6.1.1 Type I. Gypsum ready-mixed plaster is intended for use as a base coat over gypsum latch or metal lath, or porous masonry bases. The type of mineral aggregate (sand, perlite or vermiculite), type of base and type of finish coat limit the amount of mineral aggregate to be contained in this type.

6.1.2 Type II. Gypsum neat plaster is intended for use as a base coat over gypsum lath, metal lath or porous masonry bases with the addition of a mineral aggregate on the job. It may be fibered or unfibered.

6.1.3 Type III. Gypsum wood fibered plaster is intended for use as a base coat over gypsum lath, metal lath or porous masonry bases, and contains wood fiber aggregate added at the mill. Although it has often been used without the addition of mineral aggregate on the job, the addition of one cu. ft. of sand aggregate to each 100 pounds of wood fibered plaster is permessible and improves working quality and crack resistance.

6.1.4 Type IV. Gypsum bond plaster is intended for use as a base coat plaster ton properly prepared interior monolithic concrete surfaces.

6.1.5 Type V. Gypsum gauging plaster is intended for use in the job preparation of a gypsum-lime putty finish coat, and may contain not more than 1/2 cu. ft. of mineral aggregate per 100 pounds of calcined gypsum added at the mill. Molding plaster may be considered a gauging plaster.

6.1.6 Type VI. Gypsum veneer plaster is intended for interior use over large size sheets of gypsum base.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type and class (see 1.2).
(c) Type VI, base thickness and length (see 3.2.2).
(d) Level of packaging and packing required (see 5.1 and 5.2).
(e) Quantity of plaster required (see 5.2.1 and 5.2.2).

6.3 Container size for gypsum plaster. Gypsum plaster is ordinarily available in 100 pound sacks.

GSA DC 71-3897

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.

GENERAL SERVICES ADMINISTRATION - FEDERAL SUPPLY SERVICE

SPECIFICATION COMMENT SHEET

BUDGET BUREAU NO. 29-R0175

INSTRUCTIONS

This form provides a way for users of this specification to inform the originator of problems encountered in its use. It is not to be used to request changes to accommodate proprietary features. All comments will be considered and appreciated, but please do not expect a reply. To comment: detach, complete, and mail to: General Services Administration, FSS (FMSH), Washington, D.C. 20406.

NOTE: Comments on this form do not constitute or imply authorization to waive any part of the document or serve to amend contractual requirements.

1. SPECIFICATION

SS-P-00402B(GSA-FSS) Plaster, Gypsum

2. CONTRACT NO. *(If any)*	3. QUANTITY ON CONTRACT *(Optional)*	4. DOLLAR VALUE *(Optional)*

5. GENERAL NATURE OF PROBLEM *(e.g., inspection difficulties, manufacturers unable to meet tolerances, containers collapse under normal warehousing conditions, etc.)*

6. SPECIFIC REQUIREMENTS AFFECTED *(Include paragraph number and lines of wording)*

7. SPECIFIC PROBLEMS *(e.g. tests in 4.2.2 will not assure that the battery will last required time; temperature ranges in table 2 do not conform to commercially available items.)*

8. RECOMMENDATIONS

9. NAME OF MANUFACTURER, ASSOCIATION, GOVT., AGENCY, ETC.	10. ADDRESS *(Number, Street, City, State and Zip Code)*

11. NAME AND TITLE OF SUBMITTER	12. DATE

FORM GSA FEB '69 2200

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.