QQ-C-533B
MARCH 10, 1988

CANCELLATION NOTICE

FEDERAL SPECIFICATION

Copper-Beryllium Alloy Strip
(Copper Alloy Numbers 170 and 172)

Federal Specification QQ-C-533B, dated 20 March, 1972 is hereby cancelled. Future procurements for this material should refer to ASTM B194, "Copper-Beryllium Alloy Plate, Sheet, Strip and Rolled Bar", in accordance with the following supersession table:

For Documents Listing QQ-C-533*, QQ-C-533A, and QQ-C-533B		Use ASTM B194	
Alloy Numbers		UNS Alloy Numbers	
170	172	C17000	C17200
	Tempers (Solution Heat Treated)		
A			TB00
	(Solution Heat Treated and Cold Rolled)		
1/4 H			TD01
1/2 H			TD02
H			TD04
	(Precipitation Heat Treated)		
AT			TF00
1/4 HT			TH01
1/2 HT			TH02
HT			TH04
	(Mill Hardened)**		
			TM00
			TM01
			TM02
(No Equivalent)			TM03
			TM04
			TM05
			TM06

* Alloy defined by Beryllium content of 1.80 - 2.05% only.
** Precipitation heat treated by the material manufacturer and no further thermal treatment is normally required.

Custodians:

Army -- MR
Navy -- AS
Air Force -- 20

Preparing Activity:

Army -- MR

FSC 9535

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06Z
Check the source to verify that this is the current version before use.