MIL-C-70577
AMENDMENT 1
15 MAY 1987

MILITARY SPECIFICATION SHEET

CELLULOSE, KRAFT PROCESS WOODPULP

This Amendment forms a part of Military Specification MIL-C-70577 (AR), dated 14 November 1985, and is approved for use by the U.S. Army Armament, Munitions and Chemical Command, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

The attached insertable replacement pages listed below are replacements for stipulated pages. When the new pages have been entered in the document, insert the amendment as the cover sheet to the specification.

Replacement page	Page replaced
1	1
2	2
3	3

Custodian:
Army-AR

Preparing Activity:
Army-AR

(Project 1315-A905)

FSC-1315

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:43Z
Check the source to verify that this is the current version before use.

MILITARY SPECIFICATION

CELLULOSE, KRAFT PROCESS WOODPULP

This specification is approved for use by the US Army Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. - This specification establishes the requirements and quality assurance provisions for the manufacture and acceptance of one grade of Kraft process cellulose woodpulp for use in combustible cartridge cases.

2. APPLICABLE DOCUMENTS

2.1 Government documents

2.1.1 Specifications and standards. - Unless otherwise specified, the following specifications and standards of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-A-48078	Ammunition, Standard Quality Assurance Provisions, General Specification for

STANDARDS

MILITARY

*

MIL-STD-129	Marking for Shipment

2.2 Other publications. - The following documents form a part of this specification to the extent specified herein.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Armament Research and Development Center, Attn: AMSMC-QA, Dover, New Jersey 07801-5001 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC-1315

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:43Z
Check the source to verify that this is the current version before use.

Supersedes page 1 dated 14 November 1985.

TECHNICAL ASSOCIATION OF THE PULP AND PAPER INDUSTRY (TAPPI) Test Methods

T-233 hm-82	Fiber Length of Pulp by Classification
T-230 om-82	Viscosity of Pulp
T-429 os-78	Alpha-cellulose in Paper
T-223 os-78	Pentosans in Wood and Pulp
T-236 os-76	Kappa Number of Pulp
T-211 om-80	Ash in Wood and Pulp

(Application for copies should be made to The Technical Association of the Pulp and Paper Industry, Technology Park, P.O. Box 105113, Atlanta, GA, 30348).

*AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM E300	Recommended practice for sampling industrial chemicals

(Application for copies should be addressed to the American Society For Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

2.3 Order of precedence. - In the event of conflict between the text of this specification and the referenced specifications cited herein, the text of this specification shall take precedence.

3. REQUIREMENTS

3.1 General. - The kraft process cellulose woodpulp shall comply with requirements given in this detailed specification as well as applicable drawings and referenced specifications.

3.2 Material. - The material shall be kraft process cellulose woodpulp, meeting the requirements of this specification.

3.3 Properties. - The properties of the kraft process cellulose woodpulp shall be as specified in Table I when tested in accordance with the applicable test methods:

TABLE I

	Property	Minimum	Maximum	Applicable Test Method
	Fiber Length (mm)	2	3.5	4.3.1
	Viscosity (centipiose)	10	25	4.3.2
*	Alpha Cellulose (%)	84		4.3.3
	Pentosans (%)	5		4.3.4
*	Lignin (%)		1.1	4.3.5
	Ash Content		0.25	4.3.6

3.4 Workmanship. - The best commercial practices shall be used in the manufacture of the product furnished under this specification. Procedures

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:43Z
Check the source to verify that this is the current version before use.

and controls shall be employed which preclude conditions which may adversely affect the safety and reliability of the produce when tested in accordance with 4.3.7.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. - Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such specifications are deemed necessary to assure supplies and services conform to prescribed requirements. Unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this specification.

4.2 Quality Conformance Inspection

4.2.1 Lot formation. - A lot shall consist of one or more batches of kraft process cellulose woodpulp produced by one manufacturer, in accordance with the same specification, or same specification revision, under one set of operating conditions.

4.2.2 Testing. - It is emphasized that all applicable safety rules, regulations, practices and procedures be followed in handling and processing the kraft process cellulose woodpulp.

* 4.2.2.1 Sampling. - A representative sample shall be withdrawn from each batch or lot of kraft process cellulose woodpulp, in accordance with paragraph 28.4 of ASTM E300. Each sample shall be tested independently in accordance with the applicable methods given in 4.3. If the sample fails to meet any of the test requirements, the batch or lot shall be subjected to a retest. If, upon retesting, a subsequent sample fails to meet any of the test requirements, the batch or lot shall be rejected.

4.3 Test methods and procedures. - All tests given in this section shall be performed using prescribed procedures given in the Technical Association of the Pulp and Paper Industry (TAPPI) Official Test Methods. See 6.3 for use of equivalent test methods.

4.3.1 Fiber length. - The sample shall be tested for fiber length in accordance with TAPPI Test method T-233 hm-82.

4.3.2 Viscosity. - The sample shall be tested for viscosity in accordance with TAPPI method TM-230 om-82.

4.3.3 Alpha cellulose. - The sample shall be tested for Alpha Cellulose in accordance with TAPPI Test method T-429 os-78.

4.3.4 Pentosans. - The sample shall be tested for pentosans in accordance with TAPPI Test method T-223 os-78.

4.3.5 Lignin. - The sample shall be tested for lignin in accordance with TAPPI Test method T-236 os-76.

4.3.6 Ash content. - The sample shall be tested for Ash Content in accordance with TAPPI Test method T-211 om-80.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:43Z
Check the source to verify that this is the current version before use.

Supersedes page 3 dated 14 November 1985.