INCH-POUND

MIL-C-70770 (AR)
AMENDMENT 1
13 April 1993

MILITARY SPECIFICATION

CONTAINERS, SHIPPING AND STORAGE:
PA 137, PA 138, AND PA 141, FOR
THE M139 MINE DISPENSER SYSTEM

This Amendment forms a part of MIL-C-70770 (AR), dated 4 November 1992, and is approved for use by the U.S. Army Armament, Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 31

4.5.7: Delete in its entirety and substitute the following:

"4.5.7 Destructive test prior to production. Prior to production and as part of first article, workmanship samples shall be taken and examined for compliance to 3.5.1 and 3.5.2 and dimensionally for thickness. Each destructive test as specified in drawing 12564879 shall first be performed on the base shell and then on the cover shell. All samples for destructive testing shall be taken along the 0^{o} axis of the triaxial cloth. Sections shall also be taken at bracket secondary lamination as specified on the applicable drawing. Workmanship specimens shall be labeled by part number and section description. The specimens shall be retained as a standard for later use in maintaining good workmanship during production. If any of the specimens fail to meet the requirements listed in drawing 12564879, the entire shell lot shall be rejected."

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project: 1095-A263)

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:59Z
Check the source to verify that this is the current version before use.