INCH-POUND

A-A-50063B
January 14, 1991
SUPERSEDING
A-A-50063A
July 31, 1987

COMMERCIAL ITEM DESCRIPTION

BOOTS, KNEE AND HIP (RUBBER)

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification ZZ-B-530.

1. CLASSIFICATION

1.1 Classification. This commercial item description covers rubber boots in whole sizes 5 through 15 in the following types:

Type I - Knee length
Type II - Hip length

2. SALIENT CHARACTERISTICS

2.1 Description. The boots shall be heavy duty vulcanized rubber boots made over the manufacturer's regular boot lasts using rubber and rubber/cotton cloth parts in accordance with the manufacturer's standard practice. Type II boots shall have an adjustable top strap and knee patch.

2.2 Dimensions. For type I boots, the height (inside) at the back and front shall be not less than 14-1/2 inches. For type II boots, the extreme height (inside) shall be not less than 34 inches and the crotch height (inside) shall be not less than 29 inches. The girth measured around the inside of the type II boot at the crotch shall not be less than 23 inches. The circumference at the calf of the type I and II boot lasts shall be not less than 16 inches for sizes 5, 6, and 7; 16-1/2 inches for sizes 8 and 9; 17 inches for sizes 10 and 11; and 18 inches for sizes 12 through 15.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to: Commander, U.S. Army Natick Research, Development, and Engineering Center, ATTN: STRNC-ES, Natick, MA 01760-5014.

AMSC N/A

FSC 8430

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.

2.3 Rubber/cotton parts. The cotton cloth shall be either woven or knitted and shall be frictioned, calendar coated, or spread and calendar coated with rubber compound as necessary to prepare the parts such as leg linings, toe linings, vamp forms, and reinforcement strips necessary to build a boot.

2.4 Rubber parts. The rubber parts shall be made from upper compound or outsole and heel compound. The leg cover rubber shall be calendered from upper compound and shall be a minimum of 0.025 inch thick. Other gum rubber upper parts such as vamp, counter, and reinforcement strips shall be of appropriate thickness for the intended use. The outsole shall be cleated or heavily knurled and shall be a minimum of 0.285 inch at the ball. The heel shall be a minimum of 9/16 inch at the thinnest part and shall carry the manufacturer's standard tread design. The rubber parts shall conform to the following requirements:

Compound	Characteristic	Requirement	Test method (ASTM)
Upper compound	Tensile strength:		
	- initial	1000 psi (min)	D 412
	- after aging (7 days at 158°F)	At least 75 percent of initial tensile strength	D 573 and D 412
	Elongation:		
	- initial	375 percent (min)	D 412
	- after aging (7 days at 158°F)	At least 75 percent of initial elongation	D 573 and D 412
	Ozone resistance (bent loop - 3 days, 50 pphm at 104°F)	No cracks visible to the unaided eye	D 518 Procedure B D 1149
Outsole and heel compound	Abrasive index (before and after aging - 7 days at 158°F)	35	D 1630
	Hardness (before and after aging)	60 ± 10	D 2240

2.5 Top strap assembly (type II). The strap shall be either a double cotton cloth frictioned on both sides and coated with upper compound or a rubber strap not less than 0.090 inch thick. The strap shall be not less than 9-1/2 inches long and 5/8 inch wide. The loop at the top of the strap shall be large enough to permit easy passage and secure holding over a 2-inch belt. The strap buckle shall be made of brass, aluminum, or steel, and shall be of the slide type suitable for the intended purpose. Brass buckles shall be nickel plated; aluminum buckles shall be anodized with a coat of black enamel; and steel buckles shall be either nickel plated or have baked enamel finish. The strap slot shall be not less than 5/8 inch wide and the stay slot shall be not less than 7/16 inch wide.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.

2.6 Knee patch (type II). The boot upper shall have a knee patch of not less than 60 square inches, placed to prevent chafing.

2.7 Color and finish. The boots should be black in color, although other colors may be specified (see 5.2), and have a natural heater or dull lacquer finish.

2.8 Vulcanization. The boots shall be vulcanized under pressure to insure a watertight compact unit.

2.9 Leakage. The boots shall show no evidence of leakage when subjected to compressed air at 1 pound per square inch pressure while immersed in a tank of water to within 3 inches of the top of the boot.

2.10 Marking. The manufacturer's name or trademark shall be embossed on the outsole in the shank, or a manufacturer's label shall be used. The size shall be legibly incised on the outsole in the shank, or the size may be incised on a label and the label permanently vulcanized to the boot.

3. QUALITY ASSURANCE

3.1 Certification. The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics and requirements of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, quality assurance practices, and the leakage requirements stated herein. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

3.2 Visual examination. The boots shall be examined in accordance with MIL-STD-105 for conformance to design, material and construction requirements; any component full, tight or twisted; any open seam, hole, cut or tear; any spot or stain clearly noticeable; not the color specified in the contract or purchase order. The inspection level shall be II, and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 6.5. The lot size shall be expressed in units of parts of boots. The sample unit shall be one pair of boots.

3.3 Dimensional examination. The boots shall be examined for the following defects. The lot size shall be expressed in units of pairs of boots. The sample unit shall be one pair of boots. The inspection level shall be S-3, and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

DEFECTS:

Type I boots

Inside height at back and front from insole to top less than 14-1/2 inches

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.

Type II boots

Inside height from insole to extreme top less than 34 inches
Inside height from insole to crotch less than 29 inches
Inside width at crotch less than 11-1/2 inches (with boot lying flat on table)
Strap width or length less than specified minimum
Strap or stay slot on buckle less than specified minimum
Knee patch smaller than specified

4. PACKAGING

4.1 Packaging. Each mated pair of boots of one type only, shall be secured together with cotton tape or twine to prevent separation.

4.2 Packing. Seven pairs of type I, or six pairs of type II boots of one size only, shall be packed in a fiberboard shipping container conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each fiberboard container shall be fitted with a box liner conforming to type CF class domestic variety DW, grade 275 of PPP-B-636. Prior to placing each pair of hip boots in the container, the tops shall be folded over so that the packing can be accomplished as specified. The boots shall be packed within a shipping container so that the first pair of boots has the sole of one boot against one end panel and the side of the sole of the second boot resting on the ankle of the first boot. The remaining pairs of boots shall then be placed in the container in the same manner with every other pair reversed. Inside dimensions of each container shall approximate 23-1/2 inches in length, 15 inches in width, and 15 inches in depth. Approximate dimensions are furnished as a guide only. A sheet of 30 pound minimum basis weight kraft paper conforming to A-A-203 shall be used to completely separate each pair of boots from the others. Each container shall be closed in accordance with method II as specified in the appendix of PPP-B-636.

4.3 Palletization. When specified (see 5.2), boots, packed as specified in 4.2, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet type shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary or secondary straps in accordance with bonding means C and D or film bonding means F or G. Pallet pattern shall be number 3 in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be affected by reversing the pattern of each course.

4.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129.

5. NOTES

5.1 Intended use. The boots are intended for use as waterproof boots.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.

5.2 Ordering data.

a. Title, number, and date of this document.
b. Type and size of boots required (see 1.1).
c. Color required if other than black (see 2.7).
d. When palletization is required (see 4.3).

5.3 Sources of documents.

5.3.1 Source of government documents. Copies of Military and Federal documents are available from:

Standardization Documents Order Desk
Building 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

5.3.2 Sources of nongovernment association documents.

ASTM D 412 - Standard Test Methods for Rubber Properties in Tension
ASTM D 518 - Test Methods for Rubber Deterioration - Surface Cracking
ASTM D 573 - Test Methods for Rubber - Deterioration in an Air Oven
ASTM D 1149 - Test Method for Rubber Deterioration - Surface Ozone Cracking in a Chamber (Flat Specimens)
ASTM D 1630 - Test Method for Rubber Property - Abrasion Resistance (NBS abrader)
ASTM D 2240 - Test Method for Rubber Property - Durometer Hardness

are available from:

American Society for Testing and Materials (ASTM)
1916 Race Street
Philadelphia, PA 19103-1187

MILITARY INTERESTS:

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activities:

Army - MD
Air Force - 82
DLA - CT

User activities:

Navy - MC, YD
Air Force - 45

CIVIL AGENCY COORDINATING ACTIVITY:

GSA - FSS

PREPARING ACTIVITY:

Army - GL

(Project 8430-0392)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.