MILITARY SPECIFICATION

PAPER, RECORDING, ELECTROSENSITIVE

1. SCOPE

1.1 This specification covers the manufacture and performance of electrosensitive recording paper for use with U.S. Navy sound range recorders.

2. APPLICABLE DOCUMENTS

2.1 The following specifications and standards, of the issue in effect on date of invitation for bids, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

- UU-P-31 - Paper, General Specifications and Methods of Testing
- PPP-B-585- Boxes, Wood, Wirebound
- PPP-B-591- Boxes, Fiberboard, Wood-Cleated
- PPP-B-601- Boxes, Wood, Cleated-Plywood
- PPP-B-621- Boxes, Wood, Nailed and Lock-Corner
- PPP-B-636- Box, Fiberboard
- PPP-T-76- Tape, Pressure-Sensitive Adhesive, Paper, Water Resistant

MILITARY

- MIL-P-116- Preservation, Methods of
- MIL-B-10377- Boxes: Wood-Cleated, Veneer, Paper Overlaid
- MIL-L-10547- Liners, Case, Waterproof

STANDARDS

MILITARY

- MIL-STD-105- Sampling Procedures and Tables for Inspection by Attributes
- MIL-STD-129- Marking for Shipment and Storage

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. - The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

OFFICIAL CLASSIFICATION COMMITTEE
Uniform Freight Classification Rules

(Application for copies should be addressed to the Official Classification Committee, 1 Park Avenue at 33rd Street, New York 16, N. Y.)

3. REQUIREMENTS

3.1 Basic characteristics of paper stock. -

3.1.1 General description. - The paper stock shall be a white absorbent paper manufactured from bleached sulphite or sulphate wood pulp or esparto-wood pulp mixture. It shall be free from undigested pulp, bleach residues or other materials likely to cause discoloration of the impregnated paper during storage, or fading of the trace subsequently produced upon it. All alum and coloring matter shall be removed in the preparation of the pulp and sufficient starch shall be added to stiffen the finished paper. Rosin, or other sizing agent, shall not be used. Slight alkalinity shall be maintained by the retention in the paper of from 2 to 3 percent by weight of precipitated chalk of good quality. Particular care shall be taken during the manufacture of the paper to avoid the inclusion of particles of metallic iron (see 4.4.1.1).

3.1.2 Equilibrium moisture content. - The equilibrium moisture content of the paper corresponding to a relative humidity of not less than 60 percent at 20°C., when determined by the method specified in 4.4.1.2, shall not exceed 12 percent by weight of the dried paper.

3.1.3 Chemical composition. -

3.1.3.1 Acid soluble alkalinity. - The acid soluble alkalinity, determined by the method specified in 4.4.1.3.1, shall be not less than 2.0 percent nor more than 3 percent by weight of the dry paper, calculated as $CaCO_3$.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:37Z
Check the source to verify that this is the current version before use.

Acid soluble calcium. - The acid soluble
:termined by the method specified in
shall be not less than 2.0 percent nor
:.0 percent by weight of the dry paper
s $CaCO_3$.

Carbonated ash content. - The carbon-
the stock paper, when determined by
specified in 4.4.1.3.3, shall be not
1 4.0 percent by weight of the dry paper.

Iron content. - The iron content of the
when determined by the method speci-
1.3.4, shall not exceed 0.05 percent
)f the dry paper calculated as Fe.

pH value. - The pH value of the water
ared and tested by the method speci-
i.3.5 shall be not less than 7.0, nor
.5.

hysical characteristics. - The physical
tics of the stock paper shall be as
)le I when tested in accordance with

able I - Physical characteristics
)f stock paper (without coating).

stic	Requirement
:e ss t c r	90±5 grams per square meter 5.5±0.25 mils (1 mil=0.001 inch) 0.64±0.05
h ne on)	Not less than 20 pounds
h m)	Not less than 9 pounds
ie on)	Less than 4.25 percent
on)	Less than 7 percent

Texture and finish. - The texture and
the stock paper shall be such that no
ble surface roughening will occur due to
nent of the fibers when the tip of a stylus
nal spring loading of 14 grams traverses
at all speeds ranging from 1.5 inches per
a maximum of 300 inches per second.

npregnation of paper. -

3.2.1 Composition of impregnating solution. - The composition of the impregnating solution shall be as shown in table II.

Table II - Composition of impregnating solution.

Component	Weight	Percent of component (by weight of water added)
Potassium iodide (of analytical reagent quality)	6 pounds	5.0
Soluable starch (of analytical reagent quality)	3 pounds	2.5
Sodium hydroxide	0.25 ounce	0.013
Distilled water	120 pounds	
Formaldehyde (40 percent solution)	12 ounces	0.625
"SHIRLAN N.A." (or other antimould agent approved by the bureau or agency concerned)	0.38 ounce	0.02

3.2.2 Preparation of impregnating solution. - The impregnating solution shall be prepared by the following method:

(a) Make the starch into a thin paste with 6 pounds of distilled water. Raise the remainder of the water (less 12 ounces) to boiling point, and add first the potassium iodide and then, slowly, the starch paste to the boiling liquid. Allow the mixture to boil for an additional 2 minutes and then cool to air temperature.

(b) Dissolve the sodium hydroxide in 4 ounces of water, and add this solution carefully to the mixture until the pH of the mixture is raised to a value between 8.0 and 8.5. Then add 12 ounces of a 40 percent solution of formaldehyde.

(c) Dissolve the "SHIRLAN N.A." in 8 ounces of hot water (70° to 80°C.). Filter this solution through paper to remove the particles of insoluble matter and add the filtrate, with stirring, to the starch-iodide solution.

(d) The final mixture shall be almost clear and colorless with no sediment.

3.2.3 Method of impregnation. - The stock paper shall be passed through the impregnating solution at such a rate that the moisture content of the impregnated roll, immediately prior to sealing in its container, is between the limits specified in 3.3.2. (To obtain the high solution "pick-up" required, rubber or rubber sleeved rolls with critically controlled loading pressure are strongly recommended.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:37Z
Check the source to verify that this is the current version before use.

3.2.3.1 Contamination. - The most scrupulous care shall be taken to avoid contamination of the paper during the whole of its processing and subsequent handling before it is sealed in its container. In particular, proximity to sources of sulphurous fumes, to tobacco smoke or other agents likely to pollute the atmosphere, shall be carefully avoided. Special attention shall also be paid to avoiding contamination of the paper with specks of dust, rust, or particles of metallic iron. Corrosion-resistant steel bench tops, vessels, and roller fitting are recommended to ensure this.

3.2.3.2 Each batch of impregnating solution shall not be used for more than one day. Care shall be taken to ensure that the last rolls passed through the solution contain the quantity of potassium iodide specified herein.

3.3 Characteristics of impregnated rolls. -

3.3.1 General description. - The impregnated rolls shall be white or very pale cream in color, free from dark spots, discoloration or other imperfections. No creases or wrinkles shall be permitted in a finished roll of impregnated paper.

3.3.2 Moisture content. - The moisture content of the impregnated rolls immediately prior to sealing in their containers shall be 13 ± 1/2 ounces per 90 feet of length.

3.3.3 Chemical composition. -

3.3.3.1 Water soluble calcium. - When tested in accordance with 4.4.2.2.1, the water soluble calcium shall be not more than 0.3 percent of the weight of the dry paper.

3.3.3.2 Acid soluble calcium. - When tested in accordance with 4.4.2.2.2, the acid soluble calcium shall be not less than 1.7 percent nor more than 3.0 percent the weight of the dry paper.

3.3.3.3 Potassium iodide content. - The potassium iodide content of the impregnated rolls determined by the method specified in 4.4.2.2.3, shall be 0.6 ± 0.05 ounce per length of 90 feet.

3.3.3.4 pH value. - The pH value of the water extract prepared by the method specified in 4.4.2.2.4, shall be not less than 7.0, nor more than 8.5.

3.3.4 Physical characteristics. -

3.3.4.1 Width of paper. - The width of the paper after impregnation shall be not less than 6-1/32 inches and not more than 6-3/16 inches.

3.3.4.2 Outside diameter of roll. - The outside diameter of the impregnated rolls shall not exceed 3.600 inches as determined by an ac gauge.

3.3.4.3 Length of rolls. - The length of pregnated rolls shall be approximately 90 fe

3.3.4.4 Winding. - Even winding shall b tained throughout the entire length of the ro end faces shall be as flat and free from rin as possible, so that, when tested with a str edge, the "troughs" shall not permit a 40 m gauge or wire to pass. The roll shall also trally positioned on the tubular former (see so that the paper roll projects equally at ea of the roll.

3.3.4.5 Tensile strength. - The impreg paper in its moist condition shall be capabl standing a tension of at least 7 pounds on th (see 3.4.1) when tested in accordance with

3.3.4.6 Warning line to denote end of r continuous "WARNING" line to denote the a ing end of the roll shall be marked with ind every roll of paper. This line shall extend distance of 5 to 6 feet from the inner (form the roll and at approximately 1/4 inch from hand edge of the paper as seen in its record position.

3.3.5 Trace characteristics. - At the wi speed of 1.7 inches per second, individual t (spaced approximately 1/16 inch apart) shal clearly visible with 0.7 volt across the styl

3.4 Tubular formers. -

3.4.1 Dimensions. - The tubular former the moist impregnated paper is finally woun 6.10 ± 0.015 inches wide. It shall have an diameter of 1.25 ± 0.03 inches an outside d of 1.50 ± 0.03 inches.

3.4.2 Material. - The tubular former sl constructed of a suitable grade of polished nished bakelite or other synthetic compositi will not introduce any adverse chemical rea the impregnated paper when rolled thereon. tubular former shall also, if necessary, be to ensure a very low amount of moisture ab Metal formers shall not be used.

3.5 Marking. - A printed label bearing t ing inscriptions in BLOCK TYPE shall be s affixed to the outside of the container:

(a) KEEP IN COOL STORAGE. THIS IS NOT TO BE OPENED OR UNSI UNTIL REQUIRED FOR USE. THIS CARTON CONTAINS POTA

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:37Z
Check the source to verify that this is the current version before use.

IODIDE IMPREGNATED ELECTROSENSITIVE PAPER FOR USE WITH U.S. NAVY SOUND RANGE RECORDERS.

(b) CONTRACT NO._____
MANUFACTURER'S NAME (OR INITIALS)_____
BATCH NO. OF PAPER BASE_____
SOLUTION BATCH NO._____
ROLL NO._____
SIZE OF ROLL_____
WEIGHT OF PACKAGED ROLL_____
DATE PACKAGED_____

3.5.1 The type used in inscription specified in 3.5 (a) shall be considerably larger and bolder than the remainder of the inscription on the label. Special care shall be taken to use an adhesive that will ensure permanent attachment of the label to the container. The label shall be made long enough to encircle the container and provide a generous overlap. The label information specified in 3.5 (b) shall be inserted in the spaces indicated. The letter size used for inserting the manufacturer's name shall not exceed the smallest used for the remainder of the labels.

3.6 Federal stock number. - A Federal stock number will be required. Requests for stock numbers shall be made to the bureau or agency concerned.

3.6.1 The stock number with proper manufacturing prefix letters as assigned by the bureau or agency concerned, shall be stamped with india ink in letters 3/16-inch high in two places across each face of the roll.

3.7 Workmanship. - Workmanship shall be of the highest grade throughout and in accordance with the best commercial practice in the manufacturing of sensitized material.

4. QUALITY ASSURANCE PROVISIONS

4.1 The supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government. Inspection records of the examination and tests shall be kept complete and available to the Government as specified in the contract or order. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Sampling. -

4.2.1 Definition of lot for inspection of basic paper stock. - For purposes of sampling basic paper stock, a lot shall consist of all basic paper stock of one batch submitted for inspection at the same time.

4.2.2 Definition of lot for inspection of impregnated paper. - For purposes of sampling impregnated paper, a lot shall consist of impregnated paper made from the same batch of basic paper stock, the same batch of impregnating solution, and submitted for inspection at the same time.

4.2.3 Sampling for inspection of basic paper stock. - From each lot of basic paper stock presented for inspection, a suitable number of samples shall be selected for inspection in accordance with 4.3.1.

4.2.4 Sampling for examination of sealed containers. - A random sample of filled containers shall be selected in accordance with Standard MIL-STD-105 at inspection level I and acceptance quality level, 2.5 percent defective, to verify compliance with 4.3.2.

4.2.5 Sampling for inspection of adequacy of sealed containers and impregnated rolls. - From each lot of packaged, impregnated paper, samples shall be selected as shown in table III for inspection in accordance with 4.3.3.

Table III - Sampling for inspection of adequacy of sealed containers and impregnated rolls.

Lot size of impregnated rolls	Number of samples for test	Acceptance number	Rejection number
180 and under	1	0	1
181 to 500	2	0	1
501 to 800	3	0	1
801 to 1,300	5	0	1
1,301 to 3,200	7	1	2
3,201 to 8,000	10	1	2
8,001 to 22,000	15	2	3
22,001 to 40,000	25	2	3

4.3 Inspection. -

4.3.1 Inspection of basic paper stock. - The basic paper stock samples selected in accordance with 4.2.3 shall be visually and dimensionally examined to determine conformance with this specification and shall be subjected to the tests specified in 4.4.

4.3.2 Examination of sealed containers (individual). - Each sample filled container shall be examined for defects of construction of the container for evidence of parted seams and for unsatisfactory marking. Each filled container shall also be weighed to determine accuracy of weight markings. Any container in the sample having one or more defects shall be rejected, and if the number of defective containers in any sample exceeds the acceptance

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:37Z
Check the source to verify that this is the current version before use.

number for the applicable sampling plan of Standard MIL-STD-105, the lot represented by the sample shall be rejected.

4.3.3 Inspection of adequacy of sealed containers and impregnated rolls. - The samples selected in accordance with 4.2.5 shall be tested for adequacy of packaging specified in 5.1.1. The rolls shall then be removed from the containers and examined for the visual and dimensional requirements of this specification and tested in accordance with 4.4.2. Any sample in the lot having one or more defects, either in the container or impregnated paper roll, shall be rejected. If the number of defective containers, or rolls, or a combination of both exceeds the acceptance number for the lot, the lot represented by the sample shall be rejected.

4.4 Test procedures. -

4.4.1 Testing of basic paper stock. -

4.4.1.1 Test for suitability of pulp. - Suitability of basic pulp shall be determined in accordance with method 300 of Specification UU-P-31, and other suitable means to determine compliance with 3.1.1. Alkalinity, calcium content and iron content shall be determined in accordance with 4.4.1.3.1, 4.4.1.3.2, and 4.4.1.3.4, respectively.

4.4.1.2 Test for equilibrium moisture content. - The basic stock paper selected for test in accordance with 4.2.3 shall be conditioned in accordance with method 102 of Specification UU-P-31, except that the relative humidity shall be at least 60 percent. After a constant weight is attained, the equilibrium moisture content shall be rapidly and accurately determined in accordance with method 240 of Specification UU-P-31, except that the moisture content shall be reported as a percent of the dry weight of the paper (see 3.1.2).

4.4.1.3 Tests for chemical composition. -

4.4.1.3.1 Acid soluble alkalinity. - The acid soluble alkalinity shall be determined by the following method: Weight 5 grams (g.) of the paper, cut into small pieces and place in a 250 milliliter (mℓ) stoppered flask. Add 200 mℓ of N/40 hydrochloric acid and place on a mechanical shaker for 1 hour. Titrate 100 mℓ of the filtered liquid with N/10 sodium hydroxide, using methyl orange as an indicator. Carry out a blank determination omitting only the sample. From the difference between the two titrations, calculate the acid soluble alkalinity as a percentage by weight of $CaCO_3$ on the dry paper. (Save titration material for acid soluble calcium determination in accordance with 4.4.1.3.2.)

4.4.1.3.2 Acid soluble calcium. - After the titration conducted in 4.4.1.3.1, from the same portion of the extract, the calcium content shall be determined by any standard chemical method and calculated as a percentage by weight of $CaCO_3$ on the dry paper.

4.4.1.3.3 Carbonated ash content. - The carbonated ash content shall be determined by the following method: Ignite 5 g. of the paper stock in a porcelain crucible. Heat slowly at first until the paper is completely charred and finally brought to bright redness in a furnace until all carbonaceous matter has been completely removed. Cool to room temperature; add 1 mℓ of water and 0.25 g. of pure powdered ammonium carbonate. Warm gently to evaporate to dryness and finally heat in an oven kept at 150°F. until a constant weight is attained. Calculate the weight of ash as a percentage by weight of the dry paper (see 3.1.3.3). (Save carbonated ash for iron content determination in accordance with 4.4.1.3.4.)

4.4.1.3.4 Iron content. - The total iron content of the carbonated ash specified in 4.4.1.3.3, shall be determined by any suitable standard method, and calculated as a percentage by weight of the dry paper from which it was derived (see 3.1.3.4).

4.4.1.3.5 pH value. - The pH value of the stock paper shall be determined in accordance with method 200 of Specification UU-P-31 (see 3.1.3.5).

4.4.1.4 Tests for physical characteristics. -

4.4.1.4.1 Substance (basic weight). - The substance of the paper shall be determined in accordance with method 110 of Specification UU-P-31, except that results shall be reported in grams per square meter.

4.4.1.4.2 Thickness. - The thickness of the paper shall be determined in accordance with method 173 of Specification UU-P-31.

4.4.1.4.3 Apparent specific gravity. - From the results obtained in 4.4.1.4.1 and 4.4.1.4.2, the apparent specific gravity shall be calculated.

4.4.1.4.4 Tensile strength and stretch. - Tensile strength and stretch shall be determined in accordance with method 171 of Specification UU-P-31.

4.4.2 Testing of impregnated paper. -

4.4.2.1 Moisture content. - The moisture content of the impregnated paper shall be rapidly and accurately determined in accordance with method 240 of Specification UU-P-31, except that the moisture content shall be reported in ounces per 90 feet of length (see 3.3.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:37Z
Check the source to verify that this is the current version before use.

4.4.2.2 Tests for chemical composition. -

4.4.2.2.1 Test for water soluble calcium. - The water soluble calcium content shall be determined by the following method: Cut off exactly 4 feet of the moist impregnated paper and tear up into small pieces. Place in a 600 mℓ beaker and add 200 mℓ of boiling water. Let stand for 30 minutes on a boiling water bath with occasional stirring and then decant the extract. Add an additional 200 mℓ of boiling water to the paper and repeat the extraction for 10 minutes. Repeat this extraction with an additional two 200 mℓ portions of boiling water. (Retain the paper chips for testing in accordance with 4.4.2.2.2.) Filter the combined extracts and make up to a volume of 1000 mℓ with water. Determine the calcium content of 500 mℓ of solution by any standard chemical method. Calculate the calcium as a percentage of $CaCO_3$ on the dry paper (see 3.3.3.1). (Retain the remaining 500 mℓ of the filtered solution for determination of potassium iodide content in accordance with 4.4.2.2.3.)

4.4.2.2.2 Test for acid soluble calcium. - The acid soluble calcium shall be determined by the following method: Dry the paper residue, resulting from the extraction in 4.4.2.2.1, in an oven kept at 100° to 105°C. until a constant weight is attained. Determine the acid soluble calcium content by any standard chemical method. Calculate the result as a percentage by weight of $CaCO_3$ on the dry extracted paper (see 3.3.3.2).

4.4.2.2.3 Test for potassium iodide content. - The potassium iodide content shall be determined by the following method:

(a) Pipette 100 mℓ of the filtered extract, prepared as specified in 4.4.2.2.1, into a large nickel crucible (200 mℓ capacity). Add 2 g. of sodium hydroxide and evaporate carefully to dryness. (The liquid can be conveniently evaporated to complete dryness by means of an infrared dryer.) Cover the crucible and ignite at 450° to 500°C. for 1 hour. Dissolve the melt in about 20 mℓ of water and transfer to a 200 mℓ distillation flask, keeping the total volume below 100 mℓ. Add 2 g. of analytical reagent quality ferrous sulphate and 2 g. of analytical reagent quality ferric ammonium sulphate; mix and connect the flask to a splash head and double trap (all joints shall be of ground glass), containing 25 mℓ of 10 percent solution of potassium iodide.

(b) Connect the flask also to a tap funnel containing 40 mℓ of sulphuric acid (70 mℓ of concentrated H_2SO_4 plus 30 mℓ of water), the upper end of the tap funnel being connected to a source of nitrogen. With a very small flow of nitrogen, run the sulphuric acid very gradually while swirling the flask. When the addition of acid has been completed, boil the contents of the flask gently so that about 30 mℓ of water distills during a period of about 30 minutes. During the distillation it is necessary to cool the trap in iced water and to keep a slow current of nitrogen flowing through the apparatus.

(c) Transfer the contents of the trap to a 500 mℓ conical flask, if necessary, using a few more mℓs of 10 percent potassium iodide solution to dissolve all the solid iodine. Make up the volume to approximately 300 mℓ with distilled water. Add 10 mℓ of 2N hydrochloric acid and titrate in the usual way with N/50 sodium thiosulphate solution. Calculate the potassium iodide content as ounces per 90 feet of length (see 3.3.3.3).

4.4.2.2.4 pH value. - The pH value of the impregnated paper shall be determined in accordance with method 200 of Specification UU-P-31.

4.4.2.3 Tensile strength test. - The impregnated wet paper shall be placed in a suitable test machine so that the full width of the paper is held while the paper is tested in tension with the grain. The clearance distance between the jaws shall be not less than 9 inches nor more than 12 inches (see 3.3.4.5).

5. PREPARATION FOR DELIVERY

5.1 Packaging. -

5.1.1 Unit packaging. - Each individual impregnated moist roll shall be placed in a barrier bag fabricated from polyethylene immediately after it emerges from the impregnating machine. After the roll has been placed in its bag, the outer layer of paper which has been in contact with the operator's hand shall be removed. The bag shall then be heat sealed. The packaged rolls shall be immediately packaged in their outer containers to minimize exposure to light. Each roll shall be individually packaged in a snug fitting water vaporproof metal end, spiral wound container capable of passing the quick leak test specified in Specification MIL-P-116.

4.1.2 Intermediate packaging. - Six rolls of recording paper, packaged as specified in 5.1.1, shall be placed in a corrugated fiberboard box conforming to Specification PPP-B-636. The fiberboard box shall be constructed of 275 pounds

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:37Z
Check the source to verify that this is the current version before use.

minimum Mullen test fiberboard. The box shall be provided with corrugated fiberboard separator sheets to accommodate the six unit containers, and top and bottom corrugated fiberboard pads shall be provided for the full inside length and width of the box. The separator sheets and pads shall be of 200 pounds minimum Mullen test corrugated fiberboard.

5.2 Packing (see 6.1). -

5.2.1 Level A. - Material shall be packed in containers conforming to any one of the following specifications at the option of the supplier:

Specification	Box	Type or class
PPP-B-585	Wood, Wirebound	Class 3 Use
PPP-B-591	Fiberboard, Wood-Cleated	Overseas Type
PPP-B-601	Wood, Cleated-Plywood	Overseas Type
PPP-B-621	Wood, Nailed and Lock Corner	Class 2
PPP-B-636	Fiberboard	Class 2
MIL-B-10377	Wood-Cleated, Veneer Paper Overlaid	Overseas Type

Shipping containers shall have caseliners conforming to Specification MIL-L-10547. Caseliners shall be closed and sealed in accordance with the appendix to Specification MIL-L-10547. Caseliners for Class 2 fiberboard boxes conforming to Specification PPP-B-636 may be omitted provided all corners and edge seams and manufacturer's joints are sealed with minimum 1-1/2 inch wide tape conforming to Specification PPP-T-76. Boxes shall be closed, strapped or banded in accordance with the applicable box specification or appendix thereto. The gross weight of wood or wood-cleated boxes shall not exceed 200 pounds.

5.2.2 Level B. - Material shall be packed in containers conforming to any of the following specifications at the option of the supplier:

Specification	Box	Type or class
PPP-B-585	Wood, Wirebound	Class 1 or 2 Use
PPP-B-591	Fiberboard, Wood-Cleated	Domestic Type
PPP-B-601	Wood, Cleated-Plywood	Domestic Type
PPP-B-621	Wood, Nailed and Lock Corner	Class 1
PPP-B-636	Fiberboard	Class 2
MIL-B-10377	Wood-Cleated Veneer Paper Overlaid	Domestic Type

Box closures shall be as specified in the applicable box specification or appendix thereto. The gross weight of wood or wood-cleated boxes shall not exceed 200 pounds.

5.2.3 Level C. - Material shall be packed in containers of the type, size and kind commonly used for the purpose, in a manner that will insure safe delivery and acceptance at destination. Shipping containers shall comply with the Uniform Freight Classification Rules and Regulations or rules and regulations of other carriers, as applicable to the mode of transportation.

5.3 Marking. - In addition to any special marking required by the contract or order, interior packages and exterior containers shall be marked in accordance with Standard MIL-STD-129.

6. NOTES. -

6.1 Ordering data. - Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Selection of applicable level of packing required (see 5.2)

Patent notice. - When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Preparing activity:
Navy-Bureau of Ships
(Project No. 7530-N001Sh)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:37Z
Check the source to verify that this is the current version before use.