INCH-POUND
A-A-50129B
May 1, 2019
SUPERSEDING
A-A-50129A
March 7, 1996

COMMERCIAL ITEM DESCRIPTION

CLOTH, FLANNEL, LIGHTWEIGHT

The General Services Administration has authorized the use of this Commercial Item Description (CID) for all federal agencies.

1. SCOPE. This Commercial Item Description covers the requirements for cotton flannel lightweight cloth used as interfacing to manufacture coats, caps and clean surfaces.

2. CLASSIFICATION. This cloth shall be available in one (1) type.

3. SALIENT CHARACTERISTICS.

3.1 Description. The cloth shall be a plain weave, cotton fiber and it shall be napped on both sides to meet the requirements specified in Table I. The color and width of the cloth shall be as specified in the contract or purchase order.

3.2 Color. The color of the finished cloth shall be natural or dyed as specified (see 7.5) and shall meet the colorfastness requirements when tested as specified in 3.3. The use of dyes and compounds containing elementary sulfur capable of oxidation to sulfuric acid is prohibited. The dyed cloth shall be "Free" of labile sulfur when tested as specified in 3.4.

3.2.1 Standard sample. The finished cloth shall match the standard sample for shade and appearance.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: Attn: DLA Troop Support, 700 Robbins Avenue, Philadelphia, PA 19111-5096. Since contact information can change, verify the currency of the address information using Acquisition Streamlining and Standardization Information System (ASSIST) online database https://assist.dla.mil/.

AMSC N/A FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:39Z
Check the source to verify that this is the current version before use.

3.2.2. Visual shade matching. The color and appearance of the cloth shall match the standard sample when viewed using the AATCC Evaluation Procedure 9, Option A, with sources simulating artificial daylight D75 illuminant with a color temperature of 7500 (± 200) K illumination of 100 (± 20) foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2856 (± 200) K.

3.3 Requirements. The finished napped cloth shall conform to the requirements specified in Table I when tested in accordance with test methods in Table I.

TABLE I. Requirements and test methods

Characteristics	Requirement	Test method
Fiber identification Cotton	 See 3.1	 AATCC 20 (see 7.4)
Weight, oz./sq.yd. (min.)	4.0	ASTM D3776/D3776M
Yarns per inch (min.) Warp Filling	 42 40	 ASTM D3775 ASTM D3775
Breaking strength, lbs. (min.) Warp Filling	 32 19	 ASTM D5034 ASTM D5034
Dimensional stability, percent (max.) Warp Filling	 2.0 2.0	 AATCC 135, (3)(III)(Aiii) AATCC 135, (3)(III)(Aiii)
Colorfastness (colored only), (min.) Crocking Laundering (after three(3) cycles) Perspiration (acid and alkaline)	 3.5 3-4 3-4	 AATCC 8 1/ AATCC 61, Test 3A 2/ AATCC 15 2/

1/ Rated using AATCC Procedure 8, AATCC 9 Step Chromatic Transference Scale
2/ Rated using the AATCC Evaluation Procedure 1, Gray Scale for Color Change and AATCC Evaluation Procedure 2, Gray Scale for Staining.

3.4 Presence of labile sulfur. In the determination of labile sulfur in textile materials with lead acetate, two (2) 1.50 gram (± 0.01) gram samples from each material submitted for evaluation shall be tested. Each of the two (2) samples shall be cut into very small pieces and placed into separate test tubes. The samples shall be submersed in a stannous chloride solution that contains 100 grams of stannous chloride crystals ACS in 100 millimeters of hydrochloric acid ACS (35 percent concentration) and 50 milliliters of distilled water. A filter paper wet out with a 5.0 percent lead acetate solution shall be placed over the top of the test tube. The lead acetate solution contains 5.0 grams of lead acetate CP reagent grade and enough distilled water to make up a 100 milliliter solution; if the solution is not clear, add a few drops (one at a time) of glacial acetic acid until the solution is clear. The test tube containing the textile sample, stannous chloride and wet filter paper shall be heated over a low flame until the solution is boiling. The

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:39Z
Check the source to verify that this is the current version before use.

solution should not be heated for more than 15 seconds. A brown to black stain on the filter paper should be evaluated as follows.

Free	-	The filter paper shows no discoloration of staining of any kind.
Slight	-	The filter paper shows a light tan to light brown discoloration stain.
Moderate	-	The filter paper shows a dark brown discoloration stain.
Severe	-	The filter paper shows a black color stain.

3.5 Length and put-up. Unless otherwise specified (see 7.5), for Government procurement only, the cloth shall be furnished in continuous lengths of not less than 40 yards and shall be put-up full width on rolls.

3.6 Labels. Each roll of finished cloth shall be labeled or ticketed for fiber content in accordance with the Rules and Regulations under the Textile Fiber Products Identification Act (see 7.1.2).

3.7 Workmanship. The finished cloth shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the contractor's own quality assurance standards and the quality assurance standards defined by the technical data in the bid package.

4. REGULATORY REQUIREMENTS. Unless otherwise specified the offer/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

5. PRODUCT CONFORMANCE PROVISIONS.

5.1 Product conformance. The finished cloth provided shall meet the salient characteristics of this Commercial Item Description, conform to the producer's specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance.

5.2 Market acceptance. This finished cloth must have been sold to the commercial market or the Government.

5.3 End item inspection procedures. Sampling for inspection shall be conducted in accordance with ANSI/ASQ Z1.4 - Sampling Procedures and Tables for Inspection of Attributes (see 7.2.2).

5.4 Visual examination. The finished cloth shall be examined for the defects listed below as defined in ASTM D3990:

Material	Any hole, cut, or tear.
	Puckered, wrinkled or creased/pleated material
Label	Label missing, incorrect, or illegible. Required information missing from the label.
Packaging	Not packaged in accordance with the contract or purchase order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:39Z
Check the source to verify that this is the current version before use.

5.5 Acceptance criteria. Acceptance criteria shall be as specified in the contract or purchase order (see 7.5).

6. PACKAGING. Preservation, packing, and marking shall be as specified in the contract or purchase order (see 7.5).

7. NOTES.

7.1 Sources of Government documents.

7.1.1 Copies of Government documents are available online at https://quicksearch.dla.mil.

7.1.2 Rules and Regulations under the Textile Fiber Products Identification Act are available online at https://www.ftc.gov.

7.2 Sources for Non-Government documents.

7.2.1 AATCC test methods are available online at https://www.aatcc.org.

7.2.2 ANSI/ASQ Z1.4 – Sampling Procedures are available online at https://www. asq.org.

7.2.3 ASTM Standards are available online at https://www.astm.org.

7.3 Intended use. This cloth is intended for use on interfacing of clothing items or to clean surfaces.

7.4 Certificate of compliance. The contracting activity may select to accept a certificate of compliance for stated requirement.

7.5 Ordering data. The contract or purchase order should specify the following:

a. Title, number, and date of this commercial item description
b. Color required (see 3.2)
c. Length put-up required (see 3.5)
d. Labeling information (see 3.6)
e. Product conformance provisions (see 5.)
f. Packaging requirement (see 6.)

7.6 Subject terms.

Cotton
Interfacing
Napped

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:39Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

Custodians:
Army - GL
Navy - NU
Air Force – 11

Review Activities
Army - MD
Navy - MC

CIVIL COORDINATING AGENCY ACTIVITY

GSA-FAS

Preparing Activity:

DLA-CT

(Project 8305-2019-007)

Note: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:39Z
Check the source to verify that this is the current version before use.