INCH-POUND

MIL-C-48882D (AR)
AMENDMENT 2
23 August 1994
SUPERSEDING
AMENDMENT 1
25 September 1992

MILITARY SPECIFICATION

CHARGE, PROPELLING, 81MM
PARTS AND CONTAINER ASSEMBLY

This Amendment forms a part of MIL-C-48882D (AR), dated 5 March 1990, and is approved for use by the U.S. Army Armament, Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

2.1.2, under Drawings: Change title for Drawing 9313721 as follows:

"Packing and Marking for Box, Fiberboard, Outer for Charge, Propelling or Container Assembly."

PAGE 4

3.9: Delete in its entirety and substitute the following:

"3.9 Homogeneity of material. The material used to manufacture the parts and assemblies shall be uniform in structure or composition throughout. The presence of spots 1/4 inch or larger shall indicate non-homogeneity. The presence of thin membrane-like areas in the nose sections of the part or assembly shall indicate non-homogeneity. The top and bottom halves shall not exhibit non-homogeneities including cracks, splits, cuts, tears, rips or holes when tested as specified in 4.5.7. The Government shall establish visual standards prior to production with the assistance of the contractor."

AMSC N/A FSC 1315
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:42Z
Check the source to verify that this is the current version before use.

PAGE 7

Table I, Closure: Delete "Composition ...1/ ...100 2/ ...3.2 ...4.5.1" and substitute "Composition ...1/ 4/ ...100 2/ ...3.2 ...4.5.1"

Container Assembly: Delete "Composition ...5 2/ ...3.2 ...4.5.1" and substitute "Composition 4/ ...5 2/ ...3.2 ...4.5.1"

Notes, add Note 4 as follows: "4/ Microphotographs shall serve as evidence of acrylic fibrillation."

PAGE 10

4.2.2.2: Delete Minor 201.

PAGE 12

4.4.2.4, Major 101: Delete "101 ...Composition 1/ ...100 2/ ...3.2 ...4.5.1" and substitute "101 ...Composition 1/ 4/ ...100 2/ ...3.2 ...4.5.1"

Minor 201: Delete "Length 3/" and substitute "Length (if applicable) 3/".

Add the following:

"Minor	Title	AQL	Reg Para.	Para. Ref
205	Diameter (if applicable) 3/	0.65%	3.2	Gage"

Notes, add Note 4 as follows: "4/ Microphotographs shall serve as evidence of acrylic fibrillation."

PAGE 13

4.4.2.5, Major 106: Delete "106 Composition ...5 1/ ...3.2 ...4.4.3.1/4.5.1" and substitute "106 Composition (3/) ...5 1/ ...3.2 ...4.4.3.1/4.5.1"

Notes, add Note 3 as follows: "3/ Microphotographs shall serve as evidence of acrylic fibrillation."

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:42Z
Check the source to verify that this is the current version before use.

4.4.2.6, Title block - Delete:

"Packing and Marking for Box, Fiberboard, Outer for Charge, Propelling, M205 or Container Assembly"

and substitute

"Packing and Marking for Box, Fiberboard, Outer for Charge, Propelling or Container Assembly"

PAGE 17

* 4.4.3.1, Delete in its entirety and substitute the following:

"4.4.3.1 Composition. The container moldings and closure material shall be selected from each lot and tested in accordance with 4.5.1. The container moldings shall be free of silicone. The lot shall be rejected if the sample fails to comply with the requirements."

* 4.4.3.2, Delete in its entirety and substitute the following:

"4.4.3.2 Stability heat test (134.5 C). The container moldings and closure material shall be selected from each lot and tested in accordance with 4.5.2. The container moldings shall be free of silicone. The lot shall be rejected if the sample fails to comply with the requirements."

PAGE 20

* 4.5.1.3.3.1, Delete in its entirety and substitute the following:

"4.5.1.3.3.1 Nitrocellulose. Schulze-Tiemann Method for Nitrocellulose (NC) Determinations. Calibrate a eudiometer tube prior to assembly of the Schulze-Tiemann apparatus by suspending the tube in an upside down position and filling this with incremental volumes of aqueous ethanol solution from a buret. Take a reading on the eudiometer tube for each volume of aqueous ethanol transferred from the buret. Subtract each volume measured with the buret from the corresponding reading on the eudiometer tube. Take the average of the differences between the buret and eudiometer readings. This average is the eudiometer volume correction X.

The value of X is positive if the buret readings are smaller than the eudiometer readings and vice versa.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:42Z
Check the source to verify that this is the current version before use.

Assemble a 250-ml round-bottom flask, gas evolution apparatus, eudiometer tub, NaOH bath, led band, heating mantle and leveling bulb as shown in Figure 1.

Calibrate the apparatus with dry standard A.C.S. grade KNO_3.Follow the procedure of analysis below using 0.5-0.7 g of standard KNO_3 weighed to the nearest 0.1 mg. Calculate the factor of the apparatus according to the following equation:

$$F = \frac{616.8W(273.15+T)}{(V-X)\ (B-C-P-3.48)}$$

F = S-T Method Correction Factor
W = Mass of KNO_3 (g)
T = Temperature of Condenser Water (degrees C)
V = Volume of Gas in Eudiometer Tube (ml)
B = Barometric Pressure (mmHg)
C = Temperature Correction (mm Hg), See paragraph 4.5.1.3.3.2
P = Vapor Pressure of Water over 33% W/W NaOH at T (mm Hg), See paragraph 4.5.1.3.3.3
X = Eudiometer Volume Correction (ml)

Prepare samples as follows: Cut sample into 1/4 inch pieces or smaller. Dry to constant weight using the microwave moisture analyzer then store in a desiccator.

Fill the eudiometer tube with the NaOH solution by means of the leg bulb. Weigh between 0.7 and 1.0 g of specimen to the nearest 0.1 mg and transfer this into the round-bottom flask. Add 30 ml of deionized (DI) water, heat the water to boiling and purge the flask/gas evolution apparatus assembly with steam for 5 to 10 minutes. Remove the heat for a minute then add 25 ml of $FeCl_2$ solution, 25 ml concentrated HCl, and 10 ml of DI water.

Place the eudiometer tube over the tip of the gas evolution apparatus and allow the reaction to continue for 20-30 minutes or until the bubbling has stopped. Add 30 ml of DI water through the addition funnel in a similar manner and continue heating for 5 to 10 more minutes. Move the eudiometer tube away from the gas evolution apparatus, turn off the heat, and release the vacuum in the flask by opening the addition funnel stopcock. Allow the eudiometer tube to stand for at least 10 minutes, then read the gas volume on the eudiometer tube to the nearest 0.1 ml at equilibrium pressure with the atmosphere using the leveling bulb.

Source: https://assist.dla.mil -- Downloaded: 202640-22T19:42Z
Check the source to verify that this is the currentversion before use.

Calculate the NC content of sample according to the following equation:

$$\%NC = \frac{2.246F(V-X)\ (B-C-P-3.48)}{NW(273.15+T)}$$

V = Volume of Gas in Eudiometer Tube (ml)
X = Eudiometer Volume Correction
B = Barometric Pressure (mm Hg)
C = Temperature Correction (mm Hg), See para. 4.5.1.3.3.2
P = Vapor Pressure of Water over 33% (w/w) NaOH at T (mm Hg), See para. 4.5.1.3.3.3
F = S-T Method Correction Factor
N = Percent Nitrogen in NC (%)
W = Mass of Sample (g)
T = Temperature of Condenser Water (degrees C)

Preparation of $FeCl_2$ Solution

Prepare the solution by adding 1000 g of $FeCl_2 .4H_2O$, 1200 ml DI water, and 70 ml of concentrated HCl into a 5-liter round-bottom flask. Attach a reflux condenser and reflux for 20 minutes. Cool to room temperature. Slowly add 20 grams of iron fillings or powder to the cool solution. When the gas evolution stops, filter quickly. Use A.C.S. grade chemicals.

Preparation of NaOH Solution, 33% (w/w)

Dissolve 330 g of reagent grade NaOH in 670 g of DI water.

PAGE 21

* Delete Figure 1 and substitute a new Figure 1 (attached).

Source: https://assist.dla.mil -- Downloaded: 202610-22T19:42Z
Check the source to verify that this is the currentversion before use.




FIGURE 1.
Apparatus for the determination of nitrocellulose by the Schulze-Tiemann method

Source: https://assist.dla.mil -- Downloaded: 2026/04-22 19:42:22
Check the source to verify that this is the latest version before use.

* 4.5.1.3.4.1, Delete in its entirety and substitute the following:

"4.5.1.3.4.1 Alternate Method

Preparation of samples. Each sample shall be cut into approximately 1/4 inch squares or circles. Cut and dry, in microwave or oven, approximately 2.5 g from each sample and cool in desiccator. From each sample, approximately 1.0 g test specimen shall be weighed to the nearest 0.2 mg. Test is destructive and sample shall be removed from the lot.

Analytical procedure

Solvent Extraction

Place the test specimen in a centrifuge bottle and add about 50 ml of absolute methanol. Completely homogenize the specimen in methanol for approximately 2 minutes with a polytron homogenizer. Turn the homogenizer to low speed, then with a squirt bottle of technical grade acetone, slowly add the acetone down the shaft of the homogenizer until the level reaches about 1/2 inch below the shoulder of the bottle. Stir at slow speed for 2 minutes. Centrifuge the contents in the bottle for 5 minutes and decant the liquid. Repeat the dispersion of the specimen in acetone without methanol, centrifuge the mixture, and decant the clear liquid. Rinse the polytron shaft with acetone and save the rinsing in the centrifuge bottle containing the specimen. Set up a vacuum filter equipped with an appropriate filter paper. Swirl the contents in the bottle then pour the entire mixture into the filter funnel. Turn on the vacuum. Rinse the shaft with more acetone, catching the rinsing in the bottle, and pouring this into the filter funnel until all the fibers have been transferred into the filter. When all the liquid has drained into the flask, rinse the sides of the funnel with acetone to collect all the fibers on the filter paper. Leave the vacuum on for about one minute to dry the specimen. Remove the vacuum funnel then carefully remove the filter paper and folding this over the specimen to insure no loss of material.

Source: https://assist.dla.mil -- Downloaded: 202640-22T19:42Z
Check the source to verify that this is the currentversion before use.

Reagents

SODIUM HYDROXIDE - 400 g solid NaOH dissolved in H_2O and diluted to one liter

THIOSULFATE SOLUTION - 102 g $Na_2S_2O_3.5\ H_2O$ dissolved in H_2O and diluted to one liter

SULFURIC ACID - 93-98% H_2SO_4, N_2Free

HYDROCHLORIC ACID STANDARD SOLUTION - 0.1N

SODIUM HYDROXIDE STANDARD SOLUTION - 0.1N

BORIC ACID SOLUTION - 40 g H_3BO_4 dissolved in one liter aqueous solution

POTASSIUM HYDROGEN PHTHALATE - Reagent grade

PHENOLPHTHALEIN INDICATOR - 1 g phenolphthalein dissolved in 200 ml ethyl alcohol

KJEL-FAST CATALYST

KJELDAHL DIGESTION CATALYST - Mercury-Free such as Kelmate NT

Apparatus

Use a Buchi or CEM Kjel-Fast digester, or equivalent, a pyrex reaction tube or flask, a distillation adapter and a Buchi distillation unit.

Digestion

Using the Buchi Digester

Place the filter paper containing the specimen in a reaction tube and add one packet of Kjeldahl digestion catalyst and 25 ml of concentrated H_2SO_4. Attach the reaction tube to a manifold (by means of a clamp) which in turn is connected to a water aspirator. Set the reaction tube in the Buchi digester, turn on the latter and allow the tube and content to cool to room temperature.

Source: https://assist.dla.mil -- Downloaded: 202640-22T19:42Z
Check the source to verify that this is the current version before use.

Using the Kjel-Fast Digestor

Turn on the CEM Kjel-Fast digestion unit and water supply. (The power switch is on the bottom right corner or the back. The water spigot is behind the unit.)

The Kjel-Fast unit will prompt:

S-1 SET TIME -

Press 45 ENTER. Then the prompt will be:

S-1 SET POWER -

Press 100 ENTER

There are four stages to the program; the unit will prompt you for the next stage after each is entered. The program is as follows:

S-1 SET TIME = press 45 ENTER
S-1 SET POWER = press 100 ENTER
S-2 SET TIME = press 45 ENTER
S-2 SET POWER = press 100 ENTER
S-3 SET TIME = press 320 ENTER
S-3 SET POWER = press 80 ENTER
S-4 SET TIME = press 100 ENTER
S-4 SET POWER = press 65 ENTER

If a wrong number is pressed, press 0 four times to clear the display. If a wrong number is discovered after ENTER is pressed, press ENTER until the display shows SYSTEM READY then press PROG and start from the beginning. If the program is entered correctly, the system status display will read SYSTEM READY and the time remaining display will read 0740. If any problems occur, check the CEM Operation and Service manual for the Kjel-Fast system for more information. With the peristaltic pump in the forward position, lift the switch in the rear of the unit while holding a beaker under the extension tube. Pump Kjel-Fast Catalyst through the system until about 5 mls is pumped through the extension tube. Place the specimen and one packet of Kjeldahl catalyst in the labeled reaction vessel. Add 15 mls concentrated sulfuric acid to the reaction vessel. Place the reaction vessel with insulator on the vessel pedestal inside the microwave cavity. The vessel will catch the Kjel-Fast Catalyst solution that enters the distribution tube. Press start and run the system to completion for about 8 minutes.

Source: https://assist.dla.mil -- Downloaded: 202640-22T19:42Z
Check the source to verify that this is the current version before use.

Distillation

Before turning on the distillation unit, open the tap water line and check the $NaOH$-$Na_2S_2O_3$ solution and the H_2O reservoirs to make sure that these containers have sufficient amounts of these liquids. Note: The $NaOH$-$Na_2S_2O_3$ solution is a mixture of 10N $NaOH$ solution and a 102 g/l $Na_2S_2O_3.5H_2O$ in a 5:1 ratio. Turn the power switch on. Install an empty distillation and a receiving vessel into the unit. Preheat the unit for about 5 minutes. Install the distillation vessel containing the test specimen digest and a receiving vessel containing 100 ml of 40 g/l boric acid solution. Start the distillation and allow this to continue for about 5 minutes. Lower the receiving vessel and allow the collection tube to drip into the vessel. Set the latter aside for titration. Remove the distillation vessel from the unit and pour the remaining liquid into a waste storage container. Rinse the vessel with water and combine the rinsing with the rest in the waste container.

Analysis

Drain the 10-ml buret twice with standardized 0.1N NCL solution. Standardize the pH meter and electrode using a pH4 and a pH7 buffer solution. Titrate the specimen distillate collected from distillation with the standard 0.1N HCL solution to the pH of the blank solution. Note: The blank solution is prepared at least twice and measured for pH each week. Calculate the percent of acrylic fibers in the specimen as follows:

$$\% \text{ Acrylic Fibers} = \frac{6.05 \times V \times N}{W}$$

Where, V = Volume of standard 0.1 NHCL solution, in ml.
N = Normality of the HCL solution
W = Weight of test specimens, in grams."

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:42Z
Check the source to verify that this is the current version before use.

* 4.5.1.3.4.1, under Analysis:

Delete: "% Acrylic Fibers = $\frac{6.05 \times V \times N}{W}$

Where, V = Volume of standard 0.1N HC1 solution, in ml.
N = Normality of the HC1 solution
W = Weight of test specimens, in grams."

and substitute:

"% Acrylic Fibers = $\frac{140 \times V \times N}{KW}$

Where, V = Volume of standard 0.1N HC1 solution, in ml.
N = Actual normality of the HC1 solution
W = Weight of test specimens, in grams
K = Nitrogen content of acrylic fibers, in %."

The margins of this amendment are marked with an asterisk, or vertical line to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1315-AF92)

Source: https://assist.dla.mil -- Downloaded: 202610-22T19:42Z
Check the source to verify that this is the currentversion before use.