MIL-R-83213A
29 July 1970
SUPERSEDING
MIL-R-83213(USAF)
14 March 1969

MILITARY SPECIFICATION

REMOVERS, POTTING COMPOUND, SOLVENT TYPE

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers two types of solvent removers for stripping potting compounds from electrical components. The removers may be furnished as a one component composition or as a two component composition to be mixed equal parts by volume at time of use.

1.2 Classification. The potting composition removers shall be of the following types as specified (see 6.2).

Type I - For polyurethane ester compounds
Type II - For polyacrylate compounds

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

Federal

O-A-51	Acetone, Technical
QQ-A-250/12	Aluminum Alloy 7075, Plate and Sheet
QQ-A-250/13	Aluminum Alloy Alclad 7075, Plate and Sheet
QQ-A-591	Aluminum Alloy Die Castings
QQ-P-416	Plating, Cadmium (Electrodeposited)
QQ-S-571	Solder, Tin Alloy, Lead-Tin Alloy and Lead Alloy
TT-E-485	Enamel, Semi-Gloss, Rust-Inhibiting
ZZ-R-765	Rubber, Silicone, Low-and High-Temperature and Tear Resistant

FSC 6850

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.

PPP-C-96	Can, Metal, 28 Gage and Lighter
PPP-D-729	Drum, Metal, 55-Gallon (For Shipment of Non-corrosive Material)
PPP-P-704	Pail, Shipping, Steel (1 Through 12 Gallon)

Military

MIL-S-5626	Steel, Chrome-Molybdenum (4140) Bars, Rods, and Forging Stock (For Aircraft Application)
MIL-S-6758	Steel, Chrome-Molybdenum (4130) Bars and Reforging Stock (Aircraft Quality)
MIL-W-7139	Wire, Electrical, Polytetrafluoroethylene-insulated, Copper, 600-Volt
MIL-T-9046	Titanium and Titanium Alloy, Sheet, Strip, and Plate
MIL-C-14550	Copper plating (Electrodeposited)
MIL-W-16878/4	Wire, Electrical, Type E, 200 Degrees C. and 260 Degrees C., 600 Volts (Insulated, High Temperature) (Navy)
MIL-C-26482	Connector, Electric, Circular, Miniature, Quick Disconnect, (Navy)
MIL-C-38736	Cleaning Compound, Solvent, For Use in Integral Fuel Tanks

STANDARDS

Federal

Federal Test Method Std. No. 141	Paint, Varnish, Lacquer, and Related Materials; Methods of Inspection, Sampling and Testing
Federal Test Method Std. No. 601	Rubber: Sampling and Testing

Military

MIL-STD-129	Marking for Shipment and Storage

BULLETIN

U. S. Air Force 539	Standard Elastomer Stocks

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on the date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM B 265	Titanium and Titanium Alloy Strip, Sheet and Plate
ASTM B 298	Silver, Coated, Soft, of Annealed Copper Wire
ASTM D 445	Viscosity of Transparent and Opaque Liquids (Kinematic and Dynamic Viscosities)

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

UNIFORM CLASSIFICATION COMMITTEE - (For Rail)

Uniform Freight Classification Rates, Rules and Regulations

(Application for copies should be addressed to the Uniform Classification Committee, Room 202, Union Station, 516 W. Jackson Blvd., Chicago, Illinois 60606.)

AMERICAN TRUCKING ASSOCIATION - (For Truck)

National Motor Freight Classification Rules

(Application for copies should be addressed to the American Trucking Association, 1424 16th Street, N.W., Washington, D. C. 20036.)

3. REQUIREMENTS

3.1 Qualification. The potting compound removers furnished under this specification shall be products which are qualified for listing on the applicable qualified products list at the time set for opening of bids (see 4.3 and 6.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.

3.2 Materials. The materials used in the manufacture of the types I and II removers shall be of high quality, suitable for the intended purpose, and shall conform to the requirements of this specification.

3.2.1 Manufacturers are given latitude in the selection of raw materials for formulating the potting compound remover.

3.2.2 Toxic products and formulations. The material shall have no adverse effect on the health of personnel when used for its intended purpose. Questions pertinent to this effect shall be referred by the procuring activity to the appropriate department medical service who will act as an advisor to the procuring agency.

3.3 Physical properties

3.3.1 Appearance. The remover compounds shall contain a fluorescent dye to aid in the detection of any remover incompletely rinsed from depotted electrical components. The removers shall be free of any undissolved ingredients and shall be free from reconstituted materials.

3.3.2 Flash point. Potting compound removers, types I and II, shall have a minimum flash point of 22°F when tested as specified in 4.6.1.

3.3.3 Viscosity. Potting compound removers, types I and II, shall have a viscosity not exceeding one centistoke when tested as specified in 4.6.2.

3.3.4 Removal properties. When tested as specified in 4.6.3, types I and II removers shall dissolve or disintegrate the potting compound to not less than 40 percent removal.

3.3.5 Immersion corrosion. The change in weight of the metals and the noncorrosion of the connector, after immersion in the remover, shall be as specified in table I.

3.3.6 Electrical wire corrosion. The wires of MIL-W-7139 and MIL-W-16878/4 shall show no visible corrosion when tested as specified in 4.6.5. The insulation resistance of MIL-W-16878/4 wire shall show no decrease and MIL-W-7139 wires shall show no greater than a 1×10^4 decrease in surface resistance when tested as specified in 4.6.7.1.

3.3.7 Compatibility with connector components. Connector component insert materials of neoprene and silicone rubber shall return to within 2 durometer A units of the original hardness when tested as specified in 4.6.6.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.

Table I. Immersion Corrosion

Metal panels	Change in weight
Aluminum, Bare 7075-T6	±1.0 milligram/in.^{2}
Aluminum, Clad 7075-T6	±1.0 milligram/in.^{2}
Aluminum, 380 Die Cast	±1.5 milligram/in.^{2}
Aluminum, 380 Die Cast, copper flashed	±0.5 milligram/in.^{2}
Aluminum, 380 Die Cast, cadmium plated in accordance with QQ-P-416, Class 3, type II	±0.5 milligram/in.^{2}
Titanium, Ti-6Al-4V	±0.5 milligram/in.^{2}
Silver plate	±0.5 milligram/gm
Solder	±0.5 milligram/in.^{2}
4130 Steel	±0.5 milligram/in.^{2}
4140 Steel	±0.5 milligram/in.^{2}
Connector	No visible corrosion

3.3.8 Compatibility with electrical wire insulation. When exposed to remover, and tested at standard conditions in accordance with 4.6.7, the insulation on wire conforming to MIL-W-16878/4, type E shall show no more than 1 x 10^1 change in electrical resistance. Wire conforming to MIL-W-7139 shall show not greater than a 1 x 10^5 reduction in surface resistance.

3.3.9 Rinsibility. The removers shall rinse completely from metal and connector component surfaces when tested as specified in 4.6.8.

3.3.10 Cold stability. When tested as specified in 4.6.9, the removers that have been exposed to -15°F for 24 hours then returned to 77 ±2°F shall be equal in appearance and free from any solid precipitate as on unexposed sample.

3.3.11 Storage stability. After 6 months storage as specified in 4.6.10, the removers shall conform to all the requirements of this specification except that the solution or disintegration may decrease by a maximum of 20 percent.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (4.3)
b. Quality conformance inspection (4.4).

4.3 Qualification tests. The qualification tests shall consist of all the tests of this specification as specified under 4.6.

4.3.1 Qualification test samples. The qualification test samples shall consist of 2 gallons of the remover. The qualification samples shall be identified as specified herein and forwarded to the activity responsible for qualification as designated in the letter of authorization (see 6.3). The remover test samples shall be packaged in the containers as specified in 5.1.1.1.

REMOVERS, POTTING COMPOUND, SOLVENT TYPE

Type No.
Specification MIL-R-83213A
Manufacturer's code No.
Name of manufacturer
Submitted by (name) (date) for qualification tests in accordance with MIL-R-83213A under authorization (reference authorizing letter)

4.4 Quality conformance inspection

4.4.1 Quality conformance tests for acceptance of individual batches shall consist of the following tests:

Test	Test reference (Paragraph
a. Flash point	4.6.1
b. Removal properties	4.6.3
c. Compatibility with connector components	4.6.6
d. Electrical wire insulation compatibility	4.6.7

4.4.1.1 Batch. A batch shall be the quantity of material prepared in a single volume.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.

4.4.2 Sampling for quality conformance tests. A one-gallon sample shall be selected from each batch of the remover and subjected to the tests specified in 4.4.1. The remover shall be packaged in the containers as specified in 5.1.1.1.

4.5 Test conditions. Standard laboratory testing conditions shall be 77° ±2°F (25° ±1°C) and 50 ± 5 percent relative humidity. Except as otherwise specified herein, all test specimens shall be prepared and tested under these standard conditions.

4.6 Test methods

4.6.1 Flash point. The Tag Closed Cup Method, Federal Test Method Std No. 141, method 4291, shall be used to determine the flash point of the remover.

4.6.2 Viscosity. The viscosity shall be determined using a glass capillary type viscometer in accordance with ASTM method D 445 at 77 ± 0.5°F.

4.6.3 Removal properties. The cured potting compound will be furnished for accomplishing this and related tests (see 6.4). The type I cured compound shall have a durometer A hardness of 60 ± 4 units, and the type II shall be 50 ± 3 units, when tested in accordance with method 3021 of Federal Test Method Std. No. 601. If tests are not initiated immediately upon receipt of the cured potting compound, it shall be refrigerated at 40°F or less, to retard possible post-curing. The specimens of potting compound shall be cut into quarters and two quarters tested for each type. The quarters of type I potting compound shall weigh 14.5 ± 1.0 grams, and type II compound shall weigh 12.5 ± 1.0 grams, both weighed to the nearest 0.1 gram. These shall be transferred to 8-ounce wide-mouth jars containing 100 milliliters of remover. The loosely capped jars shall be maintained at 77 ± 2°F for 2 hours, swirling them vigorously for 15 seconds each half hour. The jars shall then be opened and the largest piece removed, drained and dried 16 hours at standard conditions (see 4.5), and reweighed. The average change in weight shall be calculated as percentage removal and the removed compound shall be in the form of either solution or small granules.

4.6.4 Immersion-corrosion. The metals and alloys to be tested are: Bare 7075-T6, QQ-A-250/12; Clad 7075-T6, QQ-A-250/13; Ti-6Al-4V, MIL-T-9046 (ASTM B 265 grade 5); 380 Die Cast Aluminum, QQ-A-591, #11; 380 Die Cast Aluminum, copper flash plated MIL-C-14550; 380 Die Cast Aluminum cadmium plated, QQ-P-416, class 3, type II; silver plated wire, ASTM B 298; solder SN60 WS, QQ-S-571; steel 4130, MIL-S-6758; and steel, 4140, MIL-S-5626. A female connector (MIL-C-26482, marked PT06CP-12-10SX) shall be wired

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.

and soldered with equal numbers of MIL-W-7139, class 2, and MIL-W-16878/4 type E wires. This connector shall be subjected to the immersion test, but no weighing shall be made.

4.6.4.1 Preparation of panels. Two specimens shall be used for this test. The 7075 and titanium panels shall be 40-mil nominal thickness by 1 inch by 2 inches in size. The aluminum die cast panels shall be cut from a casting to give pieces 2 inches long by 3/4 inch wide by 1/4 inch in thickness. Silver plated wire and solder specimens shall be 6 inches in length. Steel specimens shall be 1 inch by 2 inches by a 1/8 inch to 1/4 inch thickness. Rough or sharp edges shall be removed and all panels shall be cleaned by immersing in the cleaner solvent or MIL-C-38736, scrubbing the surface with gauze, brush, or absorbent cotton. The specimens shall be immersed in acetone, dried and weighed to the nearest 0.001 g. A duplicate specimen and a single wired female connector shall be immersed separately in loosely capped 4-ounce wide-mouth jars filled with remover.

4.6.4.2 Exposure. The panels shall be exposed for 24 hours and the connector for 6 hours at 77 ± 2°F, removed, rinsed with tap water, then deionized or distilled water, then sprayed with methyl alcohol and dried 1 hour at 212 ± 5°F, cooled and reweighed. The panel changes shall be reported in milligrams per square inch, calculating the surface area of the die cast panels to the nearest 0.1 square inch, and in milligrams per gram of silver plated wire and solder. The connector shall be inspected for apparent change and all panels examined for completeness of rinsing in accordance with 4.6.8.

4.6.5 Electrical wire corrosion. Three-inch lengths of wire conforming to MIL-W-7139, class 2, and MIL-W-16878/4, type E shall be immersed in 100 milliliters of remover for 6 hours at 77 ± 2°F. They shall be removed without rinsing and dried 16 to 20 hours at standard conditions (see 4.6). The wires shall then be transferred to a humidity chamber at 93 ± 2 percent relative humidity for 7 days (prepared by adding to a desiccator sufficient ammonium dihydrogen phosphate so that when distilled water is added and temperature equilibrium is attained at 77 ± 2°F, there shall remain an excess of the crystalline salt). The specimens shall be removed and dried 16 to 20 hours at standard conditions. The insulation surface resistance of the wires shall then be measured in accordance with 4.6.7.1. Corrosion of the wire shall be determined by stripping the ends of the 3-inch exposed wires and examining under 20X magnification for change. For comparison purposes, unexposed wires shall also be tested for insulation resistance. The change in insulation resistance between unexposed and exposed wires shall be expressed as decades of change.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.

4.6.6 Compatibility with connector components. The test shall consist of measuring the durometer A hardness in accordance with method 3021 of Federal Test Method Std. No. 601. Specimens of neoprene CR as specified in USAF Bulletin 539 and silicone rubber conforming to ZZ-R-765, class III, grade 50 shall be immersed in fresh remover of capped 4-ounce jars for 6 hours. The specimens shall be removed and rinsed thoroughly in tap water, distilled water, sprayed with methyl alcohol, and dried at 77° ± 2°F for 24 hours. The durometer A hardness values shall then be measured.

4.6.7 Compatibility with electrical wire insulation. Three-inch lengths of wire conforming to MIL-W-7139, class 2 and MIL-W-16878/4, type E shall be immersed for 6 hours at 77 ± 2°F in 100 milliliters of remover. After immersion the wires shall be removed and rinsed in tap water, then with deionized or distilled water, sprayed with methyl alcohol, and dried at standard conditions for 48 hours.

4.6.7.1 Surface electrical resistance. Three-inch lengths of wire as specified in 4.6.7 shall be wrapped with two 1/4-inch ring-type metal-foil electrodes, spaced 1.0 inch apart near the center of the specimen length. The electrodes shall be wrapped snugly around the axis of the specimen and bound with take-off leads for electrical testing of the surface between the electrodes. The surface leakage current between the electrodes shall be measured with d.c. potential of 200 to 300 volts, by noting the potential and leakage current after 1-minute electrification. No temperature correction factor shall be applied. The surface resistance in megohms shall be computed as the applied d.c. voltage multiplied by the measured overall diameter of the specimen in inches divided by leakage current in microamperes.

4.6.8 Rinsibility. The rinsibility of the remover shall be determined by visual examination of all the metal panels and the connector when rinsed as specified in 4.6.4. The examination shall be made in a darkened room or hood using an ultraviolet light with a visual cutoff filter. Inadequate rinsing shall be evidenced by visible color under UV illumination resulting from retention of the fluorescent dye used to color the remover. Special attention shall be given to examination of the wiring apertures of the connector.

4.6.9 Cold stability. A sample of remover shall be stored in a 4-ounce bottle for 24 hours at -15°F. After the remover returns to 77 ± 2°F there shall be no precipitates which can not be redissolved by moderate shaking of the container by hand.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.

4.6.10 Storage stability. A 1-gallon sample of the remover shall be stored at 77 ± 2°F for 6 months. At the end of the storage period the sample shall be tested for conformance to 3.3.4.

4.6.11 Packaging, packing, and marking. Preparation for delivery shall be examined for compliance with section 5.

4.7 Toxicological data and formulations. The supplier shall furnish the toxicological data and formulations required to evaluate the safety of the material for the proposed use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.2).

5.1.1 Level A. The remover shall be furnished in 1-gallon cans, 5-gallon pails, or 55-gallon drums.

5.1.1.1 One-gallon cans. One-gallon cans shall conform to type V, class 6, of PPP-C-96; plan B exterior coating shall be required. When specified, the cans shall be provided with a formed bridge-type handle securely affixed to the top.

5.1.1.2 Five-gallon pails. Five-gallon pails shall conform to PPP-P-704, type I. Screw cap closures and inner seals shall be furnished. When specified, the drums shall also be furnished with a flexible pouring spout. Wire handles shall be treated to resist corrosion.

5.1.1.3 Fifty-five gallon drums. Fifty-five gallon drums shall conform to PPP-D-729, type I. Cap seals and exterior coating shall be furnished on the drums. Unless otherwise specified, the coating shall conform to TT-E-485. Drums shall conform to DOT(ICC) 17C designation for air shipment.

5.1.2 Level C. Packaging shall be in accordance with the manufacturer's commercial practice.

5.2 Packing. Packing shall be level A, B or C, as specified (see 6.2).

5.2.1 Levels A and B. Remover, packaged as specified in 5.1.1, shall be packed in accordance with the appendix of PPP-C-96. Five-gallon pails and 55-gallon drums shall require no additional packing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.

5.2.2 Level C. Remover, packaged as specified in 5.1.2, shall be packed in a manner to insure carrier acceptance and safe delivery at destination. Containers shall be in accordance with rules and regulations applicable to the mode of transportation.

5.3 Marking

5.3.1 When the removers are furnished as a two component material to be mixed at time of use, the containers shall be clearly and appropriately marked:

Component A - Mix with an equal volume of Component B before use;
Component B - Mix with an equal volume of Component B before use.

5.3.2 In addition to any special marking required by the contract or order, interior packages and exterior shipping containers shall be marked in accordance with MIL-STD-129. Marking shall include specification number, applicable type and class, name of manufacturer, date of Manufacture (month and year), batch number, and recommended storage temperature.

6. NOTES

6.1 Intended use. The removers, types I and II, are intended for the removal of potting compounds from electrical connectors which are subsequently to be repotted; type I is intended for the removal of polyurethane ester and type II for the removal of polyacrylate compounds.

6.2 Ordering data. Procurement documents should specify:

a. Title, number, and date of this specification.
b. Type (see 1.2).
c. Quantity.
d. Size of container (see 5.1.1).
e. Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
f. Special marking if required (see 5.3).
g. When bridge-type handle is required on 1-gallon cans (see 5.1.1.1).
h. When flexible pouring spout is required on 5-gallon cans (see 5.1.1.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.

6.3 Qualification. With respect to products requiring qualifications, awards will be made only for products which are at the time set for opening of bids, qualified for inclusion in the applicable Qualified Products List whether or not such products have actually been so listed by that date. The attention of the suppliers is called to this requirement, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. The activity responsible for the Qualified Products List is the Air Force Materials Laboratory, Attn: MAAA, Wright-Patterson Air Force Base, Ohio 45433, and information pertaining to qualification of products may be obtained from that activity.

6.4 Potting compound samples. Samples of polyurethane ester and polyacrylate potting compounds, for use in qualifying your products, may be obtained from the Air Force Materials Laboratory, Attn: MAAA, Wright-Patterson Air Force Base, Ohio 45433.

6.5 Caution in use. Caution must be exercised in the application of the removers. Electric connectors from different suppliers may have entirely different insert materials. Electric connector suppliers use different bonding agents in assembling their products. With these variations, the qualified solution must be tested on the connectors to be depotted, before a full scale, depot-report program is instituted. Without prior testing, connectors may come apart on depotting or the insert material may be damaged or dissolved.

Custodians:

Army - MU
Navy - SH
Air Force - 11

Preparing Activity:

Air Force - 11

Project 6850-0394

Reviewer activities:

Army - MU
Navy - SH
Air Force - 70, 84

User activities:

Army - MI
Navy- OS
Air Force - 84

Other Interest:
Naval Air Rework Facility

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.

ASD(ASNPS)
Wright-Patterson AFB, O 45433

UNITED STATES AIR FORCE
OFFICIAL BUSINESS

POSTAGE AND FEES PAID

ASD(ASNPS)
Wright-Patterson AFB, O 45433

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

ORGANIZATION

CITY AND STATE | CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)* | DATE

DD, FORM 1 JAN 65 1426 REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

AFLC–WPAFB–OCT 67 2M

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:39Z
Check the source to verify that this is the current version before use.