INCH-POUND

MIL-C-60982B(AR)
AMENDMENT 5
10 November 1992
SUPERSEDING
AMENDMENT 4
5 May 1987

MILITARY SPECIFICATION

CASE, CARTRIDGE, 40MM, M169

This Amendment forms a part of Military Specification MIL-C-60982B(AR), dated 17 November 1980, and is approved for use by the US Army Armament Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.3 Change 3.3. to read as follows:

"3.3 Hardness. The hardness of the area near the mouth shall be 62 + 12 on the Rockwell 30T scale. The hardness of the base of the cartridge case shall be 64 + 10 on the Rockwell 30T scale."

* 3.6.1 Add paragraph 3.6.1:

"3.6.1 Ultrasonic inspection of barstock. The aluminum bar shall be inspected ultrasonically for internal defects such as pipe, inclusions and laminations."

PAGE 5

TABLE I: Under No. of sample units delete "*" and under NOTES delete "* The 25 cartridge cases shall be sectioned and the diameter of each vent hole shall be measured."

PAGE 8

4.4.2.1 Delete defect characteristics "Major 127" in its entirety.

Change Major 107 from "Concentricity of flange diameter with second largest outside diameter. See 4.5.1" to "Concentricity of flange diameter with second largest diameter. See 4.5.1, 0.40%, 3.2, Gage."



DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:07Z
Check the source to verify that this is the current version before use.

* Add paragraph 4.4.3.2:

"4.4.3.2 Ultrasonic inspection of barstock. The material shall be examined 100% for conformance with the criteria defined in 3.6.1. The test shall be conducted in accordance with 4.5.7. The standards shall be established jointly by representatives of the barstock supplier and the contractor."

PAGE 10

4.5.3:

Delete "and base plug"

Delete "240" and substitute "Level B"

* Delete "Level B" and substitute "72"

* 4.5.5 Change the last sentence to:

"Each specimen must exhibit a minimum tensile strength of 50,000 psi and a yield strength of 45,000 psi to 55,000 psi."

* Add paragraph 4.5.7:

"4.5.7 Ultrasonic inspection of barstock. The test procedures, acceptance/rejection criteria and equipment design shall be submitted for approval in accordance with paragraph 6.3."

5.1.1 Delete "Level C" and substitute "Level B".

PAGE 11

5.2.1 Delete "Level C" and substitute "Level B".

6.3 Delete "AMSMC-QAF-S(D), ARDC" and substitute "AMSMC-QAF-I(D), ARDEC."



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:07Z
Check the source to verify that this is the current version before use.

The margins of this amendment are marked with an asterisk or vertical lines to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assembles no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing Activity:
Army-AR

(Project 1310-A523)



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:07Z
Check the source to verify that this is the current version before use.