INCH-POUND

MIL-O-60540 (AR)
AMENDMENT 2
06 January 1994
SUPERSEDING
AMENDMENT 1
23 March 1987

MILITARY SPECIFICATION

OBTURATING BANDS, PLASTIC, RIGID, HIGH IMPACT
POLYVINYL CHLORIDE (MOLDED)

This Amendment forms a part of Military Specification MIL-O-60540 (AR), dated 30 June 1966, and is approved for use by the US Army Armament, Munitions and Chemical Command, and is avialable for use by all Departments and Agencies of the Department of Defense.

PAGE 1

Add the following new paragraphs:

"2.2 Other publications. The following document(s) form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM D 256	-	Impact Resistance of Plastics and Electrical Insulating Materials
ASTM D 638	-	Tensile Properties of Plastics
ASTM D 1243	-	Dilute Solution Viscosity of Vinyl Chloride Polymers

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103).

2.3 Order of precedence. In the event of a conflict between the text of the specification and the references cited herein (except for associated detail specifications, specification sheets or MS standards), the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:41Z
Check the source to verify that this is the current version before use.

3.2 Delete in its entirety and substitute the following:

"3.2 Material. The material shall consist of polyvinyl chloride resin of high molecular weight, suitably compounded with heat stabilizers, a suitable elastomer, lubricants and pigments. No re-grind or scrap will be allowed.

3.2.1 Inherent viscosity. Polyvinyl chloride (PVC) resin shall have an inherent viscosity greater than 0.65 when tested IAW paragraph 4.4.5.

3.2.2 Tensile strength. The minimum tensile strength of PVC compound shall be 6,000 pounds per square inch (p.s.i.) when tested IAW paragraph 4.4.6.

* 3.2.3 Tensile modulus. The tensile modulus of PVC compound shall be 360,000 p.s.i. minimum when tested IAW paragraph 4.4.7.

* 3.2.4 Izod impact strength. The izod impact strength at 23 degrees C shall not be less than 19 foot - pound nor more than 26 foot - pound when tested IAW paragraph 4.4.8."

(NOTE: Paragraphs 3.2.3 and 3.2.4, min. tensile and max. impact strength values respectively, were changed from the previous amendment 1.)

PAGE 3

Add the following new paragraphs:

"4.4.5 Inherent viscosity. The inherent viscosity shall be tested in accordance with ASTM D 1243.

4.4.6 Tensile strength. The tensile strength shall be tested as specified in ASTM D 638.

4.4.7 Tensile modulus. The tensile modulus shall be tested as spsecified in ASTM D 638.

4.4.8 Izod impact strength. The izod impact strength range shall be tested as specified in ASTM D 256."

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:41Z
Check the source to verify that this is the current version before use.

The margins of this amendment are marked with an asterisk to indicate where changes from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirement of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army - AR

Preparing activity:
Army - AR

(Project 1395-A270)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:41Z
Check the source to verify that this is the current version before use.