MIL-S-10055D
13 June 1984
SUPERSEDING
MIL-S-10055C
18 August 1971

MILITARY SPECIFICATION

STRAP, PACKBOARD: QUICK RELEASE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers one type and size of quick release packboard strap.

2. APPLICABLE DOCUMENTS

2.1 Government documents. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein.

SPECIFICATIONS

FEDERAL

V-T-285	-	Thread, Polyester
QQ-W-461	-	Wire, Steel, Carbon (Round, Bare, and Coated)
TT-E-529	-	Enamel, Alkyd, Semi-gloss
UU-P-268	-	Paper, Kraft, Wrapping
DDD-L-20	-	Label: For Clothing, Equipage, and Tentage, (General Use)
PPP-B-636	-	Boxes, Shipping, Fiberboard

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research and Development Center, Natick, MA 01760, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8465

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-C-496	-	Clips, End, Strap
MIL-W-530	-	Webbing, Textile, Cotton, General Purpose, Natural or in Colors
MIL-T-43566	-	Tape, Textile, Cotton, General Purpose, Natural or In Colors
MIL-W-44049	-	Webbing, Textile and Tape, Textile, Polypropylene, General Purpose, Natural or in Colors

STANDARDS

FEDERAL

FED-STD-751	-	Stitches, Seams, and Stitchings

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	-	Marking for Shipment and Storage
MIL-STD-147	-	Palletized Unit Loads

DRAWINGS

US ARMY NATICK RESEARCH AND DEVELOPMENT CENTER

3-1-11	-	Strap, Packboard, Quick Release; Assembly Complete
4-1-83	-	Strap, Packboard, Quick Release: Quick Release Device

(Copies of documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

2.2 Other publications. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

A 366	-	Steel, Carbon, Cold-Rolled Sheet, Commercial Quality
B 633	-	Electrodeposited Coatings of Zinc on Iron and Steel
D 3951	-	Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence.

3. REQUIREMENTS

3.1 First article. When specified, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.4).

* 3.2 Materials (see 6.5).

3.2.1 Tape, cotton. The tape for the thong shall conform to type I, class 4, 3/4 inch width of MIL-T-43566 and shall be dyed to match Olive Drab 7.

* 3.2.2 Webbing, cotton or polypropylene. The webbing shall be cotton for the strap conforming to type III, class 4, 1 inch width of MIL-W-530, or as an alternate, the webbing shall be polypropylene conforming to type III, class 4 of MIL-W-44049, and shall be dyed to match Olive Drab 7.

3.2.3 Thread, polyester. The thread for all stitching shall conform to type I or II, class 1, size FF of V-T-285. The thread shall be dyed Olive Drab S-1, C.A. 66022 and shall show fastness to weathering equal to or better than the standard shade sample (see 6.3). If no standard shade sample is available, the thread shall show good fastness to weathering.

3.2.4 Steel.

3.2.4.1 Sheet. The cold-rolled steel sheet shall be commercial quality, class 1, matte finish, in the chemical compositions specified on the drawing, conforming to ASTM A 366. Thickness shall be as specified on Drawing 4-1-83.

3.2.4.2 Wire, carbon. The carbon steel wire shall conform to composition 1020, finish 1, annealed or annealed-in-process of QQ-W-461.

3.2.5 Clip, end strap. The end strap clip shall conform to type I, class 1 or 2, size 1 inch of MIL-C-496.

3.2.6 Enamel. The enamel shall conform to type II, Olive Drab color No. 24087 of TT-E-529.

3.3 Construction. The construction shall conform to the drawings listed in section 2 and shall be as specified herein.

3.3.1 Stitches, seams and stitching. All seams and stitching shall conform to type 301 of FED-STD-751, 6 to 8 stitches per inch. Seam allowance shall be maintained with seams sewn so that no run-offs, puckers, or open seams occur. Care shall be taken to see that no needle chews occur.

3.3.1.1 Automatic box stitching. Any of the box stitching operations cited in this document may be performed with an automatic machine provided the

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

requirements for stitch pattern, stitches per inch, and size and type of thread are met; and at least three tying stitches, overlapping stitches, or backstitches are used to secure the ends of stitching.

3.3.1.2 Type 301 stitching. Ends of all stitching shall be backstitched or overstitched 1 inch minimum except when caught in other seams or stitching. Thread tensions shall be maintained so that there will be no loose stitching resulting in loose bobbin or top thread or excessively tight stitching resulting in puckering of the materials sewn. The lock shall be imbedded in the materials sewed.

3.3.1.2.1 Repairs of type 301 stitching. Repairs of type 301 stitching shall be as follows:

a. When thread breaks or bobbin run-outs occur during stitching, the stitching shall be repaired by restarting the stitching a minimum of 1 inch back of the end of the stitching. 1/

b. Thread breaks, or two or more consecutive skipped or run-off stitches noted during inspection of the item (in-process or end item) shall be repaired by overstitching. The stitching shall start a minimum of 1 inch in back of the defective area continue over the defective area and continue a minimum of 1 inch beyond the defective area onto the existing stitching. Loose or excessively tight stitching shall be repaired by removing the defective stitching without damaging the materials and restitching in the required manner. 1/

1/ When making the above repairs, the ends of the stitching are not required to be backstitched.

3.3.1.3 Thread ends. All thread ends shall be trimmed to 1/4 inch maximum length.

3.3.2 Setting of end clip. The webbing shall be inserted the full depth of the clip. The clip shall be securely attached without cutting the webbing which shall lie flat at the point of entrance.

3.3.3 Attaching thong. The tape thong shall be attached to the quick release shield as indicated on Drawing 3-1-11, with the overhand knot pulled tight.

3.3.4 Quick release.

3.3.4.1 Shield, yoke, and tongueless bar. The quick release shield, yoke, and tongueless bar with extension hook shall be fabricated from steel specified in 3.2.4.1.

3.3.4.2 Rivets and pin. The rivets and pin shall be fabricated from steel wire specified in 3.2.4.2.

3.3.4.3 Riveting. Rivets shall be securely and neatly set. The set shall be such as to allow the yoke to turn freely without being excessively loose. The

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

tongueless bar when pivoted on the 5/32 inch diameter pin shall clear the peened ends of the rivets.

* 3.4 Finish. Rough, sharp edges and burrs shall be removed from all components prior to finishing.

* 3.4.1 Quick release plating and enameling. After complete fabrication of the various components of the quick release and prior to assembly, all components shall be given 13 micrometers thick electrodeposited zinc plating conforming to classification No. Fe/Zn13, Service Condition SC3, of ASTM B 633. Following assembly, the quick release shall be given a coat of enamel conforming to 3.2.6. The coating shall level out to a uniform dry thickness, without orange peel, wrinkles, drops, streaks, or areas of thin or no film.

* 3.5 Marking. The identification marking shall be applied in the location shown on the drawing and shall conform to type IV, class 5 of DDD-L-20. The letters "US" shall be applied in the size characters and in the location indicated on the drawing and shall conform to type IV, class 9 of DDD-L-20. Fastness of class 9 marking shall be as specified for class 5 marking.

* 3.6 Workmanship. Webbing and tape shall contain no frayed or scalloped edge and shall be firmly and tightly woven. Metal components shall be free of corroded areas and shall not be broken or malformed. The quick release packboard strap shall be clean and free from grease or oil stain. The finished strap shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

* 4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in 4.4.3 and 4.4.4. The presence of any defect shall be cause for rejection of the first article.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

* 4.4.2 In-process inspection. Inspection shall be made to determine that the listed below are as specified. Whenever nonconformance is noted, correction shall be made to the item affected and the process.

a. Removal of rough and sharp edges and burrs from metal components of quick release for conformance with 3.4.

b. Zinc coating of metal components of quick release prior to assembly for conformance with 3.4.1.

* 4.4.3 End item visual examination. The end item shall be examined for the defects listed in table I. The lot size shall be expressed in units of one strap. The sample unit shall be one strap. The inspection level shall be II and the acceptable quality level (AOL), expressed in terms of defects per hundred units, shall be 2.5 for major defects, 6.5 for major and minor A combined defects, and 15.0 for total (major, minor A, and minor B combined) defects.

TABLE I. End item visual defects

Examine	Defect	Classification Major	Minor A	Minor B
Webbing and tape	Frayed or scalloped edge; not firm or not tightly woven		X	
	Any hole, cut, or tear	X		
	Broken or missing yarns, or open place		X	
Hardware	Broken	X		
	Malformed:			
	-fails to perform intended function	X		
	- but will perform intended function		X	
	Corroded area	X		
	Burr or sharp edge which may cause injury in handling	X		

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Finish of quick release	Area of no film exposing bare metal	X		
	Area of thin film exposing zinc coating			X
	Not smooth or contains wrinkles, orange peel, or streaks			X
Seams and stitching	Open seam:			
	- 1/2 inch or less			X
	- more than 1/2 inch		X	
	NOTE: A seam shall be classified as open when one or more stitches joining a seam are broken or when two or more skipped or run off stitches occur and are not overstitched. Run-offs (see open seams)			
	Thread breaks overstitched less than 1 inch			X
	NOTE: Thread break not overstitched shall be classified as an open seam.			
	Needle chews	X		
Stitching margin	Larger than specified by more than 1/16 inch			X
Seam and stitch type	Wrong seam or stitch type	X		
Stitch tension	Loose stitching resulting in loose top or loose bobbin thread			X
	Excessive tightness of stitching resulting in puckering of fabric on seams		X	
Stitches per inch	Less than minimum specified:			
	- one stitch			X
	- two or more stitches		X	
	More than maximum specified			X

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine		Defect	Classification Major	Minor A	Minor B
Stitches per inch (cont'd)	NOTE:	Variation in the number of stitches per inch, caused by the operator speeding up the machine and pulling the fabric in order to sew over heavy places or in turning corners, shall be classified as follows: a. Within the minor A defect classification - minor B defect b. Within the minor B defect classification - no defect			
Stitching ends		Overstitched less than 1 inch (except for stitching of the thong and where stitching is performed automatically)		X	
		Secured with less than three tying, overlapping or backstitches when automatic stitching is performed		X	
Boxstitching		Incomplete: - one row of stitching omitted		X	
		- two or more rows of stitching omitted	X		
		- less than specified length or width by more than 1/8 inch			X
Components		Any component part missing	X		
Construction and workmanship:					
Webbing		Not attached to quick release as specified	X		
		Not inserted the full depth of the clip			X
		Not flat at point of entrance into clip			X
Clip		Not securely attached to webbing, i.e., clip is loose			X

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Construction and workmanship: (cont'd)				
Thong	Not attached to shield as specified			X
	Overhand knot loosely tied			X
Quick release	Yoke does not turn freely on rivets		X	
	Yoke does not clear ends of shield pin		X	
	Riveted yoke excessively loose			X
	Tongueless bar does not clear peened ends of rivets	X		
	Rivet for yoke not neatly set	X		
Marking	Omitted, incorrect, illegible, misplaced, or size characters not as specified			X
Cleanness	Quick release packboard strap not clean or evidence of grease or oil stain			X
	Thread ends not trimmed (exceeding 1/4 inch maximum length)			X

4.4.4 End item dimensional examination. The end item shall be examined for conformance to the dimensions specified on the drawings. Any dimension not within the specified tolerance shall be classified as a defect. The lot size shall be expressed in units of one strap. The sample unit shall be one strap. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

* 4.4.5 Packaging inspection. An examination shall be made to determine that preservation, packing, and marking comply with the section 5 requirements. Defects shall be scored in accordance with table II. The sample unit shall be one shipping container fully packaged with the exception that it need not be closed. Examination of closure defects listed in table II shall be made on shipping containers fully packaged. The lot size shall be the number of containers in the inspection lot. The inspection level shall be S-2 and the AOL, expressed in terms of defects per hundred units, shall be 2.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

TABLE II. Packaging defects

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship:	
Applicable to level A preservation	Strap not folded into thirds Quick release assembly not located between the folds. Strap not stacked on edge. Bundle not tied at each end with cotton tape or twine.
Applicable to levels A and B packing	Inside of shipping container not fitted with a taped liner. Unit packs not packed flat, two in length, two in width, and six in depth. Contents not completely covered on the top and bottom with a sheet of kraft paper. Inadequate application of components, such as: incomplete closure of container flaps, improper taping, loose strapping, or inadequate stapling. Bulged or distorted container
Content	Number of straps per bundle or shipping container, as applicable, is more or less than required.

4.4.6 Palletization inspection. An examination shall be made to determine that the palletization complies with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one palletized unit load fully packaged. The lot size shall be the number of palletized unit loads in the inspection lot. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement.
Palletization	Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded with required straps as specified.
Weight	Exceeds maximum load limits.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A. Each strap shall be laid out flat to its full length. The strap shall be folded in half and then into thirds so that the quick release assembly is located between the folds. The folded strap shall measure approximately 11 by 1-3/4 by 1-1/2 inches. Five straps shall be stacked on edge to form a bundle measuring approximately 11 by 7-1/2 by 1-3/4 inches. Each bundle shall be securely tied at each end with cotton tape or twine to form a unit pack.

5.1.2 Commercial. The straps shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Level A packing. One hundred-twenty straps, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Level A unit packs shall be packed flat two in length, two in width, and six in depth within a shipping container. Inside dimensions of each container shall approximate 22-1/2 inches in length, 15-1/2 inches in width, and 10-1/2 inches in depth. Approximate dimensions are furnished as a guide only. Each container shall have the contents completely covered on the top and bottom with a sheet of 30 pound minimum basis weight kraft paper conforming to type I, grade A of UU-P-268. Each shipping container shall be closed, in accordance with method III, waterproofed in accordance with method V and reinforced as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

5.2.2 Level B packing. One hundred-twenty straps, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Level A unit packs shall be packed flat two in length, two in width, and six in depth within a shipping container. Inside dimensions of each container shall approximate 22-1/2 inches in length, 15-1/2 inches in width and 10-1/2 inches in depth. Approximate dimensions are furnished as a guide only. Each container shall have the contents completely covered on the top and bottom with a sheet of 30 pound minimum basis weight kraft paper conforming to type I, grade A of UU-P-268. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.5.

* 5.2.2.1 Weather-resistant container. When specified, (see 6.2) the shipping container shall be a grade V3c, V3s or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.5.

* 5.2.3 Commercial packing. Straps, preserved as specified in 5.1,shall be packed in accordance with ASTM D 3951.

5.3 Palletization. When specified (see 6.2), straps shall be packed as specified in 5.2, shall be palletized in accordance with load type I of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L. Pallet patterns shall be in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course. If the container is of a size which does not conform to any of the pallet patterns specified in MIL-STD-147, the pallet pattern used shall first be approved by the contracting officer.

5.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

6.1 Intended use. The strap is approximately 5-feet long and is used to secure a load to a packboard. The strap is so designed that when the quick release device is pulled back by an attached thong, the strap loosens instantly and permits the load to drop off the packboard.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

* 6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. When a first article is required (see 3.1, 4.3, and 6.4).
c. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
d. When weather-resistant grade fiberboard shipping containers are required for level B shipments (see 5.2.2.1).
e. When palletization is required (see 5.3).

6.3 Samples. For access to a standard shade sample of thread, address the contracting activity issuing the invitation for bids.

* 6.4 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209-4. The first article should be a preproduction sample consisting of one strap. The contracting officer should include specific instructions in all acquisition documents regarding arrangements for inspection and approval of the first article.

6.5 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the document (see 3.2).

6.6 Changes from previous issue. The margins of this document are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activities:

Army - MD
Air Force - 82

User activities:

Navy - MC
Air Force - 45

Preparing activity:

Army - GL

Project No. 8465-0543

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY
US Army Natick Research and Development Center
Natick, Massachusetts 01760

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development Center
ATTN: STRNC-ES
Natick, MA 01760

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-S-10055D	Strap, Packboard: Quick Release

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK OP, 1 Apr 84

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:23Z
Check the source to verify that this is the current version before use.