MIL-C-43157 (MU)
AMENDMENT 2
10 April 1973
SUPERSEDES
AMENDMENT 1
22 June 1972

MILITARY SPECIFICATION

CLOTH, SPUN VISCOSE RAYON RESIN IMPREGNATED

This Amendment forms a part of Specification MIL-C-43157 (MU), dated 4 Sept 63.

Paragraph 3.2, Finish: Delete "(See 6.3)".

Paragraph 3.5, Table I, Class 2 and 3: Delete "6.75" and substitute "6.0".
Delete "7.25" and substitute "7.0".

Paragraph 3.7, Slippage Value (Applicable to Class I only): Delete in paragraphs 3.7.1 and 3.7.2: "min., of 60" and substitute "min., of 50".

Paragraph 3.9, Ash contents: Delete "1.0 percent max." and substitute "1.5 per. max.".

Add new paragraph:

"3.14 Stiffness (Class I only) (Only for automated line).-The cloth shall have a stiffness of 1 30/32 to 2 20/32 inches when tested as specified in 4.3.1.".

Paragraph 4.3.1, Table II: Add the following: "Stiffness 5200 10001"

Paragraph 4.3.2 , Finish : Delete the word "undyed". After "Dyeing temperature 68 ± 2°C" add the following: "The sample shall be rinsed with cold water (tap or distilled) until the rinse water is colorless.".

Paragraph 4.3.5, Stretch: Delete the formula "Percent of Stretch = $\frac{100\ (A-B)}{300 \pm B}$"

and add the following: "Percent of Stretch = $\frac{100\ (A-B)}{300 + B}$"

Paragraphs 6.3 and 6.3.1: Delete in their entirety.

CUSTODIAN:
ARMY-MU

PREPARING ACTIVITY:
ARMY-MU

PROJECT NUMBER: 8305-A-305

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 202610-21T20:49Z
Check the source to verify that this is the current version before use.