MIL-C-43157(AR)
AMENDMENT 3
30 April 1984
SUPERSEDING
AMENDMENT 2
10 April 1973

MILITARY SPECIFICATION

CLOTH, SPUN VISCOSE RAYON, RESIN IMPREGNATED

This Amendment forms a part of Military Specification MIL-C-43157(MU), dated 4 September 1963, and is approved for use by the US Army Armament, Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

3.2 Finish. Delete "(See 6.3)".

Table I. Class 2 and 3: Delete "6.75" and substitute "6.0". Delete "7.25" and substitute "7.0".

* 3.6 Breaking strength loss. Delete in its entirety.

3.7 Slippage value (applicable to Class I only):

3.7.1 Warp. Delete "min. of 60" and substitute "min. of 50".

3.7.2 Filling. Delete "min. of 60" and substitute "min. of 50".

3.9 Ash content. Delete "1.0 percent max." and substitute "1.5 percent max.".

Add a new paragraph and number it 3.13:

"3.13 Stiffness. For Class I only (for automated line only). The cloth shall have a stiffness of 1 30/32 to 2 20/32 inches when tested as specified in 4.3.1."

Renumber the previous 3.13 (Workmanship) to read, "3.14 Workmanship".

PAGE 5

4.3.1 Table II. Add the following:

"Stiffness	5200	10001"

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 202610-21T20:49Z
Check the source to verify that this is the currentversion before use.

4.3.2 Finish. Delete in its entirety and substitute the following:

"4.3.2 Finish. A finish sample of cloth approximately 6 inches, shall be dyed in a bath containing disperse dye (Eastman Brilliant Pink 3B-GLF or equal) and a direct dye (Chlorantine Fast Green 5GLL or equal) in the ratio of 2:1. The dyeing conditions are as follows:

8 grams per liter Eastman Brilliant Pink 3B-GLF
4 grams per liter Chlorantine Fast Green 5GLL
Dyeing time: 3 minutes
Dyeing temperature: 68° ± 2 degrees Centigrade (°C).
(The sample shall be rinsed with cold water (tap or distilled) until the rinse water is colorless.)

If the color of the sample after dyeing is purple, the finish is satisfactory. If the color is green, the finish of the sample is not satisfactory (see 6.8).

* 4.3.3 Determination of breaking strength loss. Delete in its entirety.

PAGE 8

4.3.5 Stretch. Delete the formula:

"Percent of stretch $= \frac{100\ (A-B)}{300 \pm B}$"

and substitute:

"Percent of stretch $= \frac{100\ (A-B)}{300 + B}$"

PAGE 10

6.3 Finish. Delete in its entirety.

* 6.4 Breaking strength loss. Delete in its entirety.

PAGE 11

* Figure 1. Delete in its entirety.


Source: https://assist.dla.mil -- Downloaded: 202640-21T20:49Z
Check the source to verify that this is the currenversion before use.

NOTE: The margins of this amendment are marked with an asterisk or vertical lines to indicate where changes (additions, modifications, corrections, deletions from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document base on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-(AR)

Preparing activity:
Army-(AR)

(Project no. 8305-A920)



Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:49Z
Check the source to verify that this is the current version before use.