INCH-POUND

MIL-C-43157 (AR)
AMENDMENT 4
02 MARCH 1990
SUPERSEDING
AMENDMENT 3
30 April 1984

MILITARY SPECIFICATION

CLOTH, SPUN VISCOSE RAYON, RESIN IMPREGNATED

This Amendment forms a part of Military Specification MIL-C-43157 (MU) dated 4 September 1963, and is approved for use within the US Army Armament Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

* 2.1 Add the following:

"MIL-STD-286 - Propellants, Solid: Sampling, Examination and Testing"

PAGE 2

3.2 Finish. Delete "(See 6.3)".

Table I. Class 2 and 3: Delete "6.75" and substitute "6.0". Delete "7.25" and substitute "7.0".

3.6 Breaking strength loss. Delete in its entirety.

3.7 Slippage value (applicable to Class I only):

3.7.1 Warp. Delete "min. of 60" and substitute "min. of 50".

3.7.2 Filling. Delete "min. of 60" and substitute "min. of 50".

3.9 Ash content. Delete "1.0 percent max." and substitute "1.5 percent max.".

* 3.12.2 Class 3. Delete in its entirety and substitute the following:

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:49Z
Check the source to verify that this is the current version before use.

"3.12.2 Class 3. The cloth shall be dyed scarlet. The dyed cloth shall be tested for compatibility with intended end items (see 4.3.7.2.1) if the dye, dyeing process or cloth supplier is changed."

Add a new paragraph and number it 3.13:

"3.13 Stiffness. For Class I only (for automated line only). The cloth shall have a stiffness of 1 30/32 to 2 20/32 inches when tested as specified in 4.3.1."

Renumber the previous 3.13 (Workmanship) to read,

"3.14 Workmanship."

PAGE 5

4.3.1 Table II. Add the following:

"Stiffness	5200	10001"

4.3.2 Finish. Delete in its entirety and substitute the following:

"4.3.2 Finish. A finish sample of cloth approximately 6 inches, shall be dyed in a bath containing disperse dye (Eastman Brilliant Pink 3B-GLF or equal) and a direct dye (Chlorantine Fast Green 5GLL or equal) in the ratio of 2:1. The dyeing conditions are as follows:

8 grams per liter Eastman Brilliant Pink 3B-GLF
4 grams per liter Chlorantine Fast Green 5GLL
Dyeing time: 3 minutes
Dyeing temperature: 68 degrees ± 2 degrees Centigrade.
(The sample shall be rinsed with cold water (tap or distilled) until the rinse water is colorless).

If the color of the sample after dyeing is purple, the finish is satisfactory. If the color is green, the finish of the sample is not satisfactory (see 6.8)."

4.3.3 Determination of breaking strength loss. Delete in its entirety.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:49Z
Check the source to verify that this is the current version before use.

PAGE 8

4.3.5 Stretch. Delete the formula:

$$\text{"Percent of strength} = \frac{100\ (A-B)}{300 \pm B}\text{"}$$

and substitute:

$$\text{"Percent of strength} = \frac{100\ (A-B)}{300 + B}\text{"}$$

PAGE 9

* 4.3.7.2: Class 3. Delete in its entirety and substitute the following:

"4.3.7.2 Class 3. In all instances the cloth shall be dyed scarlet. The scarlet dye shall produce a color closely approximating color No. 1105 of FED-STD-595. The cloth shall be dyed in accordance with a recommended commercial procedure for the particular color, with dye stuffs that will not cause deterioration of the finished cloth."

* Add a new paragraph and number it 4.3.7.2.1:

"4.3.7.2.1 Compatibility. The dyed cloth shall be tested for compatibility with each planned contact energetic material prior to end item production in accordance with MIL-STD-286, Method T408.1. Test results (including identification of dyes and energetic materials) shall be forwarded to Commander, ARDEC, ATTN: AMSMC-QAR-R(D), SMCAR-AEE-BP, Picatinny Arsenal, New Jersey 07806-5000 for evaluation."

PAGE 10

6.3 Finish. Delete in its entirety.

6.4 Breaking strength loss. Delete in its entirety.

PAGE 11

Figure 1. Delete in its entirety.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:49Z
Check the source to verify that this is the current version before use.

MIL-C-43157 (AR)
AMENDMENT 4

NOTE: The margins of this amendment are marked with an asterisk or vertical line to indicated where changes (additions, modifications, corrects, deletions) from the previous amendment were made. This was done as a convenience only and the Government assume no liability whatsoever for any inaccurancies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 8305 - A357)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:49Z
Check the source to verify that this is the current version before use.