MILITARY SPECIFICATION

BATTERY, STORAGE, NICKEL-CADMIUM (FOR TALOS MISSILE)

This specification is approved for use by the Naval Ordnance Systems Command, Department of the Navy.

1. SCOPE

1.1 Scope. This specification covers vented, rechargeable nickel-cadmium batteries for use in the TALOS missile.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on the date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

L-P-1183 - Plastic Molding Material, Acrylonitrile-Butadiene-Styrene (ABS), Rigid
FF-N-836 - Nut: Square, Hexagon, Cap, Slotted, Castle, Knurled, Welding And Single Ball Seat
FF-S-92 - Screw, Machine: Slotted, Cross-Recessed or Hexagon Head
QQ-N-290 - Nickel Plating (Electrodeposited)
PPP-B-636 - Boxes, Shipping, Fiberboard

MILITARY

MIL-M-14 - Molding Plastic And Molded Plastic Parts, Thermosetting
MIL-P-116 - Preservation, Methods of
MIL-M-20693 - Molding Plastic, Polyamide (Nylon) Rigid
MIL-C-82624 - Cells, Storage, Nickel-Cadmium (For TALOS Missile)

STANDARDS

FEDERAL

FED-STD-601 - Rubber: Sampling and Testing

FSC 6140

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-202 - Test Methods for Electronic and Electrical Component Parts

DRAWING

NAVAL ORDNANCE SYSTEMS COMMAND

Dwg. 1729538 - Battery Assembly

(Copies of specifications, standards, drawings, and publications required by the supplier in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 First Article. Unless otherwise specified in the contract or purchase order, two (2) batteries shall be manufactured for first article testing using the methods and procedures proposed for production. These first articles will be tested as specified in section 4 to determine if the proposed production method will yield an item which meets the technical and design requirements of this specification and the contract or purchase order. (See 6.2)

3.2 Part and Material Samples. Unless otherwise specified in the contract or purchase order, the first articles and each production increment of 100 batteries shall be accompanied by samples of all parts (exept cells) and materials used in those batteries. The samples of parts made of metal or elastomers shall consist of one of each metal part and three of each elastomeric part. The samples representing plastic parts shall consist of a sheet not smaller than three inches by six inches of each different plastic used.

3.3 Conflicts. In the event of any conflict between this specification and any documents referenced herein, this specification shall govern.

3.4 Battery Condition. Batteries shall be furnished in a discharged wet state with a shorting plug in the receptacle in accordance with NAVORD Dwg. 1729538.

3.5 Design and Construction. The battery shall be designed and constructed in conformance to the requirements specified herein and in NAVORD Dwg. 1729538.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

3.5.1 General. The battery shall be a two section battery--one section containing six cells connected in series having a nominal voltage of 6.6 volts and another section having 23 cells connected in series with a nominal voltage of 26.5 volts.

3.5.2 Dimensions and Weight. The dimensions and weight of the batteries shall be in accordance with NAVORD Dwg. 1729538.

3.5.3 Battery Container and Cover. The battery container and cover shall be alkali-resistant high-strength material, free of rough spots, pits, blow holes and other deformations.

3.5.4 Cells. The battery cells shall be as specified in MIL-C-82624.

3.5.5 Mounting. The cells shall be removable but securely mounted in the battery container such that they are not adversely affected by tests performed on the battery to determine its compliance with the requirements of this specification.

3.5.6 Cell Arrangement. The cells shall be placed in the battery case in accordance with NAVORD Dwg. 1729538.

3.5.7 Intercell Connectors. Intercell connectors shall conform to NAVORD Dwg. 1729538.

3.5.8 Receptacle. Each battery shall include, as its electric connections, a receptacle as shown on NAVORD Dwg. 1729538.

3.6 Parts and Materials. Parts and materials used in the battery shall be in accordance with the applicable specification in the following tabulation:

Material or Part	Applicable Specification
Nickel Plating	QQ-N-290
Machine Screws Studs and Nuts	FF-N-836 or FF-S-92
Plastic, Molded	MIL-M-14, Type MFE
Polyamide Material	MIL-M-20693, Comp A, Type III
ABS Material	L-P-1183

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

3.7 Corrosion Resistance. External metal or component parts of each cell and battery shall show no evidence of cracking, pitting, chipping, scaling, corrosion or other deleterious effects after being tested as specified in 4.6.4.1.

3.8 Alkali Absorption of Plastic Materials. When tested as specified in 4.6.4.2, plastic material shall show no cracks or blisters and shall change not more than 2.5 percent in weight or 2.0 percent in any dimension.

3.9 Alkali Resistance of Elastomeric Material. All elastomeric materials used in the battery shall show no cracks, blisters, or other deterioration after being tested in accordance with 4.6.4.3. Pads and gaskets shall have a permanent compression set of not more than 6 percent and O-rings not more than 2 percent after the test.

3.10 Electrolyte Leakage. There shall be no evidence of electrolyte leakage around the terminals, cover-to-case seal, filler cap or O-rings of any cell at any time prior to or during the performance of any of the tests specified in Section 4.

3.10.1 Cell Integrity. There shall be no evidence of electrolyte leakage from any battery cell when that cell is internally pressurized to 5 ± 1 psig.

3.11 Potassium Carbonate (K_2CO_3). The electrolyte shall not contain a K_2CO_3 concentration greater than 60 grams/liter when tested in accordance with 4.6.11.

3.12 Insulation Resistance. All current-carrying parts shall be insulated from the battery container. The insulation resistance between any current-carrying part and container shall be not less than one megohm when tested in accordance with 4.6.5.

3.13 Voltage Output. Each initially fully charged section of the battery shall maintain an output voltage within the following limits when discharged at 55 ± 1.1 amperes for not less than 8 minutes. These conditions shall be met after 2 hours or up to 30 days stand time at room ambient conditions.

NOMINAL VOLTAGE	0 TO 30 SEC	30 SEC TO 8 MIN
26.5	32 to 25 volts	30 to 25 volts
6.6	8 to 6.3 volts	7.5 to 6.3 volts

3.14 Output Voltage Ripple. Peak-to-peak ripple at any time during any discharge shall be not more than 50 millivolts for either section.

3.15 Environmental Requirements. The battery shall conform to 3.10, 3.13, and 3.14, and shall show no evidence of mechanical damage during or after the environmental conditions specified in 3.15.1 through 3.15.8.

3.15.1 Vibration, Random. The battery shall conform to 3.15 during random vibration between 20 and 2000 Hz at accelerations of 17.5 ± 0.2 g's RMS for not less than 30 seconds and 8.8 ± 0.1 g's RMS for not less than 300 seconds.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

3.15.2 Vibration, Sine. The battery shall conform to 3.15 during vibration at 35 ± 3 Hz for not less than 30 minutes at 3 ± 0.5 g's

3.15.3 Shock. The battery shall conform to 3.15 during a shock of not less than 30 g's for not more than 25 milliseconds.

3.15.4 Acceleration. The battery shall conform to 3.15 during an acceleration of not less than 25 g's for not less than 5 seconds in the forward longitudinal direction (connector end), and not less than 12 g's for not less than 10 seconds in any other direction.

3.15.5 Altitude. The battery shall conform to 3.15 when discharged for not less than 6 minutes while at a simulated altitude of not less than 80,000 feet.

3.15.6 Temperature. The battery shall conform to 3.15 when discharged for not less than 6 minutes during exposure to 350° ± 2°F.

3.15.7 Humidity. The battery shall conform to 3.15 after exposure to not less than 90 percent relative humidity at 85° to 90°F for not less than 72 hours.

3.15.8 Storage. The battery shall conform to 3.15 after storage in a charged state for any period between 2 hours and 30 days at 80° ± 5°F.

3.16 Life. The life of each section of the battery shall consist of not less than 100 charge-discharge cycles, not counting preconditioning or reconditioning cycles.

3.17 Workmanship. The battery shall be manufactured, assembled, and finished in a thoroughly workmanlike manner. Particular attention shall be paid to neatness and thoroughness of assembly and finishing. All material shall be of sound, uniform quality and condition and shall contain no defects which adversely affect operation or serviceability. Material which has been treated to conceal defects shall not be used.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities satisfactory to the Government for the performance of the inspection requirements specified herein. The Government reserves the right to perform any of the inspections set forth in this specification where such inspection is deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Classification of Tests. Inspections and tests specified herein for the batteries, parts, and material samples are classified as follows:

(a) First Article Inspection (See 4.3)
(b) Quality Conformance Inspection (See 4.4)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

4.3 First Article Inspection.

4.3.1 Procedure. Two assembled batteries and part and material samples associated with the batteries as specified in 3.2 shall be inspected as specified herein and in the sequence shown in Table I.

4.3.2 Failures. Failure of a first article or any part or material sample to pass any of the examinations or tests specified herein shall be cause for the Government to withhold production approval.

4.4 Quality Conformance Inspection.

4.4.1 Sampling from inspection lots. An inspection lot shall consist of a production increment of 100 batteries, or fraction thereof, which has been manufactured under essentially the same conditions, at essentially the same time, and from essentially the same raw materials and component parts. Two sample batteries shall be drawn at random from each such inspection lot for quality conformance inspection.

4.4.2 Procedure. The two battery samples and the part and material samples associated with the inspection lot as specified in 3.2 shall be inspected as specified herein and in the sequence shown in Table I.

4.4.3 Failures. Failure of any sample to pass any of the quality conformance examinations or tests specified herein shall be cause for the Government to reject the production batteries represented by the sample.

4.5 Inspection Conditions and Equipment.

4.5.1 Ambient Conditions. Unless otherwise specified herein, all measurements and tests shall be made at a temperature of 75° ± 10°F.

4.5.2 Electrical Indicating Instruments. All voltmeters and ammeters shall be accurate within ± 1 percent of full scale readings. The range shall be such that the readings are taken of the upper half of the scale. Timers shall be accurate within ± 0.5 percent. The sensitivity of voltmeters shall be at least 1000 ohms per volt.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

Table I. First Article and Quality Conformance Inspection Schedule

Examination	Requirement	Method	Notes
Preparation for delivery	5	4.6.1	1
Dimensions and weight	3.5.2	4.6.2.1	
Design and construction	3.4, 3.5.1, 3.5.3 through 3.5.8, 3.6, 3.17	4.6.2.2	
Visual examination	3.5.3, 3.17	4.6.3	
Corrosion resistance	3.7	4.6.4.1, 4.6.3	2
Alkali resistance of plastics	3.8	4.6.4.2, 4.6.3	2
Alkali resistance of elastomers	3.9	4.6.4.3, 4.6.3	2
Insulation resistance	3.12	4.6.5	
Preconditioning and charging	-	4.6.6, 4.6.7	
Performance	3.13, 3.10	4.6.8	
Random vibration	3.15.1, 3.13 3.14, 3.10	4.6.9.1	
Sine vibration	3.15.2, 3.13 3.14, 3.10	4.6.9.2	
Shock	3.15.3, 3.13 3.14, 3.10	4.6.9.3	
Acceleration	3.15.4, 3.13 3.14, 3.10	4.6.9.4	
Altitude	3.15.5, 3.13 3.10	4.6.9.5	
Temperature	3.15.6, 3.13 3.10	4.6.9.6	
Humidity	3.15.7, 3.13 3.10	4.6.9.7	
Stowage	3.15.8, 3.13 3.10	4.6.9.8	
Cell leakage	3.10.1	4.6.10	3
Potassium carbonate	3.11	4.6.11	3
Life	3.16, 3.13 3.10	4.6.12	

Notes:

1. This examination is not applicable to first articles or part and material samples.
2. This examination is applicable only to part or material samples, not assembled batteries, and may be performed concurrently with battery tests.
3. This examination is applicable only to cell samples taken from batteries being tested in accordance with 4.3 or 4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

4.6 Methods of Examination.

4.6.1 Preparation for Delivery. The markings, packing, packaging, and preservation shall be inspected in accordance with MIL-P-116 to determine conformance to Section 5.

4.6.2 Physical Examinations.

4.6.2.1 Dimensions and Weight. The battery shall be weighed and its dimensions measured to determine conformance to 3.5.2. These measurements shall be made on discharged batteries.

4.6.2.2 Design, Construction, and Materials. The battery shall be disassembled and examined to determine conformance to 3.4, 3.5.1, 3.5.3 through 3.5.8, 3.6, and 3.17.

4.6.3 Visual Examination. A visual examination shall be conducted using a lens having a power of not less than 10x to determine conformance to 3.5.3 and 3.17.

4.6.4 Parts and Material Tests.

4.6.4.1 Corrosion Resistance. Approximately one half of each metal part of the battery shall be wetted along its length by placing it in a solution of 1.3 ± 0.1 specific gravity potassium hydroxide (KOH) electrolyte. The parts shall be allowed to stand for not less than 16 hours at 120° ± 2°F. The parts shall then be rinsed with distilled water, allowed to dry, and visually examined in accordance with 4.6.3 to determine conformance to 3.7.

4.6.4.2 Alkali Absorption of Plastic Material. Three specimens, each approximately 2 by 3 inches, shall be cut from each different sample of plastic material. The cut edges may be sealed with the same resin used in fabrication of the battery. After being measured with a micrometer and weighed in a dry condition on a chemical balance, each specimen shall be immersed in a covered vessel containing not less than 150 cc of 1.3 ± 0.1 specific gravity potassium hydroxide (KOH). This vessel shall be held for not less than 7 days at 66° ± 1°C (150° ± 2°F). At the end of this period, the specimens shall be rinsed with distilled water and the surface shall be allowed to dry. They shall then be inspected for evidence of cracks or blisters in accordance with 4.6.3 and shall be measured and weighed and the percentage changes in dimensions and weight shall be calculated to determine conformance to 3.8.

4.6.4.3 Alkali Resistance of Elastomeric Material. Each sample elastomeric part (such as gaskets, o-rings, etc.) shall be immersed in 1.3 ± 0.1 specific gravity KOH electrolyte at ambient conditions and allowed to stand for not less than 30 days. The samples shall then be rinsed with distilled water and allowed to dry. They shall then be tested in accordance with Method 3311 of Federal Test Method Standard No. 601 and examined in accordance with 4.6.3 to determine conformance to 3.9.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

4.6.5 Insulation Resistance. The insulation resistance of a discharged battery shall be measured between current-carrying part and the container in accordance with MIL-STD-202, Method 302, Test Condition B, for 1 minute, and the resistance shall be monitored during that time to determine conformance to 3.12.

4.6.6 Preconditioning. The battery as received in a discharged condition shall be charged (each section) by constant current at the c/5 rate ± .5 percent (see note below) until the:

26.5 nominal voltage section is 35.65 ± 0.10 volts,
6.6 nominal voltage section is 9.30 ± 0.10 volts;

then charging shall be continued at the same rate for 2 hours ± .5 percent. Then each section of the battery shall be discharged at the c rate ± .5 percent to an end potential of:

23.0 ± 0.1 volts for the nominal 26.5 volt section,
6.0 ± 0.05 volts for the nominal 6.6 volt section.

Note: c is the ampere-hour rating at the 1-hour rate.

4.6.7 Charging. The battery shall be charged at a constant potential for a period of 1 hour ± .5 percent using the appropriate potential as follows:

35.6 ± 0.1 volts for the nominal 26.5 volt section,
9.3 ± 0.1 volts for the nominal 6.6 volt section.

After charging, the battery shall be allowed to stand open circuit for not less than 2 hours nor more than 30 days before proceeding with further testing.

4.6.8 Performance. Unless otherwise specified herein, each section of the battery, fully charged in accordance with 4.6.7, shall be discharged at a rate of 55 ± 1.1 amperes for not less than 8 minutes. During the discharging period, the voltage shall be monitored to determine conformance to 3.13. During shock or vibration tests, the output voltage ripple shall also be monitored to determine conformance to 3.14. During and after the discharging period, the battery shall be examined for evidence of leakage to determine conformance to 3.10.

After the discharging period, the battery shall be allowed to stand open-circuit for not less than 4 hours before proceeding with further testing.

4.6.9 Environmental Tests. The battery shall be charged in accordance with 4.6.7 prior to performing any of the following environmental tests, and mounted to the test equipment by the normal mountings as would be utilized when mounted in a missile.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

4.6.9.1 Random Vibration. The charged battery shall be subjected to random vibration along each of three mutually perpendicular axes with the following nominal spectral density characteristics at the battery mounting points. The battery shall be subjected to the performance test of 4.6.8 during the vibration and observed for conformance to 3.13, 3.14, and 3.10.

	g's Rms	Duration	Nominal Spectral Density Characteristics	
			g^2/Hz	Hz
a)	17.5 ± .2	30 + 30 seconds*	.153	20- 300
			.019	300- 500
			.115	500- 700
			.019	700- 900
			.306	900-1350
			.153	1350-2000
b)	8.8 ± .1	300 seconds*	.038	20- 300
			.005	300- 500
			.028	500- 700
			.005	700- 900
			.076	900-1350
			.038	1350-2000

* 30 seconds ± 0.5 percent at 17.5 g's followed by 300 seconds ± 0.5 percent at 8.8 g's followed by 30 seconds ± 0.5 percent at 17.5 g's.

4.6.9.2 Sine Vibration. The charged battery shall be subjected to a fixed frequency sine vibration of 35 ± 3 Hz at 3 ± 0.5 g's for not less than 15 minutes each along the longitudinal and radial axes. The battery shall be subjected to the performance test of 4.6.8 during the final 10 minutes of vibration, and observed for conformance to 3.13, 3.14, and 3.10.

4.6.9.3 Shock. The battery shall be subjected to shock while undergoing the performance test of 4.6.8 and while being observed for conformance to 3.13, 3.14, and 3.10. The shock shall have a trapezoidal characteristic with a maximum rise time of 25 milliseconds to not less than 30 g's, and dwell at a minimum of 300 g's for at least 30 milliseconds. Shock shall be measured at the battery case mounting points.

4.6.9.4 Acceleration. The battery shall be subjected to acceleration while undergoing the performance test of 4.6.8 and while being observed for conformance to 3.13, 3.14, and 3.10. The battery shall be subjected to a minimum acceleration of 25 g's for a minimum of 5 seconds in the forward longitudinal direction (connector end), 12 g's minimum for 10 seconds minimum in the rearward longitudinal direction, and 12 g's minimum for 10 seconds minimum in any lateral direction. The discharge may be intermittent to allow for axes change, the maximum open circuit for each axis change without boost charge shall be 5 minutes (total maximum of 20 minutes open circuit).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

4.6.9.5 Altitude. The charged battery shall be subjected to an absolute pressure simulating an altitude of not less than 80,000 feet. The rate of change in altitude to 80,000 feet shall be a minimum of 1500 feet per second. The battery shall be subjected to the performance test of 4.6.8, and a minimum of 6 minutes of the discharge shall be when the battery is at the simulated altitude of 80,000 feet. The battery shall be observed for conformance to 3.13 and 3.10 during and after the performance test.

4.6.9.6 Temperature. The charged battery shall be temperature-conditioned at 120° ± 2°F for not less than 4 hours, then the battery shall be immediately placed in an ambient temperature of 350° ± 2°F and subjected to the performance test of 4.6.8 for a minimum of 6 minutes, and observed for conformance to 3.13 and 3.10.

4.6.9.7 Humidity. The charged battery shall be exposed to an environment of not less than 90 percent relative humidity and a temperature of between 85° and 90°F for not less than 72 hours and then shall be subjected to the performance test of 4.6.8 and observed for conformance to 3.13 and 3.10.

4.6.9.8 Stowage. The charged battery shall be stored open-circuit for not fewer than 30 days at 80° ± 5°F, and then subjected to the performance test of 4.6.8 and observed for conformance to 3.13 and 3.10.

4.6.10 Cell Leakage Test. Three cells shall be selected at random from each battery. Using dry nitrogen, an internal pressure of 5 ± 1 psig shall be applied through an airtight adapter at the venting aperture, and the cell submerged in water for a minimum of 30 seconds and observed for leakage to determine conformance to 3.10.1.

4.6.11 Potassium carbonate. Three cells shall be selected at random from each tested battery, and electrolyte from each cell shall be tested as follows:

a. Extract 1 ml of electrolyte from the cell with a clean dry syringe or pipette, when the cell is in the fully charged condition.

b. Transfer to beaker (250 ml) and dilute with carbon dioxide free distilled water.

c. Add 3-5 drops of phenolphthalein solution (1 gm of phenolphthalien per liter of 95% alcohol is suitable--do not use a saturated phenolphthalien solution).

d. Titrate with a 0.5 N solution HCl or H_2SO_4 to the end point which is the disappearance of the pink color.

e. Add a few drops of methyl purple to solution and again titrate to end point (violet to grey to green). This change is very sensitive going through the grey state when on drop will bring the solution to the green end-point.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

f. Record the titers in milliliters as follows:

A = Phenolphthalein end point,

B = Total titration, therefore;

B-A = C

g. If C is greater than 1.70 ml, the K_2CO_3 concentration exceeds 60 grams/liter, and the cell fails this test.

4.6.12 Life test. The battery shall be cycled in accordance with 4.6.7 and 4.6.8 for a total of 100 charge-discharge cycles, including those cycles completed during previous tests, but not including pre-conditioning or reconditioning cycles. The battery shall be observed for conformance to 3.13 and 3.10 during all discharge cycles.

a. Routine Maintenance. During life cycling the battery shall be cleaned and checked and electrolyte level adjusted as required with distilled or deionized water. Intercell connectors shall not be removed during cleaning.

b. Reconditioning. Once every 25 life cycles, the battery shall be discharged by shorting each cell with not more than 1.0 ohm for not less than 24 hours, then preconditioned in accordance with 4.6.6.

5. PREPARATION FOR DELIVERY

5.1 Battery configuration. Batteries prepared for delivery shall be fully discharged, shall contain a full complement of electrolyte, and shall have a shorting bar installed across the terminals. Each cell shall have been vented prior to the installation of the battery cover.

5.2 Packaging and packing. Packaging and packing shall be level A or C as specified. (see 6.3)

5.2.1 Level A. Each battery shall be packaged and packed in a box conforming to PPP-B-636 for type CF, class weather resistant. Die-cut or scored pads, of the same material used in the box fabrication, shall be used to prevent contact of any battery protrusions with the container walls. The container closure shall be in accordance with the box specification appendix.

5.2.2 Level C. Each battery shall be packed in accordance with the requirements of the Uniform Freight Classifications.

5.3 Marking. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended Use. The batteries described herein are intended for use in the TALOS missile.

6.2 Retention of First Articles. The contract or purchase order will usually require that the procuring or testing activity retain first articles for the purpose of comparison with production units.

6.3 Ordering Data. Procurement documents should specify the following:

a. Title, number, and date of this specification and any amendment thereto.

b. The number of batteries required.

c. Shipping instructions.

d. Packaging & packing level A or C.

6.4 Applicability of Department of Transportation. These wet, electric storage batteries are of a non-spillable type, are shipped in a completely discharged condition, and are completely and securely boxed. They are, therefore, exempt from Department of Transportation packaging and labeling requirements.

Custodians:
NAVY-OS

Preparing Activity:
NAVY-OS
Project Number: 6140-N378

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION
MIL-B-82623(OS) Battery, Storage, Nickel-Cadmium (For TALOS Missile)

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?
   ☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

S/N-0102-014-1801 C-25254

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.