FF–N–103c
24 JULY 1964
SUPERSEDING
FF–N–00103b (USAF)
28 FEBRUARY 1964

FEDERAL SPECIFICATION

NAILS (SMALL) AND TACKS: CUT

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers small cut nails and cut tacks suitable for general application. Nails and staples (other than cut) are covered by FF–N–105.

1.2 Classification.

1.2.1 *Types.* Small nails and cut tacks shall be of the following types, styles and sizes as specified (see 6.1):

TYPE I—Hardware nails (cut).
- Style 1—Basket nails.
- Style 2—Clout nails.
- Style 3—Trunk nails.

TYPE II—Hardware tacks (cut).
- Style 1—Basket tacks.
- Style 2—Bill-poster tacks.
- Style 3—Carpet tacks.
- Style 4—Copper tacks.
- Style 5—Double pointed tacks.
- Style 6—Gimp tacks.
- Style 7—Hide tacks.
- Style 8—Lace tacks.
- Style 9—Trimmers tacks.
- Style 10—Upholsters tacks.

TYPE III—Shoefinders nails (cut).
- Style 1—Cobblers nails.
- Style 2—Extra-iron-clinching nails.
- Style 3—Hob nails.

TYPE IV—Shoefinders tacks (cut).
- Style 1—Hand shoe tacks.

1.3 Sizes. Small cut nails and cut tacks shall be of the sizes listed hereinafter and as specified in the invitation for bids (see 6.1).

1.4 Finishes. Small cut nails and cut tacks shall have the finishes as indicated hereinafter and as specified in the invitations for bids (see 6.1).

1.5 Shank design. Shank design shall be as shown in the illustrations and as considered standard in the industry for the particular types.

1.6 Head design. Head design shall be as shown in the illustrations and as considered standard in the industry for the particular types.

1.7 Metals. Nails and tacks procured in accordance with this specification shall be as specified hereinafter and in the invitation for bids.

2. APPLICABLE SPECIFICATIONS, STANDARDS AND OTHER PUBLICATIONS.

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitations for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

PPP–T–60 —Tape Pressure Sensitive Adhesive, Waterproof, for Packaging and Sealing

PPP–B–566—Boxes, Folding, Paperboard

FSC 5315

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

PPP–B–585—Boxes, Wood, Wirebound
PPP–B–601—Boxes, Wood, Cleated-Plywood
PPP–B–621—Boxes, Wood, Nailed and Lock Corner
PPP–B–636—Boxes, Fiberboard
PPP–B–640—Boxes, Folding, Fiberboard, Corrugated, Triple Wall
PPP–B–665—Boxes, Paperboard, Metal Stayed (Including Stay Material)
PPP–B–676—Boxes, Set-Up, Paperboard

STANDARDS

FEDERAL

FED–STD–102—Preservation, Packaging and Packing Levels
FED–STD–123—Marking for Domestic Shipping
Fed Test Method No. 151—Metals; Test Methods

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C.)

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Georgia, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, and Auburn, Wash.)

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

SPECIFICATIONS

MILITARY

MIL–L–10547—Liners, Case, Waterproof

STANDARDS

MILITARY

MIL–STD–105—Sampling Procedures and Tables for Inspection by Attributes
MIL–STD–129—Marking for Shipment and Storage

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

U S Department of Commerce Publication

R47–54—Simplified Practice Recommendation, Cut Tacks and Small Cut Nails

(Copies may be obtained from the U S Department of Commerce, Office of Technical Services, Commodity Standards Division, Washington, D. C.)

3. REQUIREMENTS

3.1 Materials. Except as otherwise specified herein, the articles covered by this specification shall be made from steel. Finished articles shall withstand the bend test specified in 4.3.1.

3.1.1 *Copper.* When specified, copper used in the manufacture of articles shall show, on analysis, not less than 98 percent pure copper (see 4.3.2).

3.2 Finishes.

3.2.1 *Galvanized or zinc coating.* Galvanized or zinc coated nails or tacks shall be reasonably smooth and shall be free from black and uncoated spots, fins, and lumps. The coating shall be not less than one ounce per square foot of surface area, tested in accordance with 4.6.2.

3.2.2 *Surface coating.* Bright, blued, enameled, tinned, brass plated, copper plated and other finishes shall be as specified in the invitation for bids (see 6.1). Tacks and

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

nails shall be sterilized when so specified. Blued or other finish is not required for tacks or nails procured for use in power driven machines, unless otherwise specified.

3.3 Dimensions.

3.3.1 Nails with flat heads or with square shoulders under the heads and all tacks shall be measured from under the head to the tip of the point.

3.3.2 **Flat** countersunk head and headless nails shall be measured from the top of the head to the tip of the point.

3.3.3 Lengths given herein are in inches and common fractions, and material thicknesses are given in decimals of an inch.

3.3.4 Dimensions of double-pointed tacks are inside dimensions.

3.4 Tolerances.

3.4.1 *Count.* The number per pound is approximate and is subject to normal manufacturing variation.

3.4.2 *Length.* Variations from specified lengths shall not exceed plus or minus $\frac{1}{32}$ inch from articles up to and including $1\frac{1}{2}$ inches in length and plus or minus $\frac{1}{16}$ inch for articles above $1\frac{1}{2}$ inches in length.

3.5 Workmanship. The workmanship shall be in conformance with the best commercial practices.

3.6 In the following tables, the various dimensions and other data are indicated:


N—Trade number (where N is not given, L is used as the trade designation).
L—Length in inches.
H—Diameter or width of head.
T—Thickness of material from which articles are formed.
No/lb—Number per pound (see 3.4.1).

4. SAMPLING, INSPECTION AND TEST PROCEDURES

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.


4.1.1 When specified, sampling shall be on a statistical basis in accordance with Military Standard MIL–STD–105, for the acceptable quality level specified.

TABLE I. Nails, Type I, Style 1 Basket. Flat head, bright finish. Packages: 1, 25, 100 lbs.



L	T	H	No./lb
5/8	0.049	0.180	2,080
6/8	0.049	0.180	1,504
7/8	0.058	0.203	1,056
1″	0.058	0.220	928


TABLE II. Nails, Type I, Style 2, Clout. Bright, Blued or Zince-Coated Finish. Packages: 1, 25, 100 lbs.



L	T	H	No./lb
6/8	0.065	0.220	960
7/8	0.0685	0.238	768
1″	0.072	0.259	576
$1\frac{1}{4}$	0.0775	0.284	384

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

TABLE III. Nails, Type I, Style 3, Trunk, Oval Head, Bright, Brass, Blued or Copper Plated Finish. Packages: 1, 25, 100 lbs.



L	T	H	No./lb
6/8	0.072	0.2485	672
7/8	0.072	0.2485	608
1″	0.083	0.2715	448
1¼	0.083	0.2715	352

TABLE IV. Tacks, Type II, Style 1, Basket. Flat Head, Bright Finish. Packages: 1, 25, 100 lbs.



N	L	T	H	No./lb
6	8/16	0.042	0.165	3,248
10	10/16	0.049	0.180	2,000
14	12/16	0.058	0.203	1,536

TABLE V. Tacks, Type II, Style 2, Bill Poster. Flat Head, Bright, Blued or Zinc-Coated Finish. Packages: 1, 25, 100 lbs.



N	L	T	H	No./lb
4	7/16	0.083	0.320	960
6	8/16	0.095	0.360	608
8	9/16	0.095	0.360	544
10	10/16	0.095	0.360	496

TABLE VI. Tacks, Type II, Style 3, Carpet. Flat Head, Blued Finish. Packages: ⅛, 1, 25, 100 lbs.



N	L	T	H	No./lb
4	7/16	0.0685	0.238	1,600
6	8/16	0.072	0.2485	1,248
8	9/16	0.072	0.259	1,104
10	10/16	0.0775	0.259	880

TABLE VII. Tacks, Type II, Style 4, Copper. Flat Head, Bright Finish, Copper Material. Packages: ⅛, 1, 25, 100 lbs.



N	L	T	H	No./lb
3	6/16	0.049	0.180	2,816
4	7/16	0.058	0.204	2,040
6	8/16	0.058	0.211	1,568
10	10/16	0.065	0.248	1,008
14	12/16	0.072	0.271	720

TABLE VIII. Tacks, Type II, Style 5, Double Pointed. Bright, Blued or Zinc-Coated Finish. (used for wire cloth) Packages: ⅛, 1, 25, 100 lbs.




N	L	Width	Wire Size*	No./lb
5	3/8	7/32	0.049	2,448
9	7/16	7/32	0.065	1,232
10	1/2	1/4	0.065	1,152
12	5/8	5/16	0.072	672

*Before Flattening

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

TABLE IX. Tacks, Type II, Style 6, Gimp. Blued or Japanned Finish. Packages: ⅛, 1, 25, 100 lbs.




N	L	T	H	No./lb
4	7/16	0.0535	0.1145	2,992
6	8/16	0.058	0.127	2,496

TABLE X. Tacks. Type II, Style 7, Hide. Flat Head, Bright or Zinc-Coated Finish. Packages: 25, 100 lbs.



N	L	T	H	No./lb
8	9/16	0.083	0.340	480
18	7/8	0.134	0.4375	224
22	1″	0.134	0.4375	192
26	1¼	0.134	0.4375	144

TABLE XI. Tacks, Type II, Style 8, Lace. Flat Head, Black Enameled or Tinned Finish. Packages: ⅛, 1, 100 lbs.



N	L	T	H	No./lb
4	7/16	0.0455	0.120	5,100
6	8/16	0.049	0.128	3,600
8	9/16	0.049	0.134	2,700
10	10/16	0.049	0.148	2,400
14	12/16	0.058	0.165	1,800

TABLE XII. Tacks, Type II, Style 9, Trimmers. Flat Head, Blued or Bright Finish. Packages: ⅛, 10, 25, 100 lbs.



N	L	T	H	No./lb
2½	5/16	0.042	0.134	5,600
3	6/16	0.0455	0.148	4,000
4	7/16	0.049	0.165	3,008
6	8/16	0.049	0.180	2,640
8	9/16	0.058	0.203	1,792
12	11/16	0.065	0.220	1,200
16	13/16	0.0685	0.238	896

TABLE XIII. Tacks, Type II, Style 10, Upholsterers. Flat Head, Bright, Blued or Zinc-Coated Finish. Packages: ⅛, 1, 10, 25, 100 lbs.



N	L	T	H	No./lb
1½	7/32	0.0455	0.148	7,400
2	4/16	0.0455	0.148	5,600
2½	5/16	0.0473	0.165	4,032
3	6/16	0.049	0.180	3,000
4	7/16	0.0535	0.203	2,400
6	8/16	0.058	0.220	1,760
8	9/16	0.0615	0.238	1,440
10	10/16	0.0637	0.2485	1,200
12	11/16	0.065	0.2485	1,040
14	12/16	0.0685	0.265	800
18	14/16	0.0775	0.284	640
22	16/16	0.083	0.320	512
24	18/16	0.083	0.312	480

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

TABLE XIV. Nails, Type III, Style 1, Cobblers. Bright or Brass Plated Finish. Packages: ⅛, 1, 100 lbs.




L	T	H	No./lb
4/8	0.065	0.109	1,952
5/8	0.065	0.109	1,504
6/8	0.065	0.109	1,344

TABLE XV, Nails, Type III, Style 2, Extra-Iron Clinching. Bright or Blued Finish. Packages: ⅛, 1, 100 lbs.



L	T	H	No./lb
3/8	0.049	0.093	4,128
7/16 or 3½/8	0.049	0.093	3,488
4/8	0.049	0.093	3,040
9/16 or 4½/8	0.049	0.093	2,864
5/8	0.049	0.093	2,256
11/16 or 5½/8	0.049	0.093	2,000
6/8	0.535	0.101	1,640
13/16 or 6½/8	0.535	0.101	1,600
7/8	0.535	0.101	1,520

TABLE XVI, Nails, Type III, Style 3, Hob. Square Grooved Head, Bright or Blued Finish. Packages: 1, 100 lbs.



L	T	H	No./lb
7/16 or 3½/8	0.134	0.380	268
4/8	0.134	0.380	264

TABLE XVII, Tacks, Type IV, Style 1, Hand Shoe. Flat Head, Bright or Blued Finish. Packages: ⅛, 1, 100 lbs.



N	L	T	H	No./lb
½	7/32	0.035	0.115	11,000
¾	9/32	0.035	0.115	8,600
1	10/32	0.040	0.115	7,700
1½	12/32	0.040	0.115	5,900
2	14/32	0.0455	0.120	5,100
2½	16/32	0.049	0.128	3,600
3	18/32	0.049	0.134	2,700
4	20/32	0.049	0.148	2,400
5	22/32	0.049	0.165	2,100
6	24/32	0.058	0.165	1,800
8	28/32	0.058	0.173	1,600

4.1.1 When specified, sampling shall be on a statistical basis in accordance with Military Standard MIL–STD–105, for the acceptable quality level specified.

4.2 Lot. All of the nails or tacks of the same type, style, size and length offered for delivery at one time shall be considered a lot for the purpose of inspection and test.

4.3 Sampling for visual and dimensional examination. Random samples shall be taken from each lot of kegs, containers or packages offered to the Government in accordance with the following Table XVIII. The sample unit for acceptance or rejection shall be one nail or tack; if the number of defective nails or tacks in the sample exceeds the acceptance number specified in Table XVIII, the lot represented by the sample shall be rejected.

4.3.1 Bend test. When specified, articles shall withstand cold bending to 90 degrees without fracture when bent by any suitable means available.

4.3.2 *Analysis for Copper.* When required by the invitation, contract or purchase order, an analysis shall be furnished showing the purity of the copper used for the production of copper articles included in the order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

TABLE XVIII. Table for visual dimensional inspection

Lot Size Nr kegs, pkgs, or containers in insp lot	Sample Size Nr kegs, pkgs or containers in sample	Nr nails, staples, from each keg, pkg or container	Acceptance number of defectives
2 to 15	2	14	1
16 to 40	3	24	3
41 to 110	5	35	5
111 to 300	7	49	6
301 to 500	10	70	9
501 to 1300	15	120	12
1301 to 3200	25	150	17
3201 to 8000	35	215	24
8001 and over	50	300	32

Analysis may be made by the manufacturer of the articles, by the producer of the material from which the articles are made, or by an acceptable commercial laboratory, and may employ any standard method normally used for such determination. Analyses thus furnished shall be certified by the supplier as representing the materials used in the production of articles included in the order.

4.4 Sampling for test. Random samples of nails or tacks shall be taken from each lot of nails or tacks offered to the Government in accordance with Table XIX. The sample unit shall be one nail or tack. When the number of nails or tacks in the sample which failed to pass the required test exceeds the acceptance number specified in Table XIX, the lot shall be rejected.

TABLE XIX. Sampling for physical tests

Lot Size—Nr kegs, pkgs, or containers in insp lot	Sample Size—Nr kegs, pkgs, containers from which sample nails shall be drawn	Sample Size—Nr nails, staples, etc., for each applicable test	Acceptance—Nr defectives in all tests
2 to 15	2	4	0
16 to 40	3	6	0
41 to 110	5	10	0
111 to 300	7	14	1
301 to 500	10	20	1
501 to 1300	15	30	2
1301 to 3200	25	50	3
3201 to 8000	35	70	5
8001 and over	50	100	6

4.5 Visual and dimensional examination. Each sample nail or tack selected in accordance with para 4.3 shall be visually and dimensionally examined to verify conformance with the requirements of Section 3 in regards to size, finish, workmanship, and material.

4.6 Test. Sample nails or tacks taken at random in accordance with para 4.4 shall be subjected to the following test.

4.6.1 *Copper analysis.* When required the purity of the copper used shall be determined by standard laboratory practices.

4.6.2 *Zinc coating.* Test for zinc coating shall be conducted in accordance with method 512.1 of Federal Test Method Standard 151.

4.7 Examination of the preparation for delivery. The preservation, packaging, packing and marking shall be examined for conformance with the requirements of Section 5.

5. PREPARATION FOR DELIVERY

(For civil agency procurement the definitions and application of the various levels of packaging and packing are defined in Fed Std No. 102.)

5.1 Packaging. Packaging shall be Level A or C as specified (see 6.1).

5.1.1 *Level A-Unit packaging.* Small nails and cut tacks. Each quantity of 1/8 pound, 1 pound or 10 pounds, as specified, (see 6.1) shall be packaged in paperboard containers conforming to Specification PPP–B–566, PPP–B–665 or PPP–B–676. Quantities of 25 pounds shall be packaged in fiberboard containers conforming to Specification PPP–B–636. Quantities of 100 pounds shall be packaged directly into a shipping container (see 5.2.1 and 5.2.2).

5.1.1.1 *Intermediate packaging.* Unless otherwise specified, 1/8 pound and 1 pound quantities shall be packaged in intermediate containers conforming to Specification PPP–B–665 or PPP–B–636. Intermediate container quantities shall not exceed 20 pounds.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

5.1.2 *Level C.* Small nails and cut tacks shall be packaged in accordance with the manufacturers commercial practice.

5.2 **Packing.** Packing shall be Level A, B or C as specified (see 6.1).

5.2.1 *Level A.* Nails or tacks packaged as specified in 5.1 shall be packed in containers conforming to Specification PPP–B–587 (class 3), PPP–B–601 (overseas type), PPP–B–621 (class 2) or PPP–B–640 (class 2), grade A). These containers shall be provided with caseliners conforming to Specification MIL–L–10547. Unpackaged nails or tacks of 100 pound quantities shall be packed directly into an overseas type container conforming to Specification PPP–B–636 or PPP–B–640. Caseliners will not be required for these containers. Fiberboard containers shall have all seams, corners and joints sealed with 3-inch minimum width tape conforming to Specification PPP–T–60, type III, class 1, color optional. As far as practicable, shipping containers shall be of uniform shape and size, of minimum cube and tare consistent with the protection required and shall contain identical quantities. The gross weight of each pack shall not exceed 200 pounds. When fiberboard boxes are used, the gross weight of these boxes shall not exceed the weight limitations of the box specification. The box shall be closed and strapped in accordance with the applicable container specification or the appendix thereto, except that flat steel strapping shall be zinc coated.

5.2.2 *Level B.* Nails or tacks packaged as specified in 5.1 shall be packed as specified in 5.2.1 except that the containers shall be of the domestic type and neither caseliners or strapping is required.

5.2.3 *Level C.* Nails and tacks shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies.

5.3 **Marking.**

5.3.1 *Civil agencies.* All shipments for civil agencies shall be marked in accordance with Fed Std No 123.

5.3.2 *Military.* In addition to any special marking required by the contract or order, all shipping containers shall be marked in accordance with MIL–STD–129.

6. NOTES

6.1 **Ordering data.** Procurement documents should specify the following:

a. Title, number, and date of this specification.
b. Type and style required (see 1.2.1.
c. Size (or length in inches) (see 1.3, 3.3 and tables).
d. Finish required (see 1.4, 3.2 and tables).
e. Material (if required).
f. Shank design required if other than specified herein.
g. Administrative provisions for inspection records (see 4.1).
h. Level of packaging and level of packing required (see 5.1 and 5.2).
i. Quantity per unit package.

6.1.1 For nails, wire brads, and staples other than specified (see Fed Spec FF–N–105). If bend test and chemical analysis are required, see 4.3.1 and 4.6.1.

6.2 Illustrations contained herein are intended to show the general design only and are not intended to preclude compliance with specification requirements.

6.3 It is believed that this specification adequately describes the characteristics necessary to secure the desired articles, and that normally, no samples will be necessary prior to award, to determine compliance with this specification. If, for any particular purpose samples with bids are necessary, they should be specifically asked for in the invitation for bids, and the particular purpose to be served by the bid sample should be definitely stated. This specification shall apply in all other respects.

6.4 Federal specifications do not include all types, sizes, materials, finishes and other descriptions of the items indicated by the titles of the specifications, but are intended to

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.

cover those types, sizes, etc., which are most suitable for Federal Government requirements.

6.5 Transportation description. The transportation descriptions and minimum weights applicable to this commodity are:

6.5.1 *Rail:—Nails, steel*

Nails, not otherwise indexed by name, steel.

Carload minimum weight 40,000 pounds.

6.5.2 *Motor:*

Nails, not otherwise indexed, steel.

Truckload minimum weight 40,000 pounds, subject to Rule 115, National Motor Freight Classification.

6.5.3 *Rail:—Copper*

Tacks or shoe nails, not otherwise indexed by name, copper.

Carload minimum weight 30,000 pounds.

6.5.4 *Motor:*

Tacks or shoe nails, not otherwise indexed.

Truckload minimum weight 30,000 pounds, subject to Rule 115, National Motor Freight Classification.

6.5.5 *Rail:—Steel*

Tacks or shoe nails, not otherwise indexed by name, steel.

Carload minimum weights 30,000 and 40,000 pounds.

6.5.6 *Motor:*

Tacks or shoe nails, not otherwise indexed, steel.

Truckload minimum weights 30,000 and 40,000 pounds, subject to Rule 115, National Motor Freight Classification.

Custodians:

Army—WC
Navy—Weps
Air Force—69

Review:

Air Force—83

Preparing Activity:

Air Force—69

Project No. 5315–0053

Review/user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:44Z
Check the source to verify that this is the current version before use.