MIL-H-14040(CmlC)

26 April 1955

MILITARY SPECIFICATION

HEADPIECE, COLLECTIVE PROTECTOR; HOSPITAL, M13

1. SCOPE

1.1 This specification covers the headpiece for a six man hospital collective protector.

2. APPLICABLE DOCUMENTS

2.1 The following specifications, standards, and drawings, of the issue in effect on date of invitation for bids, form a part of this specification:

SPECIFICATIONS

FEDERAL

ZZ-R-601	-	Rubber Goods; General Specifications (Methods of Physical Tests and Chemical Analyses).
LLL-B-631	-	Boxes; Fiber, Corrugated (For Domestic Shipment).
LLL-B-636	-	Boxes; Fiber, Solid (For Domestic Shipment).
PPP-B-601	-	Boxes, Wood, Cleated-Plywood.

MILITARY

JAN-P-106	-	Packaging and Packing for Overseas Shipment - Boxes, Wood, Nailed.
JAN-P-108	-	Packaging and Packing for Overseas Shipment - Boxes, Fiberboard (V-Board and W-Board) Exterior and Interior.
JAN-P-133	-	Packaging and Packing for Overseas Shipment - Boxes, Set-Up, Paperboard.

Source: https://assist.dla.mil -- Downloaded: 202610-18T02:47Z
Check the source to verify that this is the current version before use.

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

DRAWINGS

CHEMICAL CORPS

D5-70-19 - Headpiece, Hospital Collective Protector, M13, Bill of Material.

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Materials and components.- All materials and components shall conform to the specifications and drawings forming a part of this specification.

3.2 Manufacture.- The headpiece shall be manufactured in accordance with Drawing D5-70-20 which is listed on Drawing D5-70-19.

3.3 Eyepiece defects.- The eyepiece (see Dwg. E5-2-636) shall have no more than five defects such as specks, bubbles, blisters, etc.; the largest dimension of which shall be no greater than 1/32 inch. The eyepiece shall permit easy reading without blurring or distortion when tested as specified in 4.4.1.

3.4 Seams.

3.4.1 Construction.- Seams shall be uniform, continuous, and free from wrinkles, punctures or tears.

3.4.2 Strength.- Specimens shall not break or separate in the constricted area at a load of less than 6.0 pounds when tested as specified in 4.4.2.

3.5 Loop attachments.- The loop shall not tear or separate at less than 20 pounds when tested as specified in 4.4.3.

3.6 Pilot lot.- A pilot lot shall be produced in accordance with 4.1.1.

4. QUALITY ASSURANCE PROVISIONS

Source: https://assist.dla.mil -- Downloaded: 202610-18T02:47Z
Check the source to verify that this is the current version before use.

4.1 Lot.

4.1.1 Pilot.- Prior to the start of regular production, and following any change in regular production methods, materials, or equipment, a pilot lot of 50 complete headpieces shall be produced using the same methods, materials, and equipment as will be employed during regular production.

4.1.2 Regular production.- A production lot shall consist of the completed headpieces assembled by one manufacturer in not more than two work shifts during one calendar week from the same materials and under essentially the same manufacturing conditions. The inspection lot for nondestructive inspection, within the above limitations, shall be designated by the inspector.

4.2 Sampling.

4.2.1 For nondestructive inspection.

4.2.1.1 Pilot lot.- Each headpiece in the pilot lot shall be inspected for conformance to the applicable drawing and specification requirements.

4.2.1.2 Production lot.- Sampling for nondestructive inspection shall be conducted in accordance with the classification of defects (4.3.3) and Standard MIL-STD-105.

4.2.2 For destructive tests.

4.2.2.1 Pilot lot.- Sixteen representative headpieces shall be taken from each pilot lot for testing as specified in 4.4.2 and 4.4.3.

4.2.2.2 Production lot.- Twenty representative headpieces, ten for test and ten for retest, shall be taken from each production lot for testing as specified in 4.4.2 and 4.4.3.

4.3 Inspection.

4.3.1 Materials and components.- The inspector shall ascertain that all materials and components of the headpiece, covered by separate specifications and drawings, are in accordance with applicable specifications and drawings prior to final acceptance of the headpiece.

4.3.2 Packaging, packing, and marking.- The inspector shall inspect the packaging, packing, and marking for compliance with section 5.

4.3.3 Classification of defects.- Inspection of the headpiece shall be conducted as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

4.3.3.1 Headpiece, hospital collective protector, M13 - assembly.- (Dwg. D5-70-20 which is listed on Dwg. D5-70-19).

Categories and defects	Acceptance standards
Major	AQL 1.0 percent defectives
1. Component missing, incorrect, or incorrectly assembled or located	
2. Damage	
3. Eyepiece, optical defects	4.4.1
4. Tape missing, incorrect, or inadequate	
5. Canister mounting piece and outlet valve improperly secured	
6. Canister mounting piece thread damage or nonfunctioning	
7. Heat sealed seams and joints incorrect	
8. Contamination (grease or oil)	
Minor	AQL 2.5 percent defectives
51. Marking missing, illegible, or incorrect	
52. Contamination (other than grease or oil)	
Incidental	
None	

4.4 Tests.

4.4.1 Optical defects.- View printed matter (14-point type size) held perpendicular to the line of sight at a distance not less than 24 inches. Observe printed matter for clarity.

4.4.2 Seam strength.- Die one dumb-bell specimen conforming to type A of Specification ZZ-R-601 from each sample headpiece. The full width of the seam shall be within the constricted portion of the specimen and the long dimension of the specimen shall be approximately perpendicular to the seam. Condition the specimen at 70 ± 5°F. for a minimum of 1/2 hour. Test the specimen in accordance with the tensile strength procedure of Specification ZZ-R-601 except that the machine shall be operated at a rate of 2 inches per minute.

4.4.3 Loop attachments.- Cut out a 2 by 6-inch specimen for each loop on one-half of the sample headpieces so that the loop is at one end of the specimen and the 6-inch dimension is parallel with the long dimension of the loop. Condition specimen (or headpiece prior to cutting) for a minimum of 30 minutes at 70 ± 5°F. immediately prior to testing. Test the specimen in accordance with the tensile strength procedure of Specification ZZ-R-601 except that one of the gips of the testing apparatus shall be replaced by

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

a free rotating mandrel approximately 1/2 inch in diameter. Operate the machine with the loop over the mandrel at a rate of 2 inches per minute.

4.5 Rejection criteria.

4.5.1 Pilot lot.- If any headpiece or specimen in the pilot lot fails to meet any drawing or specification requirement, the pilot lot shall be rejected. The cause of failure shall be ascertained and corrective action instituted prior to initiation of a new pilot lot. Upon rejection of a pilot lot, a new pilot lot shall be produced and subjected to the same examination and testing as the original pilot lot. Regular production, pending approval of the pilot lot, will be at the risk of the manufacturer. No production lot shall be accepted prior to pilot lot approval.

4.5.2 Production lot.- Each regular production lot, when tested as specified in 4.4.2 and 4.4.3 shall be disposed of in accordance with table I.

Table I

Attribute	Test criteria			Retest criteria		
	Number of test specimens	Failures (test)	Lot action	Number of retest specimens	Failures (test plus retest)	Lot action
Loop attachments	10	0	Accept	10 1/	1	Accept
		1	Retest			
		2	Reject		2	Reject
Seam strength	10	0	Accept	10 2/	1	Accept
		1	Retest			
		2	Reject		2	Reject

1/ Two from each of the five remaining sample headpieces.
2/ One from each sample headpiece.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 Level A, military package.- Six headpieces shall be folded as specified on Drawing C5-70-30 (steps 1 through 6) and packaged in a style RSC W6c fiberboard box, conforming to Specification JAN-P-108 and having the corners and joints sealed in accordance with the appendix thereto. Glassine paper shall be used inside the headpiece (full size) and between all folded surfaces. The headpieces shall be separated from each other by glassine paper.

5.1.2 Level B, limited military package.- Six headpieces shall be folded as specified on Drawing C5-70-30 (steps 1 through 6) and packaged in a box conforming to type I of Specification JAN-P-133. Glassine paper shall be used inside the headpiece (full size) and between all folded surfaces. The headpieces shall be separated from each other by glassine paper.

5.1.3 Level C, Minimum military package.- Same as in 5.1.2.

5.2 Packing.

5.2.1 Level A, military pack.- Ten intermediate packages, conforming to 5.1.1, shall be packed in a style 4 nailed wood box, conforming to Specification JAN-P-106, or a cleated plywood box, conforming to Specification PPP-B-601. The box shall be strapped in accordance with the appendix to Specification JAN-P-106. The gross weight of the box shall not exceed 50 pounds.

5.2.2 Level B, limited military pack.- A uniform number of headpieces, packaged as specified in 5.1.2, shall be packed in a box conforming to Specification LLL-B-631 or LLL-B-636 for weight and size of contents.

5.2.3 Level C, minimum military pack.- Same as 5.2.2.

5.3 Marking.- In addition to any special marking required by the contract or order, all shipping containers shall be marked in accordance with Standard MIL-STD-129.

6. NOTES

6.1 Ordering data.- Procurement documents should specify the following:

a. The title, number, and date of this specification.
b. Level of packaging and packing required.

6.2 Sampling and testing.- When the contractor consistently produces high quality material and operates under a system of quality control acceptable to the Government, the Government, at its discretion, may modify in

Source: https://assist.dla.mil -- Downloaded: 20261O-18T02:47Z
Check the source to verify that this is the current version before use.

whole or in part, the sampling and testing procedures specified herein. However, the Government reserves the right to return at any time, without previous notice to the contractor, to the sampling and testing procedures specified in this specification.

6.3 Stock number.- The Federal stock number for this item is 4240-391-1003.

6.4 Supersession data.- This specification supersedes Chemical Corps Purchase Description No. 197-54-552.

Patent notice.- When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Custodian:

Army - Chemical Corps

Other interest:

Army - M

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.