MIL-P-14030(CmlC)

7 April 1955

MILITARY SPECIFICATION

PLATINUM, ANALYZED REAGENT

1. SCOPE

1.1 This specification covers one grade of platinum for use as a chemical reagent.

2. APPLICABLE DOCUMENTS

2.1 The following specifications and standard, of the issue in effect on date of invitation for bids, form a part of this specification:

SPECIFICATIONS

FEDERAL

U-M-186	-	Medicinal Products and Clinical Laboratory Reagents; General Specifications for Containers.
UU-T-111	-	Tape; Paper, Gummed (Sealing and Securing).
LLL-B-631	-	Boxes; Fiber Corrugated (For Domestic Shipment).
PPP-T-0076	-	Tape, Paper, Water Resistant Pressure-Sensitive.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:46Z
Check the source to verify that this is the current version before use.

MILITARY

JAN-P-106 - Packaging and Packing for Overseas Shipment - Boxes; Wood, Nailed.

JAN-P-108 - Packaging and Packing for Overseas Shipment - Boxes, Fiberboard (V-Board and W-Board), Exterior and Interior.

MIL-P-10225 - Packaging of Glass Containers, One-Gallon Capacity and Smaller, for Other Than Medicinal Products for Domestic Shipment.

STANDARDS

MILITARY

MIL-STD-129 - Marking for Shipment and Storage.

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Appearance.- The material shall be silver-white metal scraps.

3.2 Chemical.- The material shall conform to the chemical requirements shown in table I when tested as specified therein.

Table I.- Chemical requirements

Property	Percent by weight	Test paragraph
Silver	0.0000	4.4.1
Other foreign metals	0.01 (max.)	4.4.2

4. QUALITY ASSURANCE PROVISIONS

4.1 Lot.- A lot shall consit of platinum metal scrap which has been processed in such a manner that all the material in the lot is uniform.

4.2 Sampling.- Samples shall be taken at random from each lot for test purposes as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:46Z
Check the source to verify that this is the current version before use.

Lot size	Sample
1 to 99 bottles	1 bottle
100 to 500 bottles	2 bottles
Over 500 bottles	3 bottles

4.3 Inspection.

4.3.1 Appearance.- The inspector shall visually examine the material for compliance with 3.1.

4.3.2 Packaging, packing, and marking.- The inspector shall inspect the packaging, packing, and marking for compliance with section 5.

4.4 Tests.- Distilled water and analytical reagent grade chemicals shall be used. Unless otherwise specified, reagents shall be used full strength. Where applicable , blank determinations shall be run and corrections applied when significant. Unless otherwise specified, all weighings shall be made to four significant figures.

4.4.1 Silver.

4.4.1.1 Aqua regia.- Mix 3 parts of hydrochloric acid and 1 part of nitric acid just before ready to use.

4.4.1.2 Procedure.- Dissolve 0.50 gram (gm.) of the specimen in aqua regia. Evaporate the solution to dryness and dissolve the residue in water. If any white, insoluble portion remains, the specimen does not comply with the silver requirement of table I.

4.4.2 Other foreign metals.- Dissolve 1.000 gm. of the specimen in aqua regia and evaporate the solution to dryness. Ignite the residue and digest the resulting spongy mass in 25 milliliters (ml.) of 10-percent nitric acid for 15 minutes. Filter. Evaporate the filtrate to dryness in a tared crucible and weigh the residue. If the weight of the residue exceeds 0.1 milligram (mg.), the specimen does not comply with the foreign metals requirement of table I.

4.5 Rejection.- If any specimen fails to conform to this specification, the lot shall be rejected.

5. PREPARATION FOR DELIVERY

5.1 Preservation and packaging.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:46Z
Check the source to verify that this is the current version before use.

5.1.1 Level A, military package.- Ten gm. of the platinum shall be packaged in a screw-cap, amber-colored bottle conforming to type I, class A of Specification U-M-186. A uniform number of bottles shall be packaged in accordance with Specification MIL-P-10225 except that the box shall be made of W5c fiberboard in conformance with style RSC of Specification JAN-P-108, and shall have the flaps, corners, and joints sealed in accordance with the appendix thereto. The maximum weight of the box and contents shall not exceed 40 pounds.

5.1.2 Level B, limited military package.- Ten gm. of platinum shall be packaged in a screw-cap, amber-colored bottle conforming to type I, class A of Specification U-M-186.

5.1.3 Level C, minimum military package.- Ten gm. of platinum shall be packaged in a screw-cap, amber-colored bottle conforming to type I, class A of Specification U-M-186.

5.2 Packing.

5.2.1 Level A, military pack.- The platinum packaged as specified in 5.1.1 shall be packed in a style 4 box conforming to Specification JAN-P-106, and closed and strapped in accordance with the appendix thereto.

5.2.2 Level B, limited military pack.- A uniform number of bottles shall be packed in accordance with Specification MIL-P-10225, except that all flaps of the container shall, in addition, be sealed with 2-inch wide tape conforming to class 2 of Specification UU-T-111 or to Specification PPP-T-0076. As an alternate method of sealing, the flaps of the box may be closed with metal fastenings in accordance with Specification LLL-B-631.

5.2.3 Level C, minimum military pack.- A uniform number of bottles shall be packed in accordance with Specification MIL-P-10225, except that all flaps of the container shall, in addition, be sealed with 2-inch wide tape conforming to class 2 of Specification UU-T-111 or to Specification PPP-T-0076. As an alternate method of sealing, the flaps of the box may be closed with metal fastenings in accordance with Specification LLL-B-631.

5.3 Marking.- Each bottle shall be labeled to show the analysis or maximum impurities of the contents. In addition to any special marking required by the contract or order, all interior packages and exterior containers shall be marked in accordance with Standard MIL-STD-129.

6. NOTES

6.1 Ordering data.- Procurement documents should specify the following:

a. The title, number, and date of this specification.
b. Level of packaging and packing required (see 5.1 and 5.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:46Z
Check the source to verify that this is the current version before use.

6.2 Sampling and testing.- When the contractor consistently produces high quality material and operates under a system of quality control acceptable to the Government, the Government, at its discretion, may modify in whole or in part, the sampling and testing procedures specified herein. However, the Government reserves the right to return at any time, without previous notice tot the contractor, to the sampling and testing procedures specified in this specification.

6.3 Stock number.- The Chemical Corps stock number for this material is R105-4-140.

6.4 Supersession date.- This specification supersedes Chemical Corps Purchase Description No. 4-130.

Patent notice.- When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as. in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Custodian:

Army - Chemical Corps

Other interest:

Army - M

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:46Z
Check the source to verify that this is the current version before use.