INCH-POUND

MIL-T-14038K
16 September 1991
SUPERSEDING
MIL-T-14038J
18 October 1988

MILITARY SPECIFICATION

TENT, GENERAL PURPOSE, LARGE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers two types of rectangular, hip-roofed, pole supported, off-center ridge, general purpose tents. The tent has the following dimensions, when erected with poles, designed for use with them: Length (at eave line) 52 feet; width (at eave line) 18 feet; ridge height 12 feet, 3 inches; sidewall height 5 feet, 8 inches and door height 6 feet, 2 inches. The tents are provided with windows (including window screens), roll up type sidewalls and a sliding double door entrance at each end. The tents come with a liner, pins and poles, and a tent cover.

1.2 Classification. The tents shall be of the following types as specified (see 6.2).

Type I - Polyester Duck, Camouflage Green 483, Fire, Water and Weather Resistant
Type II - Polyester Duck, Desert Tan 459, Fire, Water and Weather Resistant

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5017 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

A-A-50057	-	Rope, Fibrous, Tent Lay
L-P-378	-	Plastic, Sheet and Strip, Thin Gauge, Polyolefin
L-S-125	-	Screening, Insect, Nonmetallic
T-C-571	-	Cords, Cotton; General and Special Purposes, Sash and Venetian Blind
T-T-871	-	Twine, Cotton, Wrapping
T-T-911	-	Twine, Fibrous, Jute
V-F-106	-	Fastener, Slide, Interlocking
V-T-285	-	Thread, Polyester
TT-P-595	-	Preservative Coating, Canvas
CCC-C-429	-	Cloth, Osnaburg, Cotton
CCC-C-467	-	Cloth, Burlap, Jute (or Kenaf)
DDD-L-20	-	Label; For Clothing, Equipage, and Tentage, (General Use)
PPP-B-601	-	Boxes, Wood, Cleated-Plywood
PPP-B-636	-	Boxes, Shipping, Fiberboard

MILITARY

MIL-P-500	-	Plates, Tent Peak, and Ridge
MIL-W-530	-	Webbing, Textile, Cotton, General Purpose, Natural or in Colors
MIL-P-549	-	Poles, Tent, Upright and Ridge
MIL-H-1608	-	Hooks, Tent
MIL-L-1709	-	Lines, Tent
MIL-S-1734	-	Slips, Tent Line
MIL-R-2327	-	Rings, Connecting, Round
MIL-P-2383	-	Pins, Tent, Wood
MIL-C-2399	-	Cement, Liquid, Tent Patching
MIL-R-3390	-	Rings, Dee
MIL-T-14056	-	Tent, Liner, General Purpose, Large, Fire, Water and Mildew Resistant
MIL-G-16491	-	Grommet, Metallic, General Specification For

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

MIL-C-20696	-	Cloth, Coated, Polyester or Nylon, Waterproof
MIL-T-40625	-	Tubing, Bias Sewn (Burlap or Osnaburg), Cloth
MIL-S-43002	-	Shield, Stovepipe, Tent, Nonmetallic
MIL-T-43566	-	Tape, Textile, Cotton or Polyester, General Purpose, Natural or in Colors
MIL-C-43627	-	Cloth, Duck, Cotton, Plied Yarns, Fire, Water, Weather and Mildew Resistant Treated, Lightdry Finish
MIL-W-43638	-	Webbing, Textile, Woven, for Tent Framing
MIL-C-44103	-	Cloth, Duck, Polyester, Fire, Water and Weather Resistant

STANDARDS

FEDERAL

FED-STD-751	-	Stitches, Seams and Stitching

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	-	Marking for Shipment and Storage

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DEPARTMENT OF THE ARMY FIELD MANUAL

FM 10-16 - General Repair of Tents, Canvas and Webbing

(Copies are available from the contracting activity or as directed by the contracting activity.)

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

5-4-540	-	Erection Instructions
5-4-541	-	Care and Maintenance Instructions
5-4-542	-	Cover
5-4-2175	-	Tent, General Purpose, Large; Assembly and Views

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

5-4-2176 - Side Wall
5-4-2177 - Right End Wall
5-4-2178 - Tent, General Purpose, Large: Left End Wall
5-4-2179 - View "G" Sections
5-4-2180 - Views and Sections
5-4-2181 - End and Side Roofs Assembly
5-4-2182 - Views A and B of End and Side Roofs Assembly
5-4-2183 - Views C and D of End and Side Roofs Assembly
5-4-2184 - End Roof
5-4-2185 - Ventilator Views and Sections
5-4-2186 - End Roof Views
5-4-2187 - Ventilator Details and Sections
5-4-2188 - Side Roofs A and B
5-4-2189 - Roof, Middle Assembly
5-4-2190 - Views A, B and C of Roof Middle Assembly
5-4-2191 - Views D and E of Roof Middle Assembly
5-4-2192 - Sections, Roof Middle Assembly
5-4-2193 - Ridge End Assembly View
5-4-2194 - Screen Door
5-4-2195 - Window Assembly
5-4-2196 - Window Details
5-4-2197 - Stovepipe Opening Details
5-4-2198 - Lugs and Miscellaneous Details
5-4-3379 - Sleeves

(Copies of drawings are available from the U.S. Army Natick Research, Development, and Engineering Center, ATTN: STRNC-UX, Natick, MA 01760-5017.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

THE COLOR ASSOCIATION OF THE UNITED STATES

Standard Color Card of America

Department of Defense Standard Color Card for Sewing Threads

Quartermaster Standard Shades of Slide Fastener Tapes

(Application for color cards should be addressed to The Color Association of the United States, 343 Lexington Avenue, New York, NY 10016-0927. If color cards are not available from The Color Association, individual color samples may be obtained from the contracting activity or as directed by the contracting activity.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 2016 - Moisture Content of Wood
D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.3.

3.2 Standard sample. Samples of the end item, when furnished, are solely for guidance and information to the contractor (see 6.3). Variation from this specification may appear in the sample, in which case this specification shall govern.

3.3 Materials and components. Materials and components shall be as specified herein and on the applicable drawings. Materials and components specified are for the two types of tents unless otherwise noted. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.3.1 Cloth, duck, polyester. The cloth for the body of the type I tent shall conform to class 1, grade A, and for the body of the type II tent shall conform to class 2, grade A of MIL-C-44103. The cloth for specific reinforcements shall conform to the requirements of 3.3.2.

3.3.2 Cloth, coated. The cloth for the ground shirts of the type I tent shall conform to type II, class 2, color Olive Drab 7 of MIL-C-20696. The cloth for the ground shirts of the type II tent shall be the same, except that the color shall be Desert Tan 459.

3.3.3 Cloth, duck, cotton. The cloth for the following reinforcements shall conform to MIL-C-43627, color Olive Drab 7, except the requirements for water resistance and colorfastness shall not apply. Reinforcements A through K, ridge reinforcements, center reinforcements, screen door lug, top door lug, and door lug.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

3.3.4 Tape, cotton. The tape for the type I tent shall be 3/4, 1, and 2 inch widths, color Olive Drab 7, conforming to type I, class 4, of MIL-T-43566. The tape for the type II tent shall be the same, except that the color shall be Desert Tan 459.

3.3.5 Webbing, cotton. The webbing for the type I tent shall be 1-1/2, 2, 2-1/2, or 4 inch widths, color Olive Drab 7 conforming to type III, class 4, of MIL-W-530. The webbing for the type II tent shall be the same, except the color shall be Desert Tan 459.

3.3.6 Webbing, textile, woven, low elongation. The low elongation webbing shall conform to types II and III of MIL-W-43638.

3.3.7 Thread, polyester. The thread shall conform to type I, class 1, subclass B of V-T-285, as indicated in table I.

TABLE I. Thread sizes

Location	Size
For all stitching except bartacking, zig-zag stitching, and stitching indicated by "Z" on drawings	Size FF for needle and bobbin
For bartacking and zig-zag stitching	Size E for needle and bobbin
For stitching indicated by "Z" on drawings	Size FF for needle and size F for looper

3.3.7.1 Color. The thread for all stitching shall match Olive Drab S-1 (C.A.66022) for the type I tent, and Khaki P-1 (C.A.66019) for the type II tent. The dyed thread shall show fastness to weathering equal to or better than the standard shade sample (see 6.3). When no standard shade sample is available, the thread shall show good fastness to weathering.

3.3.8 Screening, nonmetallic. The screening shall conform to type III, class 1 or 2, size 18 by 18, color green or type II, class 2, size 18 by 18, color green of L-S-125.

3.3.9 Cord, cotton. The braided cotton cord shall conform to type I, class 3, size 4 of T-C-571. The color shall match Olive Drab 7 for the type I tent and Desert Tan 459 for the type II tent, prior to the mildew resistant treatment. The color of the cord after treatment will be considered acceptable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

3.3.10 Film, plastic. Polyethylene film shall conform to the requirements for 0.006 inch thick, type I, class 1, grade A, B, or C, finish 1 of L-P-378 except that the thickness shall be 0.020 plus or minus 0.004 inch and the requirements for water-vapor permeability, impact resistance, slip, ink adhesion, and heat seal strength shall not be applicable.

3.3.11 Tent, liner, general purpose, large, fire, water and mildew resistant. The tent liner with cover shall conform to MIL-T-14056.

3.3.12 Lines, tent. The tent lines shall conform to MIL-L-1709. Types shall be as follows:

Type line type	Used for
I	- footstop
VI	- eave jumper line
X	- ridge jumper line
XXI	- eave guy line
XXIII	- ventilator line
XXXVIII	- ridge guy line

3.3.13 Rope, tent-lay. The tent-lay rope for stiffeners shall conform to manila or sisal, size 1 inch in circumference, three strand, furnished with a mildew resistant treatment conforming to A-A-50057.

3.3.14 Hooks, tent. The tent hooks shall conform to MIL-H-1608. Types shall be as follows:

Tent hook type	Eye shape
I, size 1-1/2 inches	- Triangle
III	- Square
IV	- Trapezoid
V	- Diamond

3.3.15 Fasteners, slide, interlocking. The slide fasteners shall conform to type III, style I, size H, stirrup pulls of V-F-106. The slide fastener chain shall be fabricated out of brass or polyester coil. The color for the brass coil shall be natural finish brass or black oxidized and for the polyester coil shall be Olive Drab. The slider for the brass chain shall be brass color, natural finish, brass or black oxidized. The slider for polyester coil shall be zinc alloy color Olive Drab. Alternatively, the slide fastener chain shall be polyester continuous monofilament in a ladder or coil type configuration. Color for the alternate chain shall be Olive Drab or natural finish brass for the type I tent, and Tan 380 or natural finish brass for the type II tent. The sliders for the alternate chain shall be brass, color natural finish brass for the type I and type II tents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

3.3.15.1 Tape, slide fastener. The slide fastener tape shall be dyed to match Olive Drab shade 7 (Cable No. 66519) for the type I tent, and dyed Tan 380 for the type II tent. The tape shall be water resistant and mildew resistant treated. Tapes made of 100 percent polyester do not require testing for mildew resistance. The color of the tape after treatment shall be considered acceptable. The tape shall show good fastness to weathering.

3.3.15.2 Window. Window fasteners shall be type I, style 2, with wire stirrup pull.

3.3.15.3 Wall corner. Corner fasteners shall be type III, style 1, with wire stirrup pull.

3.3.15.4 Chain. The length of slide fastener chains shall be such that after a slide fastener is sewed on, the tape shall not be puckered and the slider shall operate freely.

3.3.16 Grommets, metallic. The grommets shall conform to type III, class 3, size No. 4 of MIL-G-16491.

3.3.17 Plates, ridge. The ridge plates shall conform to types XIII and XIV of MIL-P-500.

3.3.18 Rings, connecting, round. The round connecting rings shall conform to class 2 or 5, size 4 of MIL-R-2327.

3.3.19 Rings, dee. The dee rings shall conform to either class 1 or 2, configuration symbol H of MIL-R-3390.

3.3.20 Rope, wire, sash cord. The wire rope shall be commercial grade, bright or galvanized finish, 1/8 inch diameter, 6 by 7 sash cord and shall have a minimum breaking strength of 500 pounds when tested as specified in 4.5.1.

3.3.21 Slips, tent line. The tent line slips shall conform to type II of MIL-S-1734.

3.3.22 Toggles, wood. The wood toggles shall be of the design and dimensions shown on Drawing 5-4-2178. They shall be fabricated from straight-grained sound and smooth lumber and shall contain not more than 15 percent moisture when tested as specified in 4.5.2. The wood for the toggles shall be free from knots, shakes, checks, splits, splintery surfaces, case hardening, or any other defect which may tend to affect appearance or weaken the wood. Any of the following woods may be used:

Hickory	Beech	Pecan	Hard Maple
Red or White Oak	Birch	Rock Elm	Ash

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

3.3.23 Poles, tent. The tent poles shall conform to the types, classes, and sizes of MIL-P-549 as follows (see 6.6):

Type I, class 2, size 12 feet 3 inches
Type I, class I, size 6 feet 2 inches
Type I, class I, size 5 feet 8 inches

3.3.24 Pins, tent, wood. The tent pins shall conform to MIL-P-2383 as follows:

Size I, 16 inches
Size II, 24 inches

3.3.25 Shield, stovepipe. The stovepipe shield shall conform to MIL-S-43002.

3.4 Construction. The construction shall conform to the drawings listed in section 2 and as specified herein.

3.4.1 Stitching, machine.

3.4.1.1 Types of stitching. All stitch types, except bartacking, shall conform to FED-STD-751 as indicated in table II.

TABLE II. Stitching types

Location	Type	Number of stitches per inch
For all stitching except zig-zag stitching, and stitching indicated by "Z" on drawings and alternatively for attachment of slide fasteners	301	5 to 7
*For zig-zag stitching	304	10 to 16
*For stitching indicated by "Z" on drawings and alternatively for attachment of slide fasteners	401	5 to 7 (chain portion of stitching shall not appear on outside of tent, vestibule, screen, or tent cover)
*For bartacking		Bartack 1/2 (± 1/16) inch in length with 1/8 ± 1/32 inch in width (bight) and shall contain 28 stitches

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

3.4.1.2 Type 301 stitching. Ends of all stitching shall be backstitched or overstitched 1/2 inch minimum except when caught in other stitching or turned under in a hem. Thread tension shall be maintained so that there will be no loose stitching resulting in puckering of the materials sewn. The lock shall be embedded in the materials sewn.

3.4.1.2.1 Repairs of type 301 stitching. Repairs of type 301 stitching shall be as follows:

a. When thread breaks or bobbin run-outs occur during sewing, the stitching shall be repaired by restarting the stitching a minimum of 1 inch back of the end of the stitching. 1/

b. Thread breaks or two or more consecutive skipped or run-off stitches noted during inspection of the item (in-process or end item) shall be repaired by overstitching. The stitching shall start a minimum of 1 inch in back of the defective area (1/2 inch on box, box-x, and W-W stitching) and continue a minimum of 1 inch beyond the defective area onto the existing stitching. Loose or excessively tight stitching shall be repaired by removing the defective stitching, without damaging the materials, and restitching in the required manner. 1/

1/ When making the above repairs, the ends of the stitching are not required to be backstitched.

3.4.1.3 Type 401 stitching. Thread tension shall be maintained so that there will be no loose stitching. Both ends of all seams or stitching produced with a 401 stitch type, when not turned under in a hem or held down by other stitching, shall have a 1/2 to 3/4 inch chain extending beyond each end. The looper (underthread) shall always be on the inside of the tent or cover. All repairs shall be made in accordance with 3.4.1.2.1a and 3.4.1.2.1b. Repairs may be made using 301 stitch type.

3.4.1.4 Type 304 and 308 zig-zag stitching. Thread tension shall be maintained so that there will be no loose or excessively tight stitching. Repairs shall be in accordance with 3.4.1.2.1a and 3.4.1.2.1b except that the stitching shall overstitch the defective stitching area a minimum of three stitches onto the existing stitching.

3.4.1.5 Bartacking. Bartacking shall be free of thread breaks and loose stitching.

3.4.1.6 Automatic stitching. Automatic stitching machines may be used to perform any of the required stitch patterns provided the requirements for the stitch pattern, stitches per inch, and size and type of thread are met, and at least three or more tying, overlapping, or back stitches are used to secure the ends of stitching.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

3.4.1.7 Thread ends. All thread ends that are visible on the finished item shall be trimmed to a length of not more than 1/4 inch.

3.4.1.8 Lubrication of thread. There shall be no lubrication of the polyester thread by any means prior to or during sewing operations (see 4.4.2).

3.4.2 Splicing of cloth. There shall be no splicing of the roof, wall, or tent cover panels. Splicing of reinforcements and sod cloth sections will be permitted. When performed, splicing shall conform to the following requirements:

(a) - 8 feet or less in length - 1 splice permitted
- more than 8 feet but not more than 12 feet in length - 2 splices permitted
- more than 12 feet in length - 3 splices permitted

(b) The shortest length of any spliced piece shall be not less than 2 feet

(c) Pieces shall be joined as shown on Drawing 5-4-2177

3.4.2.1 Stitching margins. Unless otherwise specified, all stitch margins shall be 1/8 ± 1/16 inch.

3.4.3 Attachment of slide fasteners. Care shall be exercised to trim all thread ends to 1/4 inch or less and maintain specified distances between edges of fabric attached to slide fastener tape so that there will be no interference with the operation of the slider.

3.4.4 Setting of grommets. Holes punched to receive grommets shall be smaller than the outside diameter of the grommet barrel so that the barrel must be forced through the hole. The grommets shall be securely clinched without cutting the materials (see 4.4.2).

3.4.5 Attachment of wooden toggles. Wood toggles shall be attached as shown on Drawing 5-4-2178.

3.4.6 Splicing of wire rope. The ends of the 1/8-inch diameter wire rope shall be anchored in a suitable splicing sleeve having dimensions not to exceed 7/16-inch diameter or 2-1/2-inches overall length (see 6.5) and shall have a minimum parting strength of 500 pounds when tested as specified in 4.5.1.

3.4.7 Wicking of stitching thread. There shall be no wicking of water through the tent stitching when the tent is tested as specified in 4.4.5. The cup test is intended to insure that nonwicking thread has been utilized and that no lubrication has been added to the polyester thread prior to or during the sewing operation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

3.4.8 Repairs. All necessary repairs shall be effected in accordance with Department of the Army Field Manual FM 10-16. Any repairs required shall be authorized by the contracting officer.

3.5 Marking. All labels and marking shall conform to DDD-L-20.

3.5.1 Identification label. Identification labels shall conform to type VI, class 6 and shall be 3-1/2 inches by 5-1/2 inches minimum and a blank space of at least 1-1/4 inches shall be provided on the bottom of the label for the Department of Defense inspector's stamp. Identification labels shall be stitched to the tent and cover in the locations shown on the drawings.

3.5.2 Erection instruction label. Labels of erection instructions shall conform to type VI, class 7 and shall be stitched to the tent and cover in the locations shown on the drawings. The label shall be a proportionate copy of Drawing 5-4-540 as reproduced from a glossy print of this drawing furnished by the contracting officer. The size of the label shall be, borderline to borderline, 15 $\pm$ 1/4 inches in the longer dimension, with a minimum 1/2-inch margin outside of the borderline on all sides.

3.5.3 Care and maintenance instructions label. Labels of care and maintenance instructions shall conform to type VI, class 7 and shall be stitched to the tent and cover in the locations shown on the drawings. The label shall be a proportionate copy of Drawing 5-4-541, as reproduced from a glossy print of this drawing furnished by the contracting officer. The size of the label shall be, borderline to borderline, 15 $\pm$ 1/4 inches in the longer dimension, with a minimum 1/2-inch margin outside of the borderline on all sides.

3.5.4 Special marking. The letters "U.S." on the tent and protective corner covers and special marking on cover and protective corner covers shall conform to type IV, class 9 in the size characters and in the locations shown on the drawings. Class 9 markings shall be clearly legible after subjection to accelerated weathering.

3.6 Workmanship. Cloth components shall be clean and free of holes, cuts, tears, or cloth defects such as multiple floats or broken or missing yarns. Webbing and tape shall not have frayed or scalloped edges and rope components shall be free of cuts or breaks. Thread tension shall be maintained so that there will be no loose stitching, and seam allowances shall be maintained with seams properly sewed so that no runoffs, twists, pleats, or open seams shall result. Care shall be taken in the sewing to see that no needle chews occur. Metal components shall be free of burrs, sharp edges, corroded areas and shall not be broken or malformed. The tent shall conform to the quality of product established by this specification and the occurrence of defects shall not exceed the applicable acceptable quality levels.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for ensuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to ensure compliance with all dimensional requirements.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.4.3 and 4.4.4 and shall be tested for the characteristics specified in 4.4.5. Any nonconformance shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.4.1.1 Component testing. In addition to the quality assurance provisions of the subsidiary documents, tests shall be performed on components listed below for the characteristics shown. A lot shall consist of all wood toggles, and all wire rope with wire rope splicing sleeves (if applicable) offered for inspection at one time. The inspection level shall be S-1. The acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 6.5 for component c. only. The presence of any defect for component a. or b. shall result in rejection of that component.

Component	Requirement	Test Method
a. Rope wire sash	3.3.19	4.5.1
b. Splicing sleeves wire, rope	3.4.5	4.5.1
c. Toggles, wood	3.3.21	4.5.2

4.4.2 In-process inspection. Inspection of subassemblies shall be made to ascertain that construction details which cannot be examined in the finished product are in accordance with specified requirements. The Government reserves the right to exclude from consideration for acceptance, any material or service for which in-process inspection has indicated nonconformance.

a. There shall be no lubrication of polyester thread prior to or during the sewing operations for compliance with 3.4.1.8.

b. Holes punched to receive grommets are in compliance with 3.4.4.

4.4.3 End item visual examination. The end items (tents with covers or covers only) shall be examined for the defects listed in table III. The lot size shall be expressed in units of end items. The sample unit shall be one end item. The inspection level shall be II and the AQL's, expressed in terms of defects per hundred units, shall be as follows:

For tent with cover:
40 for major defects
150 for combined major and minor A defects
250 for combined major, minor A, and minor B defects
For cover only:
10 for major defects
25 for combined major and minor A defects
100 for combined major, minor A, and minor B defects

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

TABLE III. End item visual defects

Examine	Defect	Classification Major	Minor A	Minor B
Fabric	Cut, tear or hole:			
	- greater than 1/8 inch in length or diameter:			
	- on roof	101		
	- on walls, sod cloth or cover		201	
	- more than 5 holes not greater than 1/8 inch:			
	- on roof		202	
	- on walls, sod cloth or cover			301
	Broken or missing yarn; multiple floats clearly visible at normal inspection distance (approximately 3 feet)		203	
	NOTE: Any opening larger than 1/8 inch shall be classified under one cut, tear or hole.			
Screening	Cut or tear:			
	- more than 2 inches in length	102		
	- more than 1/4 inch but not more than 2 inches in length		204	
Plastic Film	Puncture, crease or crack:			
	- 2 inches or more in length		205	
	- less than 2 inches in length			302
Webbing or tape	Edge frayed or scalloped			303
Rope components; tent lines	Any cut; any break:			
	- on ridge guy line		206	
	- on eave guy line		207	
	- on any other line			304
	Eye splice omitted		208	
	Eye splice not as specified			305
	Free ends not finished as specified			306
	Knots where required not pulled tight mechanically and can be opened by hand			307

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

TABLE III. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Hardware - general	Broken or malformed; corroded area; burrs or sharp edge	103		
	Finish omitted or not as specified	104		
	Any required component improperly installed causing failure to serve intended purpose	105		
Grommets	Misaligned with eye of tent hook obstructing passage of pole spindle	106		
	Improperly set; two or more teeth exposed (except where grommet is set as specified, but is in an area of uneven thickness which prevents uniform clinching)			308
	Clinched loosely, allowing grommet to rotate in hole			309
	Clinched excessively tight, cutting fabric:			
	- on tent	107		
	- on cover		209	
	Insecurely clinched; i.e., grommets or washers to become disengaged:			
	- on tent	108		
	- on cover		210	
	Set with barrel inserted from outside in lieu of inside:			
	- on eave or ridge		211	
	- at any other location			310
Tent hooks:				
Diamond, square or trapezoid eye	Hook not securely closed allowing connecting hardware to become disengaged			311
	Hook not set as specified			312
	Trapezoid eye reversed, causing poor distribution of pulling force on webbing			313

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

TABLE III. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Tent hooks: (cont'd)				
Triangle eye	Hook not inserted through ridge plate hole	109		
	Hook not securely closed allowing connecting hardware to become disengaged		212	
	Set with hook portion facing roof			314
Ridge plates	One or more misplaced, so that plate center hole fails to correspond with grommets on ridge resulting in obstruction of passage of pole spindle	110		
Toggles	Toggle held in place with a single turn of rope around grooves, or double turn not overhand knotted		213	
Seams and stitching	Open seams:			
	- 1/2 inch or less			315
	- More than 1/2 inch	111		
	NOTE: A seam shall be classified as an open seam when one or more stitches joining a seam are broken, or when two or more consecutive skipped or runoff stitches occur.			
Seam and stitch type	Not specified seam or stitch type	112		
	Seam twisted, pleated or badly puckered (unless otherwise classified herein)			316
	Any line of stitching not beginning or ending where specified (unless otherwise classified herein)			317
	Any seam not lapped or finished as specified			318
Raw edge (on edge required to be finished)	More than 1/2 inch in length when securely caught in stitching			319
	NOTE: Raw edge not securely caught in stitching shall be classified as an open seam.			

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

TABLE III. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Thread breaks, skipped stitches or runoffs	On stitching other than box-x or W-W stitching, overstitched less than 1 inch in each direction beyond defective stitching area for 301 and 401 type stitching and less than 3 stitches minimum on type 304 and 308 type stitching			320
	On box-x or W-W stitching, overstitched less than 1/2 inch in each direction beyond the defective stitching area			321
	NOTE: Thread breaks or two or more consecutive skipped or runoff stitches not overstitched shall be classified as open seams.			
Boxstitching	Incomplete:			
	- one row of stitching omitted		214	
	- two or more rows of stitching omitted		215	
	Any boxstitching less than specified length by more than 1/8 inch			322
"W" stitching	Incomplete:			
	- one row of stitching omitted		216	
	- two or more rows of stitching omitted	113		
	Any "W" stitching less than specified length by more than 1 inch			323
Bartacking	Bartacking less than specified length by more than 1/16 inch			324
Stitching ends	Overstitched less than 1 inch on stitch type 301 (except where ends are held down by other stitching, turned under in a hem, or where stitching is performed automatically)		217	
	Secured with less than 3 tying, overlapping or backstitches when automatic stitching is performed		218	

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

TABLE III. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Stitching ends (cont'd)	Secured with less than 1/2 inch of backstitching, overstitching, or by an increased number of stitches at the end of stitch type 304			325
	Seam pleated:			
	- on roof		219	
	- at eave or on wall			326
Rows of stitching	One or more required rows of stitching omitted:			
	- Affecting serviceability seriously	114		
	- Affecting serviceability but not seriously			327
Bartacks	One or more bartacks omitted	115		
	Any bartack not as specified or not in specified location			328
	Loose stitching, incomplete or broken			329
Component and assembly	Any component part or required operation omitted (unless otherwise classified herein)	116		
	Any operation not performed as specified (unless otherwise classified herein)			330
	Color of component not as specified			331
Cutting	Any component part not cut in accordance with directional lines indicated on pattern or not cut in accordance with document requirements	117		
Stitch tension	Tension loose, resulting in loose bobbin or top thread			332
	Tension tight, resulting in puckering of material			333
Stitches per inch	Less than minimum specified (except on panel joining seams)			
	- one stitch			334
	- two or more stitches		220	

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

TABLE III. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Stitches per inch (cont'd)	Less than minimum specified on panel joining seams		221	
	More than maximum specified:			
	- one stitch			335
	- two or more stitches		222	
	NOTE: Variation in the number of stitches per inch, caused by the operator speeding up the machine in order to sew over heavy places or heavy seams or in turning corners, shall be classified as follows:			
	a. Within the minor "A" defect classification - minor "B" defect			
	b. Within the minor "B" defect classification - no defect			
Stitching gage	Not as specified		223	
Stitching margin	Larger than specified by more than 3/16 inch:			
	- for more than 2 inches but not more than 4 inches in length			336
	- for more than 4 inches in length		224	
Stitching indicated by "Z" on drawings	Chain portion of stitching shows on outside of tent or cover		225	
Mends, darns or patches	Repairs not in accordance with Department of the Army Field Manual FM 10-16 or not authorized by the contracting officer (see 3.4.8)	118		
Components and assembly	Any component part omitted or not fabricated of applicable referenced material	119		

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

TABLE III. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Construction details:				
Hems	Constructed with partial turnunder when double turnunder is required		226	
	Twisted or pleated			337
Reinforcements	Improperly applied, causing excessive fullness on reinforcements or reinforced parts			338
Cloth splicing (see 3.4.2)	Splice in roof, wall or tent cover panels	120		
	Number of splices per reinforcement or sod cloth section more than specified		227	
	Spliced pieces not joined as shown on Drawing 5-4-2177			339
	Spliced piece shorter than 2 feet			340
Slide fastener	Not functioning properly, failing to effect a secure closure or to open freely	121		
	Not specified type or size	122		
	Slider jams or fails to interlock	123		
	Thong omitted	124		
	Damaged teeth	125		
Fastener tape	Any hole, cut or tear	126		
	Hooks flattened, broken, or missing, impairing function	127		
	Width not as specified	128		
	Any tape improperly assembled, causing failure of chain to effect a smooth and secure closure	129		
Window panes	Edges of film not caught in frame stitching:			
	- for more than 1 inch, but not more than 3 inches			341
	- for more than 3 inches		228	

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

TABLE III. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Window screens	Edges of screen not caught in stitching attaching window reinforcement webbing to opening:			
	- for 2 inches or more in length	130		
	- for less than 2 inches in length		229	
End wall side door lug	Grommet adjacent to stitched edge not inserted through both end wall half and side door lug		230	
	Top end of lug not stitched to underside of top lug "A"		231	
	Misplaced; i.e., set on right end wall or failing to overlap door edge of right end wall		232	
Eaves	Excessive fullness along eave overlap			342
Points of stress on ridge and eaves	Webbing loops engaging hardware at each stress area set loose, failing to relieve stress from canvas:			
	- on one loop			343
	- on two or more loops	131		
	NOTE: When the proper tension between the webbing and the hardware and the webbing and the tent body has been attained, only slight fullness of the fabric at stress points will result.			
Door toggle loops	Stitched to door edge on inside in lieu of outside			344
	Not securely overcast stitched to door edge		233	
	Any loop misplaced, failing to effect a smooth and secure closure of doors		234	
Toggle chapes	Any toggle chape misplaced such as right end wall chape set on outside of door in lieu of inside; left end wall chape			

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

TABLE III. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Toggle chapes (cont'd)	set in inside of door in lieu of of outside; or ends or cord not securely overcast stitched through end wall and reinforcement resulting in failure to effect a smooth and secure closure of door		235	
Ring chapes "A"	Right end wall ring chape set on outside of door in lieu of inside; left end wall ring chape set on inside of door in lieu of outside			345
	Steel cable not threaded through all rings in door area:			
	- one ring missed		236	
	- two or more rings missed	132		
Door top lug "A"	Not securely stitched through end roof, reinforcement "F", and door top lug "B"	133		
End wall top door lug "B"	Not securely stitched through reinforcement "F", end roof and top door lug "A"	134		
End wall screen door lug	Ends of lug stitched to top door lug "B" failing to provide clearance for top end of screen doors		237	
Ring chapes	Any chape not securely caught in double row of stitching assembling screen door lug to top door lug "B"		238	
Screen doors	Reversed; i.e., set to end wall halves with sod cloth on outside of tent			346
	Stitched through wall halves only; i.e., not through wall reinforcement		239	

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

TABLE III. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Wall corner lugs	Any lug not stitched through wall hems		240	
Roof ventilator screens	Edges of screen not caught in stitching attaching reinforcement webbing to ventilator opening:			
	- 2 inches or more in length	135		
	- less than 2 inches in length		241	
Ventilator flaps	Top end flaps not overlapped	136		
	Misplaced; i.e., not stitched through ventilator reinforcement		242	
Stovepipe opening drip cap	Rope stiffener omitted or not held in place by stitching at bottom edge of drip cap		243	
Stovepipe shield	Set to roof with oval opening in a horizontal position instead of vertical	137		
	Exposed stitching or needle holes			347
General	Any other construction details not performed as specified		244	
Labels	Omitted, incorrect, illegible, or misplaced:			
	- erection or maintenance instructions		245	
	- identification			348
Marking: "U.S." on tent and cover, nomenclature on cover	Omitted, incorrect, illegible or misplaced			349
Cleanness	Grease or oil stains			350
	Thread ends not trimmed to 1/4 inch or less (except in slide fastener area)			351
	Thread ends not trimmed to 1/4 inch or less in slide fastener area		246	

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

4.4.4 End item dimensional examination. The end items (tents with covers or covers only) shall be examined for the defects listed in table IV. The lot size shall be expressed in units of end items. The sample unit shall be one end item. The inspection level shall be S-3 and the AQL's, expressed in terms of defects per hundred units, shall be as follows:

For tent with cover:
2.5 for major defects
40 for combined major and minor A defects
100 for combined major, minor A, and minor B defects
For cover only:
10 for major defects
25 for combined major and minor A defects
100 for combined major, minor A, and minor B defects

TABLE IV. End item dimensional defects

Examine	Defect	Classification Major	Minor A	Minor B
Overall dimensions on tent	Smaller than specified dimensions less applicable minus tolerance indicated on drawings	101		
	Larger than specified dimensions and applicable plus tolerance indicated on drawings			301
Dimensions: Tent covers and ventilator openings (unless otherwise specified)	Smaller than specified dimension less applicable minus tolerance indicated on drawing, but not smaller than specified dimensions less twice the applicable minus tolerance			302
	Smaller than specified dimensions less twice the applicable minus tolerance indicated on drawing		201	
	Larger than specified dimensions and applicable plus tolerance indicated on drawing			303
Hems	Hems required to finish less than 3/4 inch in width, less than specified; hems required to finish 3/4 inch or more in width, less than specified by more than 1/4 inch			304

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

TABLE IV. End item dimensional defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Sod cloths	Less than 10 inches wide from bottom edges of wall to edge of sod cloth hems; end of sod cloths at locations of wall reinforcement webbing set in bottom hem less than 1-3/4 inches or more than 3-3/4 inches apart; end wall sod cloths set in bottom hem with end of cloths more than 1/2 inch from inner edge of wall reinforcement; opening between sod cloth ends off center of wall reinforcements by more than 1/2 inch		202	
	Any spliced piece less than 2 feet in length		203	
Eaves	Eaves overlap on side walls end walls less than 5-1/2 inches wide from finished bottom edge of roof section to finished top edge of wall for more than 12 inches at any one location		204	
Location dimensions (unless otherwise specified)	Not within the specified tolerance: - not exceeding twice the applicable tolerance			305
	- exceeding twice the applicable tolerance		205	
Webbing and tie tapes (except wall tie tapes)	Finished length less than specified by more than 1 inch			
	Turnunder at ends of webbing engaging hardware less than specified: - by more than 1 inch but not more than 1-1/2 inches			306
	- by more than 1-1/2 inches		206	
Wall tie tapes	Length (on either side of wall) less than 11 inches			307
Grommets	Set beyond specified location by more than 1/2 inch (unless otherwise specified)			308

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

TABLE IV. End item dimensional defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Grommets (cont'd)	Intermediate bottom wall grommets set beyond specified location by more than 2 inches			309
Rope components; tent lines	Ridge, eave, or ventilator flap lines less than specified finished length:			
	- by not more than 4 inches			310
	- by more than 4 inches but not more than 12 inches		207	
	- by more than 12 inches	102		
	Any other line less than specified finished length			
	- by more than 2 inches but not more than 6 inches		208	
	- by more than 6 inches	103		
	Eye on footstop less than 3 inches		209	
Reinforcements	Finished dimensions of reinforcements less than specified by more than 1/2 inch			311
	Any spliced piece less than 2 feet in length			312
Wall corners, inside corner lug	Any lug set beyond specified location by more than 1/8 inch			313

4.4.5 End item testing. Tents shall be tested as specified in 4.5.3 for compliance with 3.4.7. The lot size shall be expressed in units of completely fabricated tents. The sample unit shall be one completely fabricated tent. The inspection level shall be S-3. The failure of the test shall be cause for rejection of the lot.

4.4.6 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as: incomplete closure of cloth wrapping and loose stitching

4.5 Methods of inspection.

4.5.1 Strength test. Breaking strength of wire rope and a splicing sleeve (joining two ends of wire rope as specified in 3.4.6) shall be determined by subjecting the assembly to a proof load test of 500 pounds in accordance with standard commercial practice. Breakage of the wire rope or parting at the splicing sleeve shall be classified as a defect (see 4.4.1.1).

4.5.2 Moisture content of wood toggles. The moisture content of wood toggles shall be determined in accordance with the oven drying method or moisture meter method referenced in ASTM D 2016. Results shall be reported to the nearest 0.1 percent. Any nonconformance to the moisture content requirement in 3.3.22 shall be considered a defect (see 4.4.1.1).

4.5.3 Wicking of sewing thread (cup test). The tent shall be tested in three areas as follows: at the peak, ridge, or joining seam abutting the peak or ridge; at an intersection of a horizontal and vertical seam such as at an intersection of a side wall and roof; and on a roof panel seam. Suspend the seamed section of the test fabric in the center of a 6 $\pm$ 1/8 inch diameter hoop and form a depression with the seamed fabric in the hoop to a depth of 1 $\pm$ 1/4 inch. Slowly pour 500 mL of water at 77°F $\pm$ 4°F into the cupped area (depression) and observe the under surface of the fabric for water penetration. Any wicking of water along the sewing thread, identified by a discoloration or darkening of the thread within 5 minutes after water is poured, shall constitute a failure. Water leakage through the needle holes or between the plies of the lapped seamed fabric shall not be considered a failure.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A preservation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

5.1.1.1 Tent with cover. Each tent, with corner slide fasteners open, shall be spread out flat with outside facing up. Secure windows, doors, screens, blackout flaps, stove pipe and ventilator openings. Loosely coil ridge guy lines and place on tent deck. The eave guy line slips shall be brought up close to the eave line and the guy lines then placed on the tent deck facing toward the center. Fold the end walls over on the tent deck along the eave line. Use the same folding operation for the side walls. Starting with an increment of 3-1/2 feet, the ends of the tent shall be folded toward the center, resulting in two folded sections adjacent to each other. One of the folded sections shall then be folded over on top of the other section. During the folding operation, each exposed ridge plate and hooks hardware shall be centered on the fold and covered with three thicknesses of scrap (burlap or cloth, cotton duck) tentage material (one thickness underneath and two thicknesses on top). The interim folded tent dimensions at this point are approximately 4 feet by 21 feet. Fold the tent in half the length by bringing the short side edge (offset ridge side) over to the opposite edge. The completely folded tent shall measure approximately 4 feet by 4 feet by 1-1/2 feet. The folded tent shall then be placed within the cover provided and the cover tie lines securely tied. All flaps of the cover shall be neatly folded within the unit pack.

5.1.1.2 Tent cover. Tent covers, when procured separately, shall be compactly folded to measure approximately 27 inches by 36 inches with the identification marking visible and the tie lines placed with the folds. Five folded covers shall be stacked and cross tied with cotton tape or twine.

5.1.2 Commercial preservation. Each tent or cover shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Level A packing.

5.2.1.1 Complete assembly. One tent with cover preserved as specified in 5.1, one tent liner with cover as specified in 3.3.11, and tent poles and pins in the numbers specified in table V and as specified in 3.3.23 and 3.3.24 shall be packed in a snug-fitting, wood-cleated plywood shipping container conforming to overseas type, style A or J, type 3 load of PPP-B-601. Each container shall be provided with skids fabricated as specified in the container specification. The inside dimensions of the shipping container shall be 93-1/2 inches in length, 45 inches in width, and 21 inches in depth. Approximate dimensions are furnished as a guide only. Poles and pins, as specified, shall be placed flat in the bottom of the box. The tent with its cover and the liner with its cover shall be placed on top of the poles. Cushioning shall be applied as necessary to immobilize the contents and prevent abrasions. Each shipping container shall be closed and reinforced with flat strapping in accordance with the appendix of the container specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

TABLE V. Poles and pins

	Length	Quantity
Poles	12 feet 3 inches	4
	6 feet 2 inches	4
	5 feet 8 inches	12
Pins	16 inches	68
	24 inches	32

5.2.1.2 Tent with cover. One tent with cover, preserved as specified in 5.1, shall be packed in a snug-fitting wood-cleated plywood shipping container conforming to overseas type, style A of PPP-B-601. Each container shall be provided with skids fabricated as specified in PPP-B-601. Each shipping container shall be closed and reinforced with flat steel strapping in accordance with the appendix of PPP-B-601 (see 6.2).

5.2.1.3 Tent covers. The tent covers, preserved as specified in 5.1.1.2 shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, V2s of PPP-B-636. The inside of each container shall be closed, water-proofed, and reinforced with flat strapping or tape banding in accordance with the appendix of PPP-B-636 (see 6.2).

5.2.2 Level B packing.

5.2.2.1 Complete assemblies. One tent with cover preserved as specified in 5.1, tent liners with cover as specified in 3.3.11 and tent poles and tent pins in quantities specified in table V shall be packed as specified in 5.2.1.1 except that the shipping container shall be domestic type.

5.2.2.2 Tent or tent covers. One tent with cover, or ten tent covers preserved as specified in 5.1.1, shall be wrapped and sewn in cotton osnaburg cloth conforming to class 2 of CCC-C-429; or burlap cloth conforming to class 3 of CCC-C-467. The cloth wrapping shall be securely hand sewn with type I or II, 16-ply cotton twine conforming to T-T-871 or type I, size No. 2 jute twine conforming to T-T-911, with approximately one stitch to the inch and every third stitch overhand knotted. Alternately the bottom and side may be machine sewn. A minimum of five inches of wrapping material shall be gathered together on each of the four corners and securely hand sewn into ears for handles. In lieu of the sewn wrapping indicated above, bias-sewn tubing conforming to MIL-T-40625 may be used. One end of the tubing may be machine sewn. The formation of handles shall be effected by hand sewing in conformance with method described above. Whenever machine sewing is used, the thread type, stitch type, and number of stitches per inch shall conform to the requirements specified in MIL-T-40625. However, the polyester thread used in manufacturing the end item may be used for effecting the machine-sewn closure of the wrapping or tubing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

5.2.3 Commercial packing. Tents with covers, preserved as specified in 5.1, tent covers or tent with cover, tent liner with cover (see 3.3.11) and tent poles and tent pins in quantities specified in 5.2.1.1, when procured together, shall be packed in accordance with ASTM D 3951.

5.3 Marking. In addition to any special marking required by the contract or purchase order, shipping containers shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

5.3.1 Additional marking. The following shall be stencilled or imprinted on each cloth covered bundle (except where covers have been procured separately) in characters not less than 3/4 inch high:

"SEE ERECTION INSTRUCTIONS SEWED TO INSIDE OF TENT COVER"

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The tent is designed to be used primarily as a hospital ward or surgical operating room. However, it can be used for quartering troops, as a command post, fire direction center, mess hall, storage area, an assembly area or to house components of a field bakery. Although the tent is intended for use principally in temperate and tropical areas, it can be used effectively in cold climate areas by addition of a tent liner.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number and date of this specification.
b. Type of tent required (see 1.2).
c. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
d. When a first article is required (see 3.1, 4.3, and 6.3).
e. Levels of preservation and packing (see 5.1 and 5.2).
f. When tent with cover only is required (see 5.2.1.2).
g. When tent cover only is required (see 5.2.1.3).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of Federal Acquisition Regulation (FAR) 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

6.4 Sample. For access to samples, address the contracting activity issuing the invitation for bids or request for proposal.

6.5 Commercial products. The National Telephone and Supply Company's splicing sleeve, 2-134-J, used in conjunction with this company's Nicopress tool No. 31-DJ, has been found to provide a splice meeting the requirements specified in 3.4.6.

6.6 Poles, tent. Optional lightweight tent poles conforming to the following types, classes and sizes of MIL-P-43413 are available for the type I and type II tents.

Type IV, 5 feet 8 inches
Type III, 6 feet 2 inches
Type II, class B, 12 feet 3 inches

6.7 Subject term (key word) listing.

Shelter

6.8 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Preparing activity:

Army - GL

(Project 8340-0549)

Review activities:

Army - MD
Air Force - 82
DLA - CT

User activity:

Navy - YD

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:47Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	MIL-T-14038K	1991 September 16

3. DOCUMENT TITLE

TENT, GENERAL PURPOSE, LARGE

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial	(2) AUTOVON/DSN
U.S. Army Natick RD&E Center	508-651-4531	256-4531
c. ADDRESS (Include Zip Code) Commander, U.S. Army Natick RD&E Center ATTN: STRNC-UXT Natick, MA 01760-5017	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

Source: https://assist.dla.mil -- Downloaded: 2020-10-10T02:47Z
Check the source to verify that this is the current version before use.