DDD-B-151J
30 June 1988
SUPERSEDING
DDD-B-151H
October 21, 1981

FEDERAL SPECIFICATION

BEDSPREAD, COTTON, POLYESTER, COTTON/RAYON, COTTON/POLYESTER OR POLYESTER/RAYON BLEND

This specification is approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE

1.1 Scope. This specification covers the requirements for a cotton, polyester, cotton/rayon, cotton/polyester, or polyester/rayon blend bedspread.

1.2 Classification. Bedspreads shall be of the following types and sizes as specified in Table I (see 6.2).

Type I - Crinkle
  Sizes 3, 4

Type II - Dimity

Type III - deleted

Type IV - Corded
  Style A
    Sizes 1, 2, 3, 4, 5
  Style B - deleted

Type V - Corded
  Style A
    Sizes 1, 2, 3, 4, 5
  Style B - deleted

Type VI - Corded
  Style A
    Sizes 1, 2, 3, 4, 5
  Style B - deleted

AMSC N/A FSC 7210

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications

V-T-276	- Thread, Cotton
PPP-B-636	- Boxes, Shipping, Fiberboard
PPP-F-320	- Fiberboard; Corrugated and Solid, Sheet Stock (Container Grade), and Cut Shapes

Federal Standards

FED-STD-4	- Glossary of Fabric Imperfections
FED-STD-123	- Marking for Shipment (Civil Agencies)
FED-STD-191	- Textile Test Methods
FED-STD-751	- Stitches, Seams, and Stitchings

(Activities outside the Federal Government may obtain copies of Federal specifications, standards, and commercial item descriptions as outlined under General Information in the Index of Federal Specifications, Standards, and Commercial Item Descriptions. The Index, which includes cumulative bimonthly supplements as issued, is for sale on a subscription basis by the Superindentent of Documents, U.S. Government Printing Office, Washington, DC 20402.)

(Single copies of this specification and other Federal specifications and commercial item descriptions required by activities outside the Federal Government for bidding purposes are available without charge from General Services Administration Business Service Centers in Boston, MA; New York, NY; Philadelphia, PA; Washington, DC; Atlanta, GA; Chicago, IL; Kansas City, MO; Fort Worth, TX; Houston, TX; Denver, CO; San Francisco, CA; Los Angeles, CA; and Seattle, WA.)

(Federal Government activities may obtain copies of Federal standardization documents and the Index of Federal Specifications, Standards, and Commercial Item Descriptions from established distribution points in their agencies.)

Military Specifications:

MIL-T-43548	- Thread, Polyester Core: Cotton-, Rayon-, and Polyester-Covered

Military Standards:

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	- Marking for Shipment and Storage
MS 16686	- Medical Services Symbol

(Copies of military specifications and standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

RULES AND REGULATIONS UNDER THE TEXTILE FIBER PRODUCTS IDENTIFICATION ACT

(Copies may be obtained without charge from the Federal Trade Commission, Washington, DC 20580.)

TECHNICAL MANUAL OF AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS

TM 20A Analysis of Textiles: Quantitative

(Application for copies should be addressed to AATCC National Headquarters, P. O. Box 12215, Research Triangle Park, NC 27709-9989.)

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification

(Application for copies should be addressed to American Trucking Association, ATTN: Traffic Department, 1616 P Street, NW, Washington, DC 20036-1404).

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606-5808.)

3. REQUIREMENTS

3.1 Samples.

3.1.1 Guide sample. Samples, when furnished, are solely for guidance and information to the contractor (see 6.3). Variations from this specification may appear in the sample, in which case this specification shall govern.

3.1.2 Standard sample. The finished bedspread shall match the standard sample for shade, design and pattern, and shall be equal or better than the standard sample in all characteristics for which the standard sample is referenced (see 6.3). When a commercial design is selected, the approved sample shall, for the contract, become the standard for the characteristics for which it has been approved.

3.2 First article. When specified (see 6.2), the contractor shall furnish sample unit(s) for first article inspection and approval (see 4.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

3.3 Materials. (see 6.5)

3.3.1 Bedspreads. The bedspreads shall be either all cotton, all polyester, a blend of cotton/rayon, cotton/polyester, or polyester/rayon as specified in 3.3.1.1 through 3.3.1.5 (see 6.2).

3.3.1.1 Bedspreads, cotton. The yarn for the bedspreads shall be made from cotton which has been carded, drawn and spun into singles yarn for both warp and filling. The bedspreads shall meet the requirements specified in Table I when tested as specified in 4.5.

3.3.1.2 Bedspreads, cotton/rayon blend. The yarn for the bedspreads, except for the cords for type IV bedspreads which shall be all cotton, shall consist of a blend of 50 percent cotton, as specified in 3.3.1.1, and 50 percent high wet-strength modulus type rayon, with a tolerance of ± 5.0 percent for fiber content on a conditioned basis when tested as specified in 4.5.1. The bedspreads shall meet all requirements specified in Table I when tested as specified in 4.5.

3.3.1.3 Bedspreads, cotton/polyester blend. The yarn for the type IV bedspreads shall consist of a blend of cotton, as specified in 3.3.1.1 and up to 50 percent polyethylene glycol terephthalate with a tolerance of ± 5.0 percent for fiber content on a conditioned basis when tested as specified in 4.5.2. The bedspreads shall meet all requirements specified in Table I when tested as specified in 4.5.

3.3.1.4 Bedspreads, polyester/rayon blend. The yarn for the type V bedspreads shall consist of a blend of 75 percent polyester and 25 percent rayon with a tolerance of ± 5 percent for either fiber component on a conditioned basis when tested as specified in 4.5.2. The bedspreads shall meet all requirements in Table I when tested as specified in 4.5.

3.3.1.5 Bedspreads, polyester. The yarn for the type VI bedspreads shall be made of 100% polyethylene glycol therphthalate. The bedspreads shall meet the requirements specified in Table I when tested as specified in 4.5.

3.3.2 Physical requirements. The finished cloth shall conform to the requirements shown in Table I when tested as specified in 4.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Table I - Physical Requirements

Type	Size of finished bedspread (after laundering) (minimum) (inches)	Weight of finished bedspread (minimum) (ounces)	Yarns per inch (minimum) Warp	Filling	Breaking strength (minimum) (pounds) Warp	Filling
I Crinkle						
Size 3	72 by 97	27.0	72 in plain ground - 62 in crinkle	62	50	50
Size 4	72 by 106	29.0	72 in plain ground - 62 in crinkle	62	50	50
II Dimity	81 by 103	32.5	70	50	75	45
IV Corded						
Style A			Including cords			
Size 1	63 by 103	32.0	45	30	35	25
Size 2	76 by 103	39.0	45	30	35	25
Size 3	76 by 113	43.0	45	30	35	25
Size 4	90 by 113	51.0	45	30	35	25
Size 5	56 by 88	24.0	45	30	35	25
V Corded						
Style A			Including cords			
Size 1	63 by 103	32.0	54	23	100	75
Size 2	76 by 103	39.0	54	23	100	75
Size 3	76 by 113	43.0	54	23	100	75
Size 4	90 by 113	51.0	54	23	100	75
Size 5	56 by 88	24.0	54	23	100	75
VI Corded						
Style A			Including cords			
Size 1	63 by 103	31.5	54	23	100	75
Size 2	76 by 103	38.0	54	23	100	75
Size 3	76 by 113	42.0	54	23	100	75
Size 4	90 by 113	49.5	54	23	100	75
Size 5	56 by 88	24.0	54	23	100	75

3.3.3 Thread.

3.3.3.1 Thread, cotton. The cotton thread used for hemming shall be 3 ply, ticket No. 40, conforming to types IA2 and IA3 of V-T-276. The color of the thread shall match the color of the basic material. As a minimum level of acceptability, the dyed thread shall show good colorfastness to laundering, light and bleaching. As an alternate, a clear monofilament thread may be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

3.3.3.2 Thread, polyester, covered. As an alternate to the cotton thread, all bedspreads manufactured of a blend material (see 3.3.1), may use a 2 or 3 ply polyester covered thread conforming to ticket no. 40 of MIL-T-43548, except that polyester covered, polyester core thread shall not be used. The color of the thread shall match the color of the basic material. As a minimum level of acceptabiity, the dyed thread shall show a minimum of good colorfastness to laundering, light, and bleaching.

3.4 Construction. The bedspreads shall be fabricated from one piece of fabric that has straight woven selvages with the ends and/or sides of the bedspread cut parallel to the filling yarns. As an alternate, the bedspreads may be fabricated with the sides and/or ends of the bedspread cut parallel to the warp yarns. The four corners shall be cut square. The cut ends and/or sides of the bedspread shall be hemmed (see 3.4.2).

3.4.1 Stitches, seams, and stitching. The stitches, seams, and stitching types shall conform to FED-STD-751. Thread breaks shall be secured by stitching back of break not less than 1/2 inch.

3.4.2 Hems. The finished hems shall be not less than 3/4 nor more than 1 inch wide, with the raw edges turned under not less than 1/4 inch, using stitching type EFb-1. All hems shall be stitched with not less than 5, nor more than 10 stitches per inch, using stitch type 301. The stitching shall be 1/16 to 1/8 inch from the turned edge. Bedspreads furnished with selvage sides need not be side hemmed.

3.5 Design. Unless otherwise specified in the contract (see 6.2), selected commercial designs shall be furnished for the bedspreads.

3.6 Sizes. Bedspreads shall be furnished in the sizes specified in Table I (see 6.2).

3.7 Weave and finish. Bedspreads may be treated with a no press finish.

3.7.1 Type I - Crinkle.

3.7.1.1 Weave. Type I bedspreads shall be of any weave or combination of weaves that will produce an alternate crinkle stripe and smooth stripe in the finished bedspreads. The ground ends, adjacent to all crinkle stripes which measure 3/8 inch or more, shall be reinforced as follows: Eight ground ends on each side of the crinkle stripes shall be drawn in so that two ends are weaving as one (eight ends weaving as four). The stripe shall run lengthwise in the bedspreads.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

3.7.1.2 Color and colorfastness. The cloth for type I bedspreads shall be either bleached white or of alternating bleached and yarn-dyed colored stripes. The colored stripes shall be the crinkled warp yarns and shall be of the color as specified (see 6.2). As a minimum level of acceptability, the colored stripes shall have a minimum of good colorfastness to laundering, light, and bleaching when tested in accordance with 4.5.

3.7.1.3 Identification marking. When specified (see 6.2), type I bedspreads shall be marked with the letters "U.S." in block style, 1 ± 1/16 inch high, in a black marking medium, centered 16 to 18 inches from one end of underside. As a minimum level of acceptability, the marking shall show a minimum of good colorfastness to laundering and bleaching when tested in accordance with 4.5.

3.7.2 Type II - Dimity.

3.7.2.1 Weave. Type II bedspreads shall be of any weave or combination of weaves that will produce a series of narrow, medium, and wide corded stripes which run lengthwise in the bedspread.

3.7.2.2 Color. The color for type II bedspreads shall be bleached white.

3.7.2.3 Marking for medical procurement. When specified (see 6.2), type II bedspreads shall be marked with black indelible ink with the stock number 1/4 inch in height and with a caduceus of appropriate size centered between the letters "U" and "S" in accordance with type I of MS-16686. The marking shall be centered between the two sides on the underside of the 3/4 inch hem. As a minimum level of acceptability, the marking shall show a minimum of good colorfastness to laundering and bleaching when tested ion accordance with 4.5.

3.7.3 Types IV, V, and VI - Corded.

3.7.3.1 Weave. Types IV, V, and VI bedspreads shall be of a plain weave construction with a pronounced cord. The cord shall be a single or two or more ply corded yarn not less than 1/16 inch in width. The color shall contain not less than 4 cords per inch.

3.7.3.2 Color and colorfastness. The cloth for types IV, V, and VI bedspreads shall be of the color specified (see 6.2). As a minimum level of acceptability, the bedspreads shall show a minimum of good colorfastness to laundering and light when tested in accordance with 4.5.

3.8 Nonfibrous material content. The starch and protein content, including chloroform-soluble and water-soluble materials shall not exceed 5.0 percent when tested as specified in 4.5.

3.9 Fiber identification. Each bedspread shall be labeled or ticketed for fiber content in accordance with the Rules and Regulations under the Textile Fiber Products Identification Act.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

3.10 Workmanship. The finished bedspreads shall conform to the quality established by this specification. The occurance of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the government to acceptance of defective material.

4.1.2 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

1. First article inspection (see 4.3).
2. Quality conformance inspection (see 4.4).

4.3 First article inspection. When required, the first article submitted in accordance with 3.2, shall be inspected as specified in 4.4.2 for compliance with design, construction, workmanship, appearance and dimensional requirements.

4.4 Quality conformance inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

4.4.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable procurement documents.

4.4.2 Examination of the end item.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

4.4.2.1 Visual examination. The defects found during this examination shall be classified in accordance with 4.4.2.1.1, 4.4.2.1.2, and 4.4.2.1.3. The fabric imperfections listed in 4.4.2.1.1 are defined in Section I of FED-STD-4.

4.4.2.1.1 Examination of the end item. The bedspreads shall be examined on the face side only. The defects found shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the bedspread, in which case only the more serious defect will be counted. The sample unit shall be one bedspread. The lot size shall be expressed in units of one bedspread each. The acceptable quality level (AQL) shall be 2.5 major defects and 6.5 total defects per 100 units. The inspection level shall be level I of MIL-STD-105.

Table II - Classification of Defects

Defect	Classification	
	Major	Minor
1. Any cut, hole, or tear (including selvage)	X	
2. Any smash	X	
3. Floats or skips (other than those which are characteristic of the approved weave or weaves):		
a. Multiple	X	
b. Single, 3 inches or longer		X
4. Broken or missing yarns:		
a. Three or more contiguous regardless of length	X	
b. Two contiguous 9 inches or more missing	X	
c. Single, 3 inches or more missing or two, less than 9 inches		X
5. Hitch-back:		
a. Distorted area 1 square inch or more*	X	
b. Distorted area less than 1 square inch*		X
6. Knots exceeding the "E" limit shown on Sears Fabric Defect Scales**		X
7. Slubs exceeding the "G" or "1" limit shown on Sears Fabric Defect Scales**		
8. Slough-off, jerked in filling - three or more yarn thickness		X
9. Double pick or mispick - two or more yarns in shed or abrupt break in continuity of weave pattern	X	
10. Open place, crack, pick-out or starting mark - any full width more than two yarn thicknesses at widest point		X
11. Bowed or biased filling - two or more inches from horizontal at highest point		X
12. Tight or pulled yarn - clearly noticeable pucker or ridge		X
13. Wrong harness draw		X
14. Crease or wrinkle - embedded, cannot be removed by manual pressure		X
15. Spot, stain or streak:		
a. 1 inch or more in combined length and width dimensions*	X	
b. Less than 1 inch in combined length and width dimensions*		X
16. Any heavy filling bar*		X
17. Any light or fine filling bar	X	
18. Uneven weaving*		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Defect	Classification Major	Minor
19. Color not as specified	X	
20. Color not uniform or is shaded		X
21. Pattern or design - not as specified	X	
22. Loose yarn or untrimmed end protruding from face of bedspread		X
23. Temple cuts or abrasion marks	X	
24. Selvage (when edges are not hemmed):		
a. Rolled, folded, doubled, scalloped*, loose		X
b. Tight (puckered or wavy)*	X	
c. Cut or torn	X	
d. Tenter pin or tenter marks		X
25. Seam and stitch type:		
a. Wrong seam type	X	
b. Wrong stitch type	X	
26. Stitch tension:		
a. Loose, resulting in a loosely secured seam		X
b. Tight, stitches break when normal strain is applied to the seam or stitching		X
NOTE: Puckering is evidence of tight tension. When puckering is evident, seam shall be tested by exerting manual pull.		
27. Stitches per inch less than 5 or more than 10		X
28. Hem:		
a. Varies in width by more than 1/4 inch		X
b. Badly twisted, pleated, or puckered		X
c. Needle chews	X	
d. Stitching less than 1/16 or more than 1/8 inch from turned edge		X
e. Any required hem omitted	X	
29. Any corner not square cut	X	
30. Open seam:		
a. Due to broken thread or broken stitch	X	
b. Due to skipped stitches or run-off		X
31. Raw edge not securely caught in stitching (classify as open seam)		
32. Identification marking (when required):		
a. Missing, incomplete, incorrect, wrong color, illegible, or misplaced		X
b. Characters or design not as specified		X
c. Dimensions not as specified		X
d. Method of application not as specified		X

*Clearly visible at normal inspection distance (approximately 3 feet).
**See 6.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

4.4.2.1.2 Dimensional examination. The sample unit shall be one finished bedspread. The lot size shall be expressed in units of one bedspread. The AQL shall be 2.5 defects per 100 units. The sample size shall be in accordance with inspection level S-3. The bedspreads shall be examined for the defects listed below. The same type of defect shall be counted no more than once in each bedspread.

Length uneven by more than 1 1/2 inches.
Width uneven by more than 1 inch.
Hem width less than specified (see 3.4.2).
Turnunder less than specified (see 3.4.2).

4.4.2.1.3 Seconds. Second quality bedspreads shall be considered for acceptance at a reduction from contract price as stipulated in the Invitation for Bid (see 6.2). Seconds shall not exceed ten (10) percent of the total contract quantity. Seconds shall be presented to the Government separated from regular, first quality lots, and they shall be clearly designated as seconds on the shipping and inspection doucments. There shall be no marking within such a lot that would show it to be second quality. Second quality lots shall be examined as specified for first quality bedspreads in 4.4.2.1.1 and 4.4.2.1.2, except that the first two minor defects in any one bedspread, as classified under 4.4.2.1.1, shall be disregarded. Second quality bedspreads shall meet all physical and chemical tests specified in 4.5.

4.4.3 Examination of preparation for delivery. An examination shall be made to determine compliance with the requirements of Section 5. The sample unit shall be one shipping container fully prepared for delivery. Sampling shall be in accordance with MIL-STD-105. The inspection level shall be S-2 with an AQL of 4.0, expressed in terms of percent defective.

4.5 Testing of the end item. The methods of testing specified in FED-STD-191, where applicable, and as listed in Table IV shall be followed. The physical and chemical values specified in Section 3 apply to the average of the determinations made on the sample unit for test purposes as specified in the applicable test methods. All test reports shall contain the individual values utilized in expressing the final results. The sample unit shall be one full bedspread for determination of weight and shrinkage and two yards full width of the cloth for all other tests. The lot size shall be expressed in units of one bedspread each. The lot shall be unacceptable if one or more sample units fail to meet any test requirements specified. The sample size shall be as specified in Table III.

Table III - Sample size

Lot size	Sample size
800 or less	2
801 thru 22,000	3
22,001 and up	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Table IV - Test methods

Characteristic	Requirement	Test method
Yarn identification	3.3.1.1	1200 1/
	3.3.1.2	1200 and 1500 1/
	3.3.1.3	1200 and 1600 1/
	3.3.1.4	1500 and 1600 1/
	3.3.1.5	1600 1/
Fiber content	3.3.1.2	4.5.1 1/
	3.3.1.3 and 3.3.1.4	4.5.2 and 2100 1/
Size after laundering	Table I	5550 2/
Weight per bedspread	Table I	3/
Yarns per inch	Table I	5050
Breaking strength	Table I	5100 4/
Nonfibrous materials	3.8	2611
Weave	3.7	Visual 5/
Colorfastness to:		
Light	3.7	5660 6/ 7/
Laundering	3.7	5612 6/
Bleaching	3.7	5600 6/

1/ Unless otherwise specified, a supplier's certificate of compliance shall be accepted for this characteristic. The certificate of conformance shall be based on actual test results dated no more than 2 years from the initial date of the contract. These test results shall be available for inspection when requested by the government.
2/ Except the test specimens shall be one full bedspread and a commercial type mangler shall be used for pressing. The average of three measurements taken from the full width and length directions, respectively, shall be reported.
3/ One full bedspread shall be weighed and the results reported to the nearest 0.1 ounce. The weight shall be recorded prior to the laundering test and shall be obtained in a nonconditioned basis.
4/ Front jaws shall be centered on ground threads.
5/ One determination per unit with result reported as "pass" or "fail".
6/ Not applicable to undyed bedspreads.
7/ The calibration of the fadeometer and the definition of AATCC Fading Units shall be according to AATCC Test Method 16-1982. Using the formula below, 16 to 22 AFU's are acceptable as 20 SFH's.

$$\text{AATCC Fading Units} = \frac{(\ E^*)\ (20)}{1.7}$$

Where (E^*) is the color difference in CIELAB* units of color difference.

4.5.1 Fiber content for the cotton/rayon blend fabric. The cotton/rayon blend fabric shall contain the specified fiber percentages when tested in accordance with test method 20A-1971 (chemical method No. 4-59.5 percent sulfuric acid test) listed in the Technical Manual of the American Association of Textile Chemists and Colorists (see 2.2). Two specimens shall be tested from each sample unit.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

4.5.1.1 Calculations. When the weights of both the original sample and residue have been found, the fiber content percentages on a conditioned basis shall be calculated by the following formula and shall be reported to the nearest 0.1 percent:

Percentage of cotton fiber (based on dryweight) $c = \frac{R\ (100)}{DW}$

Percentage of rayon fiber (based on dryweight) $v = 100 - c$

Percentage of corrected (regain) rayon fiber $CW = \frac{c\ (100)}{100 - 0.075}$

Percentage of corrected (regain) fiber $VW = \frac{v\ (100)}{100 - 0.110}$

Percentage of cotton on conditioned basis $C = \frac{CW\ (100)}{CW + VW}$

Percentage of rayon on conditioned basis $V = 100 - CW$

Where: R = Weight of residue (ovendry)
DW = Weight of original specimen (ovendry)
c = Percentage of cotton (ovendry)
v = Percentage of rayon (ovendry)
CW = Corrected (regain) cotton
C = Percentage of cotton on conditioned basis
V = Percentage of rayon on conditioned basis

4.5.2 Fiber content for the cotton/polyester and polyester/rayon blend fabrics. The general procedure of method 2100 shall be followed and the fiber content percentage calculated as follows:

$\frac{\text{Weight of dry residual fiber X 100}}{\text{Weight of dry desized specimen}}$ = percent polyester

100 - percent polyester = percent cotton or rayon

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or Commercial as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Unit packaging for types I and II bedspreads. Each bedspread neatly folded to approximate dimensions of 14 by 23 inches shall be placed in a properly fitted polyethylene bag. The polyethylene film for the bag shall be 0.0012 inch thickness (± 25% tolerance). All seams and closures shall be heat sealed. A hole of not more than 1/4 inch in diameter shall be made at one corner of each bag to allow the excess air within the bag to escape. Alternatively, the polyethylene bag may be the tuck-in overlap type, not requiring heat seal closure.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

5.1.1.2 Unit packaging for type IV, V, and VI bedspreads. Each bedspread, size 1, 2, 3, or 5, shall be neatly folded to an approximate dimension of 11 by 18 inches; each size 4 bedspread shall be folded to an approximate dimension of 9 by 22 inches. Each folded bedspread shall be placed in a properly fitted polyethylene bag of 0.0012 inch thickness (± 25% tolerance). All seams and closures shall be heat sealed. A hole of not more than 1/4 inch in diameter shall be made at one corner of each bag to allow the excess air within the bag to escape. Alternatively, the polyethylene bag may be the tuck-in type, not requiring heat seal closure.

5.1.1.2.1 Intermediate packaging. Four (4) bedspreads packaged as specified in 5.1.1.1 or 5.1.1.2 shall be stacked and completely wrapped with commercial grade kraft paper. The wrap shall be secured with tape or twine to prevent accidental opening.

5.1.2. Special packaging. When specified (see 6.2), six bedspreads of like description shall be folded as specified in 5.1.1.1 and 5.1.1.2, stacked and wrapped as specified in 5.1.1.2.1.

5.1.3 Commercial. Bedspreads shall be packaged to afford adequate protection against physical damage during shipment from the contractor to the first receiving activity. The package and the quantity per package shall be the same as that normally used by the contractor for retail distribution.

5.2 Packing. Packing shall be level A, B, or Commercial (see 6.2).

5.2.1 Level A. Bedspreads, of one type, color, and size only, packaged as specified in 5.1, shall be packed in the quantity as specified in Table V, within a snug-fitting shipping container conforming to class weather resistant, style SFF-L, type CF, variety SW, grade V3c of PPP-B-636. The inside of each shipping container shall be fitted with a taped liner conforming to type CF, class domestic, variety SW, grade 200 of PPP-F-320. Each shipping container shall be closed, water-proofed and reinforced with flat steel strapping or tape banding in accordance with the appendix of the container specification.

5.2.2 Level B. Bedspreads, of one type, color, and size only, packaged as specified in 5.1, shall be packed in the quantity as specified in Table V, within a snug-fitting shipping container conforming to style SFF-L, type CF, class domestic, variety SW, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a taped liner conforming to type CF, class domestic, variety SW, grade 200 of PPP-F-320. Each shipping container shall be closed in accordance with method II of the appendix of the container specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Table V - Number of items in shipping containers

Type	Size	Total number of items in each shipping container
I	3 (72 by 97)	24
II	4 (72 by 106)	24
IV, V, and VI	1 (63 by 103)	24
	2 (76 by 103)	20
	3 (76 by 113)	20
	4 (90 by 113)	16
	5 (56 by 88)	30

5.2.3 Commercial. Bedspreads, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination. The quantity per shipping container shall be the same as that normally used by the contractor for retail distribution. Containers shall comply with the Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

5.3 Marking.

5.3.1 Civil agencies. Marking shall be in accordance with FED-STD-123.

5.3.2 Military agencies. Marking shall be in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. Bedspreads covered by this specification are intended for use by the Department of Defense and General Services Administration. The following types are used by the agencies:

Type I - GSA
Type II - Medical
Types IV, V, and VI - GSA and Defense

6.2 Ordering data. Purchasers should select the preferred options peritted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification
(b) Type and size required (see 1.2, Table I, 3.4, and 3.6)
(c) When first article inspection is required, the item shall be tested and should be a first article sample. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examination, quantity, and testing and approval.
(d) Whether all cotton bedspreads shall be specified (see 3.3.1)
(e) Design required (see 3.5)
(f) Colors required (see 3.7.1.2, 3.7.3.2, and 3.7.4.2)
(g) Whether type I bedspreads shall be bleached white or bleached with colored stripes (3.7.1.2)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

(h) Whether marking for type I or II bedspreads is required (see 3.7.1.3 or 3.7..2.3)
(i) Selection of applicable levels of packaging and packing (see 5.1 and 5.2)
(j) Marking required (see 5.3)
(k) Discount from unit price for seconds (see 4.3.2.1.3)

Note: In the preparation of the contract or order, it must be noted that the contractor has the option of submitting either an all cotton or all polyester bedspreads, or bedspreads composed of vaious material blends as specified in 3.3.1, except that bedspreads for medical shall be all cotton.

6.3 Samples. For access to samples of the end item, address the procuring office issuing the invitation for bids (see 3.1).

6.4 Sears Fabric Defect Scales. Sears Fabric Defect Scales are availavble from Sears, Roebuck, and Company, Department 817 (Attn: BSC 23-29), "Fabric Defect Replica Kit", Sears Tower, Chicago, IL 60684.

6.5 Recycled material. It is encouraged that recycled material when practical as long as it meets the requirements of this specification.

6.6 Subject term (key word).
Bedspread, blend
Cover, bed
Furnishings, household
Linens, bed

MILITARY INTERESTS:

Custodians
Navy - NU
Air Force - 99

Review Activities
Navy - MS
DLA - CT

User Activities
Air Force - 03, 45

CIVIL AGENCY COORDINATING ACTIVITIES:

GSA-FSS
HSS

Preparing Activity:
Navy - NU

Project No. 7210-0258

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12503 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Navy Clothing and Textile Research Facility
21 Strathmore Road, Natick, Mass. 01760

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
DDD-B-151J	Bedspread, Cotton, Polyester, Cotton/Rayon, Cotton/Poly, Poly/Rayo

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.