DDD-L-20c
February 8, 1966
SUPERSEDING
Fed. Spec. DDD-L-20b
November 22, 1961

FEDERAL SPECIFICATION

LABEL; FOR CLOTHING, EQUIPAGE, AND TENTAGE, (GENERAL USE)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the requirements of four types of labels, utilized in fabricated textile, plastic coated, and leather items.

1.2 Classification.

1.2.1 *Types and classes.* The labels shall be of the following types and classes, as specified (see 6.2 and 6.4).

Type:

I—Label, cloth, cotton, permanent coated, printed.
II—Label, cloth, cotton, permanent coated, mildew resistant treated, printed.
III—Marking, heat transfer (decalcomania).
IV—Marking, direct printing, stamping, or stencilling.

Class:

1—Identification label for garments.
2—Size label for garments.
3—Instruction labels for garments.
4—Combination identification and size label for headwear, neckwear, and handwear.
5—Identification label for equipage.
6—Identification label for tentage.
7—Instruction label for tentage.
8—Identification label for paulins and covers.
9—Special markings.
10—Personal identification label.
11—Identification label for aerial delivery items.
12—Identification label for coated items.
13—Instruction label for coated items.

2. APPLICABLE DOCUMENTS

2.1 The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

O-T-236—Tetrachloroethylene (Perchloroethylene); Technical Grade.
P-D-680—Dry Cleaning Solvent.
P-S-579—Soap, Laundry, Chip and Powdered.
UU-T-111—Tape; Paper, Gummed (Sealing and Securing).
CCC-T-191—Textile Test Methods.
PPP-B-566—Boxes, Folding, Paperboard.
PPP-B-636—Box, Fiberboard.
PPP-B-676—Boxes, Setup.

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.
Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31:
Check the source to verify that this is the current version before use.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Standard sample. Unless otherwise specified, the labels and markings shall be equal to the standard sample in respect to legibility, quality of printing, colorfastness of printing, durability of finish, and where applicable, in the ability to accept writing (see 6.2 and 6.5).

3.2 Materials.

3.2.1 *Type I label, cloth, cotton, permanent coated, printed (see* 3.2.2).

3.2.1.1 *Cloth.* The basic cloth for the label shall be cotton cloth, print, bleached white. The finished coated cloth shall have not less than 80 ends per inch in the warp and 72 picks per inch in the filling when tested as specified in 4.2.4.

3.2.1.2 *Coating.* The cloth shall be impregnated or surface coated with a synthetic resin or rubber, suitably compounded and pigmented, to conform to the performance requirements for the finished labels. The printed surface of the classes 3 and 7 instruction labels and class 11 identification label shall be impregnated or surface coated with the finishing compound after printing. The following materials shall not be used in the coating or impregnating formulations:

Thermoplastic polyvinyl butyral resin.
Proteins and their derivatives.
Starch.
Hydrophilic oils and resins.
Rosin.
Sulfur compounds.

The finished labels shall be free from objectionable odor and shall have a relatively smooth surface.

3.2.1.3 *Blocking.* The labels shall not block to an extent greater than represented by scale rating No. 2 when tested as specified in 4.2.4.

3.2.1.4 *Weight of cloth.* The weight of the coated finished cloth used for the labels shall be not less than 3.6 nor more than 4.8 ounces per square yard when tested as specified in 4.2.4. A ten percent plus tolerance over the maximum weight will be allowed for the type I or II, classes 3 and 11 labels, due to the additional coating or impregnating required after printing.

3.2.1.5 *Color.* The color of the finished label shall be bleached white.

3.2.1.6 *Printing medium.* The labels shall be printed with a black marking medium. The initial printing shall be legible and shall not show offsetting, smearing, or bleeding.

3.2.2 *Type II label, cloth, cotton, permanent coated, mildew resistant, printed.* Type II labels shall conform to all the requirements specified for type I labels and, in addition, shall be mildew resistant treated with 1.35 ± 0.25 percent 2,2' methylene bis (4-chlorophenol) by weight of the coated cloth applied either to the base cloth or to the coating or both. The mildew-inhibitor content shall be determined as specified in 4.2.4.

3.2.3 *Type III marking, heat transfer (decalcomania).* Heat transfer (decalcomania)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

markings shall be applied by a dry-heat transfer process. The initial print shall be well defined, clearly legible, and shall not show smearing, bleeding, or offsetting and shall not show objectionable strike-through of the cloth to which applied. Unless otherwise specified, the printing shall be black.

3.2.4 *Type IV marking, direct printing, stamping, or stencilling.* Unless otherwise specified, type IV markings shall be applied to the cloth by a black marking medium. The initial print shall be well defined, clearly legible, and shall not show smearing, bleeding, or offsetting and shall not show objectionable strike-through of the cloth to which applied.

3.3 Printing (see 6.2).

3.3.1 *Print type.* All classes of labels shall be printed with Gothic, sansserif type. Italic or script type shall not be used. All printing shall be in capitals except instruction labels as specified in 3.3.2.3.

3.3.2 Unless otherwise specified (see 6.2), all classes of labels shall be printed with the contents, and in the format and size of print specified below. Unless otherwise specified, the space between lines shall be not less than the following for the size specified (exclusive of space resulting from type shoulder):

6-through 16-point type sizes incl.
—space 2 points.

18-through 36-point type sizes incl.
—space 4 points.

For all type sizes larger than 36 points
—space 6 points.

The end item description to be utilized in the labels shall be as specified in the applicable end item specification or procurement document.

3.3.2.1 *Class 1, identification label for clothing items.* The contents, size of characters of inscription, and the format of class 1 labels shall be as follows (see 6.4):

Item description
—Minimum 10-point (approx. 1/8 inch).
Contract number
—Minimum 8-point (approx. 3/32 inch).
Wool or Fiber Products Act information
—Minimum 8-point (approx. 3/32 inch).

Note: The Wool Products and Fiber Products Act information shall not be included unless specified in the applicable procurement document.

3.3.2.2 *Class 2, size label for clothing items.* The contents, size of characters of the inscription, and the format of class 2 labels shall be as follows when the size is expressed adjectively (see 6.4):

Size
—Minimum 10-point (approx. 1/8 inch).
Stock number
—Minimum 8-point (approx. 3/32 inch).

When the size is expressed numerically, the size shall be printed in characters a minimum of 18 point (approximately 1/4 inch in height) with fractions of comparable size.

3.3.2.3 *Class 3, instruction labels for clothing items.* The contents, size of characters of the inscription and the format of class 3 labels, shall be as follows (see 6.4):

Item description
—Minimum 10-point (approx. 1/8 inch).
Body of instructions
—Minimum 8-point (approx. 3/32 inch).
Warnings or special notations
—Minimum 10-point (approx. 1/8 inch).

The content of the instruction labels shall be as specified in the applicable specification or procurement document. The item description and warning or special notations shall be printed in capitals. The body of the instructions shall be in capitals and lower case characters as shown by the example in the applicable end item specification or procurement document.

3.3.2.4 *Class 4, combination identification and size label for headwear, neckwear, and handwear.* The contents, size of characters of the inscription, and format of class 4 labels shall be as follows (see 6.4):

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

Item description Contact number Stock number Wool or Fiber Products Act information	SIZE

The item description and the size, when indicated adjectively, shall be in characters not less than 8 point (approximately 3/32 inch) in height, and the contract number, stock number and Wool and Fiber Products Act information in characters not less than 6 point (approximately 1/16 inch) in height. When the size is expressed numerically, the height of the numerals shall be a minimum of 18 point (approximately 1/4 inch) in height with fractions of comparable size.

Note: The Wool Products and Fiber Products Act information shall not be included unless specified in the applicable procurement document.

3.3.2.5 *Class* 5, *identification label for equipage.* The contents, size of characters of the inscription, and the format of class 5 labels shall be as follows (see 6.4):

Item description
—Minimum of 18-point (approx. 1/4 inch).
Contract number
—Minimum of 18-point (approx. 1/4 inch).
Stock number
—Minimum of 18-point (approx. 1/4 inch).
Size (when specified)
—Minimum of 18-point (approx. 1/4 inch).

3.3.2.6 *Class* 6, *identification label for tentage.* The contents, size of characters of the inscription and the format of class 6 labels shall be as specified for class 5 labels (see 6.4).

3.3.2.7 *Class* 7, *instruction labels for tentage.* The contents, size of characters, and the format of class 7 labels shall be as specified in the applicable procurement document or end item specification (see 6.2 and 6.4).

3.3.2.8 *Class* 8, *labels for paulins and covers.* The contents and the format of class 8 labels shall be as specified for class 5 labels. The size of characters for the size and class (when applicable), shall be 1-1/2 inches minimum height. The item identification, contract number, and stock number shall be in characters a minimum of 1/2 inch in height (see 6.4).

3.3.2.9 *Class* 9, *special labels and markings.* The contents, size of marking, and format of class 9 labels shall be as specified in the applicable procurement document or end item specification (see 6.2 and 6.4).

3.3.2.10 *Class* 10, *personal identification label.* The contents, size of characters of the inscription, and the format of class 10 labels shall be as follows:

Name
—Minimum 10-point (approx. 1/8-inch).
Service No.
—Minimum 10-point (approx. 1/8-inch).

When specified, the class 10 labels shall be combined with the class 1 label. When the combination is specified, the information required by the class 10 label shall precede the information required of the class 1 label.

3.3.2.11 *Class* 11, *identification label for aerial delivery items.* The contents, size of characters of the inscription, and format of class 11 labels shall be as specified in the applicable procurement document or end item specification.

3.3.2.12 *Class* 12, *identification label for coated items.* The contents, size of characters of the inscription, and the format of class 12 labels shall be as follows:

Item description
—Minimum of 10-point (approx. 1/8-inch).
Contract number
—Minimum of 10-point (approx. 1/8-inch).
Stock number
—Minimum of 10-point (approx. 1/8-inch).
Size (when specified)
—Minimum of 10-point (approx. 1/8-inch).

3.3.2.13 *Class* 13, *instruction labels for coated items.* The contents, size of charac-

Source: https://assist.dla.mil -- Downloaded: 20260410-26T12:31Z
Check the source to verify that this is the current version before use.

ters of the inscription, and the format of class 13 labels shall be as follows (see 6.4):

Item description
—Minimum 10-point (approx. 1/8-inch).
Body of instructions
—Minimum 8-point (approx. 3/32-inch).
Warnings or special notations
—Minimum 10-point (approx. 1/8-inch).

3.4 Label size. Unless otherwise specified, the size of the labels shall be at the option of the supplier governed by the contents and size of characters of the inscription, space between lines, and, as applicable, blank margins on sides of label (see 6.2).

3.4.1 *Types I and II labels.* Types I and II labels shall be provided with a 1/4 ± 1/16 inch blank margin on all four sides for sewing purposes.

3.5 Fastness of printing.

3.5.1 *Classes* 1, 2, 3, *and* 4 *labels.* Colorfastness for classes 1, 2, 3, and 4 labels shall be as specified in the applicable end item specification or procurement document. When colorfastness to laundering or drycleaning is specified, the provisions in 3.5.1.1 or 3.5.1.2 shall apply.

3.5.1.1 *Colorfastness to laundering (see* 3.5.1.3). Classes 1, 2, 3, and 4 labels shall show colorfastness to laundering transference and accelerated laundering equal to or better than the standard sample when tested as specified in 4.2.4. When no standard sample is available, the labels shall show "good" colorfastness to laundering transference; shall be clearly legible, and shall show "fair" colorfastness to accelerated laundering, except the class 3 instruction labels for clothing, which shall show "good" colorfastness to accelerated laundering when tested as specified in 4.2.4.

3.5.1.2 *Fastness to drycleaning (see* 3.5.1.3). Classes 1, 2, 3, and 4 labels shall show colorfastness to accelerated drycleaning equal to or better than the standard sample when tested as specified in 4.2.4. When no standard sample is available, the labels shall be clearly legible and show "fair" colorfastness to accelerated drycleaning except the class 3 instruction labels for clothing, which shall show "good" colorfastness to accelerated drycleaning when tested as specified in 4.2.4.

3.5.1.3 *Types III and IV, classes* 1, 2, 3, *and* 4 *labels.* Either of the fastness requirements specified in 3.5.1.1 or 3.5.1.2 shall apply to types III and IV, classes 1, 2, 3, and 4 labels, with the exception that fastness properties for class 4 labels for leather gloves be specified in the end item specification or procurement document. The test specified shall be performed on labels printed on samples of the same material of which the end item is fabricated during the course of production of the end item. In addition to the test, the labels in the fabricated end item shall show colorfastness equal to or better than the standard sample when subjected to the transference test specified in 4.2.4.

3.5.2 *Classes* 5 *and* 6 *labels.* Classes 5 and 6 labels shall be clearly legible after subjection to the accelerated laundering procedure specified in 4.2.4.

3.5.3 *Class* 7 *labels.* Class 7 labels shall be clearly legible and shall show colorfastness to accelerated laundering equal to, or better than, the standard sample when tested as specified in 4.2.4. When no standard sample is available, the class 7 labels shall be clearly legible and shall show "good" colorfastness after subjection to accelerated laundering when tested as specified in 4.2.4 (see 6.2).

3.5.4 *Class* 8 *labels.* Class 8 labels shall be clearly legible after subjection to accelerated weathering when tested as specified in 4.2.4.

3.5.5 *Class* 9 *labels.* The colorfastness properties of the class 9 labels shall be as specified in the applicable end item specification or procurement document. When re-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

quirements for any of the following characteristics are specified, conformance shall be determined as specified in 4.2.4.

Colorfastness to laundering transference.
Colorfastness to transference.
Colorfastness to accelerated laundering.
Colorfastness to accelerated drycleaning.
Colorfastness to accelerated weathering.
Colorfastness to laundering transference (wool method).

3.5.6 *Class* 10 *labels.* Class 10 labels shall show colorfastness properties as specified for class 1 labels and, in addition, shall be equal to or better than, the standard sample when subjected to the writing test specified in 4.2.4. When a combination of classes 1 and 10 labels is specified (see 3.3.2.10), the fastness of the combined label shall be as specified for class 10 labels.

3.5.7 *Class* 11 *labels.* Class 11 labels shall be clearly legible after subjection to the accelerated laundering procedure specified in 4.2.4.

3.5.8 *Classes* 12 *and* 13 *labels.* Classes 12 and 13 printed labels shall be well defined and clearly legible after being tested for crocking, both wet and dry, when tested as specified in 4.2.4. When specified, the information shall be marked directly on the coated cloth.

3.6 Workmanship. The finished labels shall be clean, free from objectionable odor, and shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels (AQLs).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Inspection. Sampling and inspection shall be performed in accordance with MIL-STD-105 except where otherwise indicated.

4.2.1 *Components and material inspection.* In accordance with 4.1, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase documents.

4.2.2 *Visual examination of the end item.* Defects found during this examination shall be classified as listed in table I. The required number of labels shall be inspected. The sample unit for this examination shall be one label. The AQL shall be 2.5 defects per hundred units. The sample size shall be in accordance with inspection level II of MIL-STD-105. The lot size shall be expressed in units of one label each.

TABLE I. *Classification of visual defects*

Labels	Defect
Labels (all types)	Misshaped or distorted.
	Objectionable odor.
Labels, printing (all types)	Incorrect.
	Omitted.
	Illegible or smeared.
	Wrong color (label or marking medium).
	Misplaced.
	Not specified size.
	Spacing between lines less than specified.
	Print type not as specified.
	Not all capitals (exception 3.3.2.3).
	Format not as specifed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

Labels	Defect
Labels (types I and II only)	Coating not as specified. Coating blistered or missing. Hole, float, broken thread, slub, smash, slough-off, or light or heavy place. Spot or stain clearly noticeable.[1] Margin for sewing purposes less than 3/16 inch or more than 5/16 inch.

[1] At normal inspection distance (approximately 3 feet).

4.2.3 *Examination of preparation for delivery requirements.* An examination shall be made to determine that packaging, packing, and marking requirements of section 5 are complied with. Defects shall be scored in accordance with the following list. The sample unit shall be one shipping container prepared for delivery with the exception that it need not be sealed. Defects of closure listed as follows shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per hundred units.

Examine	Defect
Markings	Omitted, incorrect; illegible, of improper size, location, sequence, or method of application.
Materials	Any component missing or damaged, affecting serviceability.
Workmanship	Inadequate application of components, such as incomplete closure of container flaps, improper taping, loose strapping, etc.
Bundles	Bulging or distortion of containers. Consisting of more than one type or class.
Weight of contents:	
Intermediate container	Exceeds requirement of 10 pounds.
Shipping container	Exceeds requirement of 65 pounds.

4.2.4 *Testing of the end item.* The methods of testing specified in CCC-T-191, wherever applicable and as listed in table II shall be followed. The physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test method. The sample unit shall be as follows for the specified type:

Type	Sample unit
I	300 square inches (or equivalent in cut labels)
II	340 square inches (or equivalent in cut labels)
III and IV	15 labels

The sample size shall be as follows:

Lot size (labels)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified. In the tests for colorfastness of printing, when the label is specified to be colorfast to laundering (see 3.5.1.1 and 3.5.1.3), the laundry transference test (method 5610) shall be performed first. If the labels fail this test, no other tests shall be performed and the lot shall be unacceptable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE II. *Tests*

Characteristic	Requirement paragraph	No. of determinations per sample unit	Test method	Results reported as
Texture (types I and II only):				
Warp	3.2.1.1	—	5050	—
Filling	3.2.1.1	—	5050	—
Blocking (types I and II only)	3.2.1.3	1	5872[1]	Pass or fail
Weight (oz./sq. yd.) types I and II only	3.2.1.4	—	5041	—
Coating (types I and II only)	3.2.1.2	—	[2]	—
Writing test (types I and II only)	3.5.6	1	4.2.4.1	Pass or fail
Inhibitor content (type II only)	3.2.2	—	2011	—
Fastness of printing:	3.5	—	4.2.4	—
Colorfastness to laundering transference	—	1	5610[3]	Pass or fail
Colorfastness to transference	—	1	5640[4 5]	Pass or fail
Colorfastness to accelerated laundering	—	1	4.2.4.2	Pass or fail
Colorfastness to accelerated dry-cleaning	—	1	4.2.4.3	Pass or fail
Colorfastness to accelerated weathering	—	1	5671[6]	Pass or fail
Colorfastness to laundering transference (wool)	—	1	5614[4]	Pass or fail
Colorfastness to crocking	3.5.8	—	5651	—

[1] Method 5872 shall be followed except as follows:
a. The test specimen shall consist of four finished labels plied together, face to face, back to back, and face to back.
b. If the dimensions of the finished labels are under the 4 1/2- by 4 1/2-inch size of the glass plates, they shall be placed approximately in the center of the glass plates.
c. If the dimensions of the finished labels are in excess of the 4 1/2- by 4 1/2-inch size of the glass plates, they shall be trimmed where required to the 4 1/2- by 4 1/2-inch dimensions.

[2] Accepted on the basis of supplier's certificate of compliance thereto.

[3] Method 5610 shall be followed except that in evaluating the results of this test only the staining of the color transfer cloth shall be evaluated.

[4] When a white or yellow printing medium is specified, the transfer cloth utilized in the test shall conform to the colored crock cloth specified in method 5651 of CCC-T-191.

[5] Method 5640 shall be followed except that the evaluation shall be conducted as follows:
a. When a standard sample has been established, the color transfer shall be evaluated as "satisfactory" or "unsatisfactory" by comparing the transfer produced by the standard sample with

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

that produced by the specimen under examination.

b. When no standard sample has been established, the transfer onto the transfer press cloth shall be rated as follows:

Excellent—No transfer to the transfer cloth.
Good —No more than very slight transfer of marking to transfer cloth requiring close examination.
Fair —Appreciable but not objectionable transfer of the marking to the transfer cloth readily discernible upon examination.
Poor —Objectionable transfer of the marking to the transfer cloth.

[6] The time of exposure shall be 100 standard hours.

4.2.4.1 *Writing test.* One test specimen subjected to the laundry transference procedure (method 5610) as specified in 4.2.4 and another in the state as received shall be printed, by pen, with a commercial-grade indelible black ink. The printing on the unlaundered and the laundered test specimens shall be compared with the printing on the standard sample under the same conditions of test and shall show no more skipping, smudging, or blotting than the standard sample.

4.2.4.2 *Colorfastness to laundering.*

4.2.4.2.1 *Test specimen.*

4.2.4.2.1.1 The specimen shall consist of a number of rectangles of labels weighing a total of 3.5 ± 0.3 gram (g.), each unit measuring approximately 2 by 3 inches. (Labels smaller than 2 by 3 inches shall be lap stitched together, with all printing in the same plane. Labels larger than 2 by 3 inches shall be cut to conform to the specified unit size.) Each unit of specimen shall be pinked along each edge. In addition, a thin ribbon of adhesive (see 6.7) shall be applied to the types III and IV labels to each pinked edge.

4.2.4.2.2 *Apparatus.*

4.2.4.2.2.1 *Accelerotor (see* 6.6). The machine shall be capable of varying the speed of the rotor from 0 to 4,000 r.p.m. with a 4½ inch "S" rotor. The liner for the test chamber shall be rubber ribbed, having 2 ribs per inch, with the ribs approximately 1/16 inch in height.

4.2.4.2.2.2 *Soaking chamber.* Any convenient vessel with 100 ml. per g. of specimen capacity.

4.2.4.2.2.3 *Pressing equipment.*

4.2.4.2.2.3.1 *Steam pressing.* Flat bed press at temperature of 135° to 149°C. (275° to 300°F.) hot head or polished metal top for flat fabrics; cloth top press for rough crepes.

4.2.4.2.2.3.2 *Hand pressing.* A hand iron weighing approximately 6 lbs. capable of maintaining temperatures between 135° to 149°C. (275° — 300°F.).

4.2.4.2.3 *Reagents.*

4.2.4.2.3.1 *Soap and alkali solution.* The soap and alkali solution shall contain the following in soft water (not over 50 p.p.m. in hardness calculated as $CaCO_3$):

0.2 percent soap conforming to P-S-579—type I.
0.2 percent metasilicate, technical ($Na_2SiO_3 \cdot 9\ H_2O$).
0.2 percent sodium carbonate, technical ($Na_2CO_3 \cdot 10\ H_2O$).

4.2.4.2.3.2 *Adhesive.* Adhesive, preferably a latex acrylic adhesive, for sealing sample edges of types III and IV labels to prevent fraying of samples during test cycle (6.7).

4.2.4.2.4 *Procedure.*

4.2.4.2.4.1 The specimens shall be crumpled by hand to prevent their adhering to one another and then soaked for a period of approximately 30 ± 2 minutes at 150° ± 5°F. in the soap and alkali solution of 100 ml. per g. of material.

4.2.4.2.4.2 The specimens shall then be placed in the accelerotor with 150 ml. of the soap and alkali solution at 80° ± 2°F. The speed control of the accelerotor shall be set to approximately 50 on the control dial. The motor shall then be started and quickly ad-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

justed to 2000 r.p.m. (average speed shall be used since the tachometer pointer will fluctuate).

4.2.4.2.4.3 The machine shall be run for exactly 6 minutes (including that time to adjust initial speed) without further adjustment of speed.

4.2.4.2.4.4 The machine shall be shut down at the end of the 6 minute period and the liquid allowed to drain out. The specimens shall be removed, squeezed by hand and then rinsed free from soap with soft water at approximately 105°F. The exposed test specimens shall then be hydroextracted or passed between wringer rolls to remove excess moisture and then dried by pressing between press cloths with a hand iron or flat bed press.

4.2.4.2.5 *Evaluation.* Change in color or definition of print shall be considered in rating colorfastness to laundering.

4.2.4.2.5.1 The comparison shall be made with the test specimen and the standard or comparison sample which was tested in a similar manner. The comparison shall be made at normal reading distance under average north-sky daylight or equivalent light in the standard manner.

4.2.4.2.5.2 When a standard of comparison has been established the test specimen shall be compared with the specimen tested from the standard sample and rated as follows:

Satisfactory—Equal or superior to the standard sample.
Unsatisfactory—Inferior to the standard sample.

4.2.4.2.5.3 When no standard sample for comparison has been established, unless otherwise specified, the tested specimen shall be rated as to definition and legibility of print at a normal reading distance. Specimens shall be rated as follows:

Excellent—Practically no change in legibility or definition of print.
Good—Slight change, but readily legible.
Fair —Not readily legible, but without need for deciphering.
Poor —Not readily legible, requiring deciphering.

4.2.4.3 *Fastness to drycleaning.*

4.2.4.3.1 *Test specimen.*

4.2.4.3.1.1 The test specimen shall consist of a number of rectangles of labels weighing a total of 4.5 ± 0.5 g., each unit measuring approximately 2 by 4 inches. (Labels smaller than 2 by 4 inches shall be lap stitched together, each sample faced in the same plane. Labels larger than 2 by 4 inches shall be cut to conform to the specified unit size.)

4.2.4.3.2 *Apparatus.*

4.2.4.3.2.1 *Launderometer or similar machine as described in method* 5610. This machine shall have the required metal adapter to hold stainless steel cylindrical containers 3 by 3½ inches in diameter, each equipped with a sealing device which has solvent resistant rings. One quarter inch diameter stainless steel balls are also required.

4.2.4.3.2.2 *Pressing equipment.*

4.2.4.3.2.2.1 *Steam pressing.* Flat bed press at temperature of 135° to 149°C. (275° to 300°F.); hot head or polished metal top for flat fabrics; cloth top press for rough crepes.

4.2.4.3.2.2.2 *Hand pressing.* A hand iron weighing approximately 6 lbs. capable of maintaining temperatures between 135° to 149°C. (275° to 300°F.).

4.2.4.3.2.3 Covered frame or screen suitable for drying specimen in room.

4.2.4.3.3 *Reagents.*

4.2.4.3.3.1 *Stoddards solvent.* Solvent drycleaning conforming to P-D-680.

4.2.4.3.3.2 *Perchloroethylene.* Tetrachlor-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

ethylene (perchloroethylene) technical grade conforming to O-T-236.

4.2.4.3.3.3 *Drycleaning soap.* Drycleaning soap made by dissolving 56 g. of caustic potash (KOH) in 100 ml. of water. This solution is poured slowly with constant stirring into a mixture of 340 g. of oleic acid, 400 ml. of Stoddard solvent, 100 ml. of tertiary butyl alcohol or an equal quantity of butyl cellosolve.

4.2.4.3.4 *Procedure.*

4.2.4.3.4.1 The specimen shall be placed in the stainless steel container with 150 ml. of perchlorethylene, 1 ml. of drycleaning soap and 100 stainless steel balls. The jar shall be sealed, clamped in the launderometer, and run at 80° ± 2°F. for 10 minutes at which time the solvent is drained.

4.2.4.3.4.2 Replace the solvent with 150 ml. Stoddard solvent and 1 ml. of drycleaning soap and 100 stainless steel balls and run 10 minutes at 80° ± 2°F. following the draining.

4.2.4.3.4.3 Replace the solvent with 150 ml. of perchlorethylene without drycleaning soap and with 100 stainless steel balls run for 10 minutes at 80° ± 2°F. Drain the solvent at the end of the ten minute cycle, remove specimen, blot thoroughly between paper towels or blotters, or extract centrifically to remove excess solvent and then air dry on covered frame or screen.

4.2.4.3.4.4 *Pressing.* When dry, the specimen shall be pressed as follows:

4.2.4.3.4.4.1 *Hand pressing.* Cover with a damp muslin cloth weighing 4 to 4½ ounces per square yard, previously saturated with water and wrung out to retain approximately 75 percent moisture by weight, and press with hand iron until cover cloth is dry.

4.2.4.3.4.4.2 *Steam pressing.* Lower the head of the machine and hold in contact with the cloth. During this period admit steam from the back of the press for a period of 5 to 10 seconds and maintain the head of the press down until specimen is dry.

4.2.4.3.5 *Evaluation.* Change in color, appearance, and definition of print shall be considered in rating the durability.

4.2.4.3.5.1 The comparison shall be made with the test specimen and the standard or comparison sample which was tested in a similar manner. The comparison shall be made at normal reading distance under average north-sky daylight, or equivalent standard artificial light, in the standard manner.

4.2.4.3.5.2 When a standard of comparison has been established the test specimen shall be compared with the specimen tested from the standard sample and rated as follows:

Satisfactory — Equal or superior to the standard sample.
Unsatisfactory—Inferior to the standard sample.

4.2.4.3.5.3 When no standard sample for comparison has been established, unless otherwise specified, the test specimen shall be rated as to change in color, appearance and definition of print at a normal reading distance. Specimen shall be rated as follows:

Excellent—Practically no change in legibility or definition of print.
Good —Readily legible without difficulty.
Fair —Legible without need for deciphering.
Poor —Not readily legible, requiring deciphering.

5. PREPARATION FOR DELIVERY

For civil agency procurement, the definitions and application of levels of packaging and packing shall be in accordance with Fed. Std. No. 102.

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

5.1.1 *Level A (see 6.9).*

5.1.1.1 *Types I and II.*

5.1.1.1.1 *Sizes up to and including nine square inches.* Five hundred labels, of one type and class only, shall be neatly stacked in a bundle and securely crosstied with cotton tape or twine, or crossbanded with elastic bands. A quantity of bundles of labels, of one type and class only, not exceeding a net weight of 10 pounds, shall be placed in an intermediate paperboard box as hereinafter specified.

5.1.1.1.2 *Sizes over nine square inches.* Two hundred labels, of one type and class only, shall be neatly stacked in a bundle and crosstied with cotton tape or twine or crossbanded with elastic bands. A quantity of bundles of labels, of one type and class only, not exceeding a net weight of 10 pounds, shall be placed in an intermediate paperboard box as hereinafter specified.

5.1.1.1.3 *Intermediate box.* The intermediate box shall be a snug-fitting folding paperboard box conforming to variety 1, style III, type B, class a of PPP-B-566; or a setup paperboard box conforming to type I, variety 1, class A, style 3 or 4 of PPP-B-676. Thumb notch requirements shall be optional. The box closure shall be secured with 2-inch minimum width gummed paper tape conforming to class 2 of UU-T-111 applied at the center of the length opening and extending across the bottom and up the sides.

5.1.2 *Level C.* Labels shall be packaged to afford adequate protection against deterioration and damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets these requirements.

5.2 **Packing.** Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 *Level A.*

5.2.1.1 *Types I and II.* Labels of one type and class only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, V3c or V3s of PPP-B-636. Each container shall be closed, waterproofed, and reinforced with flat steel strapping or tape banding in accordance with the appendix of the container specification. The weight of contents of each shipping container shall not exceed 65 pounds.

5.2.2 *Level B.*

5.2.2.1 *Types I and II.* Labels of one type and class only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF or SF, class domestic, variety SW, grade 275 of PPP-B-636. Each container shall be closed in accordance with method II in the appendix of the container specification. The weight of contents of each shipping container shall not exceed 65 pounds.

5.2.2.1.1 When specified, shipping containers shall be fabricated from V3c or V3s fiberboard (see 6.2).

5.2.3 *Level C.* Labels, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with rules or regulations of carriers applicable to the mode of transportation.

5.3 **Marking.**

5.3.1 *Civil agencies.* In addition to any special marking required by the contract or order, intermediate packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 *Military requirements.* In addition to any special marking required by the contract or order, intermediate packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 **Intended use.** The labels covered by

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

this specification are intended for use in items of clothing, tentage, equipage, and related items as specified for the applicable class (see 1.2 and 6.4).

6.2 Ordering data. Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

(*a*) Title, number, and date of this specification.
(*b*) Type and class required (see 1.2).
(*c*) Availability of standard sample (see 3.1 and 6.5).
(*d*) Information and illustrations to be printed on labels (when required) (see 3.3).
(*e*) Printing, color of printing, contents, and fastness, if other than specified (see 3.3.2 and 3.5).
(*f*) Contents, printing, and fastness of classes 7 and 9 labels (see 3.3.2.7, 3.3.2.9, 3.5.3, and 3.5.5).
(*g*) Contents, size of characters, and format of class 7 labels (see 3.3.2.7.)
(*h*) Size required when applicable (see 3.4 and 6.4).
(*i*) Fastness properties of type III or IV, class 4 labels when used for leather gloves (see 3.5.1.3).
(*j*) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(*k*) Whether V-board shipping containers are required for level B shipments (see 5.2.2.1.1).
(*l*) When the combination of classes 1, 2, and 3 is allowed (see 6.3).
(*m*) Types of labels and use (see 6.4).
(*n*) Special markings (see 6.4).

6.3 It is to be noted that the intent of this specification is to allow a suitable combination of classes 1, 2, and 3 labels when it is economically and structurally feasible. However, the end item specification or procurement document must state when a combining of these labels is allowed and the extent of the combination (see 6.2).

6.4 Types of labels and use. (Department of Defense only.) In order to keep the number of sizes of labels to a minimum and in the interest of standardization, it is Department of Defense policy to adhere as closely as possible to the following when procuring labels for specific use and when specifying the type of label to be utilized in an end item specification.

(a) All combat and utility clothing will utilize type I, classes 1, 2, and 3 labels with the exception of cotton shirts as noted in "d" below.
(b) Dress clothing will utilize type I, classes 1, 2, and 3 labels with the exception of cotton shirts as in "d" below. Woven labels conforming to MIL-L-15040 may be utilized for size and instruction labels on dress items, but only where they are permanently visible and the use of another type label would adversely affect the appearance of the item.
(c) All trousers will utilize the type I, classes 1, 2 and 3 labels.
(d) Cotton shirts, gloves, and miscellaneous items, will utilize the types III and IV labels (on shirts the size and stock number will be printed in the collar, and the identification label shall be printed on the left side of the tail).
(e) All woolen items, synthetic, or blends of synthetics and knitted items shall utilize type I label or woven labels as noted above for dress items.
(f) Hats and neckwear will utilize type I, class 4 labels, when possible.
(g) Type IV labels shall be utilized for classes 5 and 8 labels.
(h) Type II labels shall be utilized for classes 6 and 7 labels.
(i) Special markings such as "U.S." on tentage and equipage will normally utilize the type IV label (see 6.2).

6.5 Standard sample. For access to standard sample, address the procuring office issuing the invitation for bid.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

6.6 Accelerotor Model AB-7 has been found to meet the requirements of this test method. This model, complete with accessories, is available from Atlas Electric Devices Company, 4114 North Ravenswood Avenue, Chicago 13, Illinois (see 4.2.4.2.2.1).

6.7 Adhesive Bulcanol AL-100-58, available from Oleo Oil and Chemical Corporation, Trenton Avenue and Williams Street, Philadelphia 34, Pennsylvania, has been found to adequately seal specimen edges. Materials giving the same degree of sealing of specimen without transfer are acceptable (see 4.2.4.2.3.2).

6.8 When level B packaging requirements are specified for civil agency procurements, the requirements in 5.1.1 shall apply.

6.9 The method of packaging referred to in 5.1.1 is similar to method III of MIL-P-116, Preservation, Methods of.

MILITARY CUSTODIANS:
Army—GL
Navy—SA
Air Force—11

Review activities:
Army—MD
Navy—SA, MC
Air Force—11, 67

User activities:
Army—SM
Navy—WP

Preparing activity:
Army—GL

Review and User information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing of DOD Standardization Documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.