INCH POUND

DDD-P-56G
7 June 1994
SUPERSEDING
DDD-P-56F
27 September 1988

FEDERAL SPECIFICATION

PAD, MATTRESS, POLYESTER BATTING, QUILTED, FLAT OR FITTED

This specification is approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers two types of mattress pads, one flat, the other fitted.

1.2 Classification

1.2.1 Type and sizes. Mattress pads shall be of the following types and sizes, as specified (see 6.2).

Type I: Flat: quilted pad with bound edges
Size 1: 36 by 75 inches
Size 2: 52 by 75 inches

Tolerance: Width ± 1.0 inch, length ± 1.0 inch

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Clothing and Textiles Directorate, Attn: DPSC-FQSD, 2800 South 20th Street, Philadelphia, PA 19101-8419, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 7210

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

Type II: Fitted; quilted top pad to cover the mattress top and cloth skirt with elasticized edges to fit and cover the mattress sides (see 6.1)

Size 1:	29 by 76 by 9
Size 2:	36 by 75 by 9
Size 3:	36 by 78 by 9
Size 4:	36 by 84 by 9
Size 5:	38 by 75 by 9
Size 6:	39 by 78 by 9
Size 7:	36 by 80 by 9
Size 8:	38 by 80 by 9
Size 9:	38 by 80 by 9
Size 10	53 by 75 by 9
Size 11:	53 by 80 by 9
Size 12:	60 by 80 by 9
Size 13:	76 by 80 by 9

Tolerance:	Width	-0, +1/2 inch
	Length	-0, +1.0 inch
	Height	-0, +1/2 inch

2. APPLICABLE DOCUMENTS

2.1 Government documents

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Federal Specifications

A-A-50199	-	Thread, Polyester Core: Cotton- or Polyester-Covered
A-A-52095	-	Thread, Polyester Textured
V-T-285	-	Thread, Polyester
CCC-C-430	-	Cloth, Sheeting, Cotton, and Polyester and Cotton
DDD-L-20	-	Label: For Clothing, Equipage, and Tentage, (General Use)
PPP-B-636	-	Boxes, Shipping, Fiberboard

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

Federal Standards

FED-STD-751 - Stitches, Seams, and Stitchings

(Activities outside the Federal Government may obtain copies of Federal specifications, standards and commercial item descriptions as outlined under General Information in the Index of Federal Specifications, Standards, and Commercial Item Descriptions. The Index, which includes cumulative bimonthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, DC 20402.)

(Single copies of this specification and other Federal specifications, standards, and commercial item descriptions required by activities outside the Federal Government for bidding purposes are available without charge from General Services Administration Business Service Centers in Boston, MA; New York, NY; Philadelphia, PA; Washington, DC; Atlanta, GA; Chicago, IL; Kansas City, MO; Fort Worth, TX; Denver, CO; San Francisco, CA; Los Angeles, CA; and Seattle, WA.)

(Federal Government agencies may obtain copies of Federal standardization documents and the Index of Federal Specifications, Standards, and Commercial Item Descriptions from established distribution points in their agencies.)

Military Specifications

MIL-W-5664 - Webbing, Textile, Elastic
MIL-B-41826 - Batting, Synthetic Fibers: Polyester, (Unquilted and Quilted)

Military Standards

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads

(Copies of specifications, standards and handbooks required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

Federal Regulations

Federal Trade Commission

Rules and Regulations Under the Textile Fiber Products Identification Act

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

(Application for copies should be addressed to the Federal Trade Commission, Washington, DC 20580.)

Consumer Product Safety Commission

FF-4-72 - Standard for the Flammability of Mattress and Mattress Pads (16 CFR Part 1632)

(The Code of Federal Regulations (CFR) and the Federal Register (FR) are for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402. When indicated, reprints of certain regulations may be obtained from the Federal agency responsible for the issuance thereof.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

American Society for Testing and Materials (ASTM)

D 3951 - Standard Practice for Commercial Packaging

(Applications for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

3.2 Flammability. All mattress pads shall meet the provisions of the Consumer Product Safety Commission Standard for the Flammability of Mattresses and Mattress Pads when tested as specified in 4.4.5.

3.3 Material. It is encouraged that recycled material shall be used when practical as long as it meets the requirements of this document.

3.3.1 Cloth. The cloth for the covers of the quilted polyester batting, type I bias-cut binding and type II skirt shall be bleached white, polyester and cotton sheeting conforming to type II, class 1 or 2, style D, E, F, or G of CCC-C-430.

3.3.2 Polyester batting. Polyester batting conforming to type VII, class 8 batting of MIL-B-41826 shall be used as the filler material, except that the thickness shall be not greater than 0.52 inch and the requirements for thickness after laundering, compressional recovery after laundering, and launderability shall not apply. The bonded polyester batting shall be furnished without any cloth outer covering. The use of commercial bonded polyester batting is acceptable, provided that the batting possesses a minimum weight of 3.6 ounces per square yard, a maximum thickness of 0.52 inch, and the batting is bonded with a uniformly applied approved durable bonding agent (see 6.6).

Testing for thickness and weight shall be as specified in MIL-B-41826. The maximum concentration of the applied approved bonding agent shall not exceed 18.0 percent of the weight of the finished bonding batting. The bonding agent shall be applied to both sides of the batting filler.

3.3.3 Thread. The thread shall conform to type I or II, size AA (needle), A or AA bobbin or B (for either needle or bobbin), subclass A of V-T-285. As an alternate, the thread shall conform to A-A-50199, cotton-or polyester-covered, ticket sizes 70/2 and 50/2 for all stitch types. An additional thread alternate is permitted for all stitch types except 301. It shall conform to type II, class 1 of A-A-52095, 45 tex and 35 tex. All thread color shall be white.

3.3.4 Elastic. The elastic webbing for the skirt edges shall be one piece, white, conforming to type I, class 1, of MIL-W-5664 and be 3/8 $\pm$ 1/32 inch wide. Alternatively, the elastic shall be one piece, white, flat, heat-resistant, launderable, non-staining, treated rubber which has been compounded of natural rubber, synthetic rubber, or a mixture, and shall conform to the physical requirements shown in Table I when tested as specified in 4.4.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE I. Physical requirements of alternate skirt edge elastic

Characteristics	Requirements
Color	White
Thickness, inches (± .002)	0.030
Width, in. (± 1/16)	3/8
Yield, yds./lb. (± 10%)	60
Modulus	100% elongation at 1.3 ± 0.2 lb. pull
Change in modulus after accelerated aging (over method) (%)	20.0 (max.)

3.4 Labels. Each mattress pad shall have an identification label and a state label attached to one end of the pad.

3.4.1 Identification label. The identification label shall conform to type VI, class 5 of DDD-L-20. As an alternate, the label for the type II pad shall conform to type III, class 5 of DDD-L-20. The legend and size of characters in these labels shall be as specified below.

Legend	Size of character (inches), minimum
Nomenclature	1/8
Contract number	3/32
NSN	3/32
Textile Fiber Products Identification Act Information	3/32
Manufacturer's name	3/32
Size	3/32

3.4.2 State label. The state label shall conform to the legal requirements of the state in which the mattress pads are manufactured.

3.5 Type II design. The Type II design shall be a fitted mattress pad with quilted top and cloth skirt with elasticized edges.

3.6 Construction. The construction shall conform in all respects to the requirements specified in Tables II and III herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

3.6.1 Stitches, seams, and stitching. All stitches, seams, and stitching shall conform to FED-STD-751. The type of seam, stitching, and stitches per inch shall be as specified in Tables II and III. Seam allowances shall be maintained with seams sewn so that no raw edges, run-offs, pleats, puckers, or open seams occur. When two or more methods of seams or stitches are given for the same operation, any one may be used.

3.6.1.1 Type 301 stitching. End of all stitching shall be backstitched or overstitched not less than 1/2 inch except where ends are turned under or caught in other seams or stitching. Ends of a continuous line of stitching shall overlap not less than 1/2 inch. Thread tension shall be maintained so that there will be no loose stitching resulting in loose bobbin or top thread or excessively tight stitching resulting in puckering of the materials sewn. The lock shall be embedded in the materials sewn.

3.6.1.1.1 Repairs of type 301 stitching. Repairs of type 301 stitching shall be as follows:

a. When thread breaks, skipped stitches, run-offs, or bobbin runouts occur during sewing, the stitching shall be repaired by restarting the stitching a minimum of 1 inch back of the end of the stitching. 1/

b. Except for prestitching, thread breaks or two or more consecutive skipped or run-off stitches noted during inspection of the item shall be repaired by overstitching. The stitching shall start a minimum of 1 inch in back of the defective area, continue over the defective area, and continue a minimum of 1 inch beyond the defective area onto the existing stitching (1/2 inch over each end for box, box-x, and W-W stitching). Loose or excessively tight stitching shall be repaired by removing the defective stitching without damaging the materials, and restitching in the required manner. 1/

1/ When making the above repairs, the ends of the stitching are not required to be backstitched.

3.6.1.2 Types 503, 504, 515, and 516 stitching. Thread tension shall be maintained so that there will be no loose stitching. All repairs shall be in accordance with 3.7.1.1.1a and b. Thread tension shall be maintained so that there will be no loose or excessively tight stitching resulting in puckering of the materials sewn. Stitch types 503 and 504, which include the overedge portions of stitch types 515 and 516, shall exhibit a width or bite of 3/8 inch ± 1/32 inch. Seam allowances shall be maintained with seams sewn so that no raw edges, run-offs, twists, pleats, puckers, or open seams occur.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

3.6.1.3 Bartacks. Unless otherwise specified, all bartacks shall be 1/4 to 1/2 inch long and 1/8 ± 1/32 inch wide, and shall contain 14 stitches. Bartacking shall be free from thread breaks and loose stitching.

3.6.1.4 Thread ends. All thread ends shall be trimmed to a length of not more than 1/4 inch.

3.6.2 Replacement of defective components. During the spreading, cutting, and manufacturing process, components having material defects or damages that are classified as defects in 4.4.3 shall be removed from production and replaced with nondefective material.

3.7 Manufacturing operations requirements. The mattress pads shall be manufactured in accordance with all operations specified in Tables II and III. The contractor is not required to follow the exact sequence of operations.

3.8 Abbreviations in Table of Operations. The abbreviations used in Table II are as follows:

Stch - Stitch
In - Inch
Ndl - Needle
Bob - Bobbin
Lpr - Looper
Mchne - Machine
Brtck - Bartack
Comrcl - Commercial
Smlr - Similar
Btn - Button
Btnhl - Buttonhole
Incl - Including
Dbl - Double

TABLE II. Type I manufacturing operations requirements

NO.	OPERATION	STCH TYPE	SEAM/ STCH TYPE	STCH PER IN	THREAD NDL BOB/ LPR
1.	Cutting. a. The cover fabric shall be cut with no piecing seams on either face.				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE II. Type I manufacturing operations requirements (contd.)

NO.	OPERATION	STCH TYPE	SEAM/ STCH TYPE	STCH PER IN	THREAD NDL	THREAD BOB/ LPR
1.	Cutting. (contd.) b. The binding shall be cut on the bias, not less than 1-9/16 inches wide. c. The polyester batting shall be trimmed on all four sides.					
2.	Quilting. a. The polyester batting shall be positioned between two cover fabrics. b. The three layers shall be quilted together with one of the quilt patterns specified: zig-zag, criss-cross, or dumbbell pattern, within the specified dimensions (see below). Size 1: 36 by 75 inches Size 2: 52 by 75 inches (1) Zig-zag. The horizontal distance between the parallel rows of stitches shall be 1 ± 1/16 inch. The length of the row of stitches in each direction shall be 1-7/8 inches ± 1/8 inch. (2) Criss-cross (diamond). The distance between the horizontal points shall be 2 inches ± 1/8 inch and the distance between the vertical points shall be	301	----	7-9	A	A

Source: https://assist.dla.mil - Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE II. Type I manufacturing operations requirements (contd.)

NO.	OPERATION	STCH TYPE	SEAM/ STCH TYPE	STCH PER IN	THREAD NDL	THREAD BOB/ LPR
2.	Quilting. (contd.) 3-1/8 inches ± 1/8 inch; (i.e., the diamond shaped by criss-cross stitching shall measure 2 inches ± 1/8 inch parallel to the filling direction of the cloth). The stitching forming the sides of the diamond shall be 1-7/8 inches ± 1/8 inch.					
3.	Binding.					
	a. The edges of the mattress pad shall be bound with a continuous binding with the raw edges of the binding turned under and stitched 1/8 ± 1/16 inch from the turned edge catching all raw edges in the stitching. The binding shall begin on the short side at a corner and continue around the pad, finishing not less than 6 inches beyond the starting end of the short side of the pad.	301	BSc-1	6-10	A	A
	b. The labels shall be centered and positioned adjacent to each other on one end of the pad, with the top or bottom edges caught in the binding seam.	301	BSc-1	6-10	A	A

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE II. Type I manufacturing operations requirements (contd.)

NO.	OPERATION	STCH TYPE	SEAM/ STCH TYPE	STCH IN	THREAD NDL BOB/ LPR
4.	Cleanliness. a. All spots and stains shall be removed. b. All loose thread ends shall be trimmed.				

TABLE III. Type II manufacturing operations requirements

NO.	OPERATION	STCH TYPE	SEAM/ STCH TYPE	STCH PER IN	THREAD NDL BOB/ LPR
1.	Cutting. a. The cover fabrics for the polyester batting shall be cut with no piecing seams on either face. b. The length of the skirt fabric shall be cut to a length to fit the perimeter of the quilted pad dimensions, including seam allowances. The skirt cloth may be cut as a single continuous piece, or alternately, it may be achieved with two lengths of fabric stitched together to satisfy the total length required. c. The polyester batting shall be cut to fit the specific length and width dimensions of the pad size and shall be trimmed on all four sides.				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE III. Type II manufacturing operations requirements
(contd.)

NO.	OPERATION	STCH TYPE	SEAM/ STCH TYPE	STCH PER IN	THREAD NDL BOB/ LPR
2.	Quilting. a. The polyester batting shall be positioned between two cover fabrics. b. Quilt the three layers together with one of the quilt patterns specified: zig-zag, criss-cross, or a dumbbell pattern within the specified dimensions (see below). Size 1: 29 by 76 by 9 Size 2: 36 by 75 by 9 Size 3: 36 by 78 by 9 Size 4: 36 by 84 by 9 Size 5: 38 by 75 by 9 Size 6: 39 by 78 by 9 Size 7: 36 by 80 by 9 Size 8: 38 by 80 by 9 Size 9: 38 by 80 by 9 Size 10 53 by 75 by 9 Size 11: 53 by 80 by 9 Size 12: 60 by 80 by 9 Size 13: 76 by 80 by 9	301	---	5-9	A A
3.	Skirt. a. If the skirt length is achieved with two pieces, the pieces shall be spliced together by placing the right sides together and stitching a vertical seam.	515 or 516	SSa-2	10-14	AA or 50/2 or 45 tex A or 70/2 or 35 tex

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE III. Type II manufacturing operations requirements
(contd.)

NO.	OPERATION	STCH TYPE	SEAM/ STCH TYPE	STCH PER IN	THREAD NDL BOB/ LPR
3.	Skirt. (contd.) b. The total skirt length shall be closed by a seam created by placing the two skirt ends together and stitching. c. The top of the skirt seam(s) shall be bar-tacked with the bartack positioned so that it lies 3/8 inch ± 1/16 inch below the perpendic-ular seam created when the quilted pad and skirt are stitched together. The bartack shall straddle horizontally across the vertical seam. If the skirt seam(s) are located outside the elasticized portion of the skirt, then a bottom bartack is required 5/8 inch ± 1/16 inch above the bottom skirt edge and shall straddle horizon-tally across the vertical seam.				

Source: https://assist.dla.mil - Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE III. Type II manufacturing operations requirements
(contd.)

NO.	OPERATION	STCH TYPE	SEAM/ STCH TYPE	STCH PER IN	THREAD NDL BOB/ LPR
4.	Attach elastic. Elastic shall be attached to one edge of the mattress skirt and shall extend along the entire length of the skirt. The elastic shall be metered on at a 1-1/2 to 1 ratio (+ or - 10 percent) such that the elastic covers 1-1/2 times its original relaxed length. The elastic ends shall be bartacked.	504 or 503	SSa-1	10-14	AA or 50/2 or 45 tex A or 70/2 or 35 tex
5.	Finished skirt edge. The skirt length edges shall be finished with overedge stitching which can continue on from the the elastic stitched edges.	515 or 516	SSa-2	10-14	AA or 50/2 or 45 tex A or 70/2 or 35 tex
6.	Attach skirt to pad. The upper edge of the skirt shall be placed with the right sides together, along with the quilted pad, and stitched together. The corners may be rounded. Skirt closing seam (see 3.b.) and splice seams, if any (see 3.a.), shall be located at the corners of the mattress pad.	515 or 516	SSa-2	10-14	AA or 50/2 or 45 tex A or 70/2 or 35 tex

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE III. Type II manufacturing operations requirements (contd.)

NO.	OPERATION	STCH TYPE	SEAM/ STCH TYPE	STCH PER IN	THREAD NDL BOB/ LPR
7.	Attach label. The label will be attached to one of the width ends of the pad. A type VI label will be secured by the seam joining the skirt and pad together. A type III label shall be decalcomaniated (heat transferred) to one of the skirt width ends.	515 or 516	SSa-2	10-14	AA or 50/2 or 45 tex A or 70/2 or 35 tex
8.	Cleanliness. a. All spots and stains shall be removed. b. All loose thread ends shall be trimmed.				

3.10 Workmanship. The mattress pads shall conform to the quality of product established by this specification, and the occurrence of defects shall not exceed the applicable acceptable quality levels. No defects that affect appearance of serviceability shall be permitted.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility to ensure that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.1.1 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for assuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point or at all points in the manufacturing process necessary to assure compliance with all dimensional requirements.

4.1.2 Certificates of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

1. First article inspection (see 4.3).
2. Quality conformance inspection (see 4.4).

4.3 First article inspection. The first article, submitted in accordance with 3.1, shall be inspected as specified in 4.4.3 and 4.4.4. The presence of any defect shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable procurement document. A contractor's certificate of compliance shall be submitted for the elastic component specified in 3.4.4. In addition, when commercial polyester batting is used as filler material for the pads, a contractor's certificate of compliance shall be submitted and will be acceptable for the stated requirements listed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

Component (commercial bonded polyester batting)	Requirement paragraph
Weight	3.3.2
Thickness	3.3.2
Approved bonding agent	3.3.2
Concentration of bonding agent	3.3.2

Upon request, the certificate of compliance shall be accompanied by actual test, inspection, or other verifiable data.

4.4.2 In-process inspection. Inspection of sub-assemblies shall be made to ascertain that construction details that cannot be examined in the finished product are in accordance with specified requirements. The Government reserves the right to exclude from consideration for acceptance, any material or service for which in-process inspection has indicated nonconformance.

4.4.3 End item visual examination. The end item shall be examined for the defects listed in Table IV. The lot size shall be expressed in units of mattress pads. The sample unit shall be one mattress pad.

TABLE IV. End item visual defects

Examine	Defect	Classification	
		Major	Minor
Cloth (sheeting)	Any hole, cut, tear, mend, burn, or weak place	X	
	Objectionable or rancid odor	X	
	Cloth not as specified	X	
	Three or more contiguous broken or missing warp or filling threads	X	
	Two contiguous broken or missing warp or filling threads		X
	Loose or weakening slub		X
Cleanness	Any spot or stain, more than 1/4 inch square in area, clearly noticeable at a distance of 6 feet		X
Cover	Contains piecing seams on either face	X	

Source: https://assist.dla.mil Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE IV. End item visual defects (contd.)

Examine	Defect	Classification	
		Major	Minor
Quilting	Any thin place devoid of batting 2 inches square or more in area	X	
	Any thin place devoid of batting, more than 1 inch square in area, but less than 2 inches square in area		X
	Three or more thin places devoid of batting regardless of area	X	
	Any furrow, lump, or bulge resulting from uneven or improper distribution of the batting	X	
	Four or more untrimmed thread ends or loose threads, 1/4 inch or more in length		X
	Surface twisted, pleated, wavy, or puckered	X	
	Any pleat regardless of area, 8 inches or more in length and 1/4 inch or more in depth at widest point, or any pleat not within 5 inches from any edge extending more than 2 inches in length	X	
	Three or more pleats less than 8 inches in length and 1/4 inch or more in depth at widest point regardless of area per pad		X
	Needle chew	X	
	A run back of more than 1 inch of broken or missing stitches in the quilting	X	
	Any area evidencing complete bobbin change		X
	One or more rows of stitching omitted in quilting	X	
	Quilting dimensions not in accordance with Table II		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE IV. End item visual defects (contd.)

Examine	Defect	Classification	
		Major	Minor
Quilting (contd.)	NOTE: Row of stitches is any adjoining 1-7/8 inches ± 1/8 inch segment of either the zig-zag or criss-cross sewn pattern.		
	Stitches per inch:		
	Two or more stitches less than the number specified	X	
	One stitch more or less than the number specified		X
Binding (Type I)	Not cut in bias direction	X	
	Width not as specified (may be determined prior to stitching)	X	
	Torn or chewed	X	
	Not one continuous length per pad		X
	Closing end extends less than 6 inches beyond the starting end		X
Seams and stitching	Binding not seamed with seam type BSc-1		X
	Not stitch type 301 through-out quilting and binding		X
	Stitching margin of binding less than 1/16 inch or more than 3/16 inch		X
	Binding seam does not begin at corner on short side of pad		X
	Binding sewn with less than 6 stitches per inch		X
	Binding sewn with more than 10 stitches per inch		X
	Any open seam or run-off more than 1 inch in length	X	
	Any open seam or run-off 1 inch or less in length		X
	Pad seam not sewn with stitch type 515 or 516	X	
	Bottom skirt edge not sewn with stitch type 503 or 504	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE IV. End item visual defects - (contd.)

Examine	Defect	Classification	
		Major	Minor
Seams and stitching (contd.)	Type II seams and stitching, except quilting, sewn with less than 10 stitches per inch		X
	Type II seams and stitching, except quilting, sewn with more than 14 stitches per inch		X
	NOTE: A seam shall be classified as open when one or more stitches joining seam are broken, or when two or more consecutive skipped or run-off stitches occur.		
	Edge of pad not securely caught in binding		X
	Edge of pad not fully inserted into binding after stitching		X
	Any raw edge of binding more than 1/2 inch in length		X
	Three or more raw edges of binding or skirt per pad up to and including 1/2 inch in length		X
	Raw edge of pad covering, over 2 inches in length		X
	Two or more raw edges of pad covering, up to and including 2 inches in length		X
	Any raw edge of the pad covering regardless of length, not caught in binding stitching	X	
	NOTE: This examination will be made by turning back the edge of the binding at the raw edge locale and determining visually whether the pad covering is caught in the binding stitches.		
	Stitch tension loose, resulting in a loosely secured seam or looped stitches		X
	Stitch tension tight, stitches break when normal strain is applied to the seam or stitching		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE IV. End item visual defects - (contd.)

Examine	Defect	Classification	
		Major	Minor
Seams and stitching (contd.)	NOTE: Puckering is evidence of tight tension.		
Quilting stitching	More than 1-1/2 inches of broken or missing stitches in quilting	X	
Stitching ends	Ends of stitching not secured as specified (except when caught in other seams or stitching)		X
Thread breaks skipped or run-off stitches (unless otherwise classified herein)	Overstitched less than 1 inch in each direction beyond the defective stitching area		X
	NOTE: Thread breaks, two or more consecutive skipped or run-off stitches not overstitched shall be classified as open seams		
Labels	Missing, misplaced, incomplete, incorrect, or illegible	X	
Skirt	Does not fit pad evenly, too small or too big	X	
	Total length made up with more than two lengths	X	
	Height dimension less than 9.0 inches		X
	Skirt seams not bartacked as specified	X	
Elastic	Elastic ends not bartacked	X	
	Elastic ends not stitched with 503 or 504		X
	Elastic not completely overedged		X
	Elastic does not extend along the entire length of the skirt edge	X	

Source: https://assist.dla.mil - Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

4.4.4 End item dimensional examination. Each mattress pad examined for dimensions shall be laid in a flat position without tension. The length and width shall be the average of three measurements taken in each direction. The type II skirt height shall be measured at each corner and at the mid-section of each side length. Any average less or more than the specified length or width (including permitted tolerances) for the size required in 1.2.1 shall be classified as a defect. The lot size shall be expressed in units of mattress pads. The sample unit shall be one finished mattress pad.

4.4.5 Flammability testing. Flammability tests shall be performed in accordance with all provisions of FF-4-72 (16 CFR Part 1632). A contractor's certificate of compliance shall be furnished and will be accepted for the stated requirements. Certification shall include material details used to meet the standard.

4.4.6 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged.

Examine	Defect
Marking (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship	Inadequate, application of components, such as: incomplete closure of container flaps, loose strapping, improper taping, inadequate stapling bulged or distorted container. Bag not as specified. Bag not closed.
Content	Number of items per shipping container is more or less than required. Size shown on one or more items not as specified on shipping container. 1/

1/ For this defect, one item from each shipping container in sample shall be examined.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

4.4.7 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized loads. The sample unit shall be one palletized unit load fully packaged.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirements.
Palletization	Pallet pattern not as specified.
Weight	Exceeds maximum load limits.
Marking	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial, as specified (see 6.2).

5.1.1 Level A. Each pad shall be folded and placed in a plastic bag conforming to type I or II, style 1, 2 or 3 of PPP-B-26, or A-A-50083. Bag material shall have a minimum thickness of 0.001 inch. Bags may have venting holes. Excess air shall be removed from the bag and the bag closed.

5.1.2 Commercial. Each pad shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B or Commercial, as specified (see 6.2).

5.2.1 Level A packing. Pads, preserved as specified in 5.1, shall be packed in a shipping container conforming to style RSC-L, grade V2s of PPP-B-636. Number of pads per box and approximate inside dimensions of the box shall be as cited in Table V. Each box shall be closed, waterproofed and reinforced in accordance with the appendix of PPP-B-636.

5.2.2 Level B packing. Pads, preserved as specified in 5.1, shall be packed in a shipping container conforming to style RSC-L, grade 275 of PPP-B-636. Number of pads and approximate inside dimensions of the box shall be as cited in Table V. Each box shall be closed in accordance with method II as specified in the appendix of PPP-B-636.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE V. Packaging of mattress pads

Item	Number per box	Inside dimensions Length	Width	Depth	Pallet pattern
Type I, size 1	18	25-1/2	18-1/2	27	90
Type I, size 2	12	25-1/2	18-1/2	27	90
Type II, size 1	6	19	14-1/2	12	95
Type II, size 7	6	19-1/2	19-1/2	18	90
Type II, sizes 2, 3, 4, 5 6, 8, 9	6	21	20	12	95

5.2.3 Commercial packing. Pads, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

5.3 Palletization. Pads, preserved as specified in 5.2, shal be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Each prepared load shall be bonded with straps in accordance with bonding means C and D or film bonding means F or G. Pallet pattern shall be as cited in Table V and in accordance with the appendix of MIL-STD-147.

5.4 Marking. Marking of unit packs, shipping containers and unit loads shall be in accordance with MIL-STD-129 or FED-STD-123.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The mattress pads are intended for use on beds by military and nonmilitary agencies for the protection of mattresses. The type II pad is intended in lieu of the combined use of a mattress cover per DDD-C-628 and the type I pad specified in this document.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number and date of this specification.
b. Issue of DODISS to be cited in the solicitation and, if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
c. Types and sizes required (see 1.2.1).
d. When first article inspection is required, (see 3.2, 4.3, and 6.3), the item will be tested and should be a first article sample. The contracting officer should include specific instructions in acquisition documents regarding arrangement for examinations, quantity, and testing and approval.
e. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all procurement instruments regarding arrangements for inspection and approval of the first article.

6.4 Sample. For access to samples, address the procuring office issuing the invitation for bids.

6.5 Civil agency packaging. When level B packaging requirements are specified for civil agency procurements, the requirements in 5.1.1 shall apply.

6.6 Bonding agents. Approval of bonding agents for use in battings covered by this specification is the responsibility of the US Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014. Approval is based on more extensive evaluations, including those of toxicity, which are not set forth in this specification. Because of the time necessary to conduct a full evaluation, only those bonding agents already approved and so listed in the invitation for bids or request for proposal shall be considered acceptable for the related procurement.

6.7 Submittal for approval. Request for approval should be submitted to the US Army Natick Research, Development, and Engineering Center, attention of STSNL-VT. It should be accompanied by approximately 5 square yards (with a minimum of 2 ounces per square yard) polyester batting manufactured with the proposed bonding agent together with applicable test data. Information is to be furnished regarding the commercial designation and chemical description of the bonding agent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

(Approved lists will indicate only the commercial designation.) Chemical identification with products already approved should be made, if applicable, and any available data on skin irritancy or toxicity should be submitted. If applicable, a statement should be included, that as used, the resin is well cured and that no materials with known high toxicity are used prior to cure.

6.8 Subject term (key word) listing

Bedding
Mattress
Pad, mattress

6.9 Changes from previous issue. Marginal notations are not used in this revision with respect to the previous issue due to the extensiveness of the changes. This was done as a convenience only. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the current changes and relationship to the last previous issue.

MILITARY INTERESTS:

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review Activities:

Army - MD
Air Force - 82, 45

User Activity:

Navy - MC

CIVIL AGENCY COORDINATING ACTIVITY:

GSA - FSS

PREPARING ACTIVITY:

DLA - CT

Project No. 7210-0321

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1 The preparing activity must complete blocks 1, 2 3, and 8 In block 1, both the document number and revision letter should be given

2 The submitter of this form must complete blocks 4, 5, 6, and 7

3 The preparing activity must provide a reply within 30 days from receipt of the form

NOTE This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements

I RECOMMEND A CHANGE:	1 DOCUMENT NUMBER DDD-P-56G	2 DOCUMENT DATE (YYMMDD) 940607

3 DOCUMENT TITLE
Pad, Mattress, Polyester Batting, Quilted, Flat or Fitted

4 NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible Attach extra sheets as needed)

5 REASON FOR RECOMMENDATION

6. SUBMITTER

a NAME (Last, First, Middle Initial)	b ORGANIZATION	
c ADDRESS (Include Zip Code)	d TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8 PREPARING ACTIVITY

a NAME Defense Personnel Support Center ATTN: DPSC-FSQD (12-3-D)	b TELEPHONE (Include Area Code) (1) Commercial 215-737-8105 (2) AUTOVON 444-8103
c ADDRESS (Include Zip Code) 2800 South 20th Street P.O. Box 8419 Philadelphia, PA 19101-8419	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT Defense Quality and Standardization Office 5203 Leesburg Pike Suite 1403 Falls Church, VA 22041 3466 Telephone (703) 756-2340 AUTOVON 289-2340

DD Form 1426, OCT 89 Previous editions are obsolete

Source: https://assist.dla.mil - Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.