# DDD-T-86

AUGUST 26, 1936

FEDERAL STANDARD STOCK CATALOG

## Section IV

(Part 5)

## FEDERAL SPECIFICATION

FOR

# TAPE; COTTON, BLEACHED, DYED, OR GREY, GENERAL-USE

This specification was approved by the Director of Procurement, for the use of all departments and establishments of the Government, and shall become effective not later than May 15, 1937. It may be put into effect, however, at any earlier date after promulgation.

### A. APPLICABLE FEDERAL SPECIFICATIONS.

**A–1.** The following Federal specification, of the issue in effect on date of invitation for bids, shall form a part of this specification:

F. S. CCC–T–191. Textiles; test-methods.

**A–2.** Any special requirements of the individual departments of the Government are noted under section H.

### B. TYPE AND GRADE.

**B–1.** Tape, cotton, general-use, shall be of but one type and grade.

### C. MATERIAL AND WORKMANSHIP.

**C–1.** *Material.*—Shall be cotton.

**C–2.** *Workmanship.*—Cotton shall be thoroughly cleaned, evenly spun into yarns, and smoothly woven into tape, which shall be free from knots, broken ends, soft spots, and other imperfections which affect its appearance or may affect its serviceability. Shall be woven uniformly to full width specified, with selvages at both edges. The warp ends shall be evenly distributed throughout the tape.

### D. GENERAL REQUIREMENTS.

**D–1.** *Tolerances.*—The following tolerances from the requirements of the table will be permissible:

**D–1a.** *Width.*—Plus or minus $\frac{1}{32}$″.

**D–1b.** *Picks per inch.*—Plus any, minus two.

**D–1c.** *Weight.*—Minus 3 percent for bleached or dyed tape. The weights in the table are the minimum for grey tape.

**D–2.** *Widths.*—Shall be as specified in invitation for bids.

**D–3.** *Lengths.*—Unless otherwise specified in invitation for bids, tape shall be furnished in standard commercial rolls or spools, each containing approximately 36 yards.

Source: https://assist.dla.mil -
Check the source to verify that t

419405 O - 41

E. DETAIL REQUIREMENTS.

E–1. *Construction and physical properties.*—Shall be in accordance with table I.

TABLE I

| Width | Weight per gross yards | Ends | Picks per inch | Warp strength (minimum) |
|---|---|---|---|---|
| *Inches* | *Ounces* | | | *Pounds* |
| ¼ | 5¾ | 28 | 40 | 25 |
| ⅜ | 7 | 36 | 40 | 30 |
| 7/16 | 8¾ | 44 | 40 | 35 |
| ½ | 10 | 52 | 40 | 42 |
| ⅝ | 11½ | 60 | 40 | 50 |
| 11/16 | 13 | 68 | 40 | 58 |
| ¾ | 14½ | 76 | 40 | 65 |
| 13/16 | 16½ | 84 | 40 | 72 |
| ⅞ | 18 | 92 | 40 | 80 |
| 1 | 19½ | 100 | 40 | 85 |
| 1 1/16 | 21½ | 108 | 40 | 90 |
| 1⅛ | 23 | 116 | 40 | 95 |
| 1¼ | 25½ | 135 | 40 | 115 |

E–2. *Weave.*—The weave shall be a two up and two down single herringbone twill. (Other weaves may be specified in the invitation for bids.)

E–3. *Size of yarns.*—The approximate yarn sizes shall be: Warp—20's, filling—30's.

E–4. *Color.*—When colored tape is specified, tape shall be dyed uniformly to the required shade and show "fair fastness" when subjected to the following tests:

E–4a. *Fastness to weather.*—Samples to be exposed for 10, 20, and and 30 days.

E–4b. *Fastness to laundering.*—Test to be conducted by washing procedure of section XIV, Federal Specification CCC–T–191, Textiles; Test Methods.

E–4c. *Fastness to crocking—Vat dyes.*—When vat dyed tape is specified, it shall be dyed uniformly and show "good fastness" to the above tests and also:

E–4d. *Fastness to bleaching.*—Immerse for 1 hour at room temperature in sodium hypochlorite solution containing 0.7 percent available chlorine, rinse thoroughly, and dry as provided in F. S. CCC–T–191.

F. METHODS OF SAMPLING, INSPECTION, AND TESTS.

F–1. Any requirements applicable to the ind vidual departments are noted under section H.

F–2. *Sampling.*—A single package of eacb color and width out of each lot of not more than 1,000 packages offered for inspection shall be taken as representative of the whole.

Source: https://assist.dla.mil -- Dow
Check the source to verify that this is

**F-3.** *Inspection and tests.*—Shall be conducted in accordance with the methods prescribed in Federal Specification CCC–T–191, referred to in section A. Breaking strength tests shall be conducted by testing the full width of the tape, with the jaws of the machine 3 inches apart at start of test.

**G. PACKAGING, PACKING, AND MARKING.**

**G–1.** Any special requirements of the individual departments are noted under section H.

**G–2.**—*Packaging.*—Unless otherwise specified, commercial packages are acceptable under this specification.

**G–3.** *Packing.*—Unless otherwise specified, the subject commodity shall be delivered in standard commercial containers, so constructed as to insure acceptance by common or other carriers, for safe transportation, at the lowest rate, to the point of delivery.

**G–4.** *Marking.*

**G–4a.** *Issue packages.*—Each roll or spool and package shall be marked with the yardage.

**G–4b.** *Shipping containers.*—Unless otherwise specified, shipping containers shall be marked with the name of the material, the width, the color, and the quantity contained therein, as defined by the contract or order under which the shipment is made, the name of the contractor, and the number of the contract or order.

**H. REQUIREMENTS APPLICABLE TO INDIVIDUAL DEPARTMENTS.**

**H–1.** The following departmental specifications of the issue in effect on date of invitation for bids shall form a part of this specification:

**H–1a.** Army: United States Army Specification No. 100–2, Standard Specification for Marking Shipments. Copies of this specification may be obtained by prospective bidders without cost upon application to the distributing agency indicated in the invitation for bids.

**H–1b.** Navy: Navy Department General Specifications for Inspection of Material, copies of which may be obtained without cost upon application to the Bureau of Supplies and Accounts, Navy Department, Washington D. C.

**I. NOTES.**

**I–1.** Purchasers should exercise all options offered herein and should specify widths and colors required. If lengths other than specified in paragraph E–2 are required, the lengths desired should be indicated.

**I–2.** It is believed that this specification adequately describes the characteristics necessary to secure the desired material, and that normally no samples will be necessary prior to award to determine compliance with this specification. If, for any particular purpose, samples with bids are necessary, they should be specifically asked for in the invitation for bids, and the particular purpose to be served by the bid sample should be definitely stated, the specification to apply in all other respects.

**I–3.** An index of Federal specifications may be purchased as noted in the paragraph next below, price to be obtained from the Superintendent of Documents.

Source: https://assist.dla.mil -- D
Check the source to verify that this

**I–4.** Copies of this specification, and of F. S. CCC–T–191 may be obtained upon application, accompanied by money order, or coupon, or cash to the Superintendent of Documents, Government Printing Office, Washington, D. C. Price 5 cents.

**Notice.**—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Source: https://assist.dla.mil -- Dow
Check the source to verify that this is