September 10, 1962

SUPERSEDING
Int. Fed. Spec. DDD-T-0086c (Army-QMC)
January 15, 1962 and
Fed. Spec. DDD-T-86b
August 24, 1959
(see 6.6)

FEDERAL SPECIFICATION

TAPE, TEXTILE; COTTON, GENERAL PURPOSE (UNBLEACHED, BLEACHED, OR DYED)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers cotton tape for general use.

1.2 Classification.

1.2.1 *Types and classes.* The cotton tape shall be of three types and three classes as specified (see 6.2).

Type I. — Stay bindings, herringbone twill weave.

Type II. — Other bindings, herringbone twill weave.

Type III. — Bindings, plain weave.

Class 1. — Unbleached.

Class 2. — Bleached.

Class 3. — Dyed.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification to the extent specified herein.

Federal Specifications:

UU-P-268 — Paper, Kraft, Untreated, Wrapping.

CCC-T-191 — Textile Test Methods.

PPP-B-636—Box, Fiberboard.

PPP-T-60 — Tape; Pressure-Sensitive Adhesive, Waterproof, for Packaging and Sealing.

Federal Standards:

Fed. Std. No. 4 — Glossary of Fabric Imperfections.

Fed. Std. No. 102 — Preservation, Packaging and Packing Levels.

Fed. Std. No. 123 — Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York,

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, and Auburn, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

Military Specifications:

MIL-L-10547 — Liners, Case, Waterproof.

Military Standards:

MIL-STD-105 — Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129 — Marking for Shipment and storage.

(Copies of Military Specifications and standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply:

Munsell Neutral Standard 8.5

Munsell Neutral Standard 6.5

(Application for copies should be addressed to the Munsell Color Company, 10 East Franklin Street, Baltimore, Maryland.)

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained without charge from the Federal Trade Commission, Washington 25, D.C.)

3. REQUIREMENTS

3.1 The requirements specified in 3.8 and 3.10 apply only to tape purchased directly by the Government. All other requirements apply to tape purchased as a component for an end item by a contractor and to tape purchased directly by the Government.

3.2 Standard sample. When a standard sample is established, the tape shall match the standard sample for shade and shall be equal to, or better than, the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.4).

3.3 Materials.

3.3.1 *Yarn.* The cotton yarn counts for tape shall be as specified in 3.5. A tolerance of plus or minus 5 percent will be allowed for the specified yarn count.

3.4 Color. The tape shall be unbleached, bleached, or dyed as specified (see 6.2). Unless otherwise specified, the color shall be obtained by the use of vat dyes (see table IV). The use of sulfur dyes and dyes containing elementary sulfur or compounds capable of oxidation to sulfuric acid is prohibited. The dyestuffs shall be chosen and applied so that the dyed tape shall show no more free or sulfide sulfur than the standard sample when tested as specified in 4.2.6.

3.4.1 *Dyeing.* The colored tape shall be stock, yarn, or piece dyed.

3.4.2 *Matching.* The color shall match the standard sample under natural (north sky) daylight, or artificial daylight having a color temperature of 7500° Kelvin and shall be a good approximation to the standard sample under incandescent lamplight at 2800° Kelvin.

3.4.3 *Colorfastness.* Colorfastness shall be as specified in the applicable end item specification or as set forth in the contract or order (see 6.2). When a standard sample has been established, the test specimen shall be compared with the standard and shall be equal to or better than the standard for the color-fastness properties specified when tested as specified in 4.2.6. When no standard sample has been established, the colored tape shall be rated in accordance

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

with the adjective ratings shown in the applicable test methods.

3.4.3.1 In the absence of colorfastness requirements elsewhere, colored tape shall show colorfastness to laundering, chlorine bleaching and light after 40 standard fading hours and crocking equal to, or better than, the standard sample (see (6.4) when tested as specified in 4.2.6. When no standard sample has been established the colored tape shall show good fastness to laundering, chlorine bleaching and light after 40 standard fading hours and no more crocking than Munsell value 8.5 when tested as specified in 4.2.6. When black is specified the tape shall show no more crocking than Munsell value 6.5 when tested for wet crocking.

3.4.3.2 When requirements for any of the following characteristics are specified, conformance shall be determined as specified in 4.2.6.

Fastness to:

Laundering
Chlorine bleach
Light (40 standard fading hours)
Crocking
Wet-dry cleaning
Accel. Weather
Perspiration

3.5 Physical requirements. The physical requirements of the tape shall conform to the requirements as specified in table I and as otherwise specified herein.

TABLE I. *Physical requirements*

Type	Width (inches)	Tolerance (inches)	Warp Total yarns (min.)	Yarn counts & ply ± 5.0 percent	Filling yarns per inch (min.)	Yarn counts & ply ± 5.0 percent	Warp strength pounds (min.)
I	1/4	±1/32	28	40/2 or 20/1	38	60/2 or 30/1	25
I	3/8	do	36	do	38	do	30
I	7/16	do	44	do	38	do	35
I	1/2	do	52	do	38	do	42
I	5/8	do	60	do	38	do	50
I	11/16	do	68	do	38	do	58
I	3/4	do	76	do	38	do	65
I	13/16	do	84	do	38	do	72
I	7/8	do	92	do	38	do	80
I	1	do	100	do	38	do	85
I	1-1/16	+1/16 −1/32	108	do	38	do	90
I	1-1/8	do	116	do	38	do	95
I	1-1/4	do	132	do	38	do	115
I	1-1/2	do	164	do	38	do	130
II	3/16	±1/32	32[1]	60/2	58	60/2	22
II	1/2	do	74[2]	do	70	30/1 or 60/2	50
II	5/8	do	94[3]	do	70	do	60
III	3/16	do	13	24/2	28	do	14
III	1/4	do	17	do	28	do	18
III	3/8	do	25	do	28	do	24
III	1/2	do	34	do	28	do	35
III	9/16	do	35	do	28	do	36
III	1	do	65	do	28	do	65

[1] 8 ends left — 16 ends right — 8 ends left.
[2] 20 ends left — 34 ends right — 20 ends left.
[3] 22 ends left — 50 ends right — 22 ends left.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

3.5.1 *Weave.*

3.5.1.1 *Type I.* The weave shall be a two up and two down single or multiple herringbone twill with one or more reversals of the twill across the width of the tape. The tape shall have a woven edge on both sides.

3.5.1.2 *Type II.* The weave shall be a two up and two down herringbone twill as specified in 3.5.1.1. The tape shall have a woven edge on both sides.

3.5.1.3 *Type III.* The weave shall be plain. The tape shall have a woven edge on both sides.

3.6 Non-fibrous material. The total sizing, finishing, and other non-fibrous material shall not exceed 10.0 percent for class 1 tape; and 2.5 percent for class 2 tape; and 4.0 percent for class 3 tape when tested as specified in 4.2.6.

3.7 Shrinkage. When specified (see 6.2), the classes 1, 2, and 3 tape shall be preshrunk and shall not shrink more than 4.0 percent in the direction of the warp, when tested as specified in 4.2.6.2. The preshrinking process used shall not be identified by name or trademark on the tape, tickets, or package.

3.8 Put-up. Unless otherwise specified, the tape shall be wound on standard commercial spools containing the yardage and allowable number of pieces as specified in table II. No piece shall be less than 36 yards in length.

3.9 Fiber identification. Each spool shall be labelled, ticketed, or invoiced for fiber content in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act.

3.10 Identification tickets. Each roll shall have a ticket attached with not finer than 5-ply cotton string doubled to not less than 6 inches long. The ticket shall be made of paperboard not less than 0.020 inch in thick-

TABLE *II.*—*Put-up*

Width	Spool length (yds.)	Number of pieces (max.)		
		Type I	Type II	Type III
3/16	720 ± 2%		6	
1/4	do	4		
3/8	do	4		
7/16	do	4		
1/2	do	5	5	
5/8	do	5	5	
11/16	do	6		
3/4	do	6		
13/16	do	7		
7/8	do	7		
1	do	8		
1-1/16	504 ± 2%	5		
1-1/8	do	5		
1-1/4	do	5		
1-1/2	do	6		
3/16	1000 ± 2%			6
1/4	do			6
3/8	do			6
1/2	do			7
9/16	do			7
1	720 ± 2%			9

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

ness and the color shall be manila or light in intensity to permit easy reading of printed, stamped, or typed markings. Handwritten entries shall be prohibited. The ticket shall have clipped corners at the end where a reinforcing patch (with or without metal eyelet) is firmly affixed for attaching the tying strings. The ticket shall be legibly printed with water-insoluble ink with the following information:

Stock number

Nomenclature

Specification number

Yardage

Contract number and date

Contractor's name

Name of contracting agency

3.11 Workmanship. The tape shall conform to the quality and grade of product established by this specification. Occurrence of defects shall not exceed the applicable acceptance quality levels.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES.

4.1 Contractor's inspection responsibility. The supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government. Inspection records of the examination and tests shall be kept complete and available to the Government as specified in the contract or order. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Inspection for acceptance. Except when otherwise specified by Civil Government agencies, sampling and inspection shall be in accordance with the provisions of MIL-STD-105 except where otherwise indicated.

4.2.1 *Inspection of components.* Quality assurance provisions for components described, shall be in accordance with subsidiary specifications and drawings referenced to the extent applicable except that this specification shall govern in the event of conflict.

4.2.1.1 *Testing of yarn.* The warp and filling yarns shall be tested for yarn number in accordance with method 4021 of CCC-T-191. The sample unit for testing shall be one cone, tube, or spool each of the warp and the filling yarns. The lot size shall be expressed in units of one cone, tube, or spool each. The sample size shall be in accordance with Inspection Level L-1 of MIL-STD-105. The acceptable quality level shall be 6.5 test failures per 100 units. When specified in the procurement document, a contractor's certificate of compliance may be accepted by the Government as evidence of conformance with the yarn number as specified in table I.

4.2.2 *Yard-by-yard examination for visual defects.* The required yardage of each spool shall be inspected on both sides and visual defects classified as listed below. All defects found shall be counted regardless of their proximity one to another, except where two or more defects represent a single local condition of the tape in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The sample unit for this examination shall be 1 linear yard. The sample size shall be in accordance with Inspection Level II of MIL-STD-105. The acceptable quality level shall be 0.4 major defects and 1.5 total (major and minor combined) defects per 100 units (yards). The lot size shall be expressed in units of 1 yard each. An approximate equal number of yards shall be examined from each spool selected.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Classification of defects

Glossary No. (Fed. Std. No. 4)	Defects	Classification	
		Major	Minor
79	Abrasion marks—resulting in a weak place	X	
33	Broken or missing ends—two or more within a linear inch regardless of size of missing portion	X	
	Single, ½ inch or more in length		X
90, 91, 92	Cut, hole, or tear—any	X	
74, 75, 76[2]	Spot, stain, or streak—clearly visible[1]		X
13, 34	Float or skips—	X	
	Multiple, more than ¼ inch in combined warp and filling directions	X	X
	Multiple, ¼ inch or less in combined warp and filling directions		X
	Single, floating over 1 inch or more in length		X
	Single, over more than ½ the width of the tape		X
	Heavy filling bar, clearly visible[1]		X
3, 5, 27	Jerked-in or sloughed-off filling, slub or slug—clearly visible[1]		X
6, 28	Kink or loop, on surface of tape		X
7, 29	Knots—large, improperly pieced knots, clearly visible[1] protruding from surface or with tails extending from surface of tape		X
9	Light or fine filling bare—clearly visible[1]	X	
10	Mispick—Two or more within ½ inch	X	
	Single		X
49, 54	Loopy or loose edge—continuous loops extending over 4-½ inches or more, resulting in loose ends or ends within edge	X	
	Any intermittent or continuous loops extending over 1 inch or more in length, except continuous loops extending over more than 4-½ inches of the edge		X
	Regular or irregular floats due to skips in weave on outermost selvage edge, continually repeating for 4-½ inches or more	X	
36, 46	Mixed or dirty ends		X
48	Rolled or wavy edge which will not flatten under normal pressure		X
78	Smash—any	X	
40	Wrong draw—9 inches or more in length		X

[1]At normal inspection distance—approximately 3 feet.
[2]Except defects of spots, stains, or streaks shall be counted regardless of cause, i.e., not restricted to rust, oil, or grease.

4.2.3 *Overall examination for visual defects.* Each defect listed below shall be counted no more than once in each spool examined. The sample unit for this examination shall be one spool. The sample size and acceptance number shall be as shown in table III.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Defects

Off shade, not within established tolerances
Uneven dyeing
Poor penetration
Shaded throughout
Objectionable odor
Overall uncleannes
Preshrinkage process is identified by name or trademark on tape, tickets or package (when applicable)

TABLE III.

Lot size in spools	Sample size in spools	Maximum number of defects acceptable in sample
5 and under	1	0
6 to 15	2	0
16 to 40	3	0
41 to 110	5	0
111 to 300	7	0
301 and over	10	1

4.2.4 *Length and width examination.*

4.2.4.1 *Examination for length and width of tape on individual spools.* Each defect listed below shall be counted no more than once in each spool examined. The sample unit for this examination shall be one spool. The sample size and acceptance number shall be as shown in table III.

Defects

Width not within specified tolerance

Less than 706 yards per spool for tape 1 inch, or less in width, types I and II.

More than 734 yards per spool for tape 1 inch, or less in width, types I and II.

Less than 494 yards per spool for tape more than 1 inch in width, type I.

More than 514 yards per spool for tape more than 1 inch in width, type I.

Less than 980 yards per spool for tape 3/16 inch thru 9/16 inch in width, type III.

More than 1020 yards per spool for tape 3/16 inch thru 9/16 inch in width, type III.

Less than 706 yards per spool for tape 1 inch in width, type III.

More than 734 yards per spool for tape 1 inch in width, type III.

Any piece less than 36 yards in length.

More than the number of pieces specified in table II.

Actual gross length more than 2 yards less than gross length marked on spool ticket.

4.2.4.2 *Examination for total yardage in sample.* The lot shall be unacceptable if the total of the actual gross lengths of spools in the sample is more than 5 yards less than the total of the gross lengths marked on spool tickets.

4.2.5 *Examination of preparation for delivery requirements.* An examination shall be made to determine that packaging, packing and marking requirements of section 5 of this specification are complied with. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception it need not be sealed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be L-4 and the AQL shall be 4.0 defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible, of improper size, location, sequence, or method of application. Preshrinkage process is identified by name or trademark (when applicable).
Materials	Any component missing or damaged.
Workmanship	Inadequate application of components, such as: Incomplete closure of case liners, container flaps, improper taping, loose strapping inadequate stapling. Bulging or distortion of containers.
Weight	Net weight exceeds requirements.

4.2.6 *Testing of the end item.* The method of testing specified in CCC-T-191, wherever applicable, and as listed in table IV shall be followed. The physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test methods. The acceptable quality level for each characteristic shall be 6.5 test failures per 100 units. The sample size shall be in accordance with Level L-1 of MIL-STD-105. The lot size shall be expressed in units of 1 linear yard. The sample unit for test purposes shall be as follows:

1/4 inch thru 3/8 inch in width — 25 linear yards.

7/16 inch thru 5/8 inch in width — 20 linear yards.

11/16 inch thru 7/8 inch in width — 15 linear yards.

1 inch and wider — 10 linear yards.

4.2.6.1 *Test for presence of sulfur.* Dissolve 100 grams of stannous chloride crystals in 100 ml. of hydrochloric acid (35 percent concentration) and add 50 ml. of distilled water. One to 1.5 grams of the finished tape, cut into small pieces, shall be used for the test. Place the sample in a test tube of suitable size and cover with the stannous-chloride solution. Place a filter paper which has been moistened with one drop of 5.0 percent lead-acetate solution (made by dissolving 5 grams of reagent-grade lead acetate to 100 ml. of distilled water; add a drop of glacial acetric acid to clear up if cloudy), over the mouth of the test tube (punch needle hole in paper.) Heat the test tube slowly over a low flame until the solution is boiling. Solution shall not be boiled for more than 10 to 15 seconds, as prolonged boiling will reduce the sensitivity of the test. A brown to black stain appearing on the paper indicates the presence of sulfur. The stained filter paper shall then be compared with that obtained from the standard. If the stained area is equal to or lighter than the standard in the degree of staining, the sample shall be considered satisfactory. If the degree of staining by the sample is in excess of the standard, the sample shall be considered unsatisfactory.

4.2.6.2 *Shrinkage test for tape.*

4.2.6.2.1 *Preparation.* Five specimens of tape, each 20 inches in length shall be used for determination.

4.2.6.2.2 *Procedure.* Four liters of water at 100°F. and not over 50 p.p.m. hardness shall be entered into a suitable glass or metal container. The water shall contain 0.2 percent (based on the weight of the tape) of an anionic wetting agent. The tape specimens shall be placed into the container and kept submerged beneath the surface of the water for a period of one-half hour without agitation. At the end of this period, the specimen shall be centrifugally extracted for 5 minutes in a 17-inch diameter extractor at a speed of 1575 r.p.m. or in any other extractor for a time that will produce an equivalent extraction, and dried in a circulation air oven at a temperature of 200°F. After drying, the specimens shall be pressed using a conventional heated hand iron, care being taken to prevent stretching of tape.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

TABLE IV. — *Test requirements*

Characteristic	Specification requirement reference	Test method
Weave	3.5.1	Visual[1]
Yarns:		
Ply	3.5	Visual[1]
Total warp yarns	Table I	5050
Filling yarns per inch	Table I	5050
Breaking strength:		
Warp	Table I	5100[2]
Nonfibrous material	3.6	2611[3]
Dye identification	3.4	Std. comm[3]
Presence of sulphur	3.4	4.2.6.1[3]
Colorfastness to:		
Laundering	3.4.3	5610
Chlorine bleach	3.4.3	5600
Light (40 S.F.H)	3.4.3	5660*
Crocking	3.4.3	5651
Wet dry cleaning	3.4.3	5622
Accelerated weather	3.4.3	5670 or 5671[5]
Perspiration	3.4.3	5680[6]
Shrinkage	3.7	4.2.6.2

[1]The determination per sample unit and results reported as "pass or fail".

[2]Breaking strength shall be determined on the full width of the tape and the jaw dimensions shall be greater than the width of the tape.

[3]A contractor's certificate of compliance is acceptable for this characteristic (see 6.2).

[4]In the event of a dispute resulting from test method 5660, or as a result of suspected anomalous behavior of certain dye types or formulations, the contracting officer may authorize the exposure to natural light in accordance with method 5662.

[5]In the event of dispute resulting from the test with method 5670 or 5671, the contracting officer may authorize the exposure to natural weather in a non-industrial area in accordance with method 5672. Test method 5804, referenced in test methods 5670 and 5671 of CCC-T-191 is amended as follows:

a. Delete from title "(National Weathering Unit)".

b. The filters shall not be removed when testing.

c. Water spray nozzles shall be mounted horizontally (the water-spray assembly vertically) in the test chamber inside the specimen rack and so placed that the water shall strike the specimens evenly over their entire length in the form of a fine spray in sufficient volume to cover specimens immediately on impact. The apparatus shall be so operated that the specimens are exposed to successive cycles of 102 minutes of light without spray, and 18 minutes of light with spray.

d. The rack shall rotate about the arc at a uniform speed of one revolution per minute.

e. The pressure of the water entering the spray shall be 12-18 p.s.i., inclusive.

f. The black panel thermometer shall be mounted on a test panel rack and readings taken at a point where maximum heat is developed and where water spray is not striking the panel. The black panel temperature at the exposure plane of the specimen rack shall be 155° plus or minus 10° F, when the filters are in place and 175° plus or minus 10° F, when the filters are removed.

g. Note: Attention is called to manufacturers who own equipment which operates at one cycle in two hours. This equipment may continue to be used. However, the one cycle per minute shall be the standard procedure in the event of dispute.

[6]The transfer cloth shall consist of a warp of polyester fiber or Orlon 81 and a 6-fiber filling of equal bars of wool, spun nylon, spun rayon, spun silk, spun acetate and bleached cotton. Each 6-fiber repeat shall measure approximately 2 inches and shall be separated by a waste-filling stripe.

4.2.6.2.3 *Measurement of shrinkage.* After reaching equilibrium in the standard atmosphere, the length of the specimen shall be measured and the shrinkage computed according to the formula below:

$$\text{Shrinkage, percent} = \frac{\text{Original measurement} - \text{measurement after shrinkage}}{\text{Original measurement}} \times 100$$

Measurements shall be taken to the nearest 0.1 inch and shrinkage shall be reported to the nearest 0.1 of a percent.

5. PREPARATION FOR DELIVERY

(Fed. Std No. 102 shall be referred to for definitions and applications of the various levels of packaging and packing for civil agency procurements.)

5.1 Packaging. Packaging shall be level A, B, or C as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

5.1.1 *Level A or B.* Each spool of tape shall be wrapped with a band of transparent plastic film or with minimum 30-pound kraft paper conforming to grade B of UU-P-268. The wrap shall completely inclose the tape on the spool and shall be secured with gummed or pressure sensitive tape.

5.1.2 *Level C.* Tape shall be packaged in accordance with the industry's practice.

5.2 **Packing.** Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 *Level A.* Tape, of one type, class, and width only, packaged as specified in 5.1 shall be packed in a snug-fitting fiberboard shipping container conforming to class 2, V3c or V3s, style RSC of PPP-B-636. Each shipping container shall be provided with a type I or II, grade B or C, class 2 sealed case liner conforming to MIL-L-10547. Alternatively, in lieu of the waterproof case liner, fiberboard shipping containers shall have all seams, corners, and manufacturer's joints sealed by the application of a 3-inch-minimum width olive-drab-color cloth tape conforming to type III, class 1 of PPP-T-60. Each container shall be closed and reinforced with flat steel strapping or tape banding in accordance with the appendix of the container specification. The net weight of the contents of each shipping container shall not exceed 65 pounds.

5.2.2 *Level B.* Tape, of one type, class, and width only, packaged as specified in 5.1 shall be packed in a snug-fitting fiberboard shipping container, conforming to type I or II, class 1, style RSC of PPP-B-636, except that the minimum bursting strength of the fiberboard shall be 275 p.s.i. All flaps of the fiberboard shipping containers shall be securely sealed with an adhesive commercially used for the specific product being packed by application throughout the entire area of contact between the flaps, or by a combination of metal stitching the bottom flaps and sealing the top flaps with adhesive. The net weight of the contents of each shipping container shall not exceed 65 pounds.

5.2.3 *Level C.* Tape, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Shipping containers shall be in accordance with rules and regulations of carriers applicable to the mode of transportation.

5.3 **Marking.**

5.3.1 *Civil agencies.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 *Military requirements.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 **Intended use.** The tape covered by this specification is utilized as bindings in the fabrication of clothing and other textile items.

6.2 **Ordering data.** Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

(*a*) Title, number and date of this specification.
(*b*) Type and class required (see 1.2.1).
(*c*) Color required (see 3.4).
(*d*) When certification of yarn number is required (see 4.2.1).
(*e*) When class 1, 2 or 3 preshrunk tape is required (see 3.7).
(*f*) Put-up if other than specified (see 3.8).
(*g*) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 A suggested but not mandatory dyestuff formulation for Olive Drab No. 7 is as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Vat Olive T

Vat Olive Green B, Pr. No. 293 or Vat Olive GGL

Vat Khaki 2G, Pr. No. 122

Shaded with either or both of the following:

Vat Brown R.C.I. No. 1151 or Vat Brown BR, Pr. No. 118

Vat Yellow of suitable fastness.

6.4 For access to the standard sample address procuring office issuing the invitation for bids.

6.5 **Transportation description.** The transportation descriptions and minimum weights applicable to this commodity are:

Rail:

Tape, cotton, not otherwise indexed by name in continuous lengths of not less than 24 yards. Carload minimum weight 24,000 pounds, subject to Rule 34, Uniform Freight Classification.

MILITARY INTERESTS:

Army—E M O Q Sig

Navy—S MC Sh

Air Force—ASD

Motor:

Tape, Cotton

Motor volume minimum weight — Any quantity.

6.6 This specification incorporates the requirements of Joint Army-Navy Specification JAN-T-414 for Tape, Cotton, Woven and Federal Specification DDD-T-86 for Tape; Cotton, Bleached, Dyed or Grey, General Use. Comparison of types as pertain to DDD-T-86d is as follows:

DDD-T-86b	*JAN-T-414*	*New*	*DDD-T-86d*
Widths ¼" to 1¼" incl.			Type I
		1½	Type I
	Type I		Type II
	Type I		Type III
		3/16, ¼, 9/16	Type III

Notice. When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.