DDD-T-86e
February 21, 1966
SUPERSEDING
Fed. Spec. DDD-T-86d
September 10, 1962

FEDERAL SPECIFICATION

TAPE, TEXTILE; COTTON, GENERAL PURPOSE (UNBLEACHED, BLEACHED, OR DYED)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers cotton tape for general use.

1.2 Classification.

1.2.1 *Types and classes.* The cotton tape shall be of the following types and classes as specified (see 6.2).

Type I—Stay bindings, herringbone twill weave.

Type II—Other bindings, herringbone twill weave.

Type III—Bindings, plain weave.

Class 1—Unbleached.

Class 2—Bleached.

Class 3—Dyed.

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specification:

CCC-T-191—Textile Test Methods.

Federal Standards:

Fed. Std. No. 4—Glossary of Fabric Imperfections.

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-W-43334—Webbing and Tape, Textile, Packaging and Packing of.

Military Standard:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Rules and Regulations Under the Textile Fiber Products Identification Act.

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D. C., 20580.)

3. REQUIREMENTS

3.1 The requirements specified in 3.8 and 3.10 apply only to tape purchased directly by the Government. All other requirements apply to tape purchased as a component for an end item by a supplier and to tape purchased directly by the Government.

3.2 **Standard sample.** When a standard sample is established, the tape shall match the standard sample for shade and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.4).

3.3 **Materials.**

3.3.1 *Yarn.* The cotton yarn counts for tape shall be as specified in 3.5. A tolerance of plus or minus 5 percent will be allowed for the specified yarn count.

3.4 **Color.** The tape shall be unbeached, bleached, or dyed as specified (see 6.2). The use of sulfur dyes and dyes containing elementary sulfur or compounds capable of oxidation to sulfuric acid is prohibited. The dyestuffs shall be chosen and applied so that the dyed tape shall show no more free or sulfide sulfur than the standard sample when tested as specified in 4.3. For civil agencies, when no standard sample is available, there shall be a minimum amount of staining, of the test paper, when tested as specified in 4.3.

3.4.1 *Dyeing.* The colored tape shall be stock, yarn, or piece dyed.

3.4.2 *Matching.* The color shall match the standard sample under natural (north sky) daylight, or artificial daylight having a color temperature or 7500° Kelvin and shall be a good approximation to the standard sample under incandescent lamplight at 2800° Kelvin.

3.4.3 *Colorfastness.* Colorfastness shall be as specified in the applicable end item specification or as set forth in the contract or order (see 6.2). When a standard sample has been established, the test specimen shall be compared with the standard and shall be equal to or better than the standard for the colorfastness properties specified when tested as specified in 4.3. When no standard sample has been established, the colored tape shall be rated in accordance with the adjective ratings shown in the applicable test methods.

3.4.3.1 In the absence of colorfastness requirements elsewhere, colored tape shall show colorfastness to laundering, chlorine bleaching, and light after 40 standard fading hours and crocking equal to, or better than, the standard sample (see 6.4) when tested as specified in 4.3. When no standard sample has been established, the colored tape shall show "good" fastness to laundering, chlorine bleaching, and light after 40 standard fading hours and no more crocking than Munsell value 8.5 when tested as specified in 4.3. When black is specified, the tape shall show no more crocking than Munsell value 6.5 when tested for wet crocking.

3.4.3.2 When requirements for any of the following characteristics are specified, conformance shall be determined as specified in 4.3.

Fastness to:

Laundering.
Chlorine bleach.
Light (40 standard fading hours).
Crocking.
Wet drycleaning.
Accelerated weathering.
Perspiration.

3.5 **Physical requirements.** The physical requirements of the tape shall conform to the requirements as specified in table I and as otherwise specified herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

TABLE I. *Physical requirements*

Type	Width (inches)	Tolerance (inch)	Warp total yarns (min.)	Yarn counts & ply ± 5.0 percent	Filling yarns per inch (min.)	Yarn counts & ply ± 5.0 percent	Warp strength pounds (min.)
I	1/4	± 1/32	28	40/2 or 20/1	38	60/2 or 30/1	25
I	3/8	± 1/32	36	40/2 or 20/1	38	60/2 or 30/1	30
I	7/16	± 1/32	44	40/2 or 20/1	38	60/2 or 30/1	35
I	1/2	± 1/32	52	40/2 or 20/1	38	60/2 or 30/1	42
I	5/8	± 1/32	60	40/2 or 20/1	38	60/2 or 30/1	50
I	11/16	± 1/32	68	40/2 or 20/1	38	60/2 or 30/1	58
I	3/4	± 1/32	76	40/2 or 20/1	38	60/2 or 30/1	65
I	13/16	± 1/32	84	40/2 or 20/1	38	60/2 or 30/1	72
I	7/8	± 1/32	92	40/2 or 20/1	38	60/2 or 30/1	80
I	1	± 1/32	100	40/2 or 20/1	38	60/2 or 30/1	85
I	1-1/16	+ 1/16 − 1/32	108	40/2 or 20/1	38	60/2 or 30/1	90
I	1-1/8	+ 1/16 − 1/32	116	40/2 or 20/1	38	60/2 or 30/1	95
I	1-1/4	+ 1/16 − 1/32	132	40/2 or 20/1	38	60/2 or 30/1	115
I	1-1/2	+ 1/16 − 1/32	164	40/2 or 20/1	38	60/2 or 30/1	130
II	3/16	± 1/32	32[1]	60/2	58	60/2	22
II	1/2	± 1/32	74[2]	60/2	70	30/1 or 60/2	50
II	5/8	± 1/32	94[3]	60/2	70	30/1 or 60/2	60
III	3/16	± 1/32	13	24/2	28	30/1 or 60/2	14
III	1/4	± 1/32	17	24/2	28	30/1 or 60/2	18
III	3/8	± 1/32	25	24/2	28	30/1 or 60/2	24
III	1/2	± 1/32	34	24/2	28	30/1 or 60/2	35
III	9/16	± 1/32	35	24/2	28	30/1 or 60/2	36
III	1	± 1/32	65	24/2	28	30/1 or 60/2	65

[1] 8 ends left - 16 ends right - 8 ends left.
[2] 20 ends left - 34 ends right - 20 ends left.
[3] 22 ends left - 50 ends right - 22 ends left.

3.5.1 *Weave.*

3.5.1.1 *Type I.* The weave shall be a two up and two down single or multiple herringbone twill with one or more reversals of the twill across the width of the tape. The tape shall have a woven edge on both sides.

3.5.1.2 *Type II.* The weave shall be a two up and two down herringbone twill as specified in 3.5.1.1. The tape shall have a woven edge on both sides.

3.5.1.3 *Type III.* The weave shall be plain. The tape shall have a woven edge on both sides.

3.6 Nonfibrous material. The starch and protein content including chloroform-soluble and water-soluble material shall not exceed 10.0 percent for class 1 tape; 2.5 percent for class 2 tape; and 4.0 percent for class 3 tape, when tested as specified in 4.3.

3.7 Shrinkage. When specified (see 6.2), the classes 1, 2, and 3 tape shall be preshrunk and shall not shrink more than 4.0 percent in the direction of the warp, when tested as specified in 4.3. The preshrinking process used shall not be identified by name or trademark on the tape, ticket, label, or package.

3.8 Put-up. The tape shall be wound on standard commercial spools containing the yardage and allowable number of pieces as specified in table II. No piece shall be less than 36 yards in length. When specified, small requirements for tape may be put up on 36-yard rolls in packages of twenty rolls. The number of splices in any package of twenty 36-yard rolls shall not exceed three. No piece shall be less than 10 yards.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

TABLE II. *Put-up*

Width	Spool length (yds) ± 2 percent	Number of pieces (max.)		
		Type I	Type II	Type III
3/16	720		6	
1/4	720	4		
3/8	720	4		
7/16	720	4		
1/2	720	5	5	
5/8	720	5	5	
11/16	720	6		
3/4	720	6		
13/16	720	7		
7/8	720	7		
1	720	8		
1-1/16	504	5		
1-1/8	504	5		
1-1/4	504	5		
1-1/2	504	6		
3/16	1000			6
1/4	1000			6
3/8	1000			6
1/2	1000			7
9/16	1000			7
1	720			9

3.9 Fiber identification. Each spool or package shall be labeled, ticketed, or invoiced for fiber content in accordance with the Textile Fiber Products Identification Act.

3.10 Identification label. Each spool or package of tape shall have an identification gummed label attached to the head end of the spool or to the outside end of the package as applicable. The color of the label shall be light in intensity to permit easy reading of printed, stamped or typed markings. The use of handwritten entries is prohibited. The label shall be legibly printed with water insoluble ink with the following information:

Stock number.
Nomenclature.
Yardage.
Contract number and date.
Specification number.
Supplier's name.

3.11 Workmanship. The tape shall conform to the quality and grade of product established by this specification. Occurrence of defects shall not exceed the applicable acceptable quality levels (AQLs).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements, as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Inspection. Except when otherwise specified by civil agencies, sampling and inspection shall be in accordance with the provisions of MIL-STD-105.

4.2.1 *Component and material inspection.* In accordance with 4.1, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase documents. In addition to the quality assurance provisions of the subsidiary specifications, components and material listed in table III shall be tested for the characteristics specified and in accordance with the referenced test methods of CCC-T-191. The lot size shall be expressed in pounds and the sample unit shall be 500 yards of the cotton yarn. The lot shall be unacceptable if one or more units fail to meet any requirement specified. All test reports shall contain the individual values utilized in expressing the final result. The sample size shall be as follows:

Lot size (pounds)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

TABLE III. *Testing of components*

Characteristic	Requirement paragraph	Test method
Cotton yarn:		
Material	3.3.1	[1]
Count	3.5	4020[1]
Single	3.5	Visual[2]
Ply	3.5	Visual[2]

[1] The supplier shall submit a certificate of compliance for the characteristic.
[2] One determination per sample unit and results reported as "pass" or "fail".

4.2.2 *End item examination.* Defects found during the examination shall be classified in accordance with 4.2.2.1, 4.2.2.2, and 4.2.2.3.

4.2.2.1 *Yard-by-yard examination for visual defects.* The required yardage of each spool or roll shall be inspected on both sides and visual defects classified as listed in table IV. All defects found shall be counted regardless of their proximity one to another, except where two or more defects represent a single local condition of the tape in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The sample unit for this examination shall be 1 linear yard. The sample size shall be in accordance with level II of MIL-STD-105. The AQL shall be 0.4 major and 1.5 total (major and minor combined) defects per 100 units (yards). The lot size shall be expressed in units of 1 yard each. An approximate equal number of yards shall be examined from each spool or roll selected.

TABLE IV. *Classification of defects*

Glossary No. (Fed. Std. No. 4, sec. 1)	Defects	Classification	
		Major	Minor
79	Abrasion marks—resulting in a weak place	X	
33	Broken or missing ends—two or more within a linear inch, regardless of size of missing portion	X	
	Single, 1/2 inch or more in length ...		X
90, 91, 92	Cut, hole, or tear—any	X	
74, 75, 76	Spot, stain, or streak—clearly visible[1]		X
13, 34	Float or skips—Multiple, more than 1/4 inch in combined warp and filling directions	X	
	Multiple, 1/4 inch or less in combined warp and filling directions .		X
	Single, floating over 1 inch or more in length ...		X
	Single, over more than 1/2 the width of the tape		X
	Heavy filling bar, clearly visible[1] ...		X
3, 5, 27	Jerked-in or sloughed-off filling, slub or slug—clearly visible[1] ...		X
6, 28	Kink or loop on surface of tape ..		X
7, 29	Knots—large, improperly pieced knots, clearly visible,[1] protruding from surface or with tails extending from surface of tape		X
9	Light or fine filling bar—clearly visible[1]	X	
10	Mispick—any		X
49, 54	Edges frayed, slack, rolled, wavy, or otherwise poorly constructed, 4-1/2 inches or more ...	X	
	Less than 4-1/2 inches, but more than 1/2 inch		X
36, 46	Mixed or dirty ends		X
78	Smash—any	X	
40	Wrong draw—9 inches or more in length		X

[1] Clearly visible at normal inspection distance (approximately 3 feet).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

4.2.2.2 *Overall examination for visual defects.* Each defect listed below shall be counted no more than once in each spool or roll examined. The sample unit for this examination shall be one spool or roll. The sample size and acceptance number shall be as shown in table V.

Defects

Off shade, not within established tolerances.
Uneven dyeing.
Poor dye penetration.
Shaded throughout.
Objectionable odor.
Overall uncleanness.
Not labeled in accordance with Textile Fiber Products Identification Act.

TABLE V. *Sample size*

Lot size in spools or rolls	Sample size in spools or rolls	Maximum number of defects acceptable in sample (see 4.2.2.2 and 4.2.2.3.1)
5 or less	1	0
6 up to and including 15	2	0
16 up to and including 40	3	0
41 up to and including 110 ...	5	0
111 up to and including 300 ...	7	0
301 and over	10	1

4.2.2.3 *Length and width examination.*

4.2.2.3.1 *Examination for length and width of tape on individual spools or rolls.* Each defect listed below shall be counted no more than once in each spool or roll examined. The sample unit for this examination shall be one spool or roll. The sample size and acceptance number shall be as shown in table V.

Defects

Total yardage on spool or roll less than the applicable minimum or more than the applicable maximum length:

Type	Width	Yardage	
		Minimum	Maximum
I and II	1 inch or less	706	734
I	More than 1 inch	494	514
III	3/16 thru 9/16 inch	980	1020
III	1 inch	706	734
I, II, III (36 yd. rolls x 20)	Any	720	—

Width not within specified tolerance.
Any piece less than minimum specified.
More than the number of pieces of splices specified.
Actual gross length more than 2 yards less than gross length marked on spool ticket

4.2.2.3.2 *Examination for total yardage in sample.* The lot shall be unacceptable if the total of the actual gross lengths of spools or rolls in the sample is more than 5 yards less than the total of the gross lengths marked on spool or package tickets.

4.2.3 *Examination of preparation for delivery requirements.* An examination shall be made in accordance with the provisions of MIL-W-43334 to determine that packaging, packing, and marking requirements of section 5 of this specification are complied with.

4.3 Testing of the end item. The method of testing specified in CCC-T-191, wherever applicable, and as listed in table VI shall be followed. The physical and chemical values specified in section 3 apply to the results of the determinations made on a sample unit for test purposes as specified in the applicable test methods. All test reports shall contain the individual values utilized in expressing the final result. The sample size shall be as follows:

Lot size (yards)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

The lot shall be unacceptable if one or more units fail to meet any requirement specified. The lot size shall be expressed in units of 1 linear yard. The sample unit for testing shall be as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

1/4 inch thru 3/8 inch in width—25 linear yards.
7/16 inch thru 5/8 inch in width—20 linear yards.
11/16 inch thru 7/8 inch in width—15 linear yards.
1 inch and wider —10 linear yards.

TABLE VI. *Test methods*

Characteristic	Requirement paragraph	Test method
Weave	3.5.1	Visual[1]
Yarns:		
Total warp yarns	3.5	5050
Filling yarns per inch	3.5	5050
Breaking strength:		
Warp	3.5	5100[2]
Nonfibrous material	3.6	2611
Presence of sulfur	3.4	4.3.1[3]
Colorfastness to:		
Laundering	3.4.3	5610
Chlorine bleach	3.4.3	5600
Light	3.4.3	5660[4]
Crocking	3.4.3	5651
Wet drycleaning	3.4.3	5622
Accelerated weathering	3.4.3	5671[4]
Perspiration	3.4.3	5680
Shrinkage	3.7	4.3.2

[1] One determination per sample unit and results reported as "pass" or "fail".

[2] Breaking strength shall be determined on the full width of the tape and the jaw dimensions shall be greater than the width of the tape.

[3] A supplier's certificate of compliance is acceptable for this characteristic (see 6.2).

[4] Time of exposure shall be 40 standard fading hours.

4.3.1 *Test for presence of sulfur.* Dissolve 100 grams (g.) of stannous chloride crystals in 100 milliliters (ml.) of hydrochloric acid (35 percent concentration) and add 50 ml. of distilled water. One to 1.5 g. of the finished tape, cut into small pieces, shall be used for the test. Place the sample in a test tube of suitable size and cover with the stannous-chloride solution. Place a filter paper which has been moistened with one drop of 5.0 percent lead-acetate solution (made by dissolving 5 g. of reagent-grade lead acetate to 100 ml. of distilled water; add a drop of glacial acetic acid to clear up if cloudy), over the mouth of the test tube (punch needle hole in paper). Heat the test tube slowly over a low flame until the solution is boiling. Solution shall not be boiled for more than 10 to 15 seconds, as prolonged boiling will reduce the sensitivity of the test. A brown to black stain appearing on the paper indicates the presence of sulfur. The stained filter paper shall then be compared with that obtained from the standard. If the stained area is equal to or lighter than the standard in the degree of staining, the sample shall be considered satisfactory. If the degree of staining by the sample is in excess of the standard, the sample shall be considered unsatisfactory. For civil agencies, when no standard sample is available, there shall be a minimum amount of staining on the paper.

4.3.2 *Shrinkage test for tape.*

4.3.2.1 *Preparation.* Five specimens of tape, each 20 inches in length, shall be used for this determination, and bench marks for measurement placed 18 inches apart.

4.3.2.2 *Procedure.* Four liters of water at 100° ± 5°F. not over 50 parts per million (p.p.m.) hardness shall be entered into a suitable glass or metal container. The water shall contain 0.2 percent (based on the weight of the tape) of an anionic wetting agent. The tape specimens shall be placed into the container and kept beneath the surface of the water for a period of one-half hour without agitation. At the end of this period, the specimen shall be centrifugally extracted for 5 minutes in a 17-inch diameter extractor at a speed of 1575 revolutions per minute (r.p.m.) or in any other extractor for a time that will produce an equivalent extraction, and dried in a circulation air oven at a temperature of 200°F. After drying, the specimens shall be pressed using a conventional heated hand iron, care being taken to prevent stretching of tape.

4.3.2.3 *Measurement of shrinkage.* After reaching equilibrium in the standard atmosphere, the length of the specimen shall be measured and the shrinkage computed according to the following formula:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

$$\text{Shrinkage, percent} = \frac{\text{Original measurement} - \text{measurement after shrinkage}}{\text{Original measurement}} \times 100$$

Measurements shall be taken to the nearest 0.1 inch and shrinkage shall be reported to the nearest 0.1 of a percent.

5. PREPARATION FOR DELIVERY

(For civil agency procurement, the levels of packaging and packing protection used are defined in Fed. Std. No. 102.)

5.1 Packaging, packing, and marking of tape shall be in accordance with the applicable requirements of MIL-W-43334 (see 6.2).

5.2 **Marking.**

5.2.1 *Civil agencies.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

6. NOTES

6.1 **Intended use.** The tape covered by this specification is utilized as bindings in the fabrication of clothing and other textile items.

6.2 **Ordering data.** Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

(*a*) Title, number, and date of this specification.
(*b*) Type and class required (see 1.2.1).
(*c*) Color required (see 3.4).
(*d*) Colorfastness requirements (see 3.4.3).
(*e*) When certification of yarn number is required (see 4.2.1).
(*f*) When class 1, 2, or 3 preshrunk tape is required (see 3.7).
(*g*) Put-up, when small rolls are specified (see 3.8).
(*h*) Selection of applicable levels of packaging and packing (see 5.1).

6.3 A suggested but not mandatory dyestuff formulation for Olive Drab No. 7 is as follows:

Vat Olive T.
Vat Olive Green B, Pr. No. 293 or Vat Olive GGL.
Vat Khaki 2G, Pr. No. 122.

Shaded with either or both of the following:

Vat Brown R.C.I. No. 1151 or Vat Brown BR, Pr. No. 118.
Vat Yellow of suitable fastness.

6.4 For access to the standard sample, address procuring office issuing the invitation for bids.

6.5 **Transportation descriptions.** The following represents freight classification description and minimum weights under which the benefit of lowest carload and truckload rates for the commodity covered by this specification will be protected, provided shipments are described accordingly in covering bills of lading.

Rail:

Tape, binding, not otherwise indexed by name, in continuous lengths of not less than 24 yards to a package.
Carload minimum weight 24,000 pounds, subject to Rule 34, Uniform Freight Classification.

Motor:

Tape, binding, not otherwise indexed.
In packaged units of not less than 24 continuous yards per unit.
Truckload minimum weight 24,000 pounds subject to Rule 115, National Motor Freight Classification.

MILITARY CUSTODIANS:

Army—GL
Navy—SA
Air Force—11

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Review activities:

Army—MD, WC
Navy—SA, MC
Air Force—11, 67

User activity:

Navy—SH

Other interests:

DSA—DM

Preparing activity:

Army—GL

Review and user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing of DOD Standardization Documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

"to detach this form, cut along this line"

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity.

SPECIFICATION: Tape, Textile; Cotton, General Purpose (Unbleached, Bleached or Dyed) - DDD-T-86d

ORGANIZATION	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT
		$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

DD FORM 1 OCT 64 1426

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01762

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRE-SS
Natick, Massachusetts 01762

FOLD

"to detach this form, cut along this line"

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.