DDD–W–101

JUNE 28, 1932

SUPERSEDING
F. S. No. 263a
June 15, 1925

FEDERAL STANDARD STOCK CATALOGUE

Section IV

(Part 5)

FEDERAL SPECIFICATION

FOR

WASTE; COTTON, COLORED

This specification was approved for promulgation by the Federal Specification Board on June 28, 1932, for the use of the departments and independent establishments of the Government in the purchase of this commodity and shall become mandatory for all departments and independent establishments of the Government not later than February 15, 1933. It may be put into effect, however, at any earlier date after promulgation.

A. APPLICABLE FEDERAL SPECIFICATIONS.

A–1. The following Federal specification of the issue in effect on date of invitation for bids shall form a part of this specification:

F. S. CCC–T–191, Textiles, Test Methods (Federal Specification No. 345).

A–2. Any special requirements of the individual departments of the Government are noted in section H.

B. TYPES AND GRADES.

B–1. The waste shall be of one grade.

B–2. The grade shall be that known commercially as "firsts."

C. MATERIAL.

C–1. *Material.*—The waste shall be composed of 40 per cent (approximate) of fine, undyed, bleached or unbleached, soft cotton yarns (white waste); 10 per cent of white slasher yarns; 40 per cent (approximate) of dyed or colored fine yarns (colored waste); and 10 per cent colored slasher yarns. Both the white and colored wastes shall be properly mixed and machined into a homogeneous mass. The waste shall be practically free from yarns less than 3 inches long. It shall be free from shredded rags, or clips, and from coarse many-plied or unabsorbent yarns, threads, strings, fly sweepings, and dirt.

D. GENERAL REQUIREMENTS.

D–1. See "Detail requirements."

E. DETAIL REQUIREMENTS.

E–1. The waste shall meet the requirements of Table I.

557493 O - 43

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

TABLE I

Gross weight of bale or package (nominal)	Volume of bale (approximate)	Tare (maximum)
Pounds	*Cubic feet*	*Per cent*
5		6
50	3½	6
100	7	6
550	35	6

A variation of plus or minus 10 per cent from the nominal weight of the individual bales will be permitted.

E–2. *Moisture and tare content.*—If the weight of wrapping, including hoops or ties, exceeds the amount specified in the requirement table, or if the moisture content exceeds 7 per cent, the excess weight shall be deducted at the same price per pound that is paid for the waste; provided further, that if the tare exceeds 10 per cent of the gross weight, or the moisture content exceeds 10 per cent, the waste shall be rejected.

F. METHODS OF SAMPLING, INSPECTION, AND TESTS.

F–1. Any requirements applicable to the individual departments are noted in section H.

F–2. *Sampling.*—Not less than one sample shall be taken at random from each 1,000 units or fraction thereof, except when the shipment is over 10,000 units, in which case a sample shall be taken from each one-tenth of the shipment. In addition to the samples required for the regular tests, immediately after the total weight of the material is obtained, a sample approximately 1 to 1½ pounds shall be pulled out and weighed to the nearest one-eighth ounce. This sample shall be properly marked with identification and weight, wrapped in strong paper, and retained for test in case of dispute in regard to the moisture content.

F–3. *Testing.*—Federal Specification CCC–T–191, idential with General Specifications for Textile Materials FSB No. 345, in effect on date of invitation for bids, wherever practicable, shall be followed.

F–3a. *Moisture and tare content.*—The determination of moisture and tare content shall follow the testing procedure agreed upon by the contracting parties, such as the bone-dry or similar method.

F–3b. *Moisture content (umpire test).*—In the event of a dispute in regard to moisture content, the following procedure shall be used. The sample prepared for this purpose (see F–2) shall be shipped to a conditioning laboratory, where it shall be exposed for at least four hours to an atmosphere of 65 per cent relative humidity at 70° F. and then weighed with equivalent accuracy. When the moisture content exceeds 7 per cent the whole of the shipment may be based on the corrected weight of the sample.

$$\text{Weight of bale conditioned} = \frac{(\text{Weight of bale}) \times (\text{Weight of sample conditioned})}{\text{Weight of sample as pulled out}}$$

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:33Z
Check the source to verify that this is the current version before use.

G. PACKAGING, PACKING, AND MARKING.

G–1. Any special requirements of the individual departments of the Government are noted in section H.

G–2. *Packaging.*—Unless otherwise specified, commercial packages will be acceptable under this specification.

G–3. *Packing.*—The material shall be properly baled in clean burlap and well secured with hoops or ties. The 5-pound packages shall be wrapped in burlap well secured unless otherwise specified.

G–4. *Marking.*—Unless otherwise specified, shipping containers shall be marked with the name of the material, the size, the type, quantity contained therein, the name of the contractor, and the number of the order.

H. REQUIREMENTS APPLICABLE TO INDIVIDUAL DEPARTMENTS.

H–1. The following departmental specifications of the issue in effect on date of invitation for bids shall form a part of this specification:

H–1a. Army: United States Army Specification No. 100–2.

H–1b. Navy: Navy Department General Specification for Inspection of Material, together with Appendix III—Textiles. Copies of this specification and appendix may be obtained without cost upon application to the Bureau of Supplies and Accounts, Navy Department, Washington, D. C.

I. NOTES.

I–1. It is believed that this specification adequately describes the characteristics necessary to secure the desired material and that normally no samples will be necessary prior to award to determine compliance with this specification. If, for any particular purpose, samples with bids are necessary, they should be specifically asked for in the invitation for bids, and the particular purpose to be served by the bid sample should be definitely stated, the specification to apply in all other respects.

I–2. This specification governs all United States Government purchases of this commodity. Users are requested to retain this specification in permanent file until a revision is issued.

I–3. Interested parties are advised that an Alphabetical Index of Federal Specifications may be obtained upon application to the Superintendent of Documents, Government Printing Office, Washington, D. C., price to be obtained from the Superintendent of Documents.

I–4. Copies of this specification and also CCC–T–191 may be obtained from the Superintendent of Documents. Price, 5 cents.

Notice.—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility or any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.