DDL W-80b
September 4, 1964

SUPERSEDING
Int. Fed. Spec. DDD-W-0080a (Army-GL)
May 27, 1963 and
Fed. Spec. DDD-W-80
December 8, 1959

FEDERAL SPECIFICATION

WASHCLOTH, TERRY, COTTON

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE

1.1 Scope. This specification covers the requirements for cotton washcloths.

2. APPLICABLE SPECIFICATIONS, STANDARDS AND OTHER PUBLICATIONS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

L-P-378—Plastic Film (Polyethylene Thin Gage).
V-T-276—Thread, Cotton.
UU-P-268 — Paper, Kraft, Untreated, Wrapping.
UU-T-111 — Tape; Paper, Gummed, (Sealing and Securing).
CCC-T-191—Textile Test Methods.
DDD-L-20—Label; For Clothing, Equipage, and Tentage, (General Use).
PPP-B-636—Box, Fiberboard.
PPP-T-60 — Tape; Pressure Sensitive, Adhesive, Waterproof—For Packaging and Sealing.

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging and Packing Levels.
Fed. Std. No. 123—Marking for Domestic Shipments (Civilian Agencies).
Fed. Std. No. 751—Stitches, Seams, and Stitching.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

FSC 7210

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

TABLE I—*Physical requirements*

Weight	Yarns per inch		Ply			Finished dimensions		Break strength (minimum)	
			Warp						
Per dozen, minimum	Warp[1] (min.)	Filling[1] (min.)	Ground	Pile	Filling	Each	Tolerance	Warp	Filling
Ounce						*Inch*	*Inch*	*Lbs.*	*Lbs.*
16	68	35	2 or 1	2 or 1	1	12 by 12	± ½	40	35

[1] Either of these values may fall below this minimum by not more than three yarns, provided the combined warp and filling yarn total does not fall below 100 yarns per square inch.

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

Rules and Regulations Under the Textile Fiber Products Identification Act.

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D. C. 20407.)

3. REQUIREMENTS

3.1 Material.

3.1.1 *Yarn.* The yarn shall be made of cotton which has been cleaned, carded, drawn and spun into single or 2 ply yarns as specified in table I.

3.2 Physical requirements. The finished washcloths shall conform to the requirements specified in table I when tested as specified in 4.4.

3.2.1 *Weave.* The fabric shall consist of a ground warp, pile warp, and filling yarns woven as a single-loop terry weave except that there shall be a plain woven border 1/4 to 1/2 inch wide either on both sides and both ends or on both ends only. When the border is on both ends only it shall be located not more than 1 inch from the ends.

3.2.2 *Thread.* Thread used for stitching shall be thread, cotton, ticket No. 30, 3-ply, type IA2 of V-T-276.

3.3 Construction.

3.3.1 *Edge finishing.* All raw edges shall be overedged stitched with 10 to 14 stitches per inch of stitch type 504 and stitching type EFd-1 as specified in Fed. Std. No. 751. All ends of stitching shall be overstitched 3/4 to 1 inch. There shall be no loose or untrimmed threads on the finished washcloths.

3.4 Finish. The washcloths shall be desized and bleached white.

3.4.1 *Nonfibrous material content.* The starch and protein content including chloroform-soluble and water-soluble material of the finished cloth shall not exceed 2.0 percent when tested as specified in 4.4.

3.5 Marking for identification. When marking for identification is specified (see 6.2), each washcloth shall have an identification label conforming to the requirements of type I, class 4 of DDD-L-20, except that all references to size shall be deleted. The right side of the label shall be caught in the overedge stitching and the bottom edge of the label shall be 1/2 to 3/4 inch from the lower corner of the washcloth. The end item is intended to be laundered.

3.6 Fiber identification. Each washcloth shall be labeled, ticketed or invoiced for fiber content in accordance with the Textile Fiber Products Identification Act.

3.7 Workmanship. The finished washcloths shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the levels set by the applicable acceptable quality levels.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Inspection. Except when otherwise specified by civil Government agencies, sampling and inspection shall be performed in accordance with MIL-STD-105, except as otherwise specified.

4.2.1 *Inspection of components.* Quality assurance provisions for components described shall be in accordance with subsidiary specifications referenced to the extent applicable except that this specification shall govern in the event of conflict.

4.2.2 *Inspection of the end item.*

4.2.2.1 *Examination.* The defects found during examination shall be classified in accordance with 4.2.2.1.1, 4.2.2.1.2, and 4.2.2.1.3.

4.2.2.1.1 *Visual examination.* The washcloths shall be examined on both sides. The same occurrence of defects shall be tallied on one side only. Defects shall be counted regardless of their proximity to each other except where two or more defects represent a single local condition in the washcloth, in which case only the more serious defect shall be counted. The sample unit shall be one washcloth. The inspection level shall be level I. The acceptable quality level (AQL) shall be 2.5 major defects and 10.0 total defects (major and minor combined) per hundred units.

Defects	Classification	
	Major	Minor
Cut, hole, tear - any	X	
Smash - any	X	
Floats or skips:		
Multiple, ½ inch or more in combined warp and filling directions	X	
Multiple less than ½ inch in combined directions		X
Single - 2 inches or longer[1]		X
Broken or missing yarns, clearly visible:[1]		
Three or more contiguous, 1 inch or more missing	X	
Less than three, 1 inch or more missing		X
Wrong draw or reed marks clearly visible[1]		X
Fine filling bar, light place, clearly visible[1]	X	
Slub, slug or gout:		
⅛ inch or more in thickness and 1 inch or more in length		X
Jerked in filling, slough off:		
Three or more additional yarns in shed	X	
Less than three additional yarns in shed		X
Terry loops:		
Missing or not formed properly, pulled, 1 inch or more in combined directions	X	
Less than 1 inch in combined warp and filling directions clearly visible[1]		X
Spot, stain, streak, clearly visible[1]	X	
Any trash, motes, leaf or seed coat fragments		X
Objectionable odor		X
White washcloth not bleached	X	
Ply of yarn not as specified	X	
Thread not substantially same color as cloth		X
Overstitching missing	X	
Overstitching - less than ¾ inch		X
Wrong stitch type		X
Less than ten stitches per inch		X
More than fourteen stitches per inch		X
Loose stitch tension; resulting in a loosely secured edge		X
Raw edge over ¼ inch in length	X	
Raw edge up to and including ¼ inch in length		X
Any needle chew likely to develop into hole	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Defects	Classification	
	Major	Minor
Ends of thread not trimmed off		X
Skipped, broken or runoff stitching more than ½ inch long	X	
Skipped, broken or runoff stitching ½ inch or less in length		X
Border omitted on either or both ends	X	
Identification label (when specified):		
Missing, incorrect or illegible	X	
Insecurely attached or misplaced		X

[1] Clearly visible at normal inspection distance (approximately 3 feet).

4.2.2.1.2 *Dimensional examination.* The sample size shall be in accordance with inspection level S-3. The sample unit for the examination shall be one washcloth. The acceptable quality level (AQL) shall be 4.0 defects per hundred units.

Overall length and width—
less than 11-1/2 inches
more than 12-1/2 inches
Width of border—
less than 1/4 inch
more than 1/2 inch

4.2.2.1.3 *Examination for weight.* The sample unit shall be one dozen washcloths. Any unit that does not meet the minimum weight requirements specified in table I shall be considered a defect. The inspection level shall be S-1 and the acceptable quality level (AQL) shall be 4.0 defects per hundred units.

4.3 Examination for preparation for delivery requirements. An examination shall be made to determine that packaging, packing and marking requirements of section 5 of this specification are complied with. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be sealed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the acceptable quality level (AQL) shall be 4.0 defects per hundred units.

Examine	Defect
Marking (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence or method of application.
Materials	Any component missing.
	Any component damaged, affecting serviceability.
Workmanship	Wrap not secured as specified, incomplete closure of container flaps, loose strapping, improper taping, inadequate stapling.
	Bulging or distortion of containers. Open and noncontinuous heat sealed seams and closure of polyethylene bag. Omission of vent hole in polyethylene bag.
Content	Number of bundles or bags per container is more or less than specified.
	Number of washcloths per bundle or bag is more or less than specified.[1]

[1] For this defect, 3 bundles or bags shall be examined from each shipping container in the sample.

4.4 Testing of the end item. The methods of testing specified in CCC-T-191 wherever applicable and as listed in table III shall be followed. The physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test method. The sample unit shall be 4 washcloths. The sample size shall be in accordance with table II. The lot size shall be expressed in units of 1 washcloth each. The lot shall be unacceptable if one or more sample units fail to meet a test requirement.

TABLE II—*Sampling for tests*

Lot size	Sample size
800 or less	2
801 to 22,000	3
22,001 and up	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

TABLE II. *Test methods*

Characteristic	Requirement reference	Test method
Yarns, per inch ..	Table I	5050
Breaking strength .	Table I	5100
Weave	3.2.1	Visual[1]
Nonfibrous material	3.4.1	2611

[1]One determination shall be made on each sample unit and the results reported as "pass" or "fail".

5. PREPARATION FOR DELIVERY

(Fed. Std. No. 102 shall be referred to for definitions and application of the various levels of packaging and packing protection for civil agency procurements.)

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.2).

5.1.1 *Level A.* Twelve washcloths shall be evenly stacked, flat or center folded, and completely wrapped in 30-pound minimum basis weight kraft paper conforming to grade B of UU-P-268. Each wrapped bundle shall be cross-tied with cotton tape or twine, or secured with gummed paper tape conforming to class 1 of UU-T-111. Alternatively, the stack of twelve washcloths may be placed in a snug-fitting polyethylene bag. The minimum thickness of the polyethylene film shall be 0.00125-inch conforming to type I, grade A, B, or C, finish 1 or 2 of L-P-378. All seams and closures shall be effected by heat sealing. A 1/4-inch maximum diameter hole shall be made at one corner of each polyethylene bag to allow the excess air to escape.

5.1.2 *Level C.* Washcloths shall be packaged in accordance with the industry's practice.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 *Level A.* Three hundred washcloths, packaged as specified in 5.1 shall be packed in a snug-fitting fiberboard shipping container conforming to class 2, V3c or V3s, style RSC of PPP-B-636. All seams, corners, and manufacturer's joints shall be sealed by the application of 3-inch minimum width olive drab color cloth tape conforming to type III, class 1 of PPP-T-60. Each shipping container shall be closed and reinforced with flat steel strapping or tape banding in accordance with the appendix of the container specification.

5.2.2 *Level B.* Three hundred washcloths, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to type I or II, class 1, style RSC of PPP-B-636. The minimum bursting strength of the fiberboard shall be 275 p.s.i. All flaps of the fiberboard shipping container shall be securely sealed with an adhesive commercially used for the specific product being packed by application throughout the entire area of contact between the flaps, or by a combination of metal stitching the bottom flaps and sealing the top flaps with adhesive.

5.2.3 *Level C.* Washcloths, packaged as specified in 5.1 shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with rules or regulations of carriers applicable to the mode of transportation.

5.3 Marking

5.3.1 *Civil agencies.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 *Military requirements.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

5.3.3 *Polyethylene bagged packages.* Polyethylene bagged packages shall have the required information legibly printed or

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

stamped in black directly on the bag across the center face or on a white paper label inserted within the bag so as to permit ready identification. The bag or label shall indicate the following information:

STOCK NUMBER
NOMENCLATURE
QUANTITY

6. NOTES

6.1 **Intended use.** Washcloths covered by this specification are intended for use by the Federal agencies and the Department of Defense.

6.2 **Ordering data.** Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

(*a*) Title, number, and date of this specification.
(*b*) When marking identification is required (see 3.5).
(*c*) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 **Transportation description.** The transportation description and minimum weight applicable to this commodity is:

Rail:

Cloths, wash, made wholly of cotton.
Carload minimum weight—any quantity.

Motor:

Dry goods, not otherwise indexed.
Truckload minimum weight—any quantity.

MILITARY CUSTODIANS:

Army—GL

Navy—SA

Air Force—MAA

Interested activities:

Review:

Army—MD

Navy—SA

Air Force—MAA

Preparing activity:

Army—GL

Review/user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing of DOD Documents.

Copies of this specification may be purchased for [illegible] each

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.