DDD-W-80C
June 22, 1971
SUPERSEDING
Fed. Spec. DDD-W-80B
September 4, 1964

FEDERAL SPECIFICATION

WASHCLOTH, TERRY, COTTON

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the requirements for two types of cotton washcloths.

1.2 Classification.

1.2.1 Types. The cotton washcloth shall be of the following types as specified (see 6.2):

Type I - 16 ounce per dozen (min).

Type II - 11 ounce per dozen (min).

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

V-T-276	-	Thread, Cotton.
UU-P-268	-	Paper, Kraft, Untreated, Wrapping.
DDD-L-20	-	Label; For Clothing, Equipment, and Tentage, (General Use).
PPP-B-636	-	Box, Fiberboard.
PPP-T-45	-	Tape, Gummed, Paper, Reinforced and Plain, For Sealing and Securing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Federal Standards:

FED-STD-123	-	Marking for Domestic Shipment (Civil Agencies).
FED-STD-191	-	Textile Test Methods.
FED-STD-751	-	Stitches, Seams, and Stitchings.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	-	Marking for Shipment and Storage.
MIL-STD-147	-	Palletized and Containerized Unit Loads 40" x 48" Pallets, Skids, Runners, or Pallet-Type Base.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply:

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D. C. 20407.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification

(Application for copies should be addressed to the National Motor Freight Traffic Association, Inc., Agent, 1616 P Street, N.W., Washington, D. C. 20036.)

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Tariff Publishing Officer, Rm. 202, Union Station, 516 W. Jackson Blvd., Chicago, Illinois 60606.)

3. REQUIREMENTS

3.1 Standard sample. When a standard sample is available, the finished washcloth shall match the standard sample for shade, and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

3.2 Material.

3.2.1 Yarn. The yarn shall be made of cotton which has been cleaned, carded, drawn and spun into single or 2 ply yarns as specified in table I.

3.3 Physical requirements. The finished washcloths shall conform to the requirements specified in table I when tested as specified in 4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

TABLE I. Physical requirements

Type	Weight per dozen (minimum) 2/	Yarns per inch Warp (min.)	Yarns per inch Filling (min.)	Ply warp Ground	Ply warp Pile	Ply warp Filling	Finished dimensions Each	Finished dimensions Tolerance	Break strength (minimum) Warp	Break strength (minimum) Filling
	Ounce						Inch	Inch	Lbs.	Lbs.
I	16	68 1/	35 1/	2 or 1	2 or 1	1	12 by 12	± 1/2	40	35
II	11	59	29	2 or 1	2 or 1	1	12 by 12	± 1/2	25	25

1/ Either of these values may fall below this minimum by not more than three yarns, provided the combined warp and filling yarn total does not fall below 100 yarns per inch.

2/ The washcloths shall reach equilibrium under Standard Conditions as defined in FED-STD-191 prior to determination of weight.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

3.3.1 Weave.

3.3.1.1 Type I. The type I washcloth shall consist of a ground warp, pile warp, and filling yarns woven as a single-loop terry weave except that there shall be a plain woven border 1/4 to 1/2 inch wide either on both sides and both ends or on both ends only. When the border is on both ends only it shall be located not more than 1 inch from the ends.

3.3.1.2 Type II. The type II washcloth shall consist of a ground warp, pile warp, and filling yarns woven as single-loop terry weave. The border measurement from edge towards the body on all 4 sides of the washcloth shall be in this order: 3/8 to 5/8 inch plain weave; 1/8 to 3/8 inch terry; 1/16 to 3/16 inch plain weave; 1/8 to 3/8 inch terry; 1/16 to 3/16 inch plain weave; terry body.

3.3.2 Thread. The thread for stitching the type I washcloth shall be cotton, ticket No. 30, 3 ply, type IA2 of V-T-276. The thread for stitching the type II washcloth shall be cotton, ticket No. 50, 3 ply, type IA2 of V-T-276.

3.4 Construction.

3.4.1 Edge finishing. All raw edges shall be overedged stitched with 10 to 14 stitches per inch of stitch type 504 and stitching type EFd-1 as specified in FED-STD-751. All ends of stitching shall be overstitched 3/4 to 1 inch. There shall be no loose or untrimmed threads on the finished washcloths.

3.5 Color. The washcloths shall be desized and bleached white to match the standard sample. The bleached washcloths shall show no more yellowing or discoloration than that shown by the standard sample after 20 hours exposure to light (see 4.4). When no standard sample is available, the discoloration shall be no more than the rating as "Fair" when tested as specified in 4.4.

3.5.1 Matching. The bleached washcloths shall match the standard sample under natural (north sky) daylight or artificial daylight having a color temperature of 7500° Kelvin and shall be a good approximation to the standard sample under incandescent lamplight at 2800° Kelvin.

3.6 Nonfibrous material content. The starch and protein content including chloroform-soluble and water-soluble material of the finished cloth shall not exceed 2.0 percent when tested as specified in 4.4.

3.7 Marking for identification. When marking for identification is specified (see 6.2), each washcloth shall have an identification label conforming to the requirements of type I, class 4 of DDD-L-20, except that all references to size shall be deleted. The right side of the label shall be caught in the overedge stitching and the bottom edge of the label shall be 1/2 to 3/4 inch from the lower corner of the washcloth. The end item is intended to be laundered.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

3.7.1 Fiber identification. Each washcloth shall be labeled, for fiber content in accordance with the Textile Fiber Products Identification Act.

3.8 Workmanship. The finished washcloths shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the levels set by the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase document.

4.2.2 Inspection of the end item.

4.2.2.1 Examination. The defects found during examination shall be classified in accordance with 4.2.2.1.1, 4.2.2.1.2, and 4.2.2.1.3.

4.2.2.1.1 Visual examination. The inspection level shall be level I of MIL-STD-105 and the AQL shall be 4.0 percent defective.

Defects

Cut, hole, tear, or smash.
Three or more contiguous broken or missing yarns (clearly visible).
Terry loops improperly formed over an area of 1 square inch or bald areas of 1/2 square inch or more.
Spot, stain, streak, clearly visible.
Any trash, motes, leaf, or seed coat fragments.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Defects

Objectionable odor.
Color or shade not as specified.
Wrong stitch type or stitches per inch not as specified.
Overstitching missing or loose stitch tension resulting in a loosely secured edge.
Identification label missing, incorrect, illegible, insecurely attached or misplaced.
Border not as specified.

4.2.2.1.2 Dimensional examination. The sample size shall be in accordance with inspection level S-3. The sample unit for the examination shall be one washcloth. The acceptable quality level (AQL) shall be 4.0 percent defective.

Overall length and width -
less than 11-1/2 inches
more than 12-1/2 inches

4.2.2.1.3 Examination for weight. The sample unit shall be one dozen washcloths. Any unit that does not meet the minimum weight requirements specified in table I shall be considered a defect. The inspection level shall be S-1 and the acceptable quality level (AQL) shall be 4.0 percent defective.

4.3 Examination for preparation for delivery requirements. An examination shall be made to determine that packaging, packing and marking comply with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be sealed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the acceptable quality level (AQL) shall be 2.5 defects per hundred units.

Examine	Defect
Marking (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence or method of application.
Materials	Any component missing, damaged or not as specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

Examine	Defect
Workmanship	Wrap not secured as specified, incomplete closure of container flaps, loose strapping, improper taping, inadequate stapling. Bulging or distortion of containers. Open and noncontinuous heat sealed seams and closure of polyethlylene bag. Omission of vent hole in polyethylene bag.
Content	Number of bundles or bags per container is more or less than specified. Number of washcloths per bundle or bag or more or less than specified. 1/

1/ For this defect, 3 bundles or bags shall be examined from each shipping container in the sample.

4.3.1 Examination for palletization. An examination shall be made to determine that the palletization complies with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one palletized unit load fully prepared for delivery. The lot size shall be the number of palletized unit loads in the end item inspection lot. The inspection level shall be S-1 and the AQL shall be 6.5 defects per 100 units.

Examine	Defect
Finished dimension	Length, width, or height exceeds specified minimum requirement.
Palletization	Not as specified. Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded with required straps as specified.
Weight	Exceeds maximum load limits.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence or method of application.

4.4 Testing of the end item. The methods of testing specified in FED-STD-191 wherever applicable and as listed in table III shall be followed. The physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test method. The sample unit shall be 4 washcloths. The sample size shall be in accordance with table II. The lot size shall be expressed in units of 1 washcloth each. The lot shall be unacceptable if one or more sample units fail to meet a test requirement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

TABLE II. Sampling for tests

Lot size	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and up	5

TABLE III. Test methods

Characteristic	Requirement paragraph	Test method
Yarns, per inch	3.3	5050
Breaking strength	3.3	5100
Weave	3.3.1	Visual 1/
Discoloration	3.5	5660 1/ 2/
Nonfibrous material	3.6	2611

1/ One determination shall be made on each sample unit and the results reported as "pass" or "fail".

2/ Method 5660 shall be used, except that exposure of the specimen and standard sample shall be for 20 standard fading hours. Any specimen showing discoloration less than or equal to that of the standard sample shall be rated "pass". Any specimen showing discoloration greater than that of the standard sample shall be rated "fail". When no standard sample is available, the discoloration of the specimen shall be considered satisfactory if it is not worse than the rating of "fair" indicated in Method 5660.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B or C, as specified (see 6.2).

5.1.1 Level A. Twelve washcloths of one type only, shall be evenly stacked, flat or center-folded, and then be completely wrapped in 30-pound minimum basis weight kraft paper conforming to grade B of UU-P-268. Each paper wrapped bundle shall be cross-tied with cotton tape or twine, or secured with gummed paper tape conforming to type III, grade B of PPP-T-45. Alternatively, the stack of twelve washcloths shall be packaged in a close-fitting clear polyethylene film bag of 0.00125-inch thickness (± 25 percent tolerance). The polyethylene bag shall be

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

formed with heat sealed seams that are straight, continuous, and parallel to each other and the formed edges of the bag. The bag closure shall be effected by heat sealing with the heat seal made as close as possible to the open end or by means of a mechanical tie (paper or vinyl plastic covered soft steel wire, aluminum band, etc.). A 1/4-inch maximum diameter hole shall be made at one corner of each polyethylene bag to allow the excess air to escape.

5.1.2 Level B (civil agencies). Washcloths shall be packaged in accordance with 5.1.1 (see 6.2).

5.1.3 Level C. Washcloths shall be packaged to afford adequate protection against physical damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets this requirement.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A. Three hundred washcloths of one type only, packaged as specified in 5.1, shall be compactly packed within a snug-fitting fiberboard shipping container conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each container shall be fitted with a taped box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Each shipping container shall be closed, waterproofed, and reinforced in accordance with the appendix of PPP-B-636.

5.2.2 Level B. Three hundred washcloths of one type only, packaged as specified in 5.1, shall be compactly packed within a snug-fitting fiberboard shipping container conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each container shall be fitted with a taped box liner conforming to class domestic, variety DW, grade 275 of PPP-B-636. Each shipping container shall be closed in accordance with method II as specified in the appendix of the container specification.

5.2.2.1 When specified (see 6.2), the fiberboard shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of the container specification.

5.2.3 Level C. Washcloths, packaged as specified in 5.1 shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transporation rate for such supplies. Containers shall be in accordance with Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

5.3 Palletization (military requirement). When specified (see 6.2), washcloths of one type only, shall be palletized in accordance with load type I of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L. Pallet patterns shall be in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course. If the container is of a size which does not conform to any of the pallet patterns specified in MIL-STD-147, the pallet pattern used shall first be approved by the contracting officer.

5.4 Marking.

5.4.1 Civil agencies. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with FED-STD-123.

5.4.2 Military requirements. In addition to any special marking required by the contract or order, interior packages, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129.

5.4.3 Polyethylene bagged packages. Polyethylene bagged packages shall have the required identification information legibly printed or stamped in black directly on the bag across the center face or on a white paper label inserted within the bag so as to permit ready identification.

6. NOTES

6.1 Intended use. Washcloths covered by this specification are intended for use by the Federal agencies and the Department of Defense.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents.

(a) Title, number, and date of this specification.
(b) Type of washcloth required (see 1.2).
(c) When marking identification is required (see 3.7).
(d) Selection of the applicable levels of packaging and packing (see 5.1 and 5.2).
(e) When level B packaging is required for civil agencies (see 5.1.1).
(f) When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
(g) When palletization is required (see 5.3).

6.3 Standard sample. For access to standard sample, address the procuring office issuing the invitation for bids (see 3.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

MILITARY CUSTODIANS:

Army - GL
Navy - SA
Air Force - 82

Review activity:

Army - MD

Preparing activity:

Army - GL

CIVIL AGENCIES INTEREST:

GSA-FSS
HEW-PHS
VA
JUS-FPI

Project No. 7210-0126

Orders for this publication are to be placed with the General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

Washcloth, Terry, Cotton DDD-W-80C

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426 REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01760

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

U.S.MAIL

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRES-EQS
Natick, Massachusetts 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:33Z
Check the source to verify that this is the current version before use.