MIL-B-58022G(ME)
29 August 1983
SUPERSEDING
MIL-B-58022F(ME)
7 February 1979

# MILITARY SPECIFICATION

# BOAT, LANDING, INFLATABLE:

# ASSAULT CRAFT, 15-MAN

This specification is approved for use by the Mobility Equipment Research and Development Command, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 Scope. This specification covers a 15-man, pneumatic assault boat complete with accessories, carrying case, pumps, and paddles.

## 2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. Unless otherwise specified, the following specifications and standards of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation, form a part of this specification to the extent specified herein.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: USA Mobility Equipment Research and Development Command, ATTN: DRDME-DS, Fort Belvoir, VA 22060 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document, or by letter.

FSC 1940

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:19Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

| | |
|---|---|
| QQ-S-781 | - Strapping, Steel, and Seals. |
| PPP-B-601 | - Boxes, Wood, Cleated-Plywood. |
| PPP-B-621 | - Boxes, Wood, Nailed and Lock-Corner. |
| PPP-B-640 | - Boxes, Fiberboard, Corrugated, Triple-Wall. |

MILITARY

| | |
|---|---|
| MIL-P-116 | - Preservation, Methods of. |
| MIL-A-5540 | - Adhesive, Polychloroprene. |
| MIL-C-14505 | - Cloth, Nylon, Polychloroprene-Coated (For Pneumatic Floating Equipment). |
| MIL-C-17415 | - Cloth, Coated, and Webbing, Inflatable Boat and Miscellaneous Use. |
| MIL-G-20241 | - Gasket Material, Wool Felt, Impregnated, Adhesive, Pressure-Sensitive. |
| MIL-P-23377 | - Primer Coatings: Epoxy-Polyamide, Chemical and Solvent Resistant. |
| MIL-S-81733 | - Sealing and Coating Compound, Corrosion Inhibitive. |

STANDARDS

FEDERAL

| | |
|---|---|
| FED-STD-191 | - Textile Test Methods. |
| FED-STD-601 | - Rubber: Sampling and Testing. |

MILITARY

| | |
|---|---|
| MIL-STD-105 | - Sampling Procedures and Tables for Inspection by Attributes. |
| MIL-STD-129 | - Marking for Shipment and Storage. |
| MIL-STD-889 | - Dissimilar Metals. |
| MIL-STD-1188 | - Commercial Packaging of Supplies and Equipment. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:19Z
Check the source to verify that this is the current version before use.

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein.

DRAWINGS

ME

TA13214E9970 - Boat, Landing, Inflatable: Assault Craft, 15-Man.

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

2.1.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence.

3. REQUIREMENTS

3.1 Description. The boat, paddles, pumps, repair kit, and carrying case shall be in accordance with Top Assembly TA13214E9970 and as specified herein.

3.1.1 Drawings. The drawings forming a part of this specification are end product drawings. No deviation from the prescribed dimensions or tolerances is permissible without prior approval of the contracting officer. Where tolerances could cumulatively result in incorrect fits, the contractor shall provide tolerances within those prescribed on the drawings to insure correct fit, assembly, and operation of the boat. Any data (e.g. shop drawings, layouts, flow sheets, processing procedures, etc.) prepared by the contractor or obtained from a vendor to support fabrication and manufacture of the production item shall be made available, upon request, for inspection by the contracting officer or his designated representative.

3.2 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 4.3 and 6.3).

3.3 Material. Material shall be as specified herein and on the applicable drawings. Materials not specified shall be selected by the contractor and shall be subject to all provisions of this specification (see 6.8).

3.3.1 Material deterioration and control. The boat shall be fabricated from compatible materials, inherently corrosion resistant or treated to provide protection against the various forms of corrosion and deterioration that may be encountered in any of the applicable storage and operating environment to which the item may be exposed.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:19Z
Check the source to verify that this is the current version before use.

3.3.1.1 Dissimilar metals. Dissimilar metals, as defined in MIL-STD-889, shall be electrically insulated from one another to minimize or prevent galvanic corrosion. Insulation may be provided by an insulating barrier such as a coat of epoxy primer conforming to MIL-P-23377, or corrosion inhibiting sealant conforming to MIL-S-81733 or chromate tape conforming to MIL-G-20241. Protection against any galvanic corrosion could also be obtained by exclusion of the electrolyte if feasible.

3.3.1.2 Identification of materials and finishes. The contractor shall identify the specific material, material finish or treatment for use with components and sub-components, and shall make information available, upon request, to the contracting officer or designated representative.

3.3.2 Coating compound. The coating compound shall be as specified in MIL-C-14505.

3.3.3 Coated cloth. The uncured coated cloth used in fabrication of the boat shall conform to MIL-C-14505, class as specified on the drawings.

3.3.4 Gum sheeting and strips. Gum sheeting and strip required in the fabrication of the boat shall be made from coating compound specified in 3.3.2. Thickness shall be not less than 0.018 inch and not more than 0.026 inch; width as specified on the drawings.

3.3.5 Seaming and hinge tapes. Tapes used as seam overlaps and as hinge tape shall be cut from coated cloth specified in 3.3.3, class and width as specified on the drawings.

3.3.6 Floor material. The material used to fabricate the floors shall conform to MIL-C-14505, class 10 coated pile cloth. An alternate material may be used, conforming to MIL-C-17415, type 11 and also conforming to the tearing and breaking strength requirements of the above primary material when tested in accordance with FED-STD-191, test method 5100. If MIL-C-14505 class 10 coated pile cloth is used, a cover cloth conforming to MIL-C-14505, class 3 (table I, schedule B) shall be cemented to the top of the bottom floor before this floor is mated and cemented to the top floor.

3.3.7 Adhesive. The adhesive required in the fabrication of the boat shall conform to MIL-A-5540, class 1, form optional, color black.

3.4 Seams. All seams shall be water-and airtight to the extent specified herein, and shall develop the full strength of the coated cloth. Seam overlap for both air chamber and bulkhead fabrics shall be not less than 1-1/2 inches. Cured seams subjected to a deadweight load of 40 pounds per inch of seam width at a temperature of 200° Farhenheit (F) shall show no signs of slippage after 24 hours.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:19Z
Check the source to verify that this is the current version before use.

3.5 Flotation tube. The flotation tube shall be fabricated from the uncured coated cloth specified in 3.3.3 with the warp threads running circumferentially around the tube. Only one longitudinal seam shall be permitted in each section of the tube. All tube compartments shall withstand an air pressure of 6 pounds per square inch (psi) for a period of 10 minutes without any evidence of failure such as seam slippage, rupture, or permanent distortion. With all six compartments of the tube inflated to an air presure of 3 psi, the final pressure reading after a period of 6 hours shall be not less than 2.7 psi. With alternate compartments of the tube inflated to an air pressure of 3 psi for a period of 4 hours, the inflated compartments shall retain a pressure of not less than 2.5 psi. When tested as specified in 4.5.2.4, repeated folding of the boat, deflated, shall not cause any damage to the tube or show a decrease in pressure more than 0.3 psi below the final pressure reading obtained during the initial 6-hour air retention period.

3.6 Floor. The floor of the boat shall consist of two individual air-retaining envelopes fabricated from the material specified in 3.3.6 and as specified on the drawings, both of which shall be cemented together and vulcanized as a bonded double-layer floor as specified on the drawings. All exposed top and bottom surfaces shall have chafer panels cemented and vulcanized in place. Both the top and bottom floor compartments shall withstand an air pressure of 10 psi for a period of 10 minutes without any evidence of failure such as seam slippage, bulges, bubbles, rupture, or permanent distortion. With both floor compartments inflated to an air pressure of 7 psi, the final pressure reading after a period of 6 hours shall be not less than 6.5 psi. When tested as specified in 4.5.2.4, repeated folding of the boat, deflated, shall not cause damage to the floor or show a decrease in pressure more than 0.3 psi below the final pressure reading obtained during the initial 6-hour air retention period.

3.7 Thwart tube. The thwart tube of the boat shall be fabricated from uncured coated cloth specified in 3.3.3 with the warp threads running circumferentially around the tube. The tube shall withstand an air pressure of 6 psi for a period of 10 minutes without any evidence of failure such as seam slippage, rupture, or permanent distortion. When inflated to an air pressure of 3 psi, the final pressure reading after a period of 6 hours shall be not less than 2.7 psi. When tested as specified in 4.5.2.4, repeated folding of the boat, deflated, shall not cause damage to the thwart tube or show a decrease in pressure more than 0.3 psi below the final pressure reading obtained during the initial 6-hour air retention period.

3.8 Spray-rail tube. The spray rail shall be one continuous tube fabricated from the uncured coated cloth specified in 3.3.3, and shall be attached to the flotation tube as specified on the drawings prior to vulcanization of the boat. The spray rail tube shall withstand an air pressure of 6 psi for a period of 10 minutes without any evidence of failure such as seam slippage, rupture, or permanent distortion. When inflated to an air pressure of 3 psi, the final pressure reading



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:19Z
Check the source to verify that this is the current version before use.

after a period of 6 hours shall be not less than 2.7 psi. When tested as specified in 4.5.2.4, repeated folding of the boat, deflated, shall not cause damage to the spray-rail tube or show a decrease in pressure more than 0.3 psi below the final pressure reading obtained during the initial 6-hour air retention period.

3.9 Transom sheath. The transom board sheath shall be fabricated as specified on the drawings, and shall be watertight, except for the grommet openings, to the extent specified in 4.5.2.5 when tested as specified in 4.5.2.5.

3.10 Patch assemblies. The patch assemblies for the boat shall be fabricated as specified on the drawings, and shall be cemented to the boat prior to vulcanization. After vulcanization of the boat, the patch assemblies shall withstand the following loads without any evidence of failure or separation of the patches from the boat:

| Assemblies | Pull in pounds |
|---|---|
| Tow bridle patch | 1,000 |
| Lifeline patch | 500 |
| Transom patch (inboard) | 500 |
| Transom patch (outboard) | 200 |
| Fuel tank patch | 200 |

3.11 Fabrication. In the fabrication of the boat, all gum strips and tape splices shall overlap not less than 1/2 inch. The boat, less the tow bridle and lifeline, shall be vulcanized as a complete unit in a pressure-type autoclave. Partial curing of the floor and flotation tube separately will be permitted provided that the final vulcanization process does not conflict with other requirements of this specification. The stern end caps of the boat shall be fabricated either of the baseball or gore type construction. The bulkheads shall be of the baseball or two-piece (half sphere) type construction. All exposed coated fabric edges of the boat not required to be covered with gum strips shall be seal coated with adhesive or other appropriate sealant. Each air compartment of the flotation tube, the thwart tube, the spray-rail tube, and the air-mattress floor shall be fitted with inflation-deflation valves as specified on the drawings. When the boat is inflated to 3 psi, except the floor which shall be 7 psi, and placed on a horizontal surface, warpage or twisting of the completed boat shall be not more than 1-1/2 inches, measured vertically from any one corner. Swashing of the inner walls of the inflatable air compartment with latex or any other sealing compound shall not be permitted either before or after vulcanization. Fabrication of the boat shall insure airtightness to the degree specified herein and watertightness to the degree that, when the completed boat is inflated to prescribed operating pressures and placed in water and loaded with 3000 pounds distributed deadweight for a period of 1 hour, the boat shall not leak in excess of 1 quart of water.



Source: https://assist.dla.mil -- Downloaded: 20261O-26T04:19Z
Check the source to verify that this is the current version before use.

3.12 Dimensions. Dimensions subject to variation with air pressure shall be taken with the boat inflated to the working pressure of 3 psi, except for the two floor compartments which shall be inflated to 7 psi.

3.13 Markings. Identification and instructional markings shall be as specified on the drawings and shall be legible. Repair items shall be identified either on the item or on its packaging material by name and by applicable NSN or manufacturer's code and part number.

3.14 Repairs. The first article boats shall contain no repair patches. Any production boat shall contain not more than five patches. Patched boats shall not exceed 20 percent of the boats submitted for acceptance at one time. Applied repair patches shall be prepared from coated cloth conforming to MIL-C-14505, class 4, applied with adhesive specified in 3.3.7 and vulcanized with the local application of heat and pressure. The edges of any repair patch shall extend not less than 2 inches beyond the extremity of the defect. Gum strips as specified in 3.3.4 shall be used on the periphery of all applied patches to cover and seal the edges. Covering or overlapping of patches shall not be permitted. Applied patches shall not adversely affect the strength or serviceability of the boat, and all patched boats shall conform to the requirements of this specification. Injury or damage that exposes the base fabric (nylon) of the boat's air chamber cloth shall be repaired with patch material as specified herein. Exposed base fabric of non-air-retaining boat cloth shall be repaired with gum sheeting, cemented, and cured by applying local heat and pressure. Nonadhering surfaces of cemented material shall be repaired by recementing and curing by applying local heat and pressure, except that in cases of minor edge looseness (maximum distance of 1/4-inch from edge) on non-air-retention material, repair may be made by recementing with an appropriate air curing cement.

3.15 Reliability. In addition to the inspection specified in 4.3 for first article boats, the Government may perform additional testing as specified in 4.5.2.9 to verify the reliability of the boats. When tested as specified in 4.5.2.9 for 16 missions, the boat shall not fail to complete any mission including the use of the specified repair kit.

3.16 Workmanship. The finished boat, complete with all specified bonded and attached components, shall be free from bubbles, bulges, ripples, folds, wrinkles, puckers, defective or missing parts, or any other defects which could impair the serviceability of the boat. Surfaces to be cemented shall be thoroughly wiped clean with a cleaning solvent before applying cement and shall be free from grease and dirt, oil, excess materials used in fabrication, and any other foreign materials that could harmfully affect the application of the cement and the bonding of cemented surfaces. The accessories, carrying case, pumps, and paddles furnished with the boat shall be free of defects that could impair their serviceability.



Source: https://assist.dla.mil -- Downloaded: 20261O-26T04:19Z
Check the source to verify that this is the currentversion before use.

When subjected to the test specified in 4.5.2.8 the boat shall show no evidence of material separation, distortion, bubbles, bulges, ripples, puckers, defective or loose components, or any other defects which could adversely impair or affect the serviceability of the boat.

## 4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Component and material inspection. The contractor is responsible for insuring that components and materials used are manufactured, examined, and tested in accordance with referenced specifications, standards, and drawings, as applicable.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).

b. Quality conformance inspection (4.4).

c. Inspection of packaging (4.6).

4.3 First article inspection.

4.3.1 Examination. The first article boat(s), complete with all components, carrying case, pumps, repair items, and paddles, shall be examined as specified in 4.5.1. Presence of one or more defects shall be cause for rejection.

4.3.2 Tests. The first article boat(s) shall be tested as specified in 4.5.2.1 through 4.5.2.8, and a representative seam sample shall be tested as specified in 4.5.2.10. The samples for lap seam strength tests shall be fabricated identically to seams in the first article boat(s) from coated cloth representative of that used to fabricate the boat and vulcanized simultaneously and identically to the boat represented. The sample shall contain not less than 13 inches of linear seam and shall contain 3 inches of coated fabric extending on each side of the seam overlap. Failure of any test shall be cause for rejection.



Source: https://assist.dla.mil -- Downloaded: 20261O-26T04:19Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection.

4.4.1 Sampling for tests.

4.4.1.1 Production boats. One sample boat shall be selected at random from each lot of 50 boats or fraction thereof submitted for acceptance at one time.

4.4.1.2 Lap seams. Samples for the lap-seam tests shall be fabricated indentically to seams in the boat, except the width of overlap shall not exceed the minimum overlap used in any seam in the boat, from cloth representative of the boat, and vulcanized identically to the boats represented. The sample shall contain not less than 13 inches of linear seam and shall have not less than 3 inches of coated cloth extending on each side of the seam overlap. One lap seam sample shall be prepared and furnished for test for each 50 boats or fraction thereof submitted for acceptance at one time.

4.4.2 Examination. Each boat, complete with carrying case, pumps, paddles and repair items, shall be examined for the defects specified in 4.5.1. Presence of one or more defects shall be cause for rejection.

4.4.3 Tests.

4.4.3.1 Individual. Each boat shall be tested as specified in 4.5.2.1 through 4.5.2.3. Failure of any test shall be cause for rejection. Rejected boats may be repaired and resubmitted for test and acceptance. Repairs shall conform to 3.14. Reworking or revulcanizing shall not adversely affect the strength or serviceability of the boat.

4.4.3.2 Samples.

4.4.3.2.1 Sample production boats. Samples selected in accordance with 4.4.1.1 shall be tested as specified in 4.5.2.4 through 4 5.2.8. Failure of any test shall be cuase for rejection of the lot represented by the sample.

4.4.3.2.2 Lap-seam tests. Samples selected and fabricated in accordance with 4.4.1.2 shall be tested as specified in 4.5.2.10. Failure of any test specimen prepared from the samples shall be cause for rejection of the lot of boats represented by the samples.



Source: https://assist.dla.mil -- Downloaded: 202610-26T04:19Z
Check the source to verify that this is the currentversion before use.

4.5 Inspection procedure.

4.5.1 Examination. The boat, carrying case, pumps, paddles, and repair items shall be examined as specified herein for the following defects:

101. Materials not as specified.
102. Materials are not corrosion resistant or treated to be made corrosion resistant for the applicable storage and operating environment.
103. Dissimilar metals as defined in MIL-STD-889 are not effectively insulated from each other.
104. Contractor does not have documentation available for identification of material, material finishes or treatment.
105. Nonconformance to dimensions shown on drawings.
106. Parts incorrect, missing, not correctly attached, or damaged.
107. Fabric lapped less than 1-1/2 inches at seams.
108. Seams and tapes not covered with gum strip as shown on the drawings.
109. Warp threads not running circumferentially around the tube.
110. Gum strip and tape splices lapped less than 1/2 inch.
111. More than one longitudinal seam in tube sections.
112. Boat warped or twisted beyond amount specified.
113. Carrying handles not as shown on the drawing.
114. Snap fasteners damaged or not operating freely.
115. Fittings and fastening devices not in accordance with the drawings.
116. Installation of inflation valves not as shown on drawings.
117. Hardware finish incorrect.
118. Sewing inadequate or defective (carrying case only).
119. Fabrication of carrying case not in accordance with drawings.
120. Repair kit pocket or items therein missing or incorrect.
121. Rope work incorrect, not secured as specified.
122. Color of materials or components not as specified.
123. Identification and instruction markings incorrect or illegible.
124. Treatment and painting not as specified.
125. Repair patches not as specified.
126. More than five patches on any one production boat.
127. Patched boats comprise more than 20 percent of boats scheduled for delivery.
128. Workmanship not as specified.

4.5.2 Tests.

4.5.2.1 Overpressure. Inflate each compartment of the flotation tube, the thwart and the spray-rail tubes to a pressure of 6 psi. Inflate the double-floor compartments to a pressure of 10 psi. Nonconformance to 3.5, 3.6, 3.7, or 3.8 shall constitute failure of this test.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:19Z
Check the source to verify that this is the current version before use.

4.5.2.2 Air retention. Inflate all tubes of the completed boat with air to a pressure of 3 psi, and the double-floor compartments to a pressure of 7 psi. After not less than 1 hour, adjust the pressure in all compartments as closely as possible to the working pressure as specified above. After this adjustment, seal the valve caps in such a manner that the boat cannot be inflated without breaking the seals. After 6 additional hours, take a final pressure reading of each compartment. Adjust the final pressure reading to compensate for any temperature and barometric pressure changes during the test period. The correction for any temperature change shall be calculated in accordance with 4.5.2.2.1. For any barometric pressure change, the correction shall be in accordance with 4.5.2.2.2. Nonconformance to 3.5, 3.6, 3.7, or 3.8 shall constitute failure of this test.

4.5.2.2.1 Temperature correction. For each degree F (only) rise in temperature, 0.03 psig shall be subtracted from the final pressure reading. For each degree drop in temperature, 0.03 psig shall be added to the final pressure reading. The corresponding correction per degree celcius is 0.056 psig.

4.5.2.2.2 Barometric pressure correction. For each 0.1 inch of mercury rise in barometric pressure, 0.049 psig shall be subtracted from the final temperature corrected reading. For each 0.1 inch of mercury drop in barometric pressure, 0.049 psig shall be added to the final temperature corrected reading.

4.5.2.3 Bulkheads. After successful completion of the air tests specified in 4.5.2.1 and 4.5.2.2, inflate the bow and stern compartments on one side of the flotation tube and the middle compartment on the opposite side to an air pressure of not less than 3 psi, with the valves in the empty compartments left open. After not less than 1 hour, adjust the pressure as closely as possible to 3 psi and seal the valves as specified in 4.5.2.2. After 4 additional hours, take a final pressure reading of the inflated compartments. Adjust the final readings to compensate for temperature and barometric pressure changes as specified in 4.5 2.2. Nonconformance to 3.5 shall constitute failure of this test.

4.5.2.4 Folding and air retest. Boat(s) shall be tested as follows: Deflate all compartments, fold boat, and place in carrying case; remove boat from carrying case, inflate all tube compartments (including spray-rail and thwart tubes) to 3 psi, and the double-floor compartments to 7 psi. Repeat this cycle 25 times, except that after the first 5 cycles when the boat has been folded as before, the folded boat need not be placed in the carrying case for the remaining 20 cycles. After completion of the 25 folding cycles, inflate and test for air retention as specified in 4.5.2.2. Nonconformance to 3.5, 3.6, 3.7 or 3.8 shall constitute failure of this test.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:19Z
Check the source to verify that this is the current version before use.

4.5.2.5 Transom sheath watertightness. After the folding and air retest specified in 4.5.2.4, remove the transom board and fill the transom sheath with water to within 3 inches of the top after temporarily sealing the grommet openings in the sheath. The water level should not fall more than 0.50 inch during a 24-hour period. At the conclusion of the period, the inability of the transom sheath to retain the water level within 0.50 inch of the initial recorded water level shall constitute failure of this test.

4.5.2.6 Boat watertightness. After the transom sheath test, inflate all tube compartments of the boat to a pressure of 3 psi, and the compartments of the double-floor to 7 psi. Place the boat in water not less than 2 feet deep with sufficient breadth to allow the boat to float unobstructed. Place 3,000 pounds of material, such as filled sandbags or other noninjurious material in the boat and distribute the load evenly over the entire floor. If water-absorbing material is used for this test, such as filled sandbags, the material shall be wrapped with waterproof plastic sheeting to prevent absorption of any water that possibly leaks into the boat during this test. After the loaded boat has been in the water for 1 hour, remove the 3,000 pounds of material from the boat and measure the quantity of water in the boat. Nonconformance to 3.11 shall constitute failure of this test.

4.5.2.7 Pull resistance. Apply a pull of 1,000 pounds to each tow bridle patch, 500 pounds to each of three lifeline patches and one transom inboard loop patch, and 200 pounds to each of a fuel tank loop patch and an outboard transom patch. Pulls shall be applied through the D-rings. The pull on the tow bridle patch shall be in the direction of the tow bridle (forward). The pull on all other patches shall be normal to the plane of the patch. Position the boat so that test loads will not distort the boat. Hold each load for not less than 7 seconds and examine the attachment patch assembly for defects. Nonconformance to 3.10 shall constitute failure of these tests.

4.5.2.8 Extended air retention. Inflate the boat to working pressures (7 psi for the floor and 3 psi for the tubes) and maintain this pressure within 1/2 psi for 7 consecutive days. At the conclusion of this period inspect the boat for abnormalities such as distortion, nonadhering seams or attachments, and presence of bubbles, bulges or ripples in the floors. Nonconformance to 3.16 shall constitute failure of this test.

4.5.2.9 Demonstration of reliability. The boat shall be subjected to 16 missions. A typical mission shall be 4 hours duration, which shall consist of 30 minutes of transporting the boat to the vicinity of the water's edge, 30 minutes of before-use preparation (i.e., unpacking, inflating, putting in water), 2 hours of river crossings, 30 minutes of after-use preparation (taking out of water, deflating, repacking) for transport, and 30 minutes of transport. Approximately 25 percent of the typical missions shall consist of 30 minutes of preparation, 30 minutes of transport with the boat inflated, 2 hours of river crossings, 30 minutes of transport with the boat inflated, and 30 minutes of after-use preparation, for storage. The normal maintenance and repair of the boat with materials



Source: https://assist.dla.mil -- Downloaded: 20261O-26T04:19Z
Check the source to verify that this is the currentversion before use.

supplied with the boat shall be conducted as required in performing the missions. Transport of the boat shall be by both vehicle and portage. The river crossings (water operation) of the boat shall include the boat being propelled by a 25 horsepower (hp) outboard motor, by paddle, and by being towed by another boat. (The results of these missions will be used to verify that the contractor has furnished boats which are free from defects.) The contractor is not responsible for a mission failure caused by tears or punctures in the boat provided that all other contractural requirements are met. Nonconformance to 3.15 shall constitute failure of this test.

4.5.2.10 Lap-seam strength. Prepare six specimens by cutting the seam sample into 2-inch widths. Test three specimens to failure in accordance with FED-STD-601, method 8311. Rupture of any specimen at the seam before rupture of the coated cloth shall constitute failure of this test. If the specimens pass the above test, test the remaining three specimens as follows: subject each specimen with the seam positioned horizontally, to a tensile load (dead weight) of 80 pounds (40 pounds per inch of seam width) at a temperature of 200° F for a period of 24 hours and examine the seam for slippage. Nonconformance to 3.4 shall constitute failure of this test.

4.6 Inspection of packaging.

4.6.1 Preproduction pack inspection.

4.6.1.1 Examination. The preproduction pack shall be examined for the defects specified in 4.6.2.4. Presence of one or more defects shall be cause for rejection.

4.6.2 Quality conformance inspection of pack.

4.6.2.1 Inspection stages. Inspection shall be in two stages as follows:

a. The first stage shall include inspection of materials and methods inside the shipping container.

b. The second stage shall include inspection of materials and marking after the container is closed.

4.6.2.2 Unit of product. For the purpose of inspection, a unit of product for the first stage of inspection shall be a complete pack with the box top off. For the second stage of inspection, a unit of product shall be a completed pack ready for shipment.

4.6.2.3 Sampling. Sampling for examination shall be in accordance with MIL-STD-105.



Source: https://assist.dla.mil -- Downloaded: 202610-26T04:19Z
Check the source to verify that this is the currentversion before use.

4.6.2.4 Examination. Samples selected in accordance with 4.6.2.3 shall be examined for the following defects. AQL shall be 2.5 percent defective.

| | |
|---|---|
| 129. | Materials, methods, and containers not as specified for level A or B. Each incorrect material, methods, or container shall be considered one defect. |
| 130. | Metal surfaces requiring a preservative not coated as specified for level A. |
| 131. | Components not stowed as provided for, for level A or commercial. |
| 132. | Boat not dusted as specified for level A or commercial. |
| 133. | Boat not folded, placed in carrying case, and secured as specified for level A or commercial. |
| 134. | Strapping not as specified for level A. |
| 135. | Marking missing, illegible, incorrect or incomplete for level A, level B, or commercial. |

5. PACKAGING

5.1 Preproduction pack. The contractor shall furnish a preproduction pack for examination within the time frame specified (see 6.2) to prove, prior to starting production packaging, that the applied preservation, packing, and marking comply with the requirements of this specification. Examinations shall be those specified in Section 4 and shall be subject to surveillance and approval by the Government (see 6.4). The preproduction pack may be accomplished utilizing either the first article boat or a production boat. If the first article boat is utilized, any preservation, and packing shall be removed by the contractor at no expense to the Government, when requested by the Government, to facilitate comparison between the first article boat and production boats.

5.2 Preservation. Preservation shall be level A or commercial as specified (see 6.2).

5.2.1 Level A. Metal surfaces of the repair kit items requiring the application of a contact preservative in accordance with MIL-P-116 shall be coated with type P-1 preservative. The preservative shall conform to the applicable specification listed in, and shall be applied in accordance with MIL-P-116. Each pump with the number of hose assemblies and adapters as specified on the drawings and repair kit items of like description, with the exception of the buffing solution and repair instructions sheet, shall be preserved in accordance with MIL-P-116, method IC-1 or IC-3. The pump shall be cushioned to prevent damage to the method IC-1 or IC-3 barrier material. The repair kit items shall be placed in the repair kit pocket in a manner to prevent damage to each other and to the boat. The pumps, with hose assemblies and adapters, shall be placed in their respective pockets on the boat and the transom board shall be secured in its sheath with fasteners provided.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:19Z
Check the source to verify that this is the current version before use.

The paddles shall be placed and secured in the carrying case. The tow bridle shall be coiled or hanked and secured in the best manner for its placement with the boat. The boat shall be dusted with soapstone or talc. All components shall be stowed as provided for, and the boat shall be folded and placed in the carrying case in accordance with the instructions specified on the carrying case. The carrying case shall be secured with its respective flaps and straps.

5.2.2 Commercial. Each complete boat shall be preserved in accordance with MIL-STD-1188 and the following specific requirements. The repair items shall be placed in the repair kit pocket. The pumps, with required hose assemblies and adapters, shall be placed in their respective pockets on the boat. The transom board shall be secured in its sheath with fasteners provided. The paddles shall be placed and secured in the carrying case. The boat shall be dusted with soapstone or talc, and with the tow bridle coiled or folded and secured, the boat shall be folded and placed in the carrying case in accordance with the instructions specified on the carrying case. The carrying case shall be secured with its respective flaps and straps.

5.3 Packing. Packing shall be level A, level B, or commercial as specified (see 6.2).

5.3.1 Level A. Each carrying case containing one complete boat shall be packed in a close-fitting box conforming to PPP-B-601, overseas type, style optional, grade B, or PPP-B-621, class 2, style optional, grade B. Box closure and strapping shall be in accordance with the appendix to the applicable box specification. Strapping shall conform to QQ-S-781, class 1, type I or IV, size as applicable. Unless otherwise specified (see 6.2), strapping shall be finish B. When specified (see 6.2), strapping shall be finish A.

5.3.2 Level B. Packing shall be as specified in 5.3.1 for level A, except the boxes shall be domestic type or class as applicable. As an alternate, at the option of the contractor, a box conforming to PPP-B-640, class 2, style E may be used. Box closure and strapping shall be in accordance with the appendix to the applicable box specification.

5.3.3 Commercial. Each carrying case containing one complete boat shall be packed in accordance with MIL-STD-1188.

5.4 Marking.

5.4.1 Military. Packages and shipping containers for level A or B shall be marked in accordance with MIL-STD-129 and, in addition, the repair kit items shall be marked as specified in 3.13.

5.4.2 Commercial. Marking for commercial packaging shall be in accordance with MIL-STD-1188 and in addition, each package for the repair kit items shall be marked as specified in 3.13.



Source: https://assist.dla.mil -- Downloaded: 202610-26T04:19Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The boat is intended to carry 15 men with individual weapons and equipment in the assault phase of river crossing operations, and is capable of being propelled by either the paddles provided or by a 25 hp outboard motor. The boat may also be used for inspecting/determining stream and river bank conditions, and for general work in floating bridge construction.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number and date of this specification.

b. When a first article is required for inspection and approval and the number of units required (see 3.2).

c. Time frame required for submission of preproduction pack (see 5.1).

d. Degree of preservation and packing required (see 5.2 and 5.3).

e. When other than finish B strapping is required (see 5.3.1).

6.3 First article. When a first article inspection is required the item shall be examined and should be a first produced boat. The contracting officer should include specific instructions in the acquisition documents regarding arrangements for examinations and approval of the documents first article.

6.4 Preproduction pack. Any changes or deviations of production packs from the approved preproduction pack will be subject to the approval of the contracting officer. Approval of the preproduction pack will not relieve the contractor of his obligation to preserve, pack, and mark the boats in accordance with this specification.

6.5 Pump drawings. The contracting officer should furnish drawings for the two types of pumps furnished with the boat covered by this specification. The drawings are TA13211E9597 for the foot model pump and TA13211E9599 for the hand model pump.

6.6 Data requirements. The contracting officer should include requirements for such data as the contractor's maintenance and operation manual to be furnished with each boat.

6.7 Provisioning. The contracting officer should include provisioning requirements for repair items as necessary and instructions on shipment of boats.

6.8 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the specification (see 3.3).

Custodian:
Army - ME

Preparing activity:
Army - ME

Project 1940-A057



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:19Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

*(See Instructions – Reverse Side)*

| 1. DOCUMENT NUMBER | 2. DOCUMENT TITLE |
|---|---|
| MIL-B-55022C (ME) | |

| 3a. NAME OF SUBMITTING ORGANIZATION | 4. TYPE OF ORGANIZATION *(Mark one)* |
|---|---|
| | ☐ VENDOR |
| b. ADDRESS *(Street, City, State, ZIP Code)* | ☐ USER |
| | ☐ MANUFACTURER |
| | ☐ OTHER *(Specify)*: _____ |

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

| 7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional | b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional |
|---|---|
| c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional | 8. DATE OF SUBMISSION *(YYMMDD)* |

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE

Source: https://assist.dla.mil – Downloaded: 2026-10-26T04:19Z
Check the source to verify that this is the current version before use.

**INSTRUCTIONS:** In a continuing effort to make our standardization documents better, the DoD provides this form for use submitting comments and suggestions for improvements. All users of military standardization documents are invited to provi suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, an mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, w too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

*NOTE:* This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

*(Fold along this line)*

*(Fold along this line)*

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

**OFFICIAL BUSINESS**
PENALTY FOR PRIVATE USE $300

**BUSINESS REPLY MAIL**
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Mobility Equipment R & D Command
ATTN: DRDME-DS
Fort Belvoir, VA 22060

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:19Z
Check the source to verify that this is the current version before use.