MIL-C-60252A(MU)
30 April 1971
SUPERSEDING
MIL-C-60252(MU)
28 October 1965

MILITARY SPECIFICATION
CARTRIDGE, 7.62MM, NATO, TRACER, M62
OVERHEAD FIRE APPLICATION

1. SCOPE

1.1 This specification covers Cartridge, 7.62MM, NATO, Tracer, M62 Overhead Fire Application for use in 7.62MM weapons.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

STANDARDS

Federal

Federal Test Methods Standard No. 151 - Metals; Test Methods

Military

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-109	- Quality Assurance Terms and Definitions
MIL-STD-636	- Visual Inspection Standards for Small Arms Ammunition through Caliber .50
MIL-STD-644	- Visual Inspection Standards and Inspection Procedures for Inspection of Packaging, Packing and Marking of Small Arms Ammunition
MIL-STD-1168	- Lot Numbering of Ammunition
MIL-STD-1170	- Visual Standards and Comparison Methods for Evaluating Grain Configuration in 7.62mm Cartridge Cases

SPECIFICATIONS

Military

MIL-I-45607 - Inspection Equipment, Supply and Maintenance of

FSC 1305

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

2.1 (Cont'd)

DRAWINGS

U.S. Army Munitions Command

C7643674	- Classification of Cartridge Case Defects
C10535494	- Bullet
C10535493	- Cartridge, 7.62mm, NATO, Tracer, M62 Overhead Fire Application
F10523087	- Packing and Marking; Cartridges, 7.62mm, NATO, Overhead Fire; Linked; Cartons; Bandoleers; Box, Ammunition, M19A1; Box, Wirebound (Functional)

PUBLICATIONS

AMCR 715-505 Volume 3	- Ammunition Ballistic Acceptance Test Methods, Volume 3, Test Procedures for 7.62mm Cartridges

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 General.- The cartridge shall comply with Drawing C10535493, referenced specifications and the following:

3.1.1 Bullet.- Prior to assembly into cartridges, all bullets shall be examined for conformance with drawing C10535494 and shall be free from dents, scratches, splits, scaly metal, defective base and point, defective or missing cannelure and defective or missing igniter.

3.2 Bullet extraction.- The force required to extract the bullet from the cartridge case shall be not less than 60 pounds.

3.3 Residual stress.- The cartridge case shall not split when subjected to a one percent mercurous nitrate solution for 15 minutes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

3.4 Waterproof.- The cartridge shall not release more than one bubble of air when subjected to a pressure differential of 7-½ pounds per square inch (psi) for 30 seconds.

3.5 Accuracy.- The average of the mean radii of all targets of the sample cartridges, fired at 600 yards, shall not exceed 9 inches. The extreme spread of each target of the sample carttidges shall not exceed 45 inches.

3.6 Trace.- When viewed at night from a line parallel to the plane of the trajectory, with the line of sight perpendicular to the plane of the trajectory at each point of observation, the bullet of the tracer cartridge shall exhibit a visible trace of full luminosity from a point not greater than 100 yards from the muzzle of the weapon to a point not less than 850 yards from the muzzle. The trace shall be of a level below full luminosity, and preferably invisible, from the muzzle of the weapon to a point at least 15 yards from the muzzle.

3.7 Action time.- The action time (overall primer ignition, propellant burning and bullet-barrel time) of the cartridge shall not exceed 4 milliseconds.

3.8 Velocity.- The average velocity of the sample cartridges conditioned at 68° to 72°Fahrenheit (F.) shall be 2680 feet per second (ft/sec) plus or minus 30 ft/sec, at 78 ft. from the muzzle of the weapon. The standard deviation of the velocities shall not exceed 20 ft/sec.

3.9 Chamber pressure.- The average chamber pressure of the sample cartridges, conditioned at 68° to 72°F. shall not exceed 50,000 psi. Neither the chamber pressure of an individual sample cartridge, nor the average chamber pressure of the sample cartridges plus three standard deviations of chamber pressure, shall exceed 55,000 psi.

3.10 Temperature test.- The chamber pressure, velocity and function and casulty requirements of the sample cartridges subjected to each of the following storage conditions shall be as noted in the applicable sub-paragraphs.

Stored at 125°F for 4 hours and fired at that temperature.

Stored at -65°F for not less than 6 hours and fired at that temperature.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

3.10.1 Chamber pressure.- The average chamber pressure of the sample cartridges subjected to high and low temperature storage conditions shall not exceed 55,000 psi nor vary from the average chamber pressure of the sample cartridges of the same lot conditioned at 68° to 72°F by more than plus (+) or minus (-) 15,000 psi.

3.10.2 Velocity.- The average velocity of the sample cartridges subjected to high and low temperature storage conditions shall not vary from the average velocity of the sample cartridges of the same lot conditioned at 68° to 72°F by more than plus (+) or minus (-) 250 fps.

3.11 Function and casulty.- The cartridge shall function without casulty at ambient temperature and under the conditions specified in temperature test (3.10).

3.12 Bullet integrity.- The bullet of the cartridge shall not burst either in its passage through the barrel or in flight; neither shall the jacket of the bullet or any part thereof strip from the slug when the cartridge is fired.

3.13 Port pressure.- The average port pressure of the sample cartridges, conditioned at 68° to 72°F, shall be 12,500 ± 2,000 psi.

3.14 Grain configuration.- The grain configuration of the sidewall of the finished cartridge case shall fall within the range defined by the grain configuration standard illustrated in MIL-STD-1170, Figures 1 through 6.

3.15 Workmanship.- The requirements for workmanship are as specified on the applicable drawings, referenced specifications and the following:

3.15.1 Metal defects.- The cartridge shall be free of folds, wrinkles, deep draw scratches, scaly metal, dents and other defects.

3.15.2 Foreign matter.- The cartridge shall be free of corrosion, stains, discolorations, dirt, oil and smears of lacquer.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.- Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the government. The government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

4.1.1 Quality assurance terms and definitions.- Reference shall be made to MIL-STD-109 for definition of quality assurance terms.

4.2 First article sample.

4.2.1 Initial production sample.- At the beginning of regular production, a sample shall be submitted in accordance with contract requirements and shall consist of 3000 cartridges and 500 bullets. The sample shall be manufactured using the same materials, equipment, processes and procedures as will be used in regular production. All parts and materials, including packaging and packing, shall be the same as used for regular production and shall be obtained from the same source of supply.

4.2.1.1 Examination and test.- After inspection and provisional acceptance at source, the sample shall be inspected for all requirements of the drawings and specification at a government laboratory or such other facility specified in the contract.

4.2.1.2 Initial production sample failure.- Failure of the sample to comply with the requirements of the drawings and specifications shall result in sample disapproval. Determination as to acceptability of any initial production sample shall be based upon results of initial tests only, and no second tests shall be permitted on that initial production sample.

4.3 Inspection provisions.

4.3.1 Lot.

4.3.1.1 Submission of product.- The product shall be submitted in accordance with MIL-STD-105.

4.3.1.2 Lot identification.- Each lot of ammunition shall be identified as to type, caliber and model, as well as with a lot number in accordance with MIL-STD-1168. Each lot shall be further identified by a Federal Stock Number assigned by the procuring activity.

4.3.2 Examination.- Examination shall be performed as indicated below:

4.3.2.1 Bullet examination.- Prior to assembly into a cartridge, each bullet shall be weighed and visually examined for:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

4.3.2.1 (Cont'd)

a. Dents
b. Scratches
c. Split jacket
d. Scaly metal
e. Improperly formed or missing igniter
f. Improper basing
g. Upset or blunt points
h. Defective or missing cannelure
i. Weight
j. Presence of base closure seal

The presence of any one of these defects shall be casue for rejection of the bullet. The bullet weighings shall be accomplished on equipment capable of weighing over a range of 135 to 150 grains with an accuracy of 0.5 grains.

4.3.2.1.1 The bullets extracted from the cartridge in the bullet extraction test shall be examined for:

a. Split jacket
b. Missing igniter
c. Improper basing
d. Presence of base closure seal
e. Scaly metal

The presence of any one of these defects shall be cause for rejection of the cartridge lot.

4.3.2.2 Cartridge examination.- One hundred percent examination shall be performed for all critical defects. Examination for major and minor defects shall be performed on a class basis in accordance with the classification of defects, Table I, using applicable sampling plans and acceptance criteria of MIL-STD-105. The acceptable quality level (AQL) for the major class shall be 0.10 percent and the AQL for the minor class shall be 1.00 percent. All nonconforming cartridges shall be rejected.

4.3.2.3 Classification of defects.- The classification of defects shall be as specified in Table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

4.3.2.3 (Cont'd)

TABLE I

No.	Defect and Method of Inspection	Critical	Major	Minor	Major or Minor
	Visual 1/				
	Cartridge				
1	Discolored, dirty, oily, smeared			X	
2	Corroded; or stained, if etched		X		
	Case				
4	Round head		X		
5	Dent				X
6	Split case, any location	X			
7	Perforated case	X			
8	Draw scratch				X
9	Scratch			X	
10	Beveled underside of head		X		
11	Case mouth not crimped in cannelure		X		
12	Scaly metal				X
13	No chamfer on head (rim)		X		
14	Fold			X	
15	Wrinkle			X	
16	Buckle			X	
17	Bulge			X	
18	Illegible or missing head stamp			X	
19	Defective head			X	
20	Defective mouth			X	
21	No visible evidence of mouth anneal		X		
	Bullet				
22	Dent		X		
23	Scratch		X		
24	Split bullet jacket	X			
25	Loose bullet	X			
26	Missing cannelure		X		
27	Scaly metal (bullet)	X			
28	Upset (crooked point)		X		
30	Blunt point		X		
31	Defective cannelure		X		

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

4.3.2.3 (Cont'd)

No.	Defect and Method of Inspection	Critical	Major	Minor	Major or Minor
	Primer				
32	No primer	X			
33	Cocked primer	X			
34	Inverted primer	X			
35	Loose primer		X		
36	Nicked or dented primer			X	
37	No waterproofing material (primer pocket joint)			X	
38	Defective crimp			X	
	Gaging				
39	Total length		X		
40	Cartridge profile failure (requiring more than 20 lbs dead weight to insert in profile and alignment gage)		X		
41	Diameter of extractor groove, max		X		
42	Diameter of extractor groove, min			X	
43	Diameter of head		X		
44	Thickness of head		X		
45	Length to shoulder datum		X		
46	Depth of primer		X		
	Weighing				
47	Weight, min.	X			

1/ Refer to MIL-STD-636 for visual defect standards 1 through 38. In the event of conflict between Table I of this specification and MIL-STD-636 as to defect classification, the classification specified in Table I shall apply.

4.3.3 Tests.- The tests listed in Table II shall be conducted in accordance with the methods and procedures specified in 4.4.

4.3.3.1 Test samples.- The quantities for the various tests shall be as specified in Table II. Only cartridges having met the visual, dimensional and weight requirements shall be used in the ballistic tests, and shall have been selected in such a manner that the sample is representative of the entire lot. The cartridges shall be thoroughly mixed before being divided into samples for the various tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

4.3.3.1 (Cont'd)

TABLE II

Test	Ambient Temperature	70 + 2 F	Low Temperature (See 4.4.9.1)	High Temperature (See 4.4.9.2)	Requirement Paragraph
Bullet extraction 1/	50				3.2
Residual stress (mercurous nitrate) 1/	50				3.3
Waterproof 2/	50				3.4
Accuracy 7/	90				3.5
Trace 4/	100				3.6
Action time 1/		50			3.7
Velocity 5/		20	20	20	3.8 and 3.10
Chamber pressure 5/		20	20	20	3.9 and 3.10
Function and casulty 6/					3.10 and 3.11
Gun, Machine 7.62mm, M60	600		200	200	
Rifle, 7.62mm, M14	240		240	240	
Bullet integrity 9/	-				3.12
Port pressure 3/		20			3.13
Grain configuration 1/	10				3.14
Hardness					
Head 8/	10				Drawing
Sidewall 3/	10				Drawing

1/ Failure of two or more cartridges to comply with the applicable requirement shall be cause for rejection of the lot. If one cartridge fails in the first test, a second sample consisting of double the number of cartridges in the first sample, shall be tested. If any failing cartridges are found in the second sample the lot shall be rejected.

2/ Failure of ten or more cartridges to comply with the applicable requirement shall be cause for rejection of the lot. If more than three but less than ten cartridges fail in the first test, a second sample consisting or double the number of cartridges in the first sample shall be tested. The lot shall be rejected if, in the combined first and second sample, ten or more cartridges fail to comply with the applicable requirement.

3/ Failure of the cartridges to comply with the applicable requirement shall be cause for rejection of the lot subject to testing of a second sample consisting of double the quantity of cartridges used in the first test. Failure of the cartridges in the second sample to comply with the applicable requirement shall be cause for rejection of the lot.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

4.3.3.1 (Cont'd)

4/ The lot shall be rejected if more than twenty shots fail to comply with the applicable requirements. No second sample permitted.

5/ Failure of the cartridges in any sample to comply with the applicable requirement shall be cause for rejection of the lot subject to testing of a second sample consisting of double the quantity of cartridges used in the first test for the temperature or temperatures at which the failure occurred. Failure of the cartridges of the second sample to comply with the applicable requirement shall be cause for rejection of the lot.

6/ The lot shall be rejected when function and casulty defects plus firing defects observed in all other firing tests exceed the acceptance number for the cumulative sample in Table III. If the number of defects found in the first test exceed the acceptance number for the first sample, but is equal to or less than the acceptance number for the cumulative sample, a second sample, consisting of double the quantities specified under function and casulty test, shall be fired in all the service weapons specified therefor. This procedure shall apply regardless of the weapon or weapons in which the firing defects occurred in the first test. If the total number of defects in the combined first and second sample exceed the acceptance number for the cumulative sample the lot shall be rejected. If, in testing a second sample, defects other than those for which the second sample is being tested should occur to the extent that they exceed the acceptance number for the cumulative sample, the lot shall be rejected.

7/ Failure of two or more targets to comply with the extreme spread requirement shall be cause for rejection of the lot. If one target fails to meet the extreme spread requirement in the first test, a second sample consisting of double the number of targets in the first sample shall be tested. Failure of one or more targets of the second sample to comply with the requirement shall be cause for rejection of the lot. Failure of the cartridges to comply with the average mean radius requirement shall be cause for rejection of the lot subject to testing of a second sample consisting of double the quantity of cartridges used in the first test. Failure of the cartridges in the second sample to comply with the average mean radius requirement shall be cause for rejection of the lot.

8/ Failure of one or more cartridges to comply with the applicable requirements shall be cause for rejection of the lot. No second sample permitted.

9/ This test shall be performed in conjunction with the "Trace test". Failure of any cartridge to comply with the applicable requirement shall be cause for rejection of the lot. No second sample permitted.

4.3.3.2 Firing defects.- Firing defects and acceptance numbers shall be as specified in Table III.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

4.3.3.2 (Cont'd)

TABLE III

Defects	First Sample	Acceptance Number Cumulative (First and second samples)
1. Misfire 5/		
a. No vent hole, or obstruction in the vent area	0	-
b. Other	1	2
2. Bullet remaining in bore 1/	0	-
3. Primer		
a. Perforation in firing pin indent in primer cup		
(1) Machine guns 2/	0	-
(2) Rifles 2/	0	-
b. Escape of gas through primer cup other than 3.a	1	2
c. Escape of gas around primer cup		
(1) 50% or more than 50% of periphery	19	42
(2) Less than 50% of periphery	41	93
d. Blown primer	0	1
e. Primer falls out of pocket on retraction of bolt	0	1
f. Primer remains in pocket but is physically loose	2	5
4. Case casulties		
a. Longitudinal split 3/		
(1) Neck and shoulder (I and S)	41	93
(2) Body (J)	3	6
(3) Body (K)	0	1
(4) To head (L)	0	1
(5) Through head (M)	0	1
b. Circumferential rupture 3/		
(1) Partial, shoulder or body (J and S)	1	2
(2) Partial, body (K)	0	1
(3) Partial, head (L)	0	1
(4) Complete	0	1
5. Failure to extract	0	1
6. Weapon stoppage 4/	0	1
Total of defects 3.c (1), 3.c (2), and 4.a (1)	63	146
Total of all other listed defects	8	20

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

4.3.3.2 (Cont'd)

1/ No second sample permitted. Lot shall be rejected.

2/ If one or more defects are found in the first sample, a second sample shall be fired in the weapon(s) in which the defect occurred. The second sample shall consist of double the quantity of cartridges specified under function and casulty of Table II for such weapon(s). Prior to the testing of the second sample, the firing pin of the specific weapon(s) in which the defect originally occurred shall be replaced by a new firing pin. If an additional primer perforation is found in the second sample, the lot shall be rejected.

3/ For location of defects indicated by letters in parentheses, see Drawing C7643674.

4/ All stoppages attributable to the ammunition, with the exception of misfies, complete rupture, or failure to extract observed in all tests shall be included.

5/ Each cartridge that misfires shall be disassembled and examined for presence of vent hole in primer pocket or any obstruction, in the vent hole area of the primer pocket that can be assignable as the cause for misfire. If vent hole is missing or obstructed, the lot shall be rejected with mo second sample permitted.

4.3.4 Packaging, packing and marking.- During or immediately prior to the packaging operation, 100% examination of the cartridges shall be performed to ascertain that the cartridge type conforms to the drawing. Occurrence of any incorrect type shall be classed as a critical defect. All nonconforming cartridges shall be rejected. Inspection for packaging, packing and marking shall be in accordance with MIL-STD-644 as applicable to the drawing.

4.3.5 Inspection equipment.- Except as otherwise provided for by the contract, the contractor shall supply and maintain inspection equipment in accordance with the applicable requirements of MIL-I-45607. Simulated assessment of reference cartridges shall be made in accordance with AMCR 715-505, Vol. 3.

4.4 Test methods and procedures.

4.4.1 Bullet extraction.- The cartridges shall be tested in an approved bullet extractor machine. The rate of travel of the test head shall be not less than three nor more than six inches per minute. The test shall be conducted in accordance with AMCR 715-505, Volume 3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

4.4.2 Residual stress (mercurous nitrate).- Tests shall be conducted in accordance with AMCR 715-505, Volume 3.

4.4.3 Waterproof.- The tests shall be conducted in accordance with AMCR 715-505, Volume 3. The container shall be evacuated to a pressure of 7-½ pounds per square inch (15 inches of mercury) below atmospheric pressure, and held at that pressure for 30 seconds.

4.4.4 Accuracy.- The test shall be conducted in accordance with AMCR 715-505, Volume 3, utilizing the longest range available up to 600 yards. Ranges shorter than 200 yards shall not be used. When accuracy testing is conducted on ranges shorter than 600 yards, the average of the mean radii of the targets and the extreme spread of each target shall be multiplied by the applicable conversion factor given below:

Range (yards)	200	300	400	500
Factor	3.15	2.08	1.57	1.25

4.4.5 Trace.- The test shall be conducted in accordance with AMCR 715-505, Volume 3. Observation for bullet bursting shall be made during performance of this test in accordance with Appendix "A" (Bullet Integrity Test Procedure).

4.4.6 Action time.- The test shall be conducted in accordance with AMCR 715-505, Volume 3.

4.4.7 Velocity.- The tests shall be conducted in accordance with AMCR 715-505, Volume 3.

4.4.8 Chamber pressure.- The tests shall be conducted in accordance with AMCR 715-505, Volume 3.

4.4.9 Temperature tests.- The tests shall be conducted in accordance with AMCR 715-505, Volume 3. The weapon or weapons in which these tests are fired shall be at room temperature. Velocity and pressure difference shall be determined by firing twenty cartridges, conditioned at 68° to 72° F, for a minimum of two hours, from the same lot of ammunition, immediately prior to firing the cartridges conditioned as specified below.

4.4.9.1 Low temperature tests.- The test sample shall be stored at minus 65° F, plus or minus 5° F, for not less than 6 hours and shall be fired at that temperature.

4.4.9.2 High temperature tests.- The test sample shall be stored at plus 125° F, plus or minus 2° F, for not less than 4 hours and shall be fired at that temperature.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

4.4.10 Function and casulty.- The test shall be conducted in accordance with AMCR 715-505, Volume 3. Two machine guns and two rifles shall be used and the following number of cartridges shall be fired in each weapon:

	Rifle	Machine Gun
Ambient temperature	120	300
Low temperature	120	100
High temperature	120	100

4.4.11 Bullet integrity.- The test shall be conducted in accordance with Appendix "A". Any bullet recorded as a "Blind" by down range observers either by absence of trace or absence of noise of passing bullet and accompanied by either detection of an abnormally loud report and bright flash by the observer at the gun position or by the presence of any irregularly shaped hole in the screen, shall be considered as a bursting or stripped bullet.

4.4.12 Port pressure.- The test shall be conducted in accordance with AMCR 715-505, Volume 3.

4.4.13 Grain configuration.- The test sample shall be prepared and evaluated in accordance with MIL-STD-1170.

4.4.14 Hardness testing.- The bullets shall be extracted, the propellant removed and the primers extracted. Each cartridge case of the sample shall be prepared and placed on the appropriate test fixture for testing in accordance with Federal Test Method Standard No. 151, Method 244.1.

4.4.14.1 Case sidewall.- The average of the hardness values of the sample cases for each prescribed point along the sidewall exterior surface shall be computed and charted in accordance with the drawing requirements.

4.4.14.2 Case head.- The individual hardness value for each prescribed point on the head section of each sample case shall be recorded. Any value failing to meet the drawing requirement at a prescribed point(s) shall be cause for remeasurement of hardness at the corresponding point(s) on the opposite side of the primer pocket of the same head section from which the initial value was obtained. The higher of the two measurements shall be regarded as the value of record for determination of conformance to drawing requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

4.4.15 Defect penalty.- In any ballistic test, except function and casulty, in which the occurrence of a firing defect listed in Table III prevents the obtaining of a reliable result for the characteristic being tested, an additional shot shall be fired. That particular test shall not be penalized, but the total ballistic sample shall be penalized for such defects in accordance with Table III. Any abnormal condition not described herein shall be recorded and evaluated by the procuring agency prior to acceptance of the ammunition lot.

5. PREPARATION FOR DELIVERY

5.1 Packing, Level A. (Worldwide shipment).- The cartridges shall be packed in accordance with Drawing F10523087.

5.2 Marking and labeling.- Packing boxes shall be marked and labeled in accordance with the applicable drawing cited in 5.1.

6. NOTES

6.1 Ordering data.- Invitations for bids and contracts or orders will specify the following:

6.1.1 Title, number and date of this specification.

6.1.2 Type and level of packing.

6.1.3 Provision for the supply, maintenance and disposition of mandatory ballistic test equipment for acceptance inspection purposes.

6.1.4 Provision for the submission of acceptance inspection reports containing final inspection results for each lot of ammunition presented to the Government.

6.1.5 Provision for the identification and submission of grain configuration photomicrographs prepared in accordance with MIL-STD-1170 where submission is required.

6.1.6 Requirement for contractor to provide and maintain an inspection system in accordance with MIL-I-45608, Inspection System Requirement.

6.2 Document Availability.

6.2.1 Copies of MIL-STD-1170, required for evaluating grain configuration may be obtained on a need-to-have basis through the Commanding Officer, U.S. Army, Frankford Arsenal, Philadelphia, Pennsylvania 19137.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

6.3 Hazard notice.- The cartridge described herein and certain of its components are flammable and/or explosive and consequently present hazards in manufacture, handling, storage and shipment. The contractor should recognize these hazards and take appropriate measures to guard and protect against fire, explosion, adverse environment, corrosive atmosphere, rough handling and electrically induced incidents.

Custodian:

Army - MU

Preparing Activity:

Army - MU

Project No. 1305-A670

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

APPENDIX "A"

Bullet Integrity Test Procedure

1.0 Equipment

1.1 Equipment listed in the Trace section of the Inspection Equipment List shall be used.

1.2 Target screen, 6'x6', shall be placed 50 feet from the muzzle of the gun, in the line of fire.

2.0 Observation Points

2.1 The three observers used for the Trace test shall also observe for the Bullet Integrity Test.

3.0 Test Procedure

3.1 Preparation for firing

3.1.1 Preparation for firing shall be in accordance with AMCR 715-505, Volume 3, Chapter 1, Section 17.

3.1.2 Prior to each test, the gun to be used for the test shall be inspected. Gun shall be in clean condition, chamber and bore of the barrel shall also be clean.

3.1.3 Target screen, referenced in para. 1.2, shall be placed in specified position, so that bullets pass through the screen at its center.

3.2 Firing the test.

3.2.1 Test shall be fired in accordance with AMCR 715-505, Volume 3, Chapter 1, Section 17.

3.2.2 Each observer shall keep a shot-by-shot record. In addition to recording trace performance of each bullet, observers shall also record any abnormalities observed, e.g., large flash, loud report, erratic flight, absence of noise of passing bullet at terminal point, etc. Observers shall record performance of each bullet in order to compare records upon completion of the test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

3.2.3 The target screen shall be examined after each series of 20 rounds or anytime a suspect bursting or stripped bullet is encountered. Screen shall be renewed as often as is necessary to assure positive identification of bursting or stripped bullets.

4.0 Recording of data.

4.1 Upon completion of the test, the observers shall check their respective observations together, shot by shot. All observations shall be reported.

4.1.1 Suspect shots shall be reported by each observer, as follows:

a. Loud report
b. Large flash
c. Lack of trace
d. Erratic flight
e. Shot number

4.1.2 Target screen observations shall be reported as follows:

a. Number of holes
b. Location of holes
c. Type of holes

4.1.3 The test results are reported as follows:

a. Number of cartridges fired
b. Number and type of defects
c. Number and type of case casulties

4.1.4 The following test weapon data shall be recorded on the test sheet:

a. Receiver number
b. Barrel number
c. Total number of cartridges fired in barrel prior to test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

[ ] YES [ ] NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.