MIL-P-60523A (AR)
18 May 1979

SUPERSEDING
MIL-P-60523
16 May 1966

MILITARY SPECIFICATION

PROJECTILE, 165MM, HEP M123A1, METAL PARTS

This specification is approved for use by the US Army Armament Research and Development Command, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers Projectile, 165MM, HEP, M123A1, Metal Parts.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

PPP-F-320	Fiberboard, Sheet Stock and Cut Shapes
PPP-B-636	Box, Fiberboard

MILITARY

MIL-I-6868	Inspection Process, Magnetic Particle
MIL-C-45467	Cartridge, 165MM, HEP, M123A1, Loading Assembly and Packing
MIL-A-48078	Ammunition, Standard Quality Assurance Provisions, General Specification For

FSC: 1315

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Armament Research and Development Command, Attn. DRDAR-QA, Dover, New Jersey 07801 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

STANDARDS

MILITARY

MIL-STD-410	Nondestructive Testing Personnel Qualification and Certification
MIL-STD-1169	Packaging, Packing and Marking of Inert Ammunition Components

DRAWINGS

US ARMY ARMAMENT RESEARCH AND DEVELOPMENT COMMAND

9327406	Projectile, 165MM, HEP, M123A1, Metal Parts
8837835	Pallet for Fixed and Semifixed Shells
8845042	Cartridge, 165MM, HEP, M123A1, Loading Assembling and Packing
9327415	Envelope Drawing for Magnetic Particle Standard for M123 Body

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the Contracting Officer).

2.2 Other publications.-The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

ANSI-B46.1 Surface Texture

(Application for copies should be addressed to the American National Standard Institute (ANSI), 1430 Broadway, New York, N.Y. 10018).

ASTM E8	Tension Testing of Metallic Materials
ASTM E18	Tests for Rockwell Hardness and Rockwell Superficial Hardness for Metallic Materials
ASTM B117	Salt Spray (Fog) Testing

(Application for copies should be addressed to the American Society for Testing and Materials (ASTM), 1916 Race Street, Philadelphia, Pa 19103).

3. REQUIREMENTS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

3.1 General.-Materials, parts and assemblies shall comply with the requirements specified on the applicable drawings and referenced specifications.

3.2 Stress relief.-Projectile bodies shall be stress-relieved at a minimum temperature of 750 degrees F, for a period of one hour, minimum, following the completion of all cold work operations. Stress relief shall be uniform throughout and shall be so conducted as to produce the mechanical properties specified on the applicable drawing.

3.3 Mechanical properties.-The mechanical properties specified on the applicable drawings shall apply for the projectile body and the base plug.

3.4 Surface preparation and application of protective finish.-Where cleaning and surface pretreatment are required by component details, the process shall apply to all indicated surfaces regardless of contour configuration. The protective finish shall be as specified on the applicable drawings and shall be uniformly applied to the surfaces designated by the applicable drawings. Salt spray and other required testing shall be in accordance with the applicable drawings and specifications.

3.5 Defective raw material and metal parts components

3.5.1 Billet.-The billet shall be free from cracks, splits, cold shuts, inclusions, pipe, porosity, folds, bursts, seams, and other metal defects.

3.5.2 Projectile body and body cavity.-The projectile body, including the body cavity, shall be free from seams, cracks, splits, stringers, laps, folds, slugs, porosity, dents, scale, fins, internal burrs, draw marks, laminations, imbedded foreign matter, pits, and sharp edges.

3.5.3 Base plug.-The base plug shall be free from cracks, folds or other metal defects.

3.5.4 Visual standards.-Visual standards depicting maximum acceptable degrees of conditions described in 3.5.1, 3.5.2 and 3.5.3 will be established for each contract after the first month's or lot's production, whichever quantity is smaller. In the absence of a visual standard, the requirements of 3.5.1, 3.5.2 and 3.5.3 shall apply (see 6.5).

3.6 Proving ground tests.-The assembled projectile metal parts shall be safe to fire and shall reveal no evidence of failure when tested as specified in 4.5.5. Metal parts failure shall be:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

a. Loss or break-up of metal parts components during gun launch or flight.

b. Loose or fanning of rotating band(s).

c. Shear of rotating band(s) as evidenced by complete lack of engraving.

d. Leakage of propellant gases into base plug thread area.

3.7 First article inspection.-This specification contains technical provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

3.8 Workmanship.-The requirements for workmanship are as shown on the applicable drawings, in the applicable specifications and the following.

3.8.1 Threads.-Threads shall be full and undamaged for the entire minimum length or depth as required on the applicable drawing and shall be in accordance with the provisions of MIL-A-2550.

3.8.2 Burr.-No parts shall have a burr.

3.8.3 Foreign matter.-All parts and assemblies shall be free of chips, dirt, grease, rust, corrosion or other foreign matter.

3.8.4 Rotating band damage.-The rotating band after machining shall be protected from being nicked, burred or otherwise damaged during subsequent handling and preparation for shipment.

3.8.5 Painting and marking.-Painting and marking shall be applied in accordance with the applicable drawings and specifications. The rotating band and threads of the projectile body shall be covered in a manner which will prevent the application of paint to these surfaces.

4. QUALITY ASSURANCE

4.1 Responsibility for inspection and standard quality assurance provisions.-Unless otherwise specified herein of in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this detail specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

4.2 Classification of inspections.-The following types of inspection shall be performed on this item:

a. First Article Inspection

b. Quality Conformance Inspection

4.3 First article inspection

4.3.1 Submission.-The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation with the provisions of 4.3.2. The first article sample shall consist of the following items in the sample quantities indicated.

Part Description	Drawing	Quantity
Base Plug	8845045	85
Body (Unpainted)	8845046	35
Body Assembly	9327406	80

4.3.2 Inspections to be performed.-See MIL-A-48078 and Table specified herein.

4.3.3 Rejection.-See MIL-A-48078.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

TABLE I - FIRST ARTICLE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
	Projectile, 165MM, HEP, M123A1, Metal Parts	1 OF 1	See Below
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Body (Unpainted) (Dwg. 8845046)				
	Examination for defects	25		3.1	4.4.2.2, 4.4.2.3, 4.4.2.4
	Hardness of nose	5		3.3	4.5.1.1
	Bourrelet mechanical properties	5		3.3	4.5.1.2
	Body Assembly (painted) (Dwg. 9327406)				
	Examination for defects	25		3.1	4.4.2.5
	Salt spray test	5		3.4	4.5.4
	Base Plug (Dwg. 8845045)				
	Examination for defects	25		3.1	4.4.2.6
	Mechanical properties	5		3.3	4.5.1.3
	Salt spray test	5		3.4	4.5.4
	Ballistic Test ($70^{o} \pm 2.5^{o}F$)				
	Service pressure phase	25		3.6	4.5.5.1, 4.5.5.3
	Overpressure - recovery phase	25		3.6	4.5.5.2, 4.5.5.3

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection

4.4.1 Inspection lot formation.-Inspection lots shall comply with the lot formation provisions of MIL-A-48078.

4.4.1.1 Stress relieved lots.-Stress relieved lots shall contain cold worked bodies from not more than one heat of steel that have been cold worked by the same process, utilizing the same tooling and equipment and stress relieved in the same furnace at the same temperature for the same length of time. The stress relieved lot thus constituted shall be the basis for the selection of samples for the mechanical properties test hereinafter prescribed.

4.4.1.2 Projectile lots.-When it has been determined that bodies of a stress relieved lot has complied with the mechanical properties requirement of the applicable drawing, they may be re-grouped for assembly into projectile lots, to which will be assigned a projectile lot number. The projectile lot shall consist of bodies and base plugs produced by one supplier under one contract in one unchanged process, in accordance with the same drawing, same drawing revision, same specification and same specification revision, under conditions of continuous production free from interruptions other than those due to the end of shift, day, or workweek. The projectile lot thus constituted shall be the basis for the selection of sample for the functional tests hereinafter prescribed.

4.4.2 Examination.-See MIL-A-48078.

a. Sampling plans.-Unless otherwise specified in the Classification of Defects and Tests tables, sampling plans and procedures shall be in accordance with MIL-STD-105, Inspection Level II.

4.4.2.1 Visual inspections.-In the event of a dispute, four power (4X) magnification shall be used in performing visual inspections for defects such as burrs and foreign matter. The roughness comparison specimens prescribed by ANSI - B46.1 shall be used as a basis for surface roughness determination.

4.4.2.1.1 Defect reporting.-The contractor shall prepare a monthly report of all critical defects found, including the number of projectile metal parts inspected and corrective action taken, in accordance with Data Item Description DI-R-1721, and deliver them as specified in the contract.

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:21Z
Check the source to verify that this is the current version before use.

4.4.2.1.2 Control tool manufacture.-Dimensions marked tool control shall be gaged at the beginning of each eight hours production or fraction thereof from each machine in operation and prior to any tooling change. Where destruction of components is necessary to inspect these dimensions, measurements of the tool may be substituted, provided the contractor has established correlation between the tool dimensions and the component dimensions prior to the start of production. The contractor shall be responsible for maintaining adequate surveillance to assure that drawing requirements are being met throughout the life of the tool. All material produced prior to periodic inspection will be rejected whenever a defective tool control dimension is found.

4.4.2.1.3 Inspection of slug prior to drawing.-Each slug obtained from a billet or bloom shall be visually inspected for surface indications of cracks, splits, pipe, porosity, folds, seams and other metal defects visible to the unaided eye on all exterior surfaces of the slug. Visual standards may be selected to aid in the determination of a slug's acceptability.

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:21Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-60523A (AR)

PARAGRAPH	TITLE	SHEET 1 OF 1	DRAWING NUMBER
4.4.2.2	Body, Prior to Machining		8845046
			NEXT HIGHER ASSEMBLY
			9327406

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical					
1	Metal defective			3.5.2	Visual
2	Magnetic particle inspection			3.1	Test/4.5.6
Major					
101	Hardness of nose	(a)		3.3	Test/4.5.1.1
102	Mechanical properties of bourrelet	(b)		3.3	Test/4.5.1.2
Minor	None defined				

NOTES: a. See 4.4.3.1.1
b. See 4.4.3.1.2

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-60523A (AR)

PARAGRAPH	TITLE	SHEET 1 OF 1	DRAWING NUMBER
4.4.2.3	Body, Prior to Application of Rotating Band		8845046
			NEXT HIGHER ASSEMBLY 9327406

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical					
1	Magnetic particle inspection acceptance stamp missing			3.1	Visual
Major					
101	Diameter of rotating band seat (if applicable)		0.40%	3.1	Gage
102	Length from shoulder to front of band seat (if applicable)		0.40%	3.1	Gage
103	Foreign matter on band seat (if applicable)		0.40%	3.8.3	Visual
Minor					
201	Length from shoulder to rear of rotating band seat (if applicable)		0.65%	3.1	Gage
202	Presence of burr		0.65%	3.8.2	Manual
203	Foreign matter, except as otherwise classified		0.65%	3.8.3	Visual
204	Evidence of poor workmanship		0.65%	3.8	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-60523A (AR)

PARAGRAPH	TITLE	SHEET 1 OF 3	DRAWING NUMBER
4.4.2.4	Body, Prior to Painting		8845046
			NEXT HIGHER ASSEMBLY
			9327406

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical					
1	Hydrostatic test			3.1	Test/4.5.2
2	Air pressure test			3.1	Test/4.5.3
3	Metal defective			3.5.2	Visual
Major					
101	Runout of pitch diameter of external thread with bourrelet and shoulder		0.40%	3.1	Gage
102	Runout of pitch diameter of internal thread with bourrelet and shoulder		0.40%	3.1	Gage
103	True position of caulking groove with pitch diameter of internal thread		0.40%	3.1	Gage
104	True position of counterbore with pitch diameter of internal thread		0.40%	3.1	Gage
105	Runout of rotating band flat with bourrelet		0.40%	3.1	Gage
106	Diameter of bourrelet, min.		0.40%	3.1	Gage
107	Body diameter rear of rotating band		0.40%	3.1	Gage
108	Diameter of rotating band		0.40%	3.1	Gage
109	Length from rear face to shoulder		0.40%	3.1	Gage
110	Length from shoulder to rear undercut of rotating band, max. (if applicable)		0.40%	3.1	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-60523A (AR)

PARAGRAPH	TITLE	SHEET 2 OF 3	DRAWING NUMBER
4.4.2.4	CONTINUATION SHEET		8845046
			NEXT HIGHER ASSEMBLY
			9327406

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
111	Length from shoulder to forward undercut of rotating band, min. (if applicable)		0.40%	3.1	Gage
112	Length from shoulder to forward edge of rotating band flat		0.40%	3.1	Gage
113	Thickness of wall at nose		0.40%	3.1	Gage
114	Thickness of wall at datum length (from ogive)		0.40%	3.1	Gage
115	Thickness of wall at rear datum		0.40%	3.1	Gage
116	Wall thickness variation improper		0.40%	3.1	Gage
117	Width of rotating band flat		0.40%	3.1	Gage
118	Profile of rotating band		0.40%	3.1	Gage
119	Profile of nose (after hydrostatic and air tests)		0.40%	3.1	Gage
120	Pitch diameter of internal thread, max.		0.40%	3.1	Gage
121	Minor diameter of internal thread, max.		0.40%	3.1	Gage
122	Pitch diameter of external thread, min.		0.40%	3.1	Gage
123	Major diameter of external thread, min.		0.40%	3.1	Gage
124	Surface finish of cavity improper		0.40%	3.1	Manual
125	Length of effective internal thread, min.		0.40%	3.1	Gage
126	Thread(s) damaged or not full		0.40%	3.8.1	Visual
Minor					
201	Pitch diameter of internal thread, min.		0.65%	3.1	Gage
202	Pitch diameter of external thread, max.		0.65%	3.1	Gage
203	Length of internal thread, max.		0.65%	3.1	Gage
204	Diameter of caulking groove		0.65%	3.1	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T04:21Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-60523A (AR)

PARAGRAPH	TITLE		SHEET 3 OF 3		DRAWING NUMBER
4.4.2.4	CONTINUATION SHEET				8845046
					NEXT HIGHER ASSEMBLY
					9327406
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
205	Diameter of counterbore		0.65%	3.1	Gage
206	Diameter of internal thread chamfer		0.65%	3.1	Gage
207	Diameter of external thread chamfer		0.65%	3.1	Gage
208	Diameter of external thread undercut		0.65%	3.1	Gage
209	Diameter of cavity forward of internal thread		0.65%	3.1	Gage
210	Depth of caulking groove		0.65%	3.1	Gage
211	Depth to bottom of counterbore		0.65%	3.1	Gage
212	Length, total		0.65%	3.1	Gage
213	Width of external thread undercut		0.65%	3.1	Gage
214	Depth of undercut front and rear of rotating band (if applicable)		0.65%	3.1	Gage
215	Width of undercut front and rear of rotating band (if applicable)		0.65%	3.1	Gage
216	Surface finish improper (except as otherwise specified)		0.65%	3.1	Manual
217	Foreign matter present		0.65%	3.8.3	Visual
218	Presence of burr		0.65%	3.8.2	Manual
219	Radii missing or incorrect		0.65%	3.1	Visual
220	Chamfer missing or incorrect		0.65%	3.1	Visual
221	Marking missing, incorrect or illegible		0.65%	3.1	Visual
222	Evidence of poor workmanship		0.65%	3.8	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-60523A (AR)

PARAGRAPH	TITLE	SHEET 1 OF 1	DRAWING NUMBER
4.4.2.5	Body, After Painting		9327406
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical					
1	Metal defective			3.5.2	Visual
2	Any required inspection stamp missing			3.1	Visual
Major					
101	Diameter of bourrelet, max.		100%	3.1	Gage
102	Weight		0.40%	3.1	Balance
103	Salt spray resistance	(a)		3.4	Test/4.5.4
104	Ballistic test	(b)		3.6	Test/4.5.5
Minor					
201	Paint on threads				
202	Surface preparation or protective coating on interior or exterior surface missing or improperly applied		0.65%	3.8	Visual
203	Paint on rotating band bearing surface		0.65%	3.4	Visual
204	Foreign matter present		0.65%	3.8	Visual
205	Presence of burr		0.65%	3.8.3	Visual
206	Protective cap missing		0.65%	3.8.2	Manual
207	Evidence of poor workmanship		0.65%	3.1	Visual
			0.65%	3.8	Visual

NOTES:
a. See 4.4.3.2
b. See 4.4.3.3

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026l0-26T04:21Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-60523A (AR)

PARAGRAPH	TITLE	SHEET 1 OF 3	DRAWING NUMBER
4.4.2.6	Base Plug		8845045
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical					
1	Metal defective			3.5.3	Visual
2	Magnetic particle inspection (prior to final machining)			3.1	Test/4.5.6
3	Magnetic particle inspection acceptance stamp missing from front face (prior to packing)			3.1	Visual
Major					
101	Runout of pitch diameter of external thread with pitch diameter of internal thread and base of internal thread counterbore		0.40%	3.1	Gage
102	Runout of flange diameter with pitch diameter of internal thread and base of internal thread counterbore		0.40%	3.1	Gage
103	True position of recess diameter with pitch diameter of internal thread and base of internal thread counterbore		0.40%	3.1	Gage
104	True position of boss diameter with pitch diameter of internal thread and base of internal thread counterbore		0.40%	3.1	Gage
105	Runout of caulking groove with pitch diameter of internal thread and base of internal thread counterbore		0.40%	3.1	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET 2 OF 3	DRAWING NUMBER
4.4.2.6	CONTINUATION SHEET		8845045
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
106	Runout of diameter of thread counterbore with pitch diameter of internal thread and base of internal thread counterbore		0.40%	3.1	Gage
107	Pitch diameter of external thread, min.		0.40%	3.1	Gage
108	Major diameter of external thread, min.		0.40%	3.1	Gage
109	Pitch diameter of internal thread, max.		0.40%	3.1	Gage
110	Minor diameter of internal thread, max.		0.40%	3.1	Gage
111	Diameter of flange		0.40%	3.1	Gage
112	Diameter at datum length on caulking groove		0.40%	3.1	Gage
113	Depth of recess		0.40%	3.1	Gage
114	Length from rear face to front of flange		0.40%	3.1	Gage
115	Thread(s) damaged or not full		0.40%	3.1	Visual
116	Mechanical properties	(a)		3.3	Test/4.5.1.3
117	Salt spray resistance	(b)		3.4	Test/4.5.4
118	Ballistic test	(c)		3.6	Test/4.5.5
Minor					
201	Pitch diameter of external thread, max.		0.65%	3.1	Gage
202	Pitch diameter of internal thread, min.		0.65%	3.1	Gage

NOTES:
a. See 4.4.3.1.3
b. See 4.4.3.2
c. See 4.4.3.3

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-60523A (AR)

PARAGRAPH	TITLE		SHEET 3 OF 3		DRAWING NUMBER
4.4.2.6	CONTINUATION SHEET				8845045
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
203	Diameter of small caulking groove		0.65%	3.1	Gage
204	Diameter of internal thread counterbore		0.65%	3.1	Gage
205	Diameter of external thread undercut		0.65%	3.1	Gage
206	Diameter of external thread chamfer		0.65%	3.1	Gage
207	Diameter of recess		0.65%	3.1	Gage
208	Diameter of boss		0.65%	3.1	Gage
209	Diameter of internal thread chamfer, max. (front)		0.65%	3.1	Gage
210	Diameter of internal thread chamfer (rear)		0.65%	3.1	Gage
211	Depth to bottom of small caulking groove		0.65%	3.1	Gage
212	Depth to bottom of internal thread counterbore		0.65%	3.1	Gage
213	Depth of flat at small caulking groove, max. (if applicable)		0.65%	3.1	Gage
214	Length, total		0.65%	3.1	Gage
215	Thickness of flange		0.65%	3.1	Gage
216	Width of external thread undercut		0.65%	3.1	Gage
217	Location of wrench holes at recess		0.65%	3.1	Gage
218	Diameter of wrench holes		0.65%	3.1	Gage
219	Surface finish improper		0.65%	3.1	Manual
220	Radii missing or incorrect		0.65%	3.1	Visual
221	Chamfer missing or incorrect		0.65%	3.1	Visual
222	Depth to choulder of recess from rear face		0.65%	3.1	Gage
223	Surface preparation or protective coating missing or improperly applied		0.65%	3.4	Visual
224	Presence of burr		0.65%	3.8.2	Manual
225	Foreign matter present		0.65%	3.8.3	Visual
226	Marking missing, incorrect or illegible		0.65%	3.1	Visual
227	Evidence of poor workmanship		0.65%	3.8	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T04:24Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.7	Carton, Packing, Prior to Sealing				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major	None defined				
Minor					
201	Any support missing or damaged		0.65%	3.1	Visual
202	Separator(s) missing or damaged		0.65%	3.1	Visual
203	Contents improperly packed		0.65%	3.1	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-60523A (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.8	Cartons, Packed, After Sealing				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major	None defined				
Minor					
201	Contents loose		0.65%	3.1	Manual
202	Carton damaged, cut or gouged through all layers		0.65%	3.1	Visual
203	Carton not properly sealed		0.65%	3.1	Visual
204	Marking missing, incorrect or illegible		0.65%	3.1	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-60523A (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.9	Pallet	1 OF 1	8837835
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major	None defined				
Minor					
201	Strapping missing, broken or loose		0.65%	3.1	Visual/Manual
202	Pallet damaged		0.65%	3.1	Visual
203	Improperly packed		0.65%	3.1	Visual
204	Marking missing, improper or illegible		0.65%	3.1	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

4.4.3 Testing

4.4.3.1 Mechanical properties

4.4.3.1.1 Hardness.-Twenty five projectile bodies from the first batch of each stress-relieved lot as defined herein shall be subjected to a Rockwell Hardness test or any other method of testing satisfying the provisions of 4.4.4, using the procedure of 4.5.1.1. Following satisfactory compliance of this initial sample with the requirements of dwg. 9327406, five projectile bodies from each batch of stress-relieved lot shall be subjected to this test. If two or more projectile bodies of a sample fail to meet the hardness requirement on dwg. 9327406, the batch represented by that sample shall be rejected and a new stress-relieved lot is to be established and qualified as prescribed herein, beginning with the batch that was rejected when under reduced sampling.

4.4.3.1.2 Tensile strength of bourrelet.-Two projectile bodies of the twenty five bodies selected from the first batch of a stress relieved lot for the hardness test in 4.4.3.1.1 shall be subjected to this test. Following satisfactory compliance of this initial sample with the requirements of dwg. 8845046, two projectile bodies from every five batches of a stress-relieved lot shall be selected for this test. Failure of any tensile strength specimen to meet the yield strength and elongation requirements of dwg. 8845046 shall reject the batch of stress-relieved bodies which that sample represents and shall require the establishment of a new stress-relieved lot as prescribed in 4.4.3.1.1.

4.4.3.1.3 Tensile strength of base plug.-Two base plugs from the first batch of a stress-relieved lot shall be tested for compliance with the yield strength and elongation requirements specified on dwg. 8845045. Following the establishment of a base plug stress relieved-lot, two base plugs from every five stress-relieved batches shall be subjected to this test. Failure of any base plug tensile specimen to comply with the requirements of dwg. 8845045 shall reject the batch of base plugs represented by the specimen and shall require the establishment of a new stress-relief lot. If stress-relief or heat treatment is not performed, two base plugs per five thousand base plugs shall be subjected to this tensile test.

4.4.3.2 Surface preparation and application of protective finish.-The sample size and acceptance criteria for the inspection of surface preparation and the application of protective finish shall be in accordance with the applicable specifications. Failure to comply with the applicable specification and drawing requirements shall be cause for taking the corrective action recommended therein (see 4.5.4).

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

4.4.3.3 Proving ground tests.-The following tests shall be performed as specified in 4.5.5. Any sample failing the safety criteria specified in 3.6 shall reject the lot represented by that sample.

4.4.3.3.1 Performance phase.-Beginning with the first three lots of projectile metal parts, twenty five samples shall be tested at service pressure. Sampling shall then revert to ten samples for each lot thereafter.

4.4.3.3.2 Overpressure - recovery phase.-Beginning with the first three lots of projectile metal parts, twenty-five samples shall be tested as specified in 4.5.5.2 at overpressure. Sampling shall then revert to ten samples for each lot thereafter. A post-firing examination shall be performed on each projectile following its recovery.

4.4.4 Inspection equipment.-The inspection equipment required to perform the examinations and tests prescribed herein is described in the "Paragraph Reference/Inspection Method" column in the tables starting with 4.4.2.2. The contractor shall submit for approval inspection equipment designs in accordance with the terms in the contract. See Section 6 of MIL-A-48078 and 6.2 herein.

4.5 Test methods and procedures

4.5.1 Mechanical properties

4.5.1.1 Hardness of nose ogive.-After final stress relief, but prior to finish machining, a Rockwell Superficial Hardness Test shall be performed on the samples provided by 4.4.3.1.1. The equipment and procedures for performing this test are prescribed by ASTM E18. Five equally spaced readings shall be taken along the ogive of the projectile at points one, four, and seven inches from the tip of the projectile body nose. Two equally spaced readings shall be taken at the center of the tip of the projectile body nose if the nose is welded or brazed as allowable by dwg. 8845046.

4.5.1.2 Tensile test of projectile body.-From the samples provided in accordance with 4.4.3.1.2, two tensile test specimens conforming to the largest obtainable standard specimen for tubular products, as prescribed by ASTM E8, shall be taken from opposite sides of the body in the minimum wall thickness area rear of the nose. The equipment and procedures for performing this test are prescribed by ASTM E8.

Source: https://assist.dla.mil -- Downloaded: 202640-26T04:21Z
Check the source to verify that this is the current version before use.

4.5.1.3 Tensile test of base plug.-From the samples provided in accordance with 4.4.3.1.3, one tensile test specimen conforming to the largest obtainable standard specimen, as prescribed by ASTM E8, shall be taken from each base plug. The equipment and procedures for performing this test are prescribed by ASTM E8.

4.5.1.4 The number of specimens and their location are for the convenience of the contractor and Government and shall not restrict the contractor or Government from testing additional specimens at other locations in order to determine that the mechanical properties of stress-relieved bodies or plugs meet the drawing requirements. The criteria for obtaining the specimens and performing these tests shall be as prescribed by ASTM E8, except that elongation shall be measured to the nearest thousandth (0.000) prior to conversion into percent elongation. Percent elongation shall be recorded to the nearest tenth (0.0 Percent).

4.5.2 Hydrostatic test.-The body assembly shall be hydrostatically pressure tested using equipment capable of performing the test accurately and consistently. The body shall be mounted on an approved test fixture complying with the requirements of dwg. 9327406 such that three inches of the nose remains unsupported. In performing the test, the hydrostatic pressure will be applied gradually until the required pressure is reached, after which the pressure will be held for thirty seconds, minimum. The test equipment must be capable of stamping an acceptance mark (H) for accepted bodies in the location required by dwg. 9327406. A fail-safe system of operation shall also be required (see 6.6).

4.5.2.1 Calibration.-The hydrostatic and air pressure test equipment (see 4.5.3.1) shall be calibrated prior to the start of each day's operation and at periods not exceeding four hours of continuous operation. It shall also be calibrated prior to the restarting of the operation after a layoff of two hours or more; or, following the completion of unscheduled repairs or maintainance. The contractor shall prepare a written standard operating procedure, to include the inspection of projectile bodies and calibration procedures, which must be reviewed and approved by the Contracting Officer prior to the submission of the first article sample (see 6.2).

4.5.3 Air pressure test.-The projectile body shall be subjected to this test using equipment capable of performing this test accurately and consistently. Prior to testing, each projectile shall be inspected for the presence of the hydrostatic pressure acceptance stamp and each projectile body shall be dried in accordance with the requirements of dwg. 9327406. The body shall be mounted in an approved fixture in a manner such that the body shall

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

be entirely submerged in water. Observation shall be made for air leakage from each projectile body, especially the nose area. In performing this test. The air pressure will be applied until the required air pressure is reached, after which the air pressure will be held for fifteen seconds, minimum. The test equipment must be capable of stamping an acceptance mark (A) for accepted bodies in the location required by dwg. 9327406. A fail-safe system operation shall also be required (see 6.6).

4.5.3.1 Calibration.-The air pressure test equipment shall be calibrated in accordance with the requirements of 4.5.2.1. The contractor shall prepare a written standard operating procedure, to include the inspection of projectile bodies and calibration procedures, which must be reviewed and approved by the Contracting Officer prior to the submission of the first article sample (see 6.2).

4.5.4 Surface preparation and application of protective finish.-The procedures for testing the cleaning and surface treatment methods for components and assemblies shall be in accordance with the methods and acceptance criteria for testing as specified in the applicable specification. A salt spray (fog) test shall be performed on projectile bodies and base plugs, utilizing the equipment and test procedures prescribed by ASTM - B117, in accordance with the requirements of the applicable drawings and specification.

4.5.5 Proving ground test.-The samples which are to be ballistically tested as prescribed herein shall be fired in a M135 gun. The ammunition in each phase shall be temperature conditioned to 70° ± 2.5°F until all propellant is stabilized at a uniform temperature prior to firing, which normally requires a period of twenty four hours, minimum. Adequate photographic equipment shall be used to assure satisfactory coverage of each test sample's integrity and flight from the gun muzzle to the first one hundred feet of projectile flight, minimum. Muzzle velocity and maximum chamber pressure shall be recorded for all rounds fired. All samples shall be observed for safety (see 6.4).

4.5.5.1 Performance phase.-The samples selected for this phase will be fired using the service velocity propellant charge in a gun tube with a fifty percent remaining life, minimum. Target impact dispersion data shall be taken, for information only, on a vertical cloth target. The target distance is to be 900 meters from the muzzle of the gun and the cloth target size is to be 6 meters by 6 meters, minimum. Spotter rounds are to be used to assure that the weapon is zeroed and aimed at the center of the target. An aiming point or stake may be used for this purpose. Target impact, including spotters shall be measured to the nearest one-half inch in both the horizontal and vertical distance from target center. The vertical and horizontal hit pattern results shall be expressed as probable errors in mils and shall be recorded on the firing record. Target miss coordinates will be estimated and recorded along with pertinent flight observations.

Source: https://assist.dla.mil -- Downloaded: 202640-26T04:21Z
Check the source to verify that this is the current version before use.

4.5.5.2 Overpressure - recovery phase.-The samples selected for this phase will be fired for recovery, using an adjusted propellant charge to obtain a minimum mean pressure of 5600 psi and a maximum individual pressure not to exceed 6000 psi, in a gun tube with twenty five percent remaining life, maximum. Following their firing and subsequent recovery, each projectile body shall be examined for evidence of splits or breakup (including separation of the cartridge case), shearing of the rotating band as evidenced by a complete lack of engraving, and gas leakage around the base plug threads (which requires disassembly). If projectile breakup or cartridge case separation is found and is attributable to ground impact, the firing record shall be so annotated. If a projectile is not recoverable, its photographic record of firing shall then be examined (see 6.4.1).

4.5.5.2.1 Projectile deformation (information only).-The following measurements of each projectile body's diameter shall also be taken before and after firing in two planes ninety degrees apart, with the first group of diametrical readings to be taken along the plane passing through the projectile metal parts lot interfix number: Directly behind the rotating band; directly forward of the rotating band; and, four, six and sixteen inches from the projectile body base.

4.5.5.3 Safety.-All samples fired in proving ground tests shall be observed for safety, in particular, the breakup of projectile metal parts. Any ballistic sample failing the safety criteria specified herein shall be cause for the cessation of the test phase in which the failure occurs, as well as, the remainder of the ballistic test and shall reject the projectile metal parts lot represented by that sample.

4.5.5.4 Assembly of test sample cartridges.-The projectile metal parts samples shall be assembled into cartridges in accordance with dwg. 8845042, and MIL-C-45467 except that an inert fill shall be substituted for the high explosive filler and an inertly-loaded or dummy M62A2 fuze shall be used.

4.5.6 Magnetic particle inspection.-The procedures for performing this test shall be as specified in MIL-I-6868 for indirect magnetization by either the continuous method of the residual method. Both circular and longitudinal magnetization shall be used. The solid content of suspension shall be maintained at 0.2 to 0.4 milliliter (ml) of solids per 100. ml of suspension when oil is used, or 0.15 to 0.35 ml of solids per 100ml of suspension when water is used. The suspension shall be checked at the start of each day's production and at intervals of not over four hours of operation, utilizing the procedures and equipment prescribed by

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

Section 4 of MIL-I-6868. When performing the test for solid content of the suspension and it is determined that the solids content does not comply with the requirements prescribed herein, all projectile bodies and base plugs that have been tested and accepted since the last satisfactory test was performed shall be retested after the suspension's solids content has been brought to the proper level.

4.5.6.1 Verification of inspection method.-The magnetic particle inspection method for projectile bodies shall be verified using a standard fabricated in accordance with dwg. 9327415 prior to the start of each day's production and at periods not exceeding four hours of continuous operation. When using the verification standard and the defects are not indicated, all projectile bodies and base plugs that have been tested and accepted since the last satisfactory verification was performed, shall be retested after the correction action prescribed by the applicable specification has been accomplished and the inspection equipment is once again qualified by the verification prescribed herein. The contractor shall prepare a written standard operting procedure, to include: the inspection of projectile bodies and base plugs; and the preparation and use of a base plug verification standard, which must be reviewed and approved by the Contracting Officer prior to the submission of the first article sample (see 6.2).

4.5.6.2 Residual magnetism.-Each projectile body and base plug, including the verification standards, shall be de-magnetized following their inspection. The amount of residual mannetism shall be as prescribed in MIL-I-6868 and shall be checked at a frequency of five projectile bodies or base plugs per hour of inspection operation.

4.5.6.3 Operator certification.-Magnetic particle inspection personnel (operators) shal be certified as qualified as Level II in accordance with MIL-STD-410.

5. PREPARATION FOR DELIVERY

5.1 Packing and marking.-Packing and marking shall be level B in accordance with MIL-STD-1169 and this specification.

5.2 Packing

5.2.1 Body assembly.-The projectile body with cap protector shall be packaged in accordance with dwg. 8837835.

5.2.2 Base plug.-Ten base plugs shall be packed in a fiberboard box, conforming to the requirements of PPP-B-636, Style RSC. Each base plug shall be separated by a fiberboard disc. Additional discs shall be added as required to make a tight pack.

Source: https://assist.dla.mil -- Downloaded: 202640-26T04:21Z
Check the source to verify that this is the current version before use.

5.2.2.1 Material.-Fiberboard boxes and discs shall meet the requirements of PPP-F-320, Type CF, Class Domestic, Variety SW, Grade 200, B Flute.

5.2.2.2 Size.-Dimensions of boxes shall be 5 1/2 X 12 3/16 inches deep. Dimensions of the discs shall be 5 inches in diameter.

5.3 Shipping.-When component parts from more than one lot are shipped as a carload, each lot must be kept separate and the division between lots shall be clearly indicated to prevent mixing of lots while in transit.

5.4 Marking

5.4.1 Body assembly.-Palletized body assemblies shall be marked in accordance with dwg. 8837835.

5.4.2 Base plug.-Packaged base plugs shall be marked, Level B, in accordance with MIL-STD-1169.

6. NOTES

6.1 Ordering data

6.1.1 Procurement requirements.-See MIL-A-48078.

6.1.2 Data requirements.-Deliverable data required by this specification is cited in the following paragraphs:

Paragraph	Data Requirement	Applicable DID
4.4.2.1.1	Quality Inspection Defect Report	DI-R-1721

(Copies of data item descriptions required by the contractor in connection with specific procurement functions should be obtained from the procuring activity or as directed by the Contracting Officer).

6.1.2.1 Delivery of data to the technical activity.-The following address is to be added to those listed in the contract (Form DD 1423) for delivery of one copy, each, to the technical activity, of the Ammunition Data Cards and Quality Inspection Defects Reports prepared by the contractor for the duration of the contract: Commander, US Army Armament Research and Development Command, ATTN: DRDAR-QAR-E, Dover, New Jersey 07801.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

6.2 Submission of designs for approval.-See paragraph 6.2.3 of MIL-A-48078. Submit equipment designs, as required, to: Commander, US Army Armament Research and Development Command, ATTN: DRDAR-QAR-I, Dover, New Jersey 07801.

6.3 Changes from previous issue.-Due to the extensiveness of the changes, asterisks are not used in this revision to identify changes with respect to the previous issue of this specification.

6.4 Firing record information.-The ballistic test firing records shall include the serial numbers of all weapon and fire control components. Stock component lot numbers of warmers and/or spotters shall also be included. For each round fired, the record shall contain deflection, elevation, time of firing, chamber pressure, pertinent flight characteristics, and the results of the post-recovery examination (overpressure recovery phase only). The following addresses are to be added to the Ballistic Test Request (BTR) for delivery of firing test reports to the technical activity: Commander, US Army Armament Research and Development Command, ATTN: DRDAR-QAR-E and DRDAR-LCU-CV, Dover, New Jersey 07801.

6.4.1 Impact area.-During the overpressure recovery phase of the ballistic test, the proving ground shall use a soft impact area free from rocky debris so as to assure that the projectiles fired for recovery and examination are not deformed on impact.

6.5 Visual standards.-Visual standards for metal defective discontinuities will be submitted to the Contracting Officer for approval prior to their implementation in the remainder of the contract in accordance with the provisions prescribed herein and in the contract. The resubmission of visual standards for approval on subsequent contracts will also be required. The contractor should be cognizant of the following criteria which the Government will use as part of its determination in judging the acceptance of each proposed standard for subsequent use:

a. The mechanical and physical properties of the area surrounding the discontinuity should not be degraded;

b. It should be improbable for a truly rejectable discontinuity to be mistakenly interpreted as being acceptable when compared to a visual standard;

c. A discontinuity should not interfere with the subsequent loading of a projectile, nor should it interfere with or misconstrue the results of a subsequent inspection (e.g. radiographic inspection);

d. Discontinuities should not be of a depth greater than ten percent of the wall thickness surrounding the discontinuity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

6.6 Failsafe.-An inspection system required to be failsafe is defined as a system in which the failure of any electrical, mechanical, hydraulic, or pneumatic portion of the system shall result in the placement of the system in the reject made of operation and shall require a definite signal to accept the item being inspected.

6.7 Proving ground test summary.-

Phase	Sample Size	Requirement	Sampling	Procedure
Performance	10*	Safety TID (info)	4.4.3.3.1	4.5.5.3 4.5.5.1
Over-pressure	10*	Safety Recovery Deformation (info)	4.4.3.3.2	4.5.5.3 4.5.5.2 4.5.5.2.1

*The sample size for the first article test and first three lots produced shall be twenty-five (25) samples.

Custodian:
ARMY-AR

Preparing Activity:
ARMY-AR

Project No.: 1315-A208

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID

U.S. MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

COMMANDER
US ARMY ARMAMENT RESEARCH & DEVELOPMENT COMMAND
ATTN: DRDAR-QAR
DOVER, NJ 07801

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.

NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-P-60523A PROJECTILE, 165MM, HEP M123A1 METAL PARTS

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1 OCT 76 1426

EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:21Z
Check the source to verify that this is the current version before use.