INCH-POUND
MIL-T-24708(SH)
29 July 1988

MILITARY SPECIFICATION

THERMAL/ACOUSTIC INSULATION BARRIER MATERIAL: POLYIMIDE FOAM

This specification is approved for use by the Naval Sea Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers lightweight, flexible polyimide foam as a layered thermal acoustic insulation barrier material developed for use within a specific frequency range on submarines.

1.2 Classification

Type I: Polyimide foam composite layers with vapor barrier, with unpainted glass cloth facing.

Class	Thickness (inches)
Class 1 - single layer	0.50
Class 2 - double layer	1.00
Class 3 - triple layer	1.50

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, Naval Sea Systems Command, SEA 5523, Department of the Navy, Washington, DC 20362-5101 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.
Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:13Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

PPP-B-1055 - Barrier Material, Waterproofed, Flexible.
PPP-F-320 - Fiberboard; Corrugated and Solid, Sheet Stock (Container Grade) and Cut Shapes.

MILITARY

MIL-L-19140 - Lumber and Plywood, Fire-Retardant Treated.
MIL-C-20079 - Cloth, Glass; Tape, Textile Glass; and Thread, Glass and Wire - Reinforced Glass
MIL-I-24688 - Insulation Panel, Thermal and Acoustic Absorptive, Open-Cell Polyimide Foam.

STANDARDS

FEDERAL

FED-STD-313 - Material Safety Data Sheets Preparation and the Submission of.

MILITARY

MIL-STD-2073-1 - DOD Materiel Procedures for Development and Application of Packaging Requirements.

(Unless otherwise indicated, copies of federal and military specifications and standards are available from the Naval Publications and Forms Center, (ATTN: NPODS), 5801 Tabor Avenue, Philadelphia, PA 19120-5099.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted shall be those listed in the issue of the DoDISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DoDISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

C 177 - Standard Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus. (DoD adopted)

D 2724 - Standard Test Methods for Testing Bonded, Fused, and Laminated Apparel Fabrics
D 3951 - Standard Practice for Commercial Packaging. (DoD Adopted)

E 162 - Standard Test Method for Surface Flammability of Materials Using a Radiant Heat Energy Source. (DoD adopted)

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:13Z
Check the source to verify that this is the current version before use.

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.4) in accordance with 4.3.

3.2 Material. The basic material shall be flexible polyimide foam.

3.2.1 Type I barrier material shall consist of a composite of 0.5 inch flexible polyimide foam layers conforming to DOD-I-24688, type I. The layers of flexible polyimide foam shall be bonded to a polyphosphazene/barium sulfate sheet weighing 30 ± 10 percent ounces per square yard. The polyphosphazene/barium sulfate sheet shall cover 100 percent of the polyimide foam surface. On the outer layer, a single glass cloth outer facing (see 3.3) shall be bonded to a polyphosphazene/barium sulfate sheet weighing 30 ± 10 percent ounces per square yard.

3.3 Glass cloth. Glass cloth shall be in accordance with type I, class 2 of MIL-C-20079 or as approved by NAVSEA.

3.4 Form. The barrier material shall be furnished in sheets or molded shapes as specified by the contracting activity (see 6.2).

3.4.1 Sheets. Sheet dimensions and quantities shall be as specified by the contracting activity but shall not exceed 48 by 120 inches (see 6.2).

3.4.2 Molded and pre-fabricated shapes. Molded and pre-fabricated shape forms and dimensions shall be as specified by the contracting activity (see 6.2).

3.5 Peel strength. The 180 degree peel strength between the fibrous glass cloth facing and the barium sulfate loaded polyphosphazene film to which it is bonded shall be as follows (see 4.5.1):

With web (oz/in) - 4
Across web (oz/in) - 2

3.5.1 Strength of adhesion. The bond strength between the polyphosphazene barium sulfate loaded film and the flexible polyimide foam shall exceed the adhesive strength of the flexible polyimide foam when tested as specified in 4.5.1.1.

Source: https://assist.dla.mil -- Downloaded: 2026l0-20T01:13Z
Check the source to verify that this is the currentversion before use.

3.6 Toxicity. The material shall have no adverse effect on the health of personnel when used for its intended purpose (see 4.5.2). Questions pertinent to this effect shall be referred by the contracting activity to the Commander, Naval Medical Command (MEDCOM-02) who will act as an advisor to the contracting activity.

3.7 Edge preparation. There shall be no adhesives or barrier treatments on the face of the vertical edges of the flexible polyimide foam between septum layers (see 4.5.3).

3.8 Fire resistance. Type I material shall have a flame spread rate of 25 or less and smoke development of 150 or less when tested as specified in 4.5.4. Type I class 3 materials shall also be tested in accordance with the method in the Appendix. Flashover time shall be greater than 10 minutes.

3.9 Insertion loss. The type I class 3 composite barrier material specified in 3.2.1 shall have an insertion loss of not less than 60 decibels (dB) when tested as specified in 4.5.5. The Government reserves the right to verify compliance from random installed materials. Type 1, class 1 shall have an insertion loss of not less than 20 decibels and class 2 shall be not less than 40 decibels.

3.10 Flexibility. The barrier material as specified in 3.4.1 shall show no visible damage, rupture or visible cracking when tested as specified in 4.5.6.

3.11 Thermal conductivity. When tested as specified in 4.5.7, the thermal conductivity, "K" expressed in British thermal unit-inches per square foot-hour-degrees Fahrenheit [Btu-in/(ft^2-hr-^oF)] shall not exceed 0.29 at 75°F for all classes.

3.12 Material safety data sheet. The contracting activity shall be provided a material safety data sheet (MSDS) at the time of the contract award. The MSDS shall be provided in accordance with the requirements of FED-STD-313. The MSDS shall be included with each shipment of the material covered by this specification (see 6.6).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract of purchase order, the contractor may use his own or any other facilities for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:13Z
Check the source to verify that this is the current version before use.

products or supplies submitted to the Government for acceptance comply with all requirements of the contract (see 6.3). Sampling inspection, as part of the manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

(a) First article inspection (see 4.3).
(b) Quality conformance inspection (see 4.4).

4.3 First article inspection. First article inspection shall consist of the examinations and tests specified in 4.3.1 and 4.5 (see 6.3).

4.3.1 First article tests. Prior to production, first article tests shall be conducted on a sample to determine the conformance with all the tests and requirements herein (see 6.4). The test material shall be certified to be identical in composition and equivalent in manufacture to the material to be supplied later for quality conformance inspection. The first article sample shall comply with all the requirements specified herein.

4.4. Quality conformance inspection. Quality conformance inspection shall be as specified in table I (see 6.3).

TABLE I. Quality conformance inspection.

Test	Test paragraph
Peel strength	4.5.1
Edges	4.5.3
Flexibility	4.5.6

4.5 Test methods and procedures.

4.5.1 Peel strength. Peel strength shall be determined in accordance with ASTM D 2724 (see 3.5).

4.5.1.1 Strength of adhesion. The strength of adhesion shall be determined by pulling/separating polyphosphazene barium loaded film from the flexible polyimide foam material and examining for compliance to 3.5.1.

4.5.2 Toxicological formulation. To determine conformance to requirements of 3.2.1, the manufacturer of the compound shall disclose the formulation of this product to the Commander, Naval Medical Command (MEDCOM-02) Washington, D.C. 20372 for approval. The disclosure of proprietary information, which shall be held in confidence by the Navy Medical Command, shall include the name, formula, and approximate percentage by weight and volume of each ingredient in the product; the results of any toxicological testing of

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:13Z
Check the source to verify that this is the current version before use.

the product; and such other information as may be needed to permit an accurate appraisal of any toxicity problem associated with the handling, storage, application, use, disposal, or combustion of the material.

4.5.3 Edges. Type 1 composites shall be supplied with clean cut 90 degress vertical cut edges (see 3.7).

4.5.4 Fire resistance. Type 1 material shall be tested in accordance with ASTM E 162 as follows:

(a) With the glass cloth cover facing the heat source.
(b) With the flexible polyimide foam facing the heat source.

Type I material shall also be tested in accordance with the method in the Appendix.

4.5.5 Insertion loss. A minimum of 16 square feet (4 each 2 foot square) of composite barrier, type I class 1, 2 and 3 materials (specified in 3.2) shall be tested for insertion loss (see 3.9). The tests shall be performed according to procedures and at facilities approved by NAVSEA.

4.5.6 Flexibility. One layer of 1/2 inch thick barrier material, type I, class 1 as per installed configuration, 12 by 18 inches shall be cut and bent through an arc of 90 degrees on its 12 inch dimension over a 1-inch diameter mandrel. The mandrel shall be long enough to extend at least 2 inches beyond the ends of the test specimen. The specimen shall be maintained in the flexed position for 5 minutes before being released and then examined for compliance with 3.10.

4.5.7 Thermal conductivity. The thermal conductivity, "K", of the thermal acoustic insulation barrier material shall be determined in the installed configuration and as specified in ASTM C 177 (see 3.11).

4.6 Inspection of packaging. Sample packages and packs, and the inspection of the preservation-packaging, packing and marking for shipment and and storage shall be in accordance with the requirements of section 5 and the documents specified therein.

5. PACKAGING

(The packaging requirements specified herein apply only for direct Government acquisition. For the extent of applicability of the packaging requirements of referenced documents listed in section 2, (see 6.5).

5.1. General

5.1.1 Navy fire-retardant requirements.

(a) Treated lumber and plywood. Unless otherwise specified (see 6.2), all lumber and plywood including laminated veneer material used in shipping containers and pallet construction, members, blocking, bracing, and reinforcing shall be fire-retardant treated material conforming to MIL-L-19140 as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:13Z
Check the source to verify that this is the current version before use.

Levels A and B - Type II - weather resistant.
Category 1 - general use.
Level C - Type I - non-weather resistant.
Category 1 - general use.

(b) Fiberboard. Unless otherwise specified (see 6.2), fiberboard used in the construction of class-domestic, non-weather resistant fiberboard, cleated fiberboard boxes including interior packaging forms shall meet the flame spread index and the specific optic density requirements of PPP-F-320.

5.2 Preservation. Preservation shall be level A or commercial as specified (see 6.2).

5.2.1 Level A.

5.2.1.1 Sheets. Sheets in the quantity and size specified (see 3.4.1 and 6.2) shall be packed flat and enclosed in a nonbleeding, flexible, waterproofed barrier material conforming to class B-1, B-2 or E-2 of PPP-B-1055 at the contractor's option. Seams, joints, and laps shall be closed or sealed in a manner which shall afford waterproofness equal to that of the wrap itself. Each flat package shall contain one size. Packed sheets shall be secured with a minimum of two straps of filament reinforced, pressure-sensitive tape. Straps shall be placed at 1/6 the length of the package from each end. Additional straps shall be placed at approximately 20 inch intervals between the end straps.

5.2.1.2 Molded and pre-fabricated shapes. Molded and pre-fabricated shapes shall be protected in the same manner as described in 5.2.1.1, except that strapping shall be the minimum necessary to assure closure and waterproofness of the packs.

5.2.2 Commercial. Barrier material in the form and the quantity specified (see 3.4.1 and 6.2) shall be packed in accordance with ASTM D 3951.

5.3 Packing. Packing shall be level B, C or Commercial as specified (see 6.2).

5.3.1 Level B. Material, packed as specified (see 6.2.), shall be packed in a class, weather-resistant, minimum 275 grade fiberboard box conforming to MIL-STD-2073-1, Appendix C, table VII, with the variety and style at the contractor's option. Waterproofing and reinforcing shall conform to method V in accordance with the appendix to the box specification. Alternatively, packaged material may be packed in type II or III, grade D fiber drum conforming to MIL-STD-2073-1, Appendix C, table VII.

5.3.2 Level C. Material, packaged as specified (see 6.2), shall be packed in a class-domestic, minimum 275 grade fiberboard box conforming to MIL-STD-2073-1, Appendix C, table VII, with the variety and style at the contractor's option. Closure shall be accomplished by method I, except that staples shall not be used. Alternatively, packaged material may be packed in type I, grade D fiber drums conforming to MIL-STD-2073-1, Appendix C, table VII.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:13Z
Check the source to verify that this is the current version before use.

5.3.3 Commercial. Barrier material packed as specified (see 6.2), shall be packed in accordance with ASTM D 3951.

5.4 Palletized and containerized unit loads. When specified (see 6.2), shipping containers shall be palletized for shipment in accordance with MIL-STD-2073-1.

5.5 Marking. In addition to any special marking required (see 6.2), level A, B, and C interior packs, shipping containers, and palletized unit loads shall be marked in accordance with MIL-STD-2073-1, including bar coding and applicable packaging acquisition options specified (see 6.2). Commercial interior packs, shipping containers and palletized unit loads shall be marked in accordance with ASTM D 3951.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.

6.1 Intended use. Material covered by this specification is intended for use as a thermal/acoustic barrier material for use in submarines.

6.2 Acquisition requirements. Acquisition documents must specify the following:

(a) Title, number, and date of this specification.
(b) Issues of DoDISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1)
(c) If first article inspection is required (see 3.1).
(d) Form of material required (see 3.4).
(e) Dimensions of sheet (see 3.4.1).
(f) Forms and dimensions of molded shapes (see 3.4.2).
(g) When fire-retardant materials are not required (see 5.1).
(h) Level of preservation required (see 5.2).
(i) Level of packing required (see 5.3).
(j) Palletized load requirements (see 5.4).
(k) Marking and special marking requirements (see 5.5).

6.3 Consideration of data requirements. The following data requirements should be considered when this specification is applied on a contract. The applicable Data Item Descriptions (DID's) should be reviewed in conjunction with the specific acquisition to ensure that only essential data are requested/provided and that the DID's are tailored to reflect the requirements of the specific acquisition. To ensure correct contractual application of the data requirements, a Contract Data Requirements List (DD Form 1423) must be prepared to obtain the data, except where DoD FAR Supplement 27.475-1 exempts the requirement for a DD Form 1423.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:13Z
Check the source to verify that this is the current version before use.

Reference Paragraph	DID Number	DID Title	Suggested Tailoring
4.1.1	DI-E-2121	Certificate of compliance	- - - -
4.3	DI-T-4902	First article inspection report	- - - -
4.4	DI-T-5329	Inspection and test report	- - - -

The above DID's were those cleared as of the date of this specification. The current issue of DoD 5010.12-L, Acquisition Management Systems and Data Requirements Control List (AMSDL), must be researched to ensure that only current, cleared DID's are cited on the DD Form 1423.

6.4 First article. When first article inspection is required, the contracting officer should provide specific guidance to offerors whether the item should be a first article sample, and the number of items to be tested as specified in 4.3. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for examinations, approval of first article test results, and disposition of first articles. Invitations for bids should provide that the Government reserves the right to waive the requirement for samples for first article inspection to those bidders offering a product which has been previously acquired or tested by the Government, and that bidders offering such products, who wish to rely on such production or test, must furnish evidence with the bid that prior government approval is presently appropriate for the pending contract. Bidders should not submit alternate bids unless specifically requested to do so in the solicitation.

6.4.1 First article approval, certificates of compliance or any other agreements regarding this specification are valid for the original contractor only and shall be considered non-transferable and non-negotiable without written Government approval.

6.4.1.1 The Government reserves the right to reinspect or retest materials acquired under this specification for compliance conformance.

6.5 Sub-contracted material and parts. The packaging requirements or preparation for delivery of referenced documents listed in section 2 do not apply when material and parts are acquired by the contractor for incorporation into the equipment and lose their separate identity when the equipment is shipped.

6.6 Material safety data sheet MSDS). Contracting officers shall identify those activities requiring copies of MSDS's. Additional required Government information is contained in FED-STD-313. In order to obtain the MSDS, FAR clause 52.233-3 must be in the contract.

Source: https://assist.dla.mil -- Downloaded: 20260-20T01:13Z
Check the source to verify that this is the current version before use.

6.7 Subject term (key word) listing.

Conductivity
Fire resistant
Flexibility

Preparing activity:
Navy - SH
(Project 5640-N449)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:13Z
Check the source to verify that this is the current version before use.

APPENDIX

DETERMINATION OF THE FLASHOVER, POTENTIAL OF A LINING MATERIAL USING A QUARTERSCALE ROOM FIRE TEST

10. SCOPE

10.1 Scope. This method describes a procedure to determine the flashover potential of materials in a room when subjected to a fire exposure. The method described will yield a time from the introduction of the fore exposure unit the moment of flashover. This appendix is a mandatory part of the specification. The information continued herein is intended for compliance.

10.2 JUSTIFICATION

10.2.1 In the interest of reducing, both the set-up time and cost associated with fire testing in a full size room (defined as a 10 by 10 by 8 foot high room having a 30 by 80 inch high doorway), a one-quarter scale room fire test was devised to predict flashover potential of lining materials exposed to fire.

20. APPLICABLE DOCUMENTS.

Not applicable.

30. EQUIPMENT

30.1 The quarterscale room shall be constructed from a ceramic insulation board and shall form an airtight box having a ceiling and four sides. The box shall sit on a floor fabricated with the same material. The interior dimensions of the fully lined quarterscale room are 30 by 30 by 24 inches high. The doorway is located at the center of one wall and shall be 19.5 inches wide and 17 inches high to secure the proper ventilation and fire development. The height between the finished ceiling and the top of the doorway shall be 7 inches. The floor of the model room shall extend at least 12 inches outside of the doorway. The box shall be removable to allow for application of ceiling and wall covering. The entire base of the box in contact with the floor shall be made airtight.

30.2 A porous plate diffusion flame burner shall be used as the fire source. The burner shall be 3.5 inches long by 3.5 inches wide by 3 inches high, consisting of a horizontal porous plate area of 3 by 3 inches with a 0.25 inch wide steel plate perimeter and steel plate sides and bottom.

30.3 Four 10 mil chromel-alumel thermocouples shall be used, 1 inch and 3 inches below the center of the overhead and 1 inch and 2 inches below the top of the doorway.

Source: https://assist.dla.mil -- Downloaded: 20261O-20T01:13Z
Check the source to verify that this is the current version before use.

APPENDIX

40. PROCEDURES

40.1 The test material shall fully line the walls and ceiling.

40.2 Prior to testing, the fully-lined test room shall be conditioned for at least 24 hours at a relative humidity between 20 and 60 percent, and a temperature of 23 plus or minus 5 degrees Celsius (°C).

40.3 The burner source shall be positioned on the floor and snugly against one of the corners inside the test room. A methane flow rate of 0.64 cubic foot per minute shall be used to produce a constant heat input of approximately 640 Btu per minute for the duration of the test.

40.4 The test data from the four thermocouple shall be recorded as a continuous function of time.

40.5 The primary data generated by this test will be the time to flash-over, if it occurs, and the maximum temperature if flashover is not reached. Flashover is characterized by thermal flux levels equal to or greater than 2 watts per square centimeter at the floor level. This corresponds to interior temperatures of 600°C and higher, and doorway temperatures of 500°C and higher. For this test purpose, flashover is defined as the fire condition when one of the interior thermocouple measurements reach 600°C or one of the doorway measurements reaches 500°C, whichever occurs first. Flashover shall not occur within 10 minutes.

40.6 Color slides of the test material shall be taken before the test, at the point of maximum involvement, and after the fire has been extinguished.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:13Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY

COMMANDER
NAVAL SEA SYSTEMS COMMAND (SEA 55Z3)
DEPARTMENT OF THE NAVY
WASHINGTON, DC 20362-5101

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12503 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

COMMANDER
NAVAL SEA SYSTEMS COMMAND (SEA 55Z3)
DEPARTMENT OF THE NAVY
WASHINGTON, DC 20362-5101

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:13Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-T-24708(SH)	THERMAL/ACOUSTIC INSULATION BARRIER MATERIAL: POLYIMIDE FOAM

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*:

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:13Z
Check the source to verify that this is the current version before use.