AMENDMENT
TO
INTERIM FEDERAL SPECIFICATION

BINDER, LOOSE-LEAF, RING: ONE-PIECE COVER

This amendment was developed by Standardization Division, Federal Supply Service, General Services Administration, Washington, D. C. 20406, based upon currently available technical information. The General Services Administration has authorized this amendment as a part of Interim Federal Specification UU-B-001254(GSA-FSS) dated March 20, 1970.

PAGE 3

Paragraph 3.1.1.1, change "RB 60-75" to RB 60 (Minimum)" for the 0.036 and 0.040 inch thick requirement.

Paragraph 3.1.1.3, change "R30T 56.5-67" to "R30T 56.5-72" for the 0.015 and 0.020 inch thick requirement.

Table I, delete and substitute the following:

TABLE I. Rubber bonded cellulose fiber requirements

Requirement	Thickness	
	0.025-inch	0.030-inch
BASIS WEIGHT (24 inch, by 36 inch. 500 sheets), MINIMUM	315 lbs.	350 lbs.
TENSILE BREAKING STRENGTH, MINIMUM		
Machine direction	160 lbs./in. of width	180 lbs./in. of width
Cross direction	50 lbs./in. of width	60 lbs./in. of width

Table II, 3rd entry under "Physical Property", change "flexture" to "flexure".

PAGE 5

Paragraph 4.1.1, add the following after the last sentence:

"Unless otherwise specified, the sample size shall be the sample unit specified in the applicable test method, selected at random within the shipment."

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.